



## UvA-DARE (Digital Academic Repository)

### Design issues for improved environmental performance of dye-sensitized and organic nanoparticulate solar cells

Reijnders, L.

**DOI**

[10.1016/j.jclepro.2009.10.021](https://doi.org/10.1016/j.jclepro.2009.10.021)

**Publication date**

2010

**Document Version**

Final published version

**Published in**

Journal of cleaner production

[Link to publication](#)

**Citation for published version (APA):**

Reijnders, L. (2010). Design issues for improved environmental performance of dye-sensitized and organic nanoparticulate solar cells. *Journal of cleaner production*, 18(4), 307-312. <https://doi.org/10.1016/j.jclepro.2009.10.021>


**General rights**

It is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), other than for strictly personal, individual use, unless the work is under an open content license (like Creative Commons).

**Disclaimer/Complaints regulations**

If you believe that digital publication of certain material infringes any of your rights or (privacy) interests, please let the Library know, stating your reasons. In case of a legitimate complaint, the Library will make the material inaccessible and/or remove it from the website. Please Ask the Library: <https://uba.uva.nl/en/contact>, or a letter to: Library of the University of Amsterdam, Secretariat, Singel 425, 1012 WP Amsterdam, The Netherlands. You will be contacted as soon as possible.

*UvA-DARE is a service provided by the library of the University of Amsterdam (<https://dare.uva.nl>)*



## Design issues for improved environmental performance of dye-sensitized and organic nanoparticulate solar cells

L. Reijnders\*

IBED, University of Amsterdam, Nieuwe Achtergracht 166, 1018 WV Amsterdam, The Netherlands

### ARTICLE INFO

#### Article history:

Received 23 July 2009

Received in revised form

19 October 2009

Accepted 23 October 2009

Available online 1 November 2009

#### Keywords:

Dye-sensitized solar cell

Organic solar cell

Nanoparticle

Environmental improvement

### ABSTRACT

Though environmental improvement has been claimed for the application of nanotechnology to solar cells, several characteristics of the fullerene-based organic, and the dye-sensitized nanoparticulate, solar cell are not conducive to such improvement. These include relatively high energy and materials inputs in the production of nanoparticles, a relatively low solar radiation to electricity conversion efficiency, a relatively short service life, the use of relatively scarce metals and relatively poor recyclability, if compared with the multicrystalline Si solar cell which currently is the market leader. Moreover, the lack of data and the inability of current methods to handle hazards of nanoparticles generate problems in conducting comparative life cycle assessment of nanoparticulate solar cells. So far, the claimed environmental advantage can not be substantiated for fullerene-based and dye-sensitized nanoparticulate solar cells. There are options for the environmental improvement of these nanoparticulate solar cells, but actual development does not seem to focus on environmental improvement.

© 2009 Elsevier Ltd. All rights reserved.

### 1. Introduction

It has been argued that the application of nanotechnology holds a promise for much improved environmental performance [1–5]. This promise has also been argued to apply to photovoltaic or solar cells [1–5]. Photovoltaic cells currently predominantly employ Si crystals which have a much larger than 100 nm diameter [6]. Among current Si-based solar cells the market leader is multicrystalline (mcSi), employing solar grade Si (which can be produced from primary metallurgical grade Si) [6]. The production process for mcSi solar cells may change in the near future due to the introduction of ribbon Si, which lowers the life cycle energy input (and costs) [6].

To look at the environmental performance of photovoltaic cells using nanotechnology, solar cells will be considered here which exploit nanoparticles (<100 nm) for power generation. Many types of nanoparticles are considered for application in solar cells, including nanocrystalline Si, C nanoparticles such as fullerenes (usually C<sub>60</sub> or C<sub>61</sub> and their derivatives) and a variety of metal, metal oxide, sulphide (S), arsenide (As), telluride (Te) and selenide (Se) nanoparticles [7–12]. Frontrunners among nanoparticulate photovoltaic cells are the dye-sensitized solar cells (also DS(S)C or

Grätzel cells), which use TiO<sub>2</sub> nanoparticles [12], and fullerene-based organic solar cells [9,11]. These cells are frontrunners because they are the object of relatively much research and development work and some commercialization. DS(S)Cs are marketed by companies such as 3G Solar, G24 Innovations, Solarprint and Dyesol, and fullerene-based organic solar cells by Konarka Technologies. Both DS(S)C and fullerene-based organic solar cells will be considered here.

The DS(S)C consists of a nano-TiO<sub>2</sub> photo electrode, an organometallic or organic dye (sensitizer), an electrolyte and a counter electrode. Between the electrodes of an organic solar cell is usually a 'bulk heterojunction' layer of fullerenes and polymers. A buffer layer for the electrode of e.g. TiO<sub>2</sub> or LiF may also be included.

The TiO<sub>2</sub> of the DS(S)C may be on a layer containing In (indium) and/or Sn (tin), and the electrodes of nanoparticulate cells may contain the same metals (In, Sn), Pt (platinum), Au (gold), Cr (chromium) or Al (aluminum).

This paper will discuss major determinants of the 'cradle to grave' or life cycle environmental performance of the DS(S)C and the fullerene-based organic solar cells which serve the electricity grid for 25 years and options for their environmental improvement. A comparison will be made with mcSi cells which serve the electricity grid and do not employ nanoparticles, on the basis of the production of the same amount of kilowatt-hours (kWh).

Claims about the environmental advantage of solar cells employing nanoparticles can be traced back to the much lower

\* Tel.: +31 20 5256206; fax: +31 20 5257431.

E-mail address: [l.reijnders@uva.nl](mailto:l.reijnders@uva.nl)

input of materials in the solar cells themselves, which (*ceteris paribus*) has a favorable impact on environmental performance in life cycle assessment [4,8,12]: 'less is better'.

On the other hand, there may also be characteristics of nanoparticulate solar cells which may have (*ceteris paribus*) the opposite effect of increasing life cycle environmental impact or burden.

The following characteristics of current dye-sensitized and fullerene-based nanoparticulate solar cells come to mind [14–21]:

- producing nanoparticles may require much larger inputs of energy (in practice fossil fuels) and materials than the production of the same mass of larger-sized materials [13],
- a relatively low efficiency in converting solar irradiation into electricity, if compared with mcSi cells [14,20,21],
- a relatively short service life [15–19],
- relatively poor recyclability of nanoparticle-based solar cells,
- the use of metals derived from relatively scarce natural resources, such as Pt, Au, Sn, In and Ru (ruthenium).

The combined effect of these aspects may well be substantial. Analyses of the life cycle CO<sub>2</sub> emission kW h<sup>-1</sup> of current DS(S)Cs show a relatively high emission, if compared to current mcSi cells [12,20,21]. Similarly, present life cycle CO<sub>2</sub> emissions per kWh from fullerene-based cells exceed those of mcSi cells [22]. Raugi and Franckl have suggested a relatively high life cycle CO<sub>2</sub> emission kW h<sup>-1</sup> for future DS(S)C, if compared with solar cells based on ribbon Si [6].

The aspects of nanoparticle-based photovoltaic cells which can have a negative impact on environmental performance are not only important because of their weight in assessing the life cycle environmental impact. Also they may provide a focus for environmentally improved design of nanoparticulate cells.

It should be noted though, that with currently available data and methods, there are problems for comparative studies concerning the nanoparticulate cells discussed here. Nanoparticulate solar cells may use materials for which available life cycle assessment databases contain no, or insufficient, data to allow for proper environmental assessment, e.g. [22] and the implications of improvement options regarding DS(S)Cs and fullerene-based solar cells for life cycle inputs of energy and materials are often uncertain. Also, current life cycle assessment methodology is unable to properly handle the hazard of mineral nanoparticles [23].

In Section 2, aspects of nanoparticulate cells which can add to the environmental burden will be discussed in turn. In Section 3 the lack of data and proper methodology will be discussed. This will be followed in Section 4 by suggestions for environmental improvement. Section 5 will summarize the conclusions from this paper.

## 2. Aspects of nanoparticulate solar cells which are not conducive to environmental improvement

### 2.1. Relatively high inputs in the production of nanoparticles

The nanoparticulate solar cells considered here, are characterized by lower direct inputs of materials and a lower life cycle energy input than mcSi cells [12,22]. The environmental advantage of nanoparticulate solar cells is however limited by the relatively high input of energy and materials in the production of TiO<sub>2</sub> and fullerene nanoparticles, if compared with larger-sized TiO<sub>2</sub> and C particles [13,22,24]. TiO<sub>2</sub> nanoparticles may require at least a 3–4

times larger input of energy than conventional TiO<sub>2</sub> particles, whereas on a kg for kg basis the input of precursor may be increased by a factor 1.5–3.9 [13,24]. The production of fullerenes is energy intensive and is estimated [21] to require between 25 and 129 GJ of primary energy per kg C<sub>60</sub>. C<sub>60</sub> production can also be highly material intensive. For instance, an estimated 385 kg of benzene is currently needed as feedstock for the production of 1 kg C<sub>60</sub> by combustion [22].

### 2.2. Relatively low conversion efficiency

The nanoparticulate photovoltaic cells considered here, have as yet a lower solar radiation to electricity conversion efficiency than mcSi solar cells. The reported maximal efficiencies for the DS(S)C and single junction fullerene-based organic cells are ~11.2% and 5.4%, respectively [14]. The maximum reported efficiency for standard multicrystalline Si cells is 18.7% [14], whereas mass-produced commercial mcSi cells have a conversion efficiency of about 14.4% [20].

The current difference in efficiency between nanoparticulate and mcSi cells may partly be due to differences in technological learning. The current mcSi solar cells are further on the learning curve than the nanoparticle-based solar cells considered here, which are under development since the late 1980s and early 1990s, whereas Si-based cells are under development since the 1950s [12,15,25,26]. However, there are estimates of the potential for further efficiency improvement of the nanoparticulate solar cells considered here. For fullerene-based organic solar cells, it has been argued that practicable maximum conversion efficiency may be in the order of 10–11%, when not in tandem [27–29]. For DS(S)C the maximum achievable efficiency has been estimated at 12% [12]. Thus, it would seem likely that with similar technological learning the conversion efficiency of DS(S)C and fullerene-based organic solar cells may still be poorer than in case of mcSi solar cells (also [6]).

### 2.3. Relatively short service life

On solar irradiation, photovoltaic cells are subject to demanding conditions [15–19]. McSi photovoltaic cells, serving the electricity grid, have in these conditions a useful lifetime (service life) of 25–30 years [15,20]. During this time the solar radiation to electricity conversion efficiency of the cells remains over 80% of the original value.

Experiments with DS(S)C have shown that they are relatively vulnerable to the harsh conditions, under which solar cells have to operate. Intrusion of O<sub>2</sub> and H<sub>2</sub>O leads to rapid deterioration of DS(S)C performance [19]. Performance may also be reduced by high temperatures and ultraviolet irradiation [18,19]. Leakage and degradation of DS(S)C liquid electrolyte have been shown to be problems too [12,18,19,30].

Damage to organic constituents due to the intrusion of O<sub>2</sub> and H<sub>2</sub>O is also a matter of concern for the fullerene-based solar cells [27–29,31–35]. Electrode material reactions with the rest of the cell and damage to organic cells at high temperatures tend to be larger for organic solar cells than in the case of mcSi cells [15]. Furthermore, partial oxidation of electron contact material has been shown to negatively affect cell performance over time. Instability of morphology due to phase separation has also been shown to be a problem [9]. Enveloping solar cells in a way that minimizes the intrusion of O<sub>2</sub> and H<sub>2</sub>O has been shown to extend the service life of organic solar cells [15,29,32–34]. However, current enveloping materials (usually synthetic polymers) are subject to degradation when exposed to solar radiation [15]. Their use is associated with an expected service life which is still well below 10 years and considerably adds to material inputs in the production of solar cells [9,15,33–35].

There is great uncertainty about the service life achievable by mass-produced nanoparticulate solar cells, but as yet it would seem to be substantially shorter than for standard Si cells. It has been suggested, that for the DS(S)C a useful lifetime of 10 years is 'within reach' [19], but this as yet would not seem the case for organic solar cells [15,22,28,31–35].

#### 2.4. Poor recyclability

Recyclability is important to reduce the cradle to grave environmental burden of products. When recycling takes place and if the environmental burden thereof, including transport, is relatively low, the initial environmental burden of solar cell production can partly be distributed over the original and the recycled products and this tends to lower the environmental burden of the original product [36,37]. mcSi cells can be recycled into high quality secondary products at a relatively low cost [38,39]. Si from discarded mcSi solar cells can be used as a resource for the production of new solar cells, and this has a substantial environmental benefit (when not corrected for differences in transport between discarded cells and virgin resources) [38,39].

Recycling of nanoparticulate solar cells has not drawn a major research effort so far. However experience with post-consumption recycling of waste from electrical equipment has shown that, when substantial amounts are present, the metals in nanoparticulate cells can in all probability be recycled into products with high quality applications [40–43]. But beyond metals, recyclability seems low. In part, the design of nanoparticulate solar cell uses the interpenetration of substances (C<sub>60</sub> and polymer, TiO<sub>2</sub> and dye) and this is not conducive to recycling [44]. Recycling of composite polymeric materials (which are a major constituent of organic solar cells and may be important in DS(S)C with a relatively long service life) has turned out to be a problem [44]. Only low quality applications of secondary composites have been found, and in practice such composites often end up being incinerated or landfilled [44]. Recycling of non-composite synthetic polymers, which can be enveloping materials for nanoparticulate solar cells [15,22,33–35], is more attractive [44]. However, when such materials are substantially degraded, as is likely to occur during a long service life [15], only low quality applications would still be possible [44]. Thus it would seem likely that, given present cell design, unlike in the case of mcSi cells, only a very limited part of the nanoparticulate solar cells can be recycled into high quality applications (at acceptable cost). This negatively affects their environmental performance, if compared with mcSi cells.

#### 2.5. The use of metals derived from relatively scarce natural resources

Depletion of natural resources is often viewed as an aspect of life cycle environmental assessment which contributes to the environmental burden, e.g. [20]. Because Si is the second most abundant element in the earth's crust [25], the environmental burden of Si use due to resource depletion is very low. On the other hand, the use of metals derived from relatively scarce natural resources, corresponds with a relatively heavy environmental burden. In the category of such compounds come Au, Ru and Pt (applied in DS(S)C), and In and Sn (applied in DS(S)C and organic nanoparticulate cells) [9–12,45–47].

Using depletion of natural resources in life cycle assessment has been criticized, e.g. in the case of metals, because dissipation and disposal rather than depletion is problematical [48]. If this line of reasoning is followed, this aspect of the environmental burden will be largely determined by the degree of recycling that is achieved (see Section 2.4).

### 3. Missing data for life cycle assessment

Though current databases include adequate data for the life cycle assessment of mcSi cells [20,49], this is quite different for nanoparticulate cells [6,12,21,22]. As yet, standard methodologies for life cycle assessment do not allow for the inclusion of nanoparticle hazard [23]. This problem is not easily remedied. Hazard is usually handled by life cycle assessment on the basis of weight of the substances released into the environment. However the hazard of mineral nanoparticles such as TiO<sub>2</sub> is rather determined by number, surface area, nature of the surface and structure [50]. Also, information about several non-nanoparticulate components in nanoparticulate solar cells, such as a variety of polymers and dyes, is largely missing in databases currently used for life cycle assessment of solar cells and this also seems to hold for dyes and polymers that are currently used in efforts to improve conversion efficiency and service life ([6,12,21,22] and Section 4). This holds for energy input and related CO<sub>2</sub> emissions, but even more for other aspects of environmental impact such as depletion of natural resources, (eco)toxicity, acidification, eutrophication and impact on the ozone layer.

### 4. Options for the improvement of environmental performance of nanoparticulate solar cells

If one takes an overall view, the environmental advantage of lower direct material inputs in the nanoparticulate solar cells considered here, is counterbalanced by relatively high inputs of energy and materials in nanomaterial production, additional inputs of materials for enveloping cells to prevent deterioration, poorer conversion efficiency, lower useful service life, use of metals from relatively scarce natural resources and/or poorer recyclability. Currently this leads to a relatively low life cycle emission of CO<sub>2</sub> kW h<sup>-1</sup> for mcSi cells if compared with dye-sensitized and fullerene-based solar cells (see Table 1).

As pointed out in the Introduction, disadvantages of the nanoparticulate solar cells considered here may in the future lead to a relatively high life cycle CO<sub>2</sub> emission kW h<sup>-1</sup>, if compared with solar cells based on ribbon Si. Thus, in the further development of nanoparticle-based photovoltaic cells, the aspects that negatively affect environmental performance are issues to preferentially address.

So far, environmental improvement of nanoparticulate cells has not been the object of a systematic research effort. Nevertheless, a number of suggestions for improvement of the solar cells

**Table 1**

Environmental attributes of multicrystalline Si (mcSi) versus dye-sensitized and fullerene-based nanoparticulate solar cells

Relative advantage of dye-sensitized and fullerene-based nanoparticulate solar cells, relevant to environmental performance	Relative advantage of mcSi solar cells relevant to environmental performance	Current overall environmental performance
<ul style="list-style-type: none"> <li>- Low direct input of materials in nano particulate cells</li> <li>- Low life cycle energy input in nanoparticulate cells, though nanoparticle production is relatively energy intensive</li> </ul>	<ul style="list-style-type: none"> <li>- Longer service life of mcSi cells</li> <li>- Higher conversion of solar energy to electricity by mcSi cells</li> <li>- Better recyclability of mcSi cells</li> <li>- More abundant natural resources for materials for mcSi cells</li> </ul>	Relatively low life cycle CO <sub>2</sub> emission kWh <sup>-1</sup> for mcSi cells, if compared with the nano particulate cells considered here

considered here can be made. One is the reduction of the life cycle input of materials in nanoparticle production, and more generally: reduction of the life cycle materials input of nanoparticulate solar cells. Reduction of the life cycle input of materials has been important in improving the environmental performance of mcSi solar cells [6,39] and may also be significant in improving the environmental performance of nanoparticulate cells. For instance, Kato et al. [21] have shown that reduced life cycle inputs of acetone and isopropanol could substantially decrease the life cycle CO<sub>2</sub> emission of the DS(S)C which they studied.

Other suggestions for environmental improvement of the nanoparticulate solar cells considered here will be discussed in the following. This discussion includes matters relevant to the environmental impact of those suggestions.

#### 4.1. Improving energy efficiency

An obvious target for improvement is increasing the solar radiation to electricity conversion and lowering energy input in the production of nanoparticles to be included in photovoltaic cells. The former is the object of much development work, e.g. [12,27–29,51–53]. As pointed out in Section 2.2 the best reported performance of DS(S)C is not far from its achievable maximum. This is different for fullerene-based organic cells but here recent conversion efficiency improvement seems slow, e.g. [51].

Remarkably, in efforts to improve conversion efficiency there is little attention to the life cycle environmental impact of materials suggested in this context. For instance, the use of pyridine derivatives, such as benzimidazole compounds, has been suggested as an option to improve the efficiency of polymeric DS(S)C. Because pyridine derivatives may have substantial biological activity [54,55], their potential release during the product life cycle and the impact thereof should be considered in assessing the environmental performance of DS(S)C which include such compounds.

As to the input of energy in nanoparticle production, there may be various ways to generate specific nanoparticles with strongly varying energy inputs [13,24]. This allows for the selection of relatively energy-efficient production processes, which in turn can be improved by technological learning [6].

#### 4.2. Substituting compounds derived from scarce natural resources and improving recycling

Substituting compounds derived from relatively scarce natural resources by substances derived from more abundant resources may lead to environmental improvement, when it is assumed that this depletion adds to the environmental burden. It has been proposed that Ru-compounds may be substituted by organic dyes, e.g. [45]. However, when considering such substitution one should be aware of side effects that may have an upward effect on the environmental burden. For instance, Burke et al. [45] have argued that the replacement of ruthenium compounds by planar organic dyes may necessitate the employment of an additional TiO<sub>2</sub> layer. Also electrodes of aluminum, which is relatively abundant in the earth's crust, to replace rarer metals have been shown to be easily photocorroded when applied in organic cells; this may strongly reduce service life [4,45].

In the case of mcSi solar cells, recycling (not corrected for differences in transport of discarded solar cells and virgin materials) has been found to substantially reduce the life cycle environmental burden [38,39]. One might expect the improvement to be less in the case of the nanoparticulate cells considered here, because recycling would probably be restricted to metals and perhaps non-composite polymers, as pointed out in Section 2.4.

#### 4.3. Extension of service life

Extension of service life may much improve the environmental performance of nanoparticulate cells. For instance it has been estimated that increasing service life of organic cells on glass to 10–20 years may make such cells environmentally competitive with current mcSi cells, whereas for their plastic counterparts a service life of 1–5 years may suffice, when the extension of service life does not require the additional input of materials and energy [22].

There are options for the extension of service life of both DS(S)C and organic cells.

Options to improve stability by improved enveloping of cells have been outlined in Section 2.3. These are subject to environmental trade-offs because they tend to imply increased life cycle materials intensity.

Leakage from DS(S)C is linked to the use of a liquid electrolyte which may vary in volatility. Replacement of the liquid electrolyte by a solid one (in practice by an organic polymer) can eliminate leakage of electrolyte by DS(S)C [56,57]. However, the polymeric electrolytes may be subject to relatively rapid degradation mediated by TiO<sub>2</sub>, when there is intrusion of oxygen and water [15,58]. Addition of radical scavengers may limit such degradation [59]. Moreover, the solar radiation to electricity conversion efficiency tends to be reduced when the liquid polymer is substituted by a solid polymer [56,57]. Another option is the use of a semi-solid state gel as electrolyte. Many of the gels investigated thus far have a lowered conversion efficiency, but a gel polymer incorporating TiO<sub>2</sub> nanoparticles has been reported to have a conversion efficiency similar to DS(S)Cs with liquid electrolyte [60–65]. However, it may well be that incorporation of TiO<sub>2</sub> nanoparticles reduces cell stability, when there is intrusion of oxygen and water [58], which again may be counteracted to some extent by the inclusion of radical scavengers [59]. A variety of suggestions have been made to increase the oxidation resistance, and the chemical and morphological stability of polymers which in turn may extend the service life of solar cells, including more rigid structures, cross-linking of polymer chains, the use of p–n block polymers and the use of a variety of conjugated polymers, e.g. [9,66]. So far there are no evaluations of the life cycle environmental impacts of such polymers, which may confer improved stability. A fullerene variety has been proposed that has much improved photostability, but its application as yet leads to a much reduced conversion efficiency [66]. The problems with oxidation of electron contact material in organic cells may be reduced by the inclusion of high stability metals [17,46,47,67], which are however derived from relatively scarce natural resources. There can be environmental trade-offs for the expansion of service life, but there is no focus on optimizing such trade-offs in actual development.

#### 4.4. Selecting options for environmental improvement

Options which reduce the life cycle input of materials, while at least maintaining the service life and conversion efficiency of nanoparticulate solar cells, would seem interesting environmental improvement options, e.g. [21]. Beyond that, selecting the best short-term options for environmental improvement is difficult with currently available data. For instance, increasing service life and efficiency are at first sight attractive options, e.g. [22], but it is not clear whether they would be achievable without increasing the current life cycle environmental burden, as is supposed in available studies, e.g. [22].

## 5. Conclusion

Though environmental improvement has been claimed for the application of nanotechnology to solar cells [1–5], several characteristics of the nanoparticulate solar cells considered here are not conducive to such improvement (see also Table 1). These include relatively high inputs of energy and materials in the production of nanoparticles, a relatively low solar radiation to electricity efficiency, a relatively short service life, the need for enveloping materials to limit the intrusion of H<sub>2</sub>O and O<sub>2</sub>, the use of relatively scarce natural resources and/or relatively poor recyclability if compared with mcSi solar cells. Also, missing data and the inability to handle nanoparticle hazard generate problems for proper comparative life cycle assessment of nanoparticulate cells. So far, the claimed environmental advantage of the nanoparticulate solar cells considered here can not be substantiated. If one aims at environmental improvement of nanoparticulate solar cells, the relatively high inputs of energy and materials in the production of nanoparticles, the overall life cycle inputs of materials, the relatively low solar radiation to electricity conversion, the relatively short service life and the use of more abundant natural resources and/or improved recyclability are objects for improved process and product design. However, in actual development work there seems to be no focus on achieving (net) environmental improvement. This is at variance with the attention to environmental improvement in the development of other types of solar cells, e.g. [20,39,49].

## Acknowledgement

The comments of reviewers are gratefully acknowledged.

## References

- [1] Hart SL, Milstein MB. Creating sustainable value. *Academy of Management Executive* 2003;17:56–67.
- [2] Lin-Easton PC. It's time for environmentalists to think small. *The Georgetown International Environmental Law Review* 2002;14:107–33.
- [3] Zach M, Hägglund C, Chakarov D, Kasemo B. Nanoscience and nanotechnology for advanced energy systems. *Current Opinion in Solid State and Materials Science* 2006;10:132–43.
- [4] Rickerby DG, Morrison M. Nanotechnology and the environment: a European perspective. *Science and Technology of Advanced Materials* 2007;8:19–24.
- [5] Serrano E, Rus G, Garcia-Martinez J. Nanotechnology for sustainable energy. *Renewable and Sustainable Energy Reviews* 2009;13:2373–84.
- [6] Raugei M, Frankl P. Life cycle impacts and costs of photovoltaic systems: current state of the art and future outlooks. *Energy* 2009;34:392–9.
- [7] Tipnis R, Bernkopf J, Jia S, Krieg J, Li S, Storch M, et al. Large-area organic photovoltaic module- fabrication and performance. *Solar Energy Materials & Solar Cells* 2009;93:442–6.
- [8] Wadia C, Alivisatos AP, Kammen DM. Materials availability expands the opportunity for large-scale photovoltaics deployment. *Environmental Science & Technology* 2009;43:2072–7.
- [9] LiGui L, GuangHao LU, XiaoNiu Y, Enle Z. Progress in polymer cells. *Chinese Science Bulletin* 2007;52:145–58.
- [10] Chowdhury A, Mukhopadhyay S, Ray S. Fabrication of thin film nanocrystalline silicon solar cell with low light-induced degradation. *Solar Energy Materials & Solar Cells* 2009.
- [11] Saunders BR, Turner ML. Nanoparticle-polymer photovoltaic cells. *Advances in Colloid and Interface Science* 2008;138:1–23.
- [12] Greijer H, Karlson L, Lindquist S, Hagfeldt A. Environmental aspects of electricity generation from a nanocrystalline sensitized solar cell system. *Renewable Energy* 2001;23:27–39.
- [13] Meyer DE, Curran MA, Gonzalez MA. An examination of existing data for the industrial manufacture and use of nanocomponents and their role in the life cycle impact of nanoproducts. *Environmental Science & Technology* 2009;43:1256–63.
- [14] Green MA, Emery K, Hishikawa Y, Warta W. Solar efficiency tables (version 33). *Progress in Photovoltaics Research and Applications* 2009;17:85–94.
- [15] Jorgensen M, Norrman K, Krebs FC. Stability/degradation of polymer solar cells. *Solar Energy Materials & Solar Cells* 2008;92:686–714.
- [16] Lee JY, Bhattacharya B, Kim YH, Jung H, Park J. Self degradation of polymer electrolyte based dye-sensitized solar cells and their remedy. *Solid State Short Communications* 2009;149:307–9.
- [17] Zimmermann B, Würfel M, Niggemann M. Longterm stability of efficient inverted P3HT: PCBM solar cells. *Solar Energy Materials & Solar Cells* 2009;93:491–6.
- [18] Kato N, Takeda Y, Highuchi K, Takeichi A, Sudo E, Tanaka H, et al. Degradation of dye-sensitized solar cell module after long-term stability test under outdoor working conditions. *Solar Energy Materials & Solar Cells* 2009;93:893–7.
- [19] Figgemeier E, Hagfeldt A. Are dye-sensitized nano-structured solar cells stable? An overview of device testing and component analyses. *International Journal of Photoenergy* 2004;6:127–40.
- [20] Mohr HJ, Meijer A, Huijbregts MAJ, Reijnders L. Environmental impact of thin-film GaInP/GaAs and multicrystalline silicon solar modules produced with solar energy. *International Journal of Life Cycle Assessment* 2009;14:225–35.
- [21] Kato T, Yoshie R, Uemiyama S, Yoshida T, Tahara K. Evaluation of CO<sub>2</sub> reduction effect of dye-sensitized solar cell by LCA. *Journal of the Japan Institute of Energy* 2007;86:978–86.
- [22] Roes AL, Alsema EA, Blok K, Patel MK. Ex-ante environmental and economic evaluation of polymer photovoltaics. *Progress in Photovoltaics Research and Applications* 2009;17:372–93.
- [23] Bauer C, Buchgeister J, Hirschner R, Poganietz WR, Schebek L, Warsen J. Towards a framework for life cycle thinking in the assessment of nanotechnology. *Journal of Cleaner Production* 2008;16:910–26.
- [24] Osterwalder N, Capello C, Hungerbühler K, Stark WJ. Energy consumption during nanoparticle production: how economic is dry synthesis? *Journal of Nanoparticle Research* 2006;8:1–9.
- [25] Tsakalacos L. Nanostructures in photovoltaics. *Materials Science and Engineering R* 2006;62:175–89.
- [26] Wen FS, Li WL, Liu Z, Wei HZ. Effect of electrode modification on organic photovoltaic devices. *Materials Chemistry and Physics* 2006;95:94–8.
- [27] Sullivan P, Jones TS. Pentacene/fullerene (C<sub>60</sub>) heterojunction solar cells: device performance and degradation mechanisms. *Organic Electronics* 2008;9:656–60.
- [28] Saunders BR, Turner ML. Nanoparticle-polymer photovoltaic cells. *Advances in Colloid and Interface Science* 2008;138:1–23.
- [29] Koster LJA, Mihailetschi VD, Blom PWM. Ultimate efficiency of polymer/fullerene bulk heterojunction solar cells. *Applied Physics Letters* 2006;88:093551.
- [30] Matsui H, Okada K, Kitamura T, Tanabe N. Thermal stability of dye sensitized solar cells with current collecting grid. *Solar Energy Materials and Solar Cells* 2009;93:1110–5.
- [31] Schrabber MC, Mühlbacher D, Koppe M, Denk P, Waldauf C, Heeger AJ, et al. Design rules for donors in bulk-heterojunction solar cells – towards 10% energy-conversion efficiency. *Advanced Materials* 2006;18:789–94.
- [32] de Freitas JN, Longo C, Nogueira AF, de Paoli M. Solar module using dye-sensitized solar cells with a polymer electrolyte. *Solar Energy Materials and Solar Cells* 2008;92:1110–4.
- [33] Krebs FC, Spangaard H. Significant improvement of polymer solar cell stability. *Chemistry of Materials* 2005;17:5235–7.
- [34] Hauch JA, Schilinsky P, Choulis SA, Childers R, Biele M, Brabec CJ. Flexible organic P3HT: PCBM bulk-heterojunction modules with more than 1 year outdoor lifetime. *Solar Energy Materials & Solar Cells* 2008;92:727–31.
- [35] Oreksi G, Wallner GM. Aging mechanisms in polymeric films for PV encapsulation. *Solar Energy* 2005;79:612–7.
- [36] Kim S, Hwang T, Lee KM. Allocation for cascade recycling system. *International Journal of Life Cycle Assessment* 1997;2:217–22.
- [37] Vogtländer JG, Brezet HC, Hendriks CJ. Allocation in recycling systems. *International Journal of Life Cycle Assessment* 2002;6:344–55.
- [38] Doi T, Tsuda I, Unagida H, Murata A, Sakuta K, Kurokawa K. Experimental study on PV module recycling with organic solvent. *Solar Energy Materials & Solar Cells* 2001;67:397–403.
- [39] de Wild-Scholten M, Alsema E. Towards cleaner solar PV. *Refocus* 2005; September/October:46–9.
- [40] Yoo J, Jeong J, Yoo K, Lee J, Kim W. Enrichment of the metallic components from waste printed circuit boards by a mechanical separation process using a stamp mill. *Waste Management* 2009;29:1132–7.
- [41] Li J, Gao S, Duan H, Liu L. Recovery of valuable materials from waste liquid crystal display panel. *Waste Management* 2009;29:2033–9.
- [42] Liu X, Tanaka M, Matsui Y. Economic evaluation of optional recycling processes for waste electronic home appliances. *Journal of Cleaner Production* 2009;17:53–60.
- [43] Kang H, Schoenung JM. Electronic waste recycling: a review of US infrastructure and technology options. *Resources, Conservation and Recycling* 2005;45:368–400.
- [44] Reijnders L. Improving resource cascading. In: Loeffe CV, editor. *Trends in conservation and recycling of resources*; 2007. p. 127–50.
- [45] Burke A, Ito S, Snaith H, Bach U, Kwiakowski J, Grätzel M. The function of a TiO<sub>2</sub> compact layer in dye-sensitized solar cells incorporating 'planar' organic dyes. *Nano Letters* 2008;8:977–81.
- [46] Murata K, Ito S. Photocurrent from photocorrosion of aluminium electrode in porphyrin/Al Schottky barrier cells. *Applied Physics Letters* 1997;71:674–6.
- [47] De Bettignies R, Leroy J, Furon M, Sentein C. Accelerated lifetime measurement of P3HT: PCBM solar cells. *Synthetic Metals* 2006;156:510–3.
- [48] Stewart M, Weidema B. A consistent framework for assessing the impacts from resource use. *International Journal of Life Cycle Assessment* 2005;10:240–7.
- [49] Ftenakis VM, Kim HC, Alsema E. Emissions from photovoltaic life cycles. *Environmental Science and Technology* 2008;42:2168–74.

- [50] Reijnders L. Hazard reduction in nanotechnology. *Journal of Industrial Ecology* 2008;12:297–306.
- [51] Kroon R, Lenes M, Hummelen JC, Blom PWM, de Boer B. Small bandgap polymers for organic solar cells. *Polymer Reviews* 2008;48:531–82.
- [52] Wang Y. Recent progress on polymer electrolytes for dye-sensitized solar cells. *Solar Energy Materials & Solar Cells* 2009;93:1167–75.
- [53] Hau SK, Yip H, Leong K, Jen AK. Spraycoating of silver nanoparticle electrodes for inverted polymer solar cells. *Organic Electronics* 2009;10:719–23.
- [54] Whittaker SG, Faustman EM. Effects of benzimidazole analogs on cultures of differentiating rodent embryonic cells. *Toxicology and Applied Pharmacology* 1992;1992(113):144–51.
- [55] Velik J, Baliharova V, Fink-Gremmels J, Bull S, Lamka J, Skalova L. Benzimidazole drugs and modulation of biotransformation enzymes. *Research in Veterinary Science* 2004;76:95–108.
- [56] Aich R, Tran-Van F, Goubard F, Beouch L, Michaleviciute A, Grazulevicius JV, et al. Hydrazon based molecular glasses for solid-state dye sensitized solar cells. *Thin Solid Films* 2008;516:7260–5.
- [57] Fredin L, Johansson EMJ, Blom T, Hedlund M, Leifer K, Rensmo H. Using a molten organic conducting material to infiltrate nanoporous semiconductor film and its use in solid state dye-sensitized solar cells. *Synthetic Metals* 2009;159:166–70.
- [58] Reijnders L. The release of TiO<sub>2</sub> and SiO<sub>2</sub> nanoparticles from nanocomposites. *Polymer Degradation and Stability* 2009;94:873–6.
- [59] Chambon S, Rivaton A, Gardette J, Firon M. Durability of MDMO-PPV and MDMO-PPV: PCBM blends under illumination in the absence of oxygen. *Solar Energy Materials & Solar Cells* 2008;92:785–92.
- [60] Statatos E, Chen Y, Dionysiou DD. Quasi-solid state dye sensitized solar cells employing nanocrystalline TiO<sub>2</sub> films made at low temperature. *Solar Energy Materials & Solar Cells* 2008;92:1358–65.
- [61] Singh PK, Kim K, Park N, Rhee H. Mesoporous nanocrystalline TiO<sub>2</sub> electrode with ionic liquid-based solid polymer electrolyte for dye-sensitized solar cell application. *Synthetic Metals* 2008;158:590–3.
- [62] Kuang D, Klein C, Ito S, Moser J, Humphry-Baker R, Evans N, et al. High-efficiency and stable mesoscopic dye-sensitized solar cells based on high molecular extinction coefficient ruthenium sensitizer and nonvolatile electrolyte. *Advanced Materials* 2007;19:1133–7.
- [63] Gamstedt H, Hagfeldt A, Kloo A. Photoelectrochemical studies of ionic liquid-containing solar cells sensitized with different polypyridyl-ruthenium complexes. *Polyhedron* 2009;28:757–62.
- [64] Arnavov S, Nechvolodova E, Lomakin S, Shchegolikin A. Photo- and thermal-oxidative stability of novel material for photovoltaics: MEH-PPV/TNF blends. *Renewable Energy* 2008;33:259–61.
- [65] Golovnin IV, Bakulin AA, Zapunidy SA, Nechvolodova EM, Paraschuk DY. Dramatic enhancement of photo-oxidation stability of a conjugated polymer in blends with organic acceptor. *Applied Physics Letters* 2008;92:243311.
- [66] Kooistra FB, Mihailetschi VD, Popescu LM, Lacraminoara M, Kronholm D, Blom PWM, et al. New C-derivative and its application in a bulk heterojunction solar cell. *Chemistry of Materials* 2006;18:3068–73.
- [67] Liu JP, Wang SS, Bian ZQ, Shan MN, Huang CH. Inverted photovoltaic device based on ZnO and organic small molecule heterojunction. *Chemical Physics Letters* 2009;470:103–6.