

# Fast thermal *cis-trans* isomerization of heterocyclic azo dyes in PMMA polymers

Paulo J. Coelho<sup>a,\*</sup>, Céu M. Sousa<sup>a</sup>, M. Cidália R. Castro<sup>b</sup>, A. Maurício C. Fonseca<sup>b</sup>, M. Manuela M. Raposo<sup>b</sup>

<sup>a</sup> Centro de Química-Vila Real, Universidade de Trás-os-Montes e Alto Douro, 5001-801 Vila Real, Portugal.

<sup>b</sup> Centro de Química, Universidade do Minho, Campus de Gualtar, 4710-057 Braga, Portugal.

## Abstract

A series of heterocyclic azo dyes were dispersed in poly(methyl methacrylate) (PMMA) matrix and the photochromic properties of the coloured films studied by UV-Vis spectroscopy. Visible irradiation of the coloured films lead to a fast decrease in the colour intensity due to the *trans-cis* photoisomerization reaction. When the light source was removed the spontaneous thermal *cis-trans* reverse isomerization occurred bringing the absorbance back to initial value with variable speed. Contrary to common azobenzenes that after photoisomerization with UV or visible light exhibit very slow thermal *cis-trans* back re-isomerization, that can last for hours or days, azo dyes bearing pyrrole, thiophene, thiazole or thiadiazole heterocycles display very fast switching between the two isomers (few seconds) even when dispersed in PMMA polymers.

**Keywords:** Heterocyclic azo dyes, optical switching, thermal *cis-trans* isomerization, PMMA, molecular switches.

---

\* Corresponding author Tel.: +351 259 350284; Fax: +351 259 350480; e-mail address: pcoelho@utad.pt

## 1. Introduction

Aromatic azo compounds are a dominant class of synthetic dyes. Through the use of appropriate substituents a wide range of highly chemically stable molecules that displays intense and tuneable colours have been produced and exploited in materials science [1-4]. These compounds exist preferentially in the *trans* form but can be photochemically converted into the *cis* form, without any bond breaking, leading to a rearrangement of the electronic structure and therefore to a noticeable change in the absorption spectra [5].

The thermally more stable *trans* isomer of the unsubstituted azobenzene is planar allowing an extension of the  $\pi$ -electronic system between the two aromatic rings. It displays an high-intensity band ( $\pi$ - $\pi^*$ ) in the ultraviolet region (ca. 320 nm) and a weaker broad-band at 450 nm ( $n$ - $\pi^*$  transition) that is responsible for the yellow colouration. When irradiated with UV light the *trans* isomer is converted into the *cis* that has an out-of-plane configuration of the aromatic groups attached to the azo group. In this species, the  $\pi$ - $\pi^*$  band shifts to shorter wavelengths while there is an increase in the strength of the  $n$ - $\pi^*$  transition at 450 nm. As a result the *trans-cis* photoisomerization leads to colour intensification [5].

Substitution at the *para* position with strongly donating groups such as dimethylamino, shifts the main absorption band into the visible spectrum causing an overlap with the  $n$ - $\pi^*$  band and originating strong chromophoric systems. Since the *cis* isomer absorbs at lower wavelength (50 to 70 nm) the visible irradiation of a coloured solution of these dyes is accompanied by a noticeable decrease in the colour intensity [1].

Azobenzene belong to T-type photochromic systems, which means that when the irradiation source is removed the colour intensity increases again due to the spontaneous thermal *cis-trans* isomerization reaction that follows a first-order kinetic process (Fig. 1). So these molecular switches can be shifted between two different states by the simple application of an external light input, followed by a natural return to the starting point. Since the *trans-cis* isomerization is free from side reactions, the use of light as the external stimuli for these molecular switches allows an easy, clean, quick and remote control of the system using simple devices [6-9].

As the N=N isomerization is photochemically and thermally reversible, the UV-Vis irradiation of these dyes, at the maximum wavelength of the *trans* isomer, leads after some time to a photostationary state constituted by a mixture of *trans* and *cis* forms (Fig. 1). The ratio between the two isomers depends on the light intensity, on the rates of the isomerization reaction, the quantum yields of the photochemical reactions and on the extinction coefficients of each isomer. Considering a small absorption of the *cis* isomer at the maximum wavelength of the *trans* isomer, the percentage of the *cis* isomer present at the photostationary equilibrium can be estimated by the decrease in the absorbance at this wavelength. A 30% decrease in the absorbance indicates that nearly 30% of the *trans* isomer was converted to the *cis* [10].

**Fig. 1.** Photochemical discoloration and thermal colouration processes

Although the photoinduced *trans-cis* isomerization reaction is quite fast, depending essentially on the power of the light source, the thermal reconversion into the *trans* form is much more slower being the rate determining step of the *trans-cis-trans* process. The main factor affecting the thermal relaxation rate of the *cis*-isomer and therefore the response time of these molecular switches is the molecular structure of the system [1,11-13].

The lifetime of the *cis* form of azo benzene derivatives, in solution, is usually very high, from several hours to a few days, although the introduction of electron donating or electron withdrawing groups in the azobenzene structure leads clearly to a faster thermal reconversion. This effect is enhanced when both electron donating and electron withdrawing groups are present in the 4 and 4' positions (push/pull system). For example, the lifetime of the *cis* isomer of 4-nitro-4'-methoxyazobenzene in solution was found to be 22 min [1,5].

The introduction of hydroxyl groups in the azobenzene structure has a dramatic effect on the thermal stability of the *cis* isomer in particular in protic solvents like ethanol. For instance, the *cis* isomer of *p*-hydroxyazobenzene displays a thermal relaxation time of 31 min in toluene solution, but its lifetime in ethanol is just 0.2 s.<sup>14</sup> The increase of the thermal isomerization kinetic rate seems to be associated with the formation of hydrogen bonding between the azo group and/or the hydroxyl group and the solvent that favours a hydrazone-like electronic distribution with a simple N-N bond which facilitates the rotation to the more stable *trans* isomer [15]. This effect is particularly important in *ortho*-substituted azophenols that show very low *cis* relaxation times due to the formation of intramolecular hydrogen bonding between the OH and the azo group, even in apolar solvents like toluene. For example the lifetime of the *cis*-2-hydroxy-5-methylazobenzene in toluene is just 0.65 s.<sup>1</sup>

Azobenzenes are robust molecules that can be easily incorporated into a wide variety of materials. The azo chromophores can be incorporated into polymers by covalent linking or they can be simply dispersed on the polymer matrix [16-18]. Both amorphous and liquid-crystalline systems have been extensively studied [19-23]. Recent applications tend to exploit the reversible geometrical and electronic modifications that occur during the switching between the two isomers (for example, the dipole moment changes from 0.5 D in the planar *trans* form, to 3 D in the *cis* isomer). The incorporation of azobenzene derivatives in polymers led, for example, to a series of new materials that exhibit birefringence properties [24-26]. When irradiated with polarized light a re-orientation of the azo groups occurs, leading to a change in the refractive index of the material. Similarly, the change in the shape of the azobenzene molecule during the photoisomerization has been used to create materials that show macroscopic mechanical deformations upon light irradiation [27-31].

Although this system is perfectly reversible and thousands of irradiation cycles can be consecutively perform without significant degradation, the lifetime of the *cis* form of azobenzene derivatives is usually very high (several

hours/days) and therefore the return to the more stable *trans* isomer is normally incredibly slow [32]. Only through the introduction of specific substituents in the azobenzene structure, it is possible to obtain compounds exhibiting fast isomerization rates at room temperature. Therefore getting simple and fast molecular switches is still a challenge.

Most of the azo chromophores known belong to the azobenzene class which includes compounds with two phenyl rings linked through an azo-bridge. However, the studies on the optical switching of these compounds include usually only one compound per publication. There are few reports where a variety of azo compounds are studied in the same conditions and none of them include heterocyclic azo dyes [1,33-37]. These type of compounds have only recently been the subject of an extensive study [38-43]. Besides their classic applications as synthetic dyes and pigments, heteroaryl diazo chromophores containing five-membered aromatic heterocycles, exhibit second-order nonlinear optical (NLO) [44-45] as well as photochromic properties. We have shown that, donor-acceptor substituted azo dyes possessing heteroaromatic rings like pyrrole, thiophene, thiazole, benzothiazole and thiadiazole display photochromic properties in solution [10, 45-48]. Visible irradiation of these dyes leads to a significant decrease in the colour intensity due to the *trans-cis* photoisomerization and after removal of the illumination a fast thermal process leading to the *trans* form is observed. The kinetic rate of the thermal back-reaction is dependent on the structure of the heterocycle but usually is in the range 0.01 to 1.6 s<sup>-1</sup>. This means that a complete *trans-cis-trans* cycle can be performed in 1 to 100 s. In this paper we show that the switching between the two isomers of a series of heteroaromatic azo dyes dispersed in PMMA polymers can also be performed in few seconds, at room temperature, with a noticeable change in the colour intensity of the material.

## 2. Experimental

### 2.1. Preparation of the films

The heteroaromatic azo dyes presenting pyrrole, thiophene, thiazole, benzothiazole and thiadiazole rings were prepared according to published methods [45, 49-53]. The poly(methyl methacrylate) used for this study (Alfa Aesar) has an average molecular weight of 550.000.

A mixture of poly(methyl methacrylate) (1.0 g) in CH<sub>2</sub>Cl<sub>2</sub> (10 mL) was heated at 60 °C with occasional stirring with a glass rod for 20 min after which a transparent solution was obtained. A solution of the azo compound (1.0 mg) in CH<sub>2</sub>Cl<sub>2</sub> (2.0 mL) was then added to the PMMA solution and after stirring for 2 min the polymer solution was transferred into a Petri dish and kept at room temperature for 6 days during which the solvent evaporated and a coloured transparent and detachable thin film of the polymer was formed. The round films (9 cm diameter) display a mass around 1.0 g with a 0.1% weight percentage of the dye. The films thickness were measured with a digital Vernier Caliper and found to be between 0.05 and 0.10 mm. Fig. 2 shows a PMMA thin film doped with heterocyclic azo dye 7.

**Fig. 2.** Photographs of a PMMA thin film doped with heterocyclic azo dye 7.

## 2.2. Photochromic measurements

The photochromic properties of the materials were studied by UV–Vis using a CARY 50 Varian spectrophotometer equipped with a 50 W Ozone free Xenon lamp (6255 Oriel Instruments). The light from the UV lamp was filtered using water (61945 Oriel Instruments) and a long-pass filter (Schott GG 420,  $\lambda > 420$  nm) filters and then carried to the spectrophotometer holder at the right angle to the monitoring beam using an optical fiber system. Sample films were cut (approximately  $3 \times 1$  cm<sup>2</sup>) and introduced in the thermostated (20 °C) spectrometer holder establishing a 45° angle with the monitoring and irradiating beams. In a preliminary experiment, the visible  $\lambda_{\text{max}}$  of the material was determined and then the absorbance at the  $\lambda_{\text{max}}$  was measured while performing visible light irradiation/dark cycles.

## 3. Results and discussion

The heteroaromatic azo dyes presented in this study can be divided in 3 groups according to the nature of the aromatic ring linked to the diazene moiety. Compounds **1** and **2** are thienylpyrrole azo dyes linked to a phenyl ring and possessing propyl or *p*-methoxyphenyl groups linked to the pyrrole ring. Compounds **3-5** are thienylpyrrole azo dyes linked to thiazole or benzothiazole heterocycles, through positions 2 or 6, and possessing propyl or *p*-fluorophenyl groups in the nitrogen atom of the pyrrole. Compounds **6** and **7** are bithiophene azo dyes linked to substituted thiadiazole or phenyl groups (Scheme 1).

**Scheme 1.** Structure of the heteroaromatic azo dyes **1-7** with a *trans* configuration.

The PMMA thin films of these compounds were all deeply coloured (orange to pink) with a maximum absorption band of the stable *trans* form between 422 and 516 nm (Table 1).

These values are in accordance with those observed for these dyes in acetone solutions. A strong bathochromic shift of the  $\lambda_{\text{max}}$  was observed for thienylpyrrole **2** substituted with a *p*-nitrophenyl group (500 nm) when compared to the thienylpyrrole **1** with a phenyl group (422 nm). The substitution of the phenyl ring by a thiazole group (**3**) or benzothiazole (**4-5**) led also to a strong bathochromic shift of the  $\lambda_{\text{max}}$  especially when the benzothiazole ring (**5**) is linked through the 2-position ( $\Delta\lambda = 86$  nm).

Visible light irradiation of PMMA thin films of these compounds led to a decrease of the absorption at the  $\lambda_{\max}$  (13-54%) reaching a photostationary state after less than 30 s of irradiation. At the same time, an increase in the band located near 400 nm, which can be attributed to the formation of *cis* isomer (Fig. 3), was observed. This means that the irradiation leads only to a partial conversion of the *trans* isomer into the *cis* and therefore at the photostationary equilibrium both isomers are still present. When the light source was removed the absorption increased, with variable speed, to the initial value (Fig. 4). Although in solution a first order mono-exponential equation perfectly fits the colouration curve, for all these compounds dispersed in PMMA there is a deviation from the mono-exponential behaviour: a plot of  $\ln(A_{\infty}-A(t))$  as a function of time is not linear (Fig. 5). The system exhibits an anomalous fast component in the first seconds that is responsible for most of the colouration and a slower component (around 10 times slower) that leads to a slow return to the initial absorbance. The thermal colouration curves were found to fit better to a bi-exponential equation that considers the time evolution of two components with different kinetics rates:

$$A(t) = A_1 e^{-k_1 t} + A_2 e^{-k_2 t} + A_{\max}$$

where  $A(t)$  is the absorbance at  $\lambda_{\max}$  at any instant  $t$ ,  $A_1$  and  $A_2$  are proportional factors,  $k_1$  and  $k_2$  two thermal colouration rates and  $A_{\max}$  the absorbance in the dark when time approaches infinity. This behaviour is related with the lack of homogeneity of the polymeric structure which has different chemical environments where the photochromic molecule can operate. As a result, some molecules, in the same polymer, exhibit faster relaxation than others. This behaviour can, however, be fitted to a bi-exponential model comprising a fast and a slow component.

**Fig. 3.** UV-Vis Absorption spectra of azo dye **7** in PMMA, before (—) and after (----) visible light irradiation.

**Fig. 4.** Visible irradiation/dark cycles for azo dye **7** in PMMA.

**Fig. 5.** Plot of  $\ln(A_{\infty}-A(t))$  vs  $t$  for the thermal isomerization of azo dye **7**.

The visible irradiation/dark cycles can be repeated several times and the behaviour of the materials was fully reproducible indicating that under these experimental conditions no significant degradation was observed (Fig. 4). Since the colouration processes is described best by two different rate constants, the half-time life of the *cis* isomer varies in time being lower in the beginning. Nevertheless, for comparison purposes the time for the colouration regain half of the value loss upon irradiation was calculated for each compound. The results are presented in Table 1.

Table 1

For all these azo dyes the absorption decrease under visible light was very fast and after less than 30 s an equilibrium between the *trans* and *cis* isomers was attended corresponding to a loss of 13-54% of the initial colouration. On the contrary, the rate of the thermal back *cis-trans* isomerization depends quite significantly on the structure of the heteroaromatic azo dye.

Thienylpyrrole azo dye **1** with a phenyl group attached to the azo function shows a very slow *cis-trans* isomerization with a long relaxation time for the *cis* isomer ( $t_{1/2} = 20$  min) (Fig. 6). The introduction of a nitro substituent on the *para* position of the phenyl group (azo dye **2**) leads, as expected, to a strong increase of the thermal *cis-trans* kinetic rate with an initial half-time life of the *cis* isomer around 33 s, which means that, for this compound, it takes around 10 minutes for the system to return to the initial composition. The substitution of the nitrophenyl group by a thiazole heterocycle has a dramatic effect on the speed of the *cis-trans* isomerization. For azo dye **3**, the switching between the *trans* and *cis* isomers can be performed in few seconds with a noteworthy change in the visible absorption of the material: in 4 s the colour intensity decreases 17% upon visible irradiation and returns to the initial value in about 1 min (Fig. 7).

**Fig. 6.** Visible irradiation/dark cycle for the thienylpyrrole azo dye **1** in PMMA.

**Fig. 7.** Visible irradiation/dark cycles for the thienylpyrrole azo thiazole dye **3** in PMMA.

The effect of the electronic nature of the aromatic ring linked to the azo function can also be seen comparing azo dyes **3**, **4** and **5**. Benzothiazole azo dye **4**, where the electron-deficient benzothiazole is linked to the azo group through the 2-position displays similar behaviour as azo thiazole **3**, characterized by a fast switching speed; after 2 s of visible irradiation the system reaches a photostationary equilibrium and the thermal back isomerization occurs in 20 s (Fig 8). However, when the linkage is made through the 6-position of the benzothiazole the compound resembles the phenyl azo dye **1** and display a very slow thermal back reaction with a relaxation time of the *cis* isomer around 13 min.

**Fig. 8.** Visible irradiation/dark cycles for the thienylpyrrole azo benzothiazole dye **4** in PMMA.

Bithiophene azo dyes exhibit a analogous behaviour: azo dye **6** with *p*-nitrophenyl group attached to the azo function present a rather high thermal stability of the *cis*-isomer ( $t_{1/2} = 13.4$  s), nevertheless, the substitution of the

phenyl group by a thiadiazole (azo dye **7**) increased the switching rate and for the later compound, after visible irradiation, the systems returns to the initial state in around 1 min.

The photochromic behaviour exhibited by this set of heteroaromatic azo dyes dispersed in PMMA polymer is similar to the one previously observed in acetone solutions.<sup>44-47</sup> Due to the presence of a slow decay component, not observed in solution, the kinetics of the *cis-trans* isomerization in PMMA polymers is globally slower. However, for azo dyes **3-4**, **6-7**, where the slow decay component is less significant (19-28%), the initial half-life time, which is affected mainly by the fast decay component, is very similar to that observed in solution (ex: compound **3**  $t_{1/2}$  (sol)=0.8 s,  $t_{1/2}$  (PMMA)=1.3 s; compound **6**  $t_{1/2}$  (sol)=18 s,  $t_{1/2}$  (PMMA)=13 s). For these materials the switching between both isomers can be performed in few seconds.

#### 4. Conclusion

PMMA thin films doped with heterocyclic azo dyes showed photochromic properties. Visible irradiation of these coloured films lead to a fast decrease in the colour intensity due to the *trans-cis* photoisomerization reaction. When placed in the dark the spontaneous thermal *cis-trans* reverse isomerization occurred bringing the absorbance back to initial value with variable speed depending on the structure of the heterocyclic azo dyes. Thiazole, benzothiazole and thiadiazole azo dyes **3**, **4** and **7** linked to thienylpyrrole or bithiophene systems showed the fastest response to the light stimulus allowing to perform fully reproducible decoloration/colouration cycles in few seconds. The behaviour of these heteroaromatic azo dyes contrasts with common azobenzene derivatives that show usually very slow thermal *cis-trans* isomerization, which makes them much more attractive for application as molecular switches.



## Acknowledgments

Thanks are due to the *Fundação para a Ciência e Tecnologia* (Portugal) and FEDER-COMPETE for financial support through the Centro de Química - Universidade do Minho, Projects PTDC/QUI/66251/2006 (FCOMP-01-0124-FEDER-007429), PEst-C/QUI/UI0686/2011 (F-COMP-01-0124-FEDER-022716) and a PhD grant to M. C. R. Castro (SFRH/BD/78037/2011). The NMR spectrometer Bruker Avance III 400 is part of the National NMR Network and was purchased within the framework of the National Program for Scientific Re-equipment, contract REDE/1517/RMN/2005 with funds from POCI 2010 (FEDER) and FCT.

## References

- [1] J. Garcia-Amoros, D. Velasco, *Beilstein J. Org. Chem.* 8 (2012) 1003.
- [2] S. K. Yesodha, C. K. S. Pillai, N. Tsutsumi, *Prog. Polym. Sci.* 29 (2004) 45.
- [3] O. Kulikovska, L. M. Goldenberg, *J. Stumpe, J. Chem. Mat.* 19 (2007) 3343.
- [4] F. Ercole, T. P. Davis, R. A. Evans, *Polym. Chem.* 1 (2010) 37–54
- [5] D. L. Ross, J. Blanc, in: G.H. Brown (ed), *Photochromism*, Wiley-Interscience, New York, 1971, pp 471– 556.
- [6] G. S. Kumar, D. C. Neckers, *Chem. Rev.* 89 (1989) 1915.
- [7] L. Kulikovsky, O. Kulikovska, L. M. Goldenberg, J. Stumpe, *ACS Appl. Mater. Interfaces* 1 (1995) 1739.
- [8] T. Ide, Y. Ozama, K. Matsui, *J. Non-Cryst. Solids* 357 (2011) 100.
- [9] O. Kulikovska, L. M. Goldenberg, J. Stumpe, *J. Chem. Mat.* 19 (2007) 3343.
- [10] P. J. Coelho, L. M. Carvalho, A. M. C. Fonseca, M. M. M. Raposo, *Tetrahedron Lett.* 47 (2006) 3711.
- [11] U. Georgi, P. Reichenbach, U. Oertel, L. M. Eng, B. Voit, *React. Funct. Polym.* 72 (2012) 242.
- [12] A. A. Beharry, O. Sadoyski, G. A. Woolley, *J. Am. Chem. Soc.* 133 (2011) 19684.
- [13] N. A. Wazzan, P. R. Richardson, A. C. Jones, *Photochem. Photobiol. Sci.* 9 (2010) 968.
- [14] M. Emond, T. Le Saux, S. Maurin, J. B. Baudin, R. Plasson, L. Jullien, *Chem. Eur. J.* 16 (2010) 8822.
- [15] M. Kojima, S. Nebashi, K. Ogawa, N. Kurita, *J. Phys. Org. Chem.* 18 (2005) 994.
- [16] F. D. Jochum, L. zur Borg, P. J. Roth, P. Theato, *Macromolecules* 42 (2009) 7854.
- [17] H. El Ouazzani, K. Iliopoulos, M. Pranaitis, O. Krupka, V. Smokal, A. Kolendo, B. Sahraoui, *J. Phys. Chem. B* 115 (2011) 1944.
- [18] M.C. Larciprete, D. Dini, R. Ostuni, C. Sibilìa, M. Bertolotti, X. Alvarez-Mico, R. Gomez-Bombarelli, M. Cappeddu, M. Scalora, M.J. Bloemer, *J. Mater. Sci.* 42 (2007) 7866.
- [19] X. Q. Zhang., C. S. Wang, X. M. Lu, Y. Zeng, *Optik* 123 (2012) 26.
- [20] S. Freiberg, F. Lagugne-Labarthe, P. Rochon, A. Natansohn, *Macromolecules* 36 (2003) 2680.

- [21] D. Rais, Y. Zakrevskyy, J. Stumpe, S. Nespurek, Z. Sedlakova, *Opt. Mater.* 30 (2008) 1335.
- [22] J. Garcia-Amoros, H. Finkelmann, D. Velasco, *Chem. Eur. J.* 17 (2011) 6518.
- [23] J. Garcia-Amoros, M. Martinez, H. Finkelmann, D. Velasco, *J. Phys. Chem. B* 114 (2010) 1287.
- [24] L. M. Saiz, A. B. Orofino, M. M. Ruzzo, G. F. Arenas, P. A. Oyanguren, M. J. Galante, *Polym. Int.* 60 (2011) 1053.
- [25] C. R. Mendonca, L. Misoguti, A. A. rade, S. B. Yamaki, V. D. Dias, T. D. Z. Atvars, O. N. Oliveira, *Opt. Mater.* 30 (2007) 216.
- [26] M. Jin, Q. X. Yang, R. Lu, L. Y. Pan, P. C. Xuea, Y. Y. Zhao, *Opt. Mater.* 24 (2003) 445.
- [27] C. J. Barrett, J. I. Mamiya, K. G. Yager, T. Ikeda, *Soft Matter* 3 (2007) 1249.
- [28] A. Natansohn, P. Rochon. *Adv. Mater.* 11 (1999) 1387.
- [29] J. P. Abid, M. Frigoli, R. Pansu, J. Szeftel, J. Zyss, C. Larpent, S. Brasselet, *Langmuir* 27 (2011) 7967.
- [30] H. Koshima, N. Ojima, H. Uchimoto, *J. Am. Chem. Soc.* 131 (2009) 6890.
- [31] D. Bublitz, M. Helgert, B. Fleck, L. Wenke, S. Hvilsted, P. S. Ramanujam, *Appl. Phys. B-Lasers. Opt.* 70 (2000) 863.
- [32] C. Barrett, A. Natansohn, P. Rochon, *Chem. Mat.* 7 (1995) 899.
- [33] M. Kamruzzaman, Y. Kuwahara, T. Ogata, S. Ujiie, S. Kurihara, *Polym. Int.* 60 (2011) 730.
- [34] D. G. Whitten, P. D. Wildes, J. G. Pacifici, G. Irick, *J. Am. Chem. Soc.* 93 (1971) 2004.
- [35] H. Rau, *J. Photochem. Photobiol. A.* 42 (1988) 321.
- [36] N. J. Bunce, G. Gerguson, C. L. Forber, G. J. Stachnyk, *J. Org. Chem.* 52 (1987) 394.
- [37] J. Dokic, M. Gothe, J. Wirth, M. V. Peters, J. Schwarz, S. Hecht, P. Saalfrank, *J. Phys. Chem. A.* 113 (2009) 6763.
- [38] S. Kucharski, R. Janik, H. Motschmann, C. Raduge, *New J. Chem.* 23 (1999) 765.
- [39] G. Wang, F. Gan, J. Wang, L. Yang, Z. Xu, *J. Phys. Chem. Solids* 63 (2002) 501
- [40] E. Brown, G. Granneman, *J. Am. Chem. Soc.* 97 (1975) 621.
- [41] V. A. Barachevsky, A. M. F. Oliveira-Campos, L. V. Stebunova, L. V. Chudinova, V. G. Avakyan, I. A. Maslyanitsyn, V. D. Shigorin, *Zh Nauchii Prikladnoi Fotografii* 47 (2002) 4.
- [42] J. Otsuki, K. Suwa, K. Narutaki, C. Sinha, I. Yoshikawa, K. Araki, *J. Phys. Chem. A.* 109 (2005) 8064.
- [43] L. Yang, G. Wang, J. Wang, G. Wang, Z. Xu, *Optik* 113 (2002) 189.
- [44] M. M. M. Raposo, M. C. R. Castro, M. Belsley, A. M. C. Fonseca, *Dyes Pigments* 91 (2011) 454.
- [45] M. M. M. Raposo, A. M. C. Fonseca, M. C. R. Castro, M. Belsley, M. F. S. Cardoso, L. M. Carvalho, P. J. Coelho, *Dyes Pigments* 91 (2011) 62.
- [46] P. J. Coelho, L. M. Carvalho, J. C. V. P. Moura, M. M. M. Raposo, *Dyes Pigments* 82 (2009) 130.
- [47] P. J. Coelho, M. C. R. Castro, A. M. C. Fonseca, M. M. M. Raposo, *Dyes Pigments* 92 (2012) 745.

- [48] P. J. Coelho, M. C. R. Castro, S. S. M. Fernandes, A. M. C. Fonseca, M. M. M. Raposo, *Tetrahedron Lett.* 53 (2012) 4502.
- [49] M. M. M. Raposo, A.M.R.C. Sousa, A. M. C. Fonseca, G. Kirsch, *Tetrahedron* 61 (2005) 8249-8256.
- [50] M. M. M. Raposo, A. M. F. P. Ferreira, M. Belsley, J. C. V. P. Moura, *Tetrahedron* 64 (2008) 5878-5884.
- [51] MMM Raposo, AMFP Ferreira, MMF Pereira, M Belsley, JCVF Moura *Dyes Pigments* 83 (2009) 59.
- [52] M. M. M. Raposo, M. C. R. Castro, P. Schellenberg, A. M. C. Fonseca, M. Belsley, *Tetrahedron* 67 (2011) 5189-5198.
- [53] M. C. R. Castro, P. Schellenberg, M. Belsley, A. M. C. Fonseca, S. S. M. Fernandes, M. M. M. Raposo, *Dyes Pigments* 95 (2012) 392-399.