

# COMPARING THE PERFORMANCE OF DIFFERENT THERMOPLASTIC MATRIX PRE-IMPREGNATED MATERIALS

M. S. Santos<sup>1</sup>, J. P. Nunes<sup>2</sup>, J. F. Silva<sup>3</sup>, P.J Novo<sup>4</sup> and A. T. Marques<sup>5</sup>

<sup>1</sup> Department of Polymer Engineering, Minho University, 4800-058 Guimaraes, Portugal

<sup>2</sup> Institute of Polymers and Composites/I3N, Minho University, 4800-058 Guimaraes, Portugal

<sup>3</sup> Dep. of mechanical Engineering ISEP, 4200-072 Porto, Portugal

<sup>4</sup> School of Tech. and Management, Polytechnic Institute of Leiria, 2411-901 Leiria, Portugal

<sup>5</sup> DEMEGI / FEUP, 4200-465 Porto, Portugal

\* Corresponding author ([jpn@dep.uminho.pt](mailto:jpn@dep.uminho.pt))

## Abstract

The aim of the present work is comparing the performance of different available thermoplastic pre-impregnated raw-materials produced by different methods.

In the last years, thermoplastic replaced with success thermosetting as matrices of long/continuous fiber reinforced composites due to the numerous advantages they present. However, it remains a challenge developing technologies to wet and impregnate fibers with thermoplastic matrices, characterized for being much more viscous than thermosets [1, 2].

Today, two major technologies are being used to wet reinforcing fibers with thermoplastic polymers [1, 2]: i) the direct melting of the polymer and, ii) the intimate fiber/matrix contact prior to final composite fabrication. Continuous fiber reinforced thermoplastic matrix pre-impregnated tapes are, for example, produced by direct melting processes. Alternatively, intimate contact processes allow producing cheap and promising pre-impregnated materials, such as, commingled fibers, co-woven fabrics and towpregs.

This work studies and compares the processability into final composite parts of three different pre-impregnated materials, produced by both of the above mentioned wetting techniques,. All studied pre-impregnated materials were based on a continuous glass fibers reinforced polypropylene matrix (GF/PP) system. One is a tape produced in a previous work [3] by the melting process (cross-head extrusion) and, from the other two produced by fiber/matrix intimate contact methods, one is a commercial available commingled fibers product and the other a towpreg produced by our own developed dry coating prototype line [4]. Pultrusion and compression molding were the manufacturing methods selected to process all the pre-impregnated materials into final composite parts.

The performance of the three studied GF/PP pre-impregnated materials was assessed by comparing final properties of the manufactured composite parts submitted to mechanical testing and microscopy analysis.

## Acknowledgements

The authors wish to thank the Engineering School of the University of Minho, PIEP – Pole for Innovation in Polymer Engineering and the School of Engineering of the Polytechnic of Porto, for the support given to this work. They also acknowledge the Portuguese Foundation for Science and Technology for the financial support of IPC through project PEst-C/CTM/LA0025/2013 (Strategic Project - LA 25 - 2013-2014).

## References

- [1] Gibson, A. G., Manson, J. A. “Impregnation technology for thermoplastic matrix composites”, *Comp. Manufacturing*, Vol 3 (4), pp. 223-233, 1992.
- [2] Bechtold G., Wiedmer S., Friedrich K. Pultrusion of Thermoplastic Composites – New Developments and Modelling Studies, *Journal of Thermoplastic Composite Materials*, Vol. 15, pp. 443-465, 2002
- [3] Novo, P. J., Silva, J. F., Nunes, J. P., van Hattum, F. W. J., Marques, A. T., “Development of a new pultrusion equipment to manufacture thermoplastic matrix composite profiles”, 15th European Conf. on Composite Materials – ECCM 15, June 24-28, Venice, Italy, 2012.
- [4] R. F. Silva, J. F. Silva, J. P. Nunes, C. A. Bernardo and A. T. Marques. “New Powder Coating Equipment to Produce Continuous Fibre Thermoplastic Matrix Towpregs”. *Materials Science Fórum*, Vol. 587-588, pp. 246-250, 2008.