

DOI: [10.29026/oea.2023.230022](https://doi.org/10.29026/oea.2023.230022)

High-performance warm white LED based on thermally stable all inorganic perovskite quantum dots

Jr-Hau He*

All inorganic CsPbBr₃ quantum dots (QDs) are regarded as excellent candidates for next-generation emitters due to their high photoluminescence quantum yield (PLQY) and defect tolerance. However, the poor stability and degraded luminescent performance may impede their further commercialization because of the separation of conventional ligands from the QDs surfaces. Recently, Zang replaced the regular oleic acid with 2-hexyl-decanoic acid (DA), which possesses higher binding energy on the QDs surfaces, to act as ligands of QDs, exhibiting PLQY of 96% and excellent stabilities against ethanol and water. WLEDs with DA-modified CsPbBr₃ QDs achieved improved thermal stability, a color rendering index of 93, a power efficiency of 64.8 lm/W and a properly correlated color temperature value of 3018 K, implying their prominent applications in solid-state lighting and displays.

He JH. High-performance warm white LED based on thermally stable all inorganic perovskite quantum dots. *Opto-Electron Adv* **6**, 230022 (2023).

It is well known that more than 20% of global electronic energy is consumed by lighting and displays every year¹, which is identified as the major challenge of reduced carbon release². Thus, it is quite urgent to develop efficient light sources to save massive amounts of electric power³. As a kind of potential solid-state light source, white light-emitting diodes (WLEDs) have received substantial attention due to their high power efficiency and eco-friendly. Conventional WLEDs' white emission originates from rare-earth phosphors excited by blue or ultraviolet LED chips⁴. However, the supply shortage of rare-earth phosphors and complex manufacturing processes hinder the large-scale and commercial applications of conventional WLEDs. In addition, their development suffers from the highly correlated color temperature (CCT) and low color rendering index (CRI), in which the cold white emission may hurt the naked eyes of hu-

mans and cause a chromatic issue. To meet the requirement of high-performance warm WLEDs, researchers pay more attention to the exploration of emitting materials with facile preparation and high PLQYs⁵.

Due to the high PLQY and low-temperature solution processability, the inorganic CsPbBr₃ perovskite quantum dots (QDs) have been regarded as the promising candidate for emitters of efficient warm WLEDs^{6,7}. Despite the rapid advances of CsPbBr₃ QDs, their commercial application in efficient warm WLEDs has been impeded, which is resulted from the poor stability of CsPbBr₃ QDs induced by the separation of conventional oleic acid (OA) ligands from the QDs surfaces. The separation of OA ligands is attributed to the weak binding between the ligands and QDs surfaces⁸. As a result, the study and design of novel ligands binding strongly to the QDs surfaces enhances the stability and luminescent

Department of Materials Science and Engineering, City University of Hong Kong, Hong Kong 999077, China.

*Correspondence: JH He, E-mail: jrhauhe@cityu.edu.hk

Received: 10 February 2023; Accepted: 28 February 2023; Published online: 8 March 2023



Open Access This article is licensed under a Creative Commons Attribution 4.0 International License.

To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2023. Published by Institute of Optics and Electronics, Chinese Academy of Sciences.

efficiency of both emitters and WLEDs.

In the recent work published in *Opto-Electronic Advances*, DOI: [10.29026/oea.2022.200075](https://doi.org/10.29026/oea.2022.200075), Prof. Zhigang Zang et al. propose a facile strategy to introduce 2-hexyl-decanoic acid (DA) ligands to replace conventional OA ones⁹. The DA ligands exhibit larger binding energy than that in OA ligands ($\Delta E = 0.202$ eV), indicating the strong binding of DA ligands to the QDs surfaces. The reduced separation of DA ligands from QDs is found to decrease surface defects, resulting in increased PLQYs of QDs up to 96% but unchanged crystal structure and PL spectra¹⁰. Further, the DA ligands binding on QDs enable to isolate the QDs from others, suppressing the interaction of QDs¹¹. Consequently, the aggregation and PL quenching of QDs are reduced, ascribed to the improved stability in solvents and enhanced luminescent performance, respectively.

The transient PL spectra and atomic force microscopy characterization can prove and clarify them. Compared with CsPbBr₃ QDs with OA ligands, the ligand-modified QDs with DA possess enhanced optoelectronic properties and stability against water and ethanol. They are employed as emitters in WLEDs¹². The authors fabricated warm WLEDs combining the green DA-CsPbBr₃ and red AgInZnS QDs with broad spectra on blue chips¹³, exhibiting a high CRI of 93, a proper CCT of 3018 K and a high power efficiency of 64.8 lm/W. This stand out among the reported WLEDs. The excellent thermal stability of operating WLEDs indicates the vital role of DA-CsPbBr₃ QDs and the prominent potentials of the fabricated WLEDs in applications of solid-state lighting and display¹⁴.

In this article, the authors focus on the critical challenge of inorganic perovskite CsPbBr₃ QDs¹⁵. The ligand

modification process is schematically shown in Fig. 1. They propose a ligand-modified strategy to solve the formidable issue of poor stability¹⁶. The DA ligands are utilized to replace the conventional OA ligands, in which the shorter lengths and di-branched chains of DA play a vital role in strong binding to the QDs surface¹⁷. As a result, the DA ligands can not only fill the surface defects of QDs but also isolate the QDs from others, enhancing the PLQY and suppressing the aggregation of QDs¹⁸. With the DA-ligand modification, the DA-CsPbBr₃ QDs exhibit excellent luminescent properties and enhanced stability against water and ethanol. The introduction of novel DA ligands is a “one stone and two birds” strategy, which can enhance the performance of CsPbBr₃ QDs directly without changing the original preparation process, crystal structures and PL spectra of QDs¹⁰. Applying the modified QDs to efficient warm WLEDs indicates the attractive role of ligand modification¹⁹. It suggests that it is a typical and effective method to promote the commercial development of inorganic perovskite quantum dots²⁰.

The authors are building on the research of Prof. Hao-Chung Kuo, Prof. Zhong Chen et al²¹. The excellent brightness, low energy consumption, and ultra-high resolution of micro-light-emitting diodes (micro-LEDs) are significant advantages²². However, the large size of traditional inorganic phosphors and the number of side defects have restricted the practical applications of small sized micro-LEDs²³. Recently, QD and non-radiative energy transfer (NRET) have been proposed to solve existing problems. QDs possess nanoscale dimensions and high luminous efficiency, and they are suitable for NRET because they are able to nearly contact the micro-LED chip²⁴. The NRET between QDs and micro-LED chip




Fig. 1 | The schematic illustration of the surface in the CsPbBr₃ QDs with ligand modification process.

further improves the color conversion efficiency (CCE) and effective quantum yield (EQY) of full-color micro-LED devices. In their review, they discussed the NRET mechanism for QD micro-LED devices, and then nano-pillar LED²⁵, nano-hole LED²⁶, and nano-ring LED in details²⁷. These structures are beneficial to the NRET between QD and micro-LED, especially nano-ring LED. Finally, the challenges and future envisions have also been described.

Display technology has gone through countless changes and penetrated every corner of our life. As a display technology, light-emitting diode (LED) has attracted attention due to its low cost, easy fabrication, and energy conservation²⁸. In 2000, the technology strategy of micro-LEDs was put forward for the first time at the Texas Tech University, which signified that LED light sources had entered the era of micro display²⁹. Compared with traditional LED screen display technologies such as mini-LED, organic-LED, etc., the micro-LEDs have the following advantages: high brightness, high luminous efficiency, low energy consumption, quick reaction, high contrast, self-illumination, long service life, ultra-high resolution, and good color saturation³⁰.

Similarly, the work of Prof. Jeongyong Kim et al³¹, supports the work of Zang et al. MXene ($M_{n+1}X_n$) is an emerging class of layered two-dimensional (2D) materials³², which are derived from their bulk-state MAX phase ($M_{n+1}AX_n$, where M: early transition metal, A: group element 13 and 14, and X: carbon and/or nitrogen)³³. MXenes have found wide-ranging applications in energy storage devices, sensors, and catalysis, owing to their high electronic conductivity and wide range of optical absorption. However, the absence of semiconducting MXenes has limited their applications related to light emission³³. Research has shown that QDs derived from MXene (MQDs) not only retain the properties of the parent MXene, but also demonstrate significant improvement on light emission and quantum yield (QY). The optical properties and photoluminescence (PL) emission mechanisms of these light-emitting MQDs have not been comprehensively investigated³⁴. Recently, work on light-emitting MQDs has shown good progress³⁵, and MQDs exhibiting multi-color PL emission along with high QY have been fabricated³⁶. The synthesis methods also play a vital role in determining the light emission properties of these MQDs³⁷. The review provided an overview of light-emitting MQDs and their synthesis methods, optical properties, and applications in

various optical, sensory, and imaging devices. The future prospects of light-emitting MQDs are also discussed to provide an insight that helps to further advance the progress on MQDs.

References

1. Sun YR, Giebink NC, Kanno H, Ma BW, Thompson ME et al. Management of singlet and triplet excitons for efficient white organic light-emitting devices. *Nature* **440**, 908–912 (2006).
2. Schreuder MA, Xiao K, Ivanov IN, Weiss SM, Rosenthal SJ. White light-emitting diodes based on Ultrasmall CdSe nanocrystal electroluminescence. *Nano Lett* **10**, 573–576 (2010).
3. Crawford MH. LEDs for solid-state lighting: performance challenges and recent advances. *IEEE J Sel Top Quantum Electron* **15**, 1028–1040 (2009).
4. Wang Y, Li XM, Song JZ, Xiao L, Zeng HB et al. All-inorganic colloidal perovskite quantum dots: a new class of lasing materials with favorable characteristics. *Adv Mater* **27**, 7101–7108 (2015).
5. Sun SB, Yuan D, Xu Y, Wang AF, Deng ZT. Ligand-mediated synthesis of shape-controlled cesium lead halide perovskite nanocrystals via reprecipitation process at room temperature. *ACS Nano* **10**, 3648–3657 (2016).
6. Li CL, Zang ZG, Chen WW, Hu ZP, Tang XS et al. Highly pure green light emission of perovskite CsPbBr₃ quantum dots and their application for green light-emitting diodes. *Opt Express* **24**, 15071–15078 (2016).
7. Lu TW, Lin XS, Guo QA, Tu CC, Liu SB et al. High-speed visible light communication based on micro-LED: A technology with wide applications in next generation communication. *Opto-Electron Sci* **1**, 220020 (2022).
8. Smock SR, Williams TJ, Brutchey RL. Quantifying the thermodynamics of ligand binding to CsPbBr₃ quantum dots. *Angew Chem Int Ed* **57**, 11711–11715 (2018).
9. Yan DD, Zhao SY, Zhang YB, Wang HX, Zang ZG. Highly efficient emission and high-CRI warm white light-emitting diodes from ligand-modified CsPbBr₃ quantum dots. *Opto-Electron Adv* **5**, 200075 (2022).
10. Brennan MC, Herr JE, Nguyen-Beck TS, Zinna J, Draguta S et al. Origin of the size-dependent Stokes shift in CsPbBr₃ perovskite nanocrystals. *J Am Chem Soc* **139**, 12201–12208 (2017).
11. Yan DD, Shi TC, Zang ZG, Zhou TW, Liu ZZ et al. Ultrastable CsPbBr₃ perovskite quantum dot and their enhanced amplified spontaneous emission by surface ligand modification. *Small* **15**, 1901173 (2019).
12. Le TH, Choi Y, Kim S, Lee U, Heo E et al. Highly elastic and >200% reversibly stretchable down-conversion white light-emitting diodes based on quantum dot gel emitters. *Adv Opt Mater* **8**, 1901972 (2020).
13. Song YH, Yoo JS, Kang BK, Choi SH, Ji EK et al. Long-term stable stacked CsPbBr₃ quantum dot films for highly efficient white light generation in LEDs. *Nanoscale* **8**, 19523–19526 (2016).
14. McKittrick J, Shea-Rohwer LE. Review: down conversion materials for solid-state lighting. *J Am Ceram Soc* **97**, 1327–1352 (2014).
15. Song JZ, Li JH, Li XM, Xu LM, Dong YH et al. Quantum dot

- light-emitting diodes based on inorganic perovskite cesium lead halides (CsPbX₃). *Adv Mater* **27**, 7162–7167 (2015).
16. Quarta D, Imran M, Capodilupo AL, Petralanda U, Van Beek B et al. Stable ligand coordination at the surface of colloidal CsPbBr₃ nanocrystals. *J Phys Chem Lett* **10**, 3715–3726 (2019).
 17. Yang DD, Li XM, Zhou WH, Zhang SL, Meng CF et al. CsPbBr₃ quantum dots 2.0: benzenesulfonic acid equivalent ligand awakens complete purification. *Adv Mater* **31**, 1900767 (2019).
 18. Almeida G, Infante I, Manna L. Resurfacing halide perovskite nanocrystals. *Science* **364**, 833–834 (2019).
 19. Krieg F, Ochsenbein ST, Yakunin S, Ten Brinck S, Aellen P et al. Colloidal CsPbX₃ (X = Cl, Br, I) nanocrystals 2.0: zwitterionic capping ligands for improved durability and stability. *ACS Energy Lett* **3**, 641–646 (2018).
 20. Pan J, Shang YQ, Yin J, De Bastiani M, Peng W et al. Bidentate ligand-passivated CsPbI₃ perovskite nanocrystals for stable near-unity photoluminescence quantum yield and efficient red light-emitting diodes. *J Am Chem Soc* **140**, 562–565 (2018).
 21. Fan XT, Wu TZ, Liu B, Zhang R, Kuo HC et al. Recent developments of quantum dot based micro-LED based on non-radiative energy transfer mechanism. *Opto-Electron Adv* **4**, 210022 (2021).
 22. Liu ZJ, Lin CH, Hyun BR, Sher CW, Lv ZJ et al. Micro-light-emitting diodes with quantum dots in display technology. *Light Sci Appl* **9**, 83 (2020).
 23. Jin SX, Li J, Li JZ, Lin JY, Jiang HX. GaN microdisk light emitting diodes. *Appl Phys Lett* **76**, 631–633 (2000).
 24. Sekiguchi H, Kishino K, Kikuchi A. Emission color control from blue to red with nanocolumn diameter of InGaN/GaN nanocolumn arrays grown on same substrate. *Appl Phys Lett* **96**, 231104 (2010).
 25. Zhang F, Liu J, You GJ, Zhang CF, Mohny SE et al. Nonradiative energy transfer between colloidal quantum dot-phosphors and nanopillar nitride LEDs. *Opt Express* **20**, A333–A339 (2012).
 26. Chanyawadee S, Lagoudakis PG, Harley RT, Charlton MDB, Talapin DV et al. Increased color-conversion efficiency in hybrid light-emitting diodes utilizing non-radiative energy transfer. *Adv Mater* **22**, 602–606 (2010).
 27. Wang SW, Hong KB, Tsai YL, Teng CH, Tzou AJ et al. Wavelength tunable InGaN/GaN nano-ring LEDs via nanosphere lithography. *Sci Rep* **7**, 42962 (2017).
 28. Pust P, Schmidt PJ, Schnick W. A revolution in lighting. *Nat Mater* **14**, 454–458 (2015).
 29. Jin SX, Li J, Lin JY, Jiang HX. InGaN/GaN quantum well interconnected microdisk light emitting diodes. *Appl Phys Lett* **77**, 3236–3238 (2000).
 30. Wu TZ, Sher CW, Lin Y, Lee CF, Liang SJ et al. Mini-LED and micro-LED: promising candidates for the next generation display technology. *Appl Sci* **8**, 1557 (2018).
 31. Sharbirin AS, Akhtar S, Kim JY. Light-emitting MXene quantum dots. *Opto-Electron Adv* **4**, 200077 (2021).
 32. Naguib M, Kurtoglu M, Presser V, Lu J, Niu JJ et al. Two-dimensional nanocrystals produced by exfoliation of Ti₃AlC₂. *Adv Mater* **23**, 4248–4253 (2011).
 33. Xue Q, Zhang HJ, Zhu MS, Pei ZX, Li HF et al. Photoluminescent Ti₃C₂ MXene quantum dots for multicolor cellular imaging. *Adv Mater* **29**, 1604847 (2017).
 34. Guan QW, Ma JF, Yang WJ, Zhang R, Zhang XJ et al. Highly fluorescent Ti₃C₂ MXene quantum dots for macrophage labeling and Cu²⁺ ion sensing. *Nanoscale* **11**, 14123–14133 (2019).
 35. Lu SY, Sui LZ, Liu Y, Yong X, Xiao GJ et al. White photoluminescent Ti₃C₂ MXene quantum dots with two-photon fluorescence. *Adv Sci* **6**, 1801470 (2019).
 36. Xu Q, Yang WJ, Wen YY, Liu SK, Liu Z et al. Hydrochromic full-color MXene quantum dots through hydrogen bonding toward ultrahigh-efficiency white light-emitting diodes. *Appl Mater Today* **16**, 90–101 (2019).
 37. Zhang CF, Cui YY, Song L, Liu XF, Hu ZB. Microwave assisted one-pot synthesis of graphene quantum dots as highly sensitive fluorescent probes for detection of iron ions and pH value. *Talanta* **150**, 54–60 (2016).

Acknowledgements

The author acknowledges the financial support by the City University of Hong Kong (9380107 and 7005943).

Competing interests

The authors declare no competing financial interests.