

# A Manganese Complex on a Gas Diffusion Electrode for Selective CO<sub>2</sub> to CO Reduction

Catherine Eagle,<sup>1</sup> Gaia Neri,<sup>1,2</sup> Verity L. Piercy,<sup>1,3</sup> Khadija Younis,<sup>1</sup> Bhavin Siritanaratkul,<sup>1</sup> Alexander J. Cowan<sup>1\*</sup>

\*acowan@liverpool.ac.uk

<sup>1</sup>Stephenson Institute for Renewable Energy and the Department of Chemistry, University of Liverpool, Liverpool, L69 7ZF

<sup>2</sup> Current address, Enapter, Pisa, Tuscany, Italy

<sup>3</sup> Current address, NSG Pilkington, Latham, Ormskirk, UK

## Abstract

Manganese carbonyl complexes have been studied extensively in solution as low cost, selective electrocatalysts with a low overpotential for CO<sub>2</sub> reduction but experiments are typically at low current densities. In this work, we examined their application in a gas diffusion electrode (GDE) flow cell and achieved partial current densities for CO,  $j_{\text{CO}}$  of  $\sim 14 \text{ mA cm}^{-2}$  ( $-0.98 \text{ V}_{\text{RHE}}$ ) with a Faradic efficiency of  $>50\%$ . Although we did observe a gradual decrease in activity for the [Mn(2,2'-bipyridine)(CO)<sub>3</sub>Br]/MWCNT (Mnbpy) GDE with a near neutral electrolyte over a 5 hr experiment, it still achieves a higher initial partial current density for CO at a lower overpotential than a Ag nanoparticle benchmark electrode. Promisingly, initial studies of the Mnbpy GDE in a zero-gap electrolyser using a reverse biased bipolar membrane (BPM) achieved FE for CO of 70% at  $50 \text{ mA cm}^{-2}$ , despite the acidic environment induced through directly contacting the membrane's cation exchange

layer. Overall this study demonstrates the potential of GDEs for CO<sub>2</sub> reduction based on a catalyst using earth abundant elements.


## Introduction

The electrocatalytic reduction of CO<sub>2</sub> to useful products has been investigated extensively within the scientific community using heterogeneous metal catalysts such as, Ag, Au and Cu.<sup>1</sup> Molecular catalysts provide an opportunity to alter product selectivity due to the ability to tune electron density at the metal centre by altering ligands and functionality.<sup>2-5</sup> One particular catalyst of note is a Re carbonyl complex ([Re(bpy)(CO)<sub>3</sub>Cl], bpy = 2,2'-bipyridine) which displayed good selectivity for CO.<sup>6</sup> The related Mn derivative (Mnbpy = [Mn(bpy)(CO)<sub>3</sub>Br]) has since been shown to operate as a low-cost, low overpotential alternative when a suitable Brønsted acid is present,<sup>7</sup> with selectivity equivalent to those achieved with Re (FE<sub>CO</sub> = 85% at -1.32 V<sub>Ag/AgCl</sub>).

CO<sub>2</sub> reduction using Mnbpy molecular catalysts has mainly been performed homogeneously in aprotic solvents with a low concentration of acid added. A small number of studies have shown that the Mn class of catalysts can operate in aqueous solvents either in solution or immobilised.<sup>8-14</sup> Unfortunately, one of the major limitations of aqueous CO<sub>2</sub> reduction is the low current densities achieved due to mass transport limitations of CO<sub>2</sub> in aqueous electrolytes ([CO<sub>2</sub>]<sub>aq</sub> at 298 K, 1 atm = 33 mM).<sup>15</sup> GDE architectures provide an opportunity to increase current densities and have been reported extensively<sup>16</sup>, particularly with heterogeneous metal catalysts. The GDE allows a high concentration of CO<sub>2</sub> to be maintained at the catalyst, even at high current densities.<sup>17,18</sup> Recently a number of examples of molecular catalysts immobilised on GDEs for CO<sub>2</sub> reduction have been reported.<sup>19,20</sup>

The only example of a Mnbpy derivative being used in a GDE cell structure that we are aware of used a modified bipyridine ligand with an aminophenyl functional group to enable covalent binding onto the carbon GDE.<sup>20</sup> In these experiments the GDE was used with a flowed, near neutral pH, catholyte (0.2 M KHCO<sub>3</sub> (aq)) at a range of potentials with good FE (FE<sub>CO</sub> ~60 %) and a maximum  $j_{CO}$  ~ 0.7 mA cm<sup>-2</sup> in variable potential experiments, although up to ~ 6 mA cm<sup>-2</sup> was reported when the same electrode

was used for longer term electrolysis under apparently identical conditions.<sup>20</sup> An alternative approach to covalent immobilisation that has been demonstrated is the simple co-deposition of Mnbp on multi-walled carbon nanotubes (MWCNT) in a Nafion solution on a planar carbon electrode. In these studies, good partial current densities could be achieved ( $j_{\text{CO}} \sim 0.6 \text{ mA cm}^{-2}$ ) even in an H-cell configuration.<sup>8,21</sup> Building on these initial studies we report here the behaviour of Mnbp/MWCNT GDEs prepared by a simple deposition method, and the behaviour of these electrodes in both a flow electrolyser (at near neutral pH) and in zero-gap configurations (both with high and low local pH at the cathode, figure 1). The pH dependence of the Mnbp GDE is of particular interest as carbonate formation and cross-over to the anode is a major loss pathway in the majority of GDE systems where anion exchange membranes (AEM) and a high local pH at the cathode are used. Carbonate cross-over leads to low  $\text{CO}_2$  utilisation yields which has been suggested to limit the commercial viability of many commonly studied low-temperature device architectures.<sup>22</sup> The use of a reverse biased bipolar membrane (BPM) or cation exchange membrane (CEM) in a zero-gap architecture provides a low local pH, reducing  $\text{HCO}_3^-/\text{CO}_3^{2-}$  formation and minimising cross-over of these species to the anode.<sup>23</sup> However, an acidic environment can lead to high levels of  $\text{H}_2$  evolution and low FE for carbon products using conventional metal electrocatalysts which poses challenges for related systems.<sup>24-26</sup> Molecular catalysts are of interest due to several demonstrating good tolerances to low pH, in particular, Mnbp derivatives have been reported to operate in solution at pH  $\sim 3.5$ .<sup>9</sup> Here we find that the Mnbp GDE is largely inactive for  $\text{CO}_2$  reduction at a high pH (in a zero-gap AEM cell) but at neutral ( $\text{KHCO}_3$  flow cell), and significantly at low pH (reverse biased BPM zero-gap cell), high FEs for CO production can be reached. Although device stabilities are limited at this point, this initial study shows that molecular catalysts based on earth abundant elements are of potential interest for use in  $\text{CO}_2$  electrolysers.



**Figure 1:** Schematic of the flow cell using an AEM and neutral electrolyte (a) and zero-gap electrolyser where either a reverse biased BPM or an AEM provide a low or high pH environment for the GDE cathode (b). The GDE structure with the catalyst/MWCNT coating shown in orange and expanded in the inset.

## Experimental

Materials: Milli-Q water (18.2 M $\Omega$ ) was used throughout. CO<sub>2</sub> (1% CH<sub>4</sub>) and CO<sub>2</sub> (CP grade) was purchased from BOC, potassium bicarbonate and potassium hydroxide from Sigma Aldrich ( $\geq 99.5\%$ ), Nafion 117 solution (~5% in a mixture of water and aliphatic alcohols) from Sigma Aldrich, the Selemion anion exchange membrane (AEM) from Bellex International and Sustainion and Fumasep FBM from FuelCellStore. ELAT LT1400 (FuelCellStore) with a thickness 454  $\mu\text{m}$  and a 5 wt% PTFE treatment was used as the GDE. RuO<sub>2</sub> nanoparticles of size 5-10 nm were used as received (FuelCellStore) as were Ag nanoparticles with size < 150 nm (Sigma Aldrich). Mnbp was synthesised according to a reported procedure.<sup>6</sup>

Electrode Preparation: Cathodes were prepared on ELAT LT1400 gas diffusion electrodes which were sprayed (back-side) with an additional 5 wt% PTFE (1 mL) layer and dried for 1 hour at 100 °C. Multi-walled carbon nanotubes (MWCNT, > 98% carbon basis) were cleaned by sonication in 5% HCl for 30 mins, filtered and dried in an oven. Catalyst inks were prepared by sonicating the cleaned MWCNT (2 mg cm<sup>-2</sup>) in ethanol (400  $\mu\text{L}$ ) and water (400  $\mu\text{L}$ ) for 1 hour, followed by the addition of Nafion 117 (2


$\mu\text{L}$ ), 60 wt% PTFE (9  $\mu\text{L}$ ) and Mnbp (0.1, 1 or 4  $\text{mg cm}^{-2}$ ) or Ag nanoparticles (4  $\text{mg cm}^{-2}$ ). This solution was sonicated for 15 minutes and painted onto 1  $\text{cm}^2$  active area (front-side) in 40  $\mu\text{L}$  portions and dried overnight at 35  $^\circ\text{C}$  in the dark. Anodes were prepared using  $\text{RuO}_2$  (42 mg) in isopropyl alcohol (2.6 mL) and water (2.6 mL) which was sonicated for 1 hour, followed by the addition of Nafion 117 (420  $\mu\text{L}$ ) and further sonication for 1 hour. For flow cell experiments the titanium electrode surface of 10.5  $\text{cm}^2$  was sprayed with the anode catalyst ink and dried at 100  $^\circ\text{C}$  for 1 hour prior to use. In the zero-gap structure the  $\text{RuO}_2$  is sprayed onto the carbon gas diffusion electrode held at 100  $^\circ\text{C}$  at a loading of 4  $\text{mg cm}^{-2}$ .

**Electrochemical Measurements:** All electrochemical measurements were performed using an Ivium Vertex potentiostat. CVs of the GDE were obtained by using the GDE as the working electrode, a platinum wire as the counter and a Ag/AgCl leak-free reference electrode. In flow cell experiments the electrolyte was 0.5 M  $\text{KHCO}_3$  (aq) and was pre-electrolysed (-0.1 mA) overnight with a titanium plate (working) and platinum wire (counter).<sup>27</sup> The electrolyte was purged with either Ar or  $\text{CO}_2$  for 1 hour prior to each experiment. An ElectroCell Micro Flow Cell was used for all flow experiments (non-zero gap). The flow cell is composed of a titanium anode plate, a stainless-steel cathode plate, separated by PTFE electrolyte flow plates and rubber gaskets. The membrane (Selemion) was sandwiched between these plates to provide an assembly in which gas was flowed through the back-side of the cathode and electrolyte was flowed over the surface of the cathode and anode (separated by the membrane).  $\text{CO}_2$  (containing 1%  $\text{CH}_4$  as an internal calibrant) or pure  $\text{CO}_2$  was flowed at 20  $\text{mL min}^{-1}$  through an Alicat mass flow controller. The catholyte and anolyte were pumped at 12  $\text{mL min}^{-1}$  and 22  $\text{mL min}^{-1}$  respectively and electrolysis begun once electrolyte had circulated through the tubing and dripped into the catholyte/anolyte beaker. The same supporting electrolyte concentrations were used for both the anolyte and catholyte. Data from the flow cell is reported with iR compensation (80%). The zero-gap electrolyser cell (Dioxide Materials) was composed of a serpentine anolyte chamber, a serpentine chamber for gas flow over the back of the cathode and two PTFE gaskets to separate the anode, membrane and cathode. Either Sustainion X37-50 (AEM, Dioxide Materials) or Fumasep (BPM, FuelCellStore) were sandwiched between the PTFE gaskets and pressed directly onto the cathode to

provide an assembly where humidified CO<sub>2</sub> was flowed over the backside of the cathode (20 mL min<sup>-1</sup>) and anolyte (1M KOH (aq)) was flowed over the anode and chronopotentiometry was run in a two-electrode set-up. Gas chromatography was performed on an Agilent 6890N with a pulsed discharge detector using a N6 helium carrier gas, or using a Varian CP-4900 MicroGC with a Molsieve 5Å column (10 m) with Ar carrier gas for H<sub>2</sub> and CO detection by a thermal conductivity detector.

## Results and Discussion


GDEs for CO<sub>2</sub> reduction were prepared by deposition of a Mnbp/MWCNT/Nafion mixture in ethanol/water onto the microporous layer of a commercial GDE. Scanning electron microscopy (SEM) and EDX- mapping show the structure of the electrode surface (figure S1) and FTIR and XPS show the presence of Mnbp on the electrode surface on the micron scale (figure S2, S3, S4). XPS analysis shows that the Mnbp coated GDE has N 1s and Mn 2p peaks that are at 400.2 eV, 641.5 eV and 647.1 eV respectively. The binding energies of the immobilised Mnbp are similar to Mnbp powder (399.5 eV, 642.1 eV and 646.2 eV, figure S4). We can conclude that the catalyst structure remains intact following deposition onto the GDE and that the interaction with the MWCNT has not substantially modified the electronic properties of the catalyst. Past studies of Mnbp on carbon supports have shown that the catalyst loading can have a profound impact on operating potential and selectivity to carbon products.<sup>28</sup> Therefore, electrodes were initially tested with variable Mnbp loadings (0.1, 1, 4 mg cm<sup>-2</sup>) in a flow electrolyser with liquid catholyte at neutral pH (0.5 M KHCO<sub>3</sub>, pH ~7.1 start, pH ~ 8.6 end, figure S5), figure 2. Chronopotentiometry experiments were recorded at 20 mA cm<sup>-2</sup> for 90 minutes. A loading of 4 mg cm<sup>-2</sup> resulted in the highest FE<sub>CO</sub> (63%) and lowest cell potential (-0.95 V<sub>RHE</sub>). H<sub>2</sub> (29% FE) and formate (6% FE) were also formed at lower levels, figure 2.



**Figure 2:** FE and cathode potential for a Mnbpys CO<sub>2</sub> reduction GDE in a flow cell with a 0.5 M KHCO<sub>3</sub> catholyte with different catalyst loadings at 20 mA cm<sup>-2</sup> (a) Time-course FE data for 4 mg cm<sup>-2</sup> Mnbpys GDE at 20 mA cm<sup>-2</sup> (b).

The FEs for formate and CO both decrease as the Mnbpys loading decreases and an increase in H<sub>2</sub> evolution occurs. At the lower Mnbpys loadings we also found that a significant fraction of charge remains unaccounted for (total FE accounted for is 81.5% and 83.4% with 0.1 and 1 mg cm<sup>-2</sup>). One possible cause of the lower FE in these experiments is formate/formic acid transport across the AEM. We repeated the experiment using a Nafion membrane which minimises this crossover and it shows a constant 5% increase in the formate FE over the course of the reaction, indicating that some formate/formic acid crosses through the AEM to be oxidised at the anode and this may account for the lower FE when an AEM is used. The formation of formate from CO<sub>2</sub> has been reported in several past studies, including on a Mnbpys catalyst derivatized with pyrene groups, which was immobilised on MWCNT in water.<sup>28</sup> However, formate production has also been reported on MWCNT in the absence of a catalyst previously.<sup>29</sup> Therefore we also prepared GDEs with only MWCNT and no Mnbpys. In experiments at 20 mA cm<sup>-2</sup> the MWCNT electrodes generate appreciable levels of formate (~10% FE) with H<sub>2</sub> being the only other product detected, figure S6. These control experiments indicate that the formate measured here is in part at least derived from the MWCNT and that CO is the primary CO<sub>2</sub> reduction product produced by the Mnbpys catalyst.

Following an initial increase in FE for both CO production and H<sub>2</sub> production over the first 25 minutes we find that the catalytic activity of the Mnbpys is relatively stable during 90 minutes of operation (figure 2b). Over 90 minutes we achieve a turnover number (TON) of 33 on the basis of the total Mnbpys deposited. (Note that this TON is a lower limit as the actual concentration of electrochemically active Mnbpys will be lower than the total deposited.) Control experiments in the absence of CO<sub>2</sub> (with a N<sub>2</sub> flow to the GDE) showed no significant CO formation demonstrating that the CO is produced as a result of the reduction of CO<sub>2</sub> and not due to the breakdown of the Mnbpys catalyst (figure S7). The increase in FE for H<sub>2</sub> and CO production over the first 25 minutes correlates with an increase in overpotential, figure 2b. Although the electrolyser is flushed with CO<sub>2</sub> for 15 minutes prior to experiments we believe that this initial onset is due to the reduction of trace O<sub>2</sub> that is present within the porous GDEs.



**Figure 3:** Mnbpys (blue) GDE and Ag (red) GDE FEs (a) and partial CO current densities (b) recorded over 60 min period when the GDE is used as the cathode in the 0.5 M KHCO<sub>3</sub> flow cell for CO<sub>2</sub> reduction.

As our initial studies identified that a 4 mg cm<sup>-2</sup> loading of catalyst gave the highest activity, all further experiments described in the manuscript use GDEs prepared in this way. To examine the potential dependence of the electrochemical response of the GDE, four different potentials have been studied, figure 3. At -0.58 V<sub>RHE</sub> there is only a very low total current density (2.6 mA cm<sup>-2</sup>) and negligible CO




production. CVs of the MnbpGDE immersed in a 0.5 M KHCO<sub>3</sub> electrolyte, (figure S8) show that at -0.58 V<sub>RHE</sub> there is a relatively small increase in current density under CO<sub>2</sub> vs. under Ar. Figure S8 indicates that the catalytically active species, [Mn(bpy)(CO)<sub>3</sub>]<sup>-</sup>, is not formed until approximately -0.8 V<sub>RHE</sub>, in-line with past reports.<sup>7,8</sup> Supporting the conclusion that [Mn(bpy)(CO)<sub>3</sub>]<sup>-</sup> is the catalytically active species, *j*<sub>CO</sub> increases to ~0.5 mA cm<sup>-2</sup> at -0.78 V<sub>RHE</sub> in the flow cell and at -0.98 V<sub>RHE</sub> *j*<sub>CO</sub> reaches a maximum of 13.7 ± 2.0 mA cm<sup>-2</sup> (56 ± 8 % FE). H<sub>2</sub> (FE 30 ± 1 %, 7.3 ± 0.2 mA cm<sup>-2</sup>) and formate (FE ~11 %, 2.7 mA cm<sup>-2</sup>) are also formed at -0.98 V<sub>RHE</sub>. We believe that this is amongst the highest CO partial current density to date for a Mn based CO<sub>2</sub> reduction catalyst either in aqueous solution or on a GDE (see table S1). At more negative potentials (-1.18 V<sub>RHE</sub>) the hydrogen evolution reaction dominates and *j*<sub>CO</sub> actually decreases (7.7 ± 1.6 mA cm<sup>-2</sup>). Under operating conditions, we anticipated a local pH increase at the GDE due to the effects of CO<sub>2</sub> reduction and hydrogen evolution. Reaction-diffusion simulations (see supporting information for full details, figure S9) of the local pH at the catalyst layer for varying current densities confirm that by 30 mA cm<sup>-2</sup> there is a marked increase in local pH to 9.8. The pH behaviour of the MnbpGDE is discussed in more detail in the following section. Previous experimental and DFT studies<sup>7,14,30-33</sup> have shown that CO<sub>2</sub> binding to [Mn(bpy)(CO)<sub>3</sub>]<sup>-</sup> is proton assisted, therefore the predicted rise in pH rationalises the decrease in *j*<sub>CO</sub> at -1.18 V<sub>RHE</sub>.

Figure 4 shows the extended stability test of the MnbpGDE and the Ag GDE in the flow cell using a 0.5 M KHCO<sub>3</sub> electrolyte (5 hours at -0.98 V<sub>RHE</sub>). The MnbpGDE initially shows a very high level of activity for CO<sub>2</sub> reduction with FE<sub>CO</sub> of 64 % and *j*<sub>CO</sub> of 26 mA cm<sup>-2</sup> within the first 30 minutes, but at > 100 minutes we see activity slowly dropping and after 5 hours the FE<sub>CO</sub> has decreased to < 20 % and the *j*<sub>CO</sub> ~ 5 mA cm<sup>-2</sup>. One possible cause of the instability of the MnbpGDE is that it is operating at higher current densities which is known to accelerate GDE flooding,<sup>34-36</sup> thought to be due to local pH changes and increased formation of KHCO<sub>3</sub>/K<sub>2</sub>CO<sub>3</sub>, but we rule this out here. Measurements of capacitance of a GDE before and after electrolysis have been shown to be an effective probe of flooding.<sup>37</sup> Figure S10 shows negligible differences in capacitance pre- and post-electrolysis (5 hours),

furthermore there are no visible water droplets collecting in the cathode gas flow channels. Therefore, for the MnbpGDE we do not believe that electrode flooding is the cause of the decrease in activity.

To assess the stability of the Mn catalyst SEM, EDX, FTIR and XPS studies were performed post-electrolysis (figure S1, S3, S4). These all show the presence of MnbpGDE on the cathode surface with no evidence of catalyst degradation. However, analysis of post-electrolysis catholyte via UV/vis spectroscopy shows the presence of d-d transitions and the broad MLCT excited state of the MnbpGDE complex<sup>8</sup> (figure S11), suggesting that Mn loss into the catholyte is the major activity loss mechanism. To assess whether the activity of the GDE could be recovered we performed experiments where the system was paused (30 minutes) to potentially re-adsorb the catalyst onto the surface of the GDE, however no recovery in  $j_{CO}$  was achieved (figure S12). As the MnbpGDE is entering the liquid electrolyte of the flow cell it is important to test whether the activity is actually arising from the catalyst suspended in the electrolyte or from the catalyst supported on the GDE. When electrolysis was carried out with a GDE with only the MWCNT/polymer coating present in a 0.5 M  $KHCO_3$  catholyte containing deliberately added MnbpGDE (~ 0.1 mM), there was no CO detected during electrolysis, confirming that the activity only arises from catalyst immobilised on the GDE, figure S13.<sup>19,38</sup>

To benchmark the activity of the MnbpGDE against a well-studied catalyst, we have prepared a conventional Ag nanoparticle (< 150 nm) GDE and tested it in the same device architecture (0.5 M  $KHCO_3$  electrolyte), figure 3a,b. The Ag electrode shows similar behaviour to previous literature reports where  $j_{CO}$  continues to increase significantly as the overpotential is increased with values of  $5.8 \pm 0.41$  mA cm<sup>-2</sup> and  $12.9 \pm 1.6$  mA cm<sup>-2</sup> at -0.98 V<sub>RHE</sub> and -1.18 V<sub>RHE</sub>.<sup>39,40</sup> It is notable that at -0.98 V<sub>RHE</sub> the CO current density is significantly greater for the MnbpGDE ( $13.7 \pm 2.0$  mA cm<sup>-2</sup>) than the benchmark Ag catalyst at this potential ( $5.8 \pm 0.41$  mA cm<sup>-2</sup>). The achieved partial current densities using the Ag GDE are relatively low when compared to those reported in alkali electrolytes<sup>41</sup> but they are in-line with past studies in  $KHCO_3$  electrolytes at low applied overpotentials<sup>42,43</sup> and we anticipate that future optimisation of the formulation of the GDE may increase the activity of both the MnbpGDE and the Ag electrodes.




**Figure 4:** FE and partial current density for CO ( $j_{CO}$ ) of Mnbp (a) and Ag (b) over 5-hour reaction operated in the flow cell. All experiments performed at  $-0.98 V_{RHE}$  in  $0.5 M KHCO_3$  (aq),  $RuO_2$  coated anode, Selenion membrane. The break in the data for the Mnbp GDE is due to a GC failure at this time point.

Experiments in a flow cell using a near neutral electrolyte ( $KHCO_3$ ) showed that the Mnbp GDE showed a good selectivity for  $CO_2$  reduction to CO, but that at higher current densities, which correlates to a higher local pH (figure S9) there is a decrease in  $j_{CO}$ . To further explore the pH dependence of the Mnbp GDE we have also carried out a study of the Mnbp GDE using zero-gap configurations. There is a high level of interest in the zero-gap architecture as a means to achieving higher current densities,<sup>44</sup> making their development of particular interest. Furthermore, by directly contacting the GDE to the cation exchange layer of a BPM or to an AEM we are able to generate acidic or alkali environments for the Mnbp catalyst.

When the Mnbp GDE is directly contacted to an AEM the activity for  $CO_2$  reduction is very low, figure S14. Even at low current densities (total cell current density  $20 mA cm^{-2}$ )  $j_{CO}$  is low and it also drops rapidly from its initial value of  $5 mA cm^{-2}$  (25% FE) after 10 minutes of electrolysis to  $\sim 1 mA cm^{-2}$  ( $\sim 5\%$  FE) at  $> 45$  minutes. The lack of activity for carbon dioxide reduction when the Mnbp GDE is contacted directly to the AEM is rationalised by the high local pH. Mechanistic studies and calculations in organic solvents have shown that  $CO_2$  binding to  $[Mn(bpy)(CO)_3]^+$  is endergonic in the

absence of a suitable Brønsted acid but that in the presence of an acid,  $[\text{Mn}(\text{bpy})(\text{CO})_3(\text{CO}_2\text{H})]$  formation is exergonic.<sup>14,31,32,45</sup> Spectroscopic studies have also directly correlated the presence of an intermediate on a low overpotential  $\text{CO}_2$  reduction pathway,  $[\text{Mn}(\text{bpy})(\text{CO})_4]^+$ , to the acid pKa.<sup>32</sup> pH dependent studies of Mnbp in water are limited but one past study<sup>9</sup> of a water-soluble analogue of Mnbp reported activity for CO production between pH 3.5 - 9 in line with the minimal  $\text{CO}_2$  reduction that occurred here in the zero-gap AEM device.



**Figure 5:** *Mnbp/MWCNT* in a reverse biased BPM zero-gap electrolyser at  $-20$ ,  $-50$  and  $-100 \text{ mA cm}^{-2}$  for ten minutes (a) and at  $-50 \text{ mA cm}^{-2}$  for 1-hour (b).

In contrast to the AEM system the reverse biased BPM zero-gap Mnbp electrolyser (acidic environment for the GDE) is active for CO production, figure 5a. At  $20 \text{ mA cm}^{-2}$  the FE for CO is  $61.6 \pm 11.3 \%$  for CO, rising to  $70.2 \pm 7.2 \%$  for CO at  $50 \text{ mA cm}^{-2}$ . At the highest current density tested ( $100 \text{ mA cm}^{-2}$ ) we did observe a decrease in FE for CO to  $30.6 \pm 1.3 \%$  indicating that the Mnbp catalyst may have reached its maximum turnover frequency. Experiments at higher current densities are complicated by the limited stability of the commercial BPM (Fumasep BPM) used here which is not recommended for use at  $> 100 \text{ mA cm}^{-2}$  for prolonged periods. A stability study of the zero-gap BPM system at  $50 \text{ mA cm}^{-2}$  (figure 5b), shows an initial drop in activity for CO production over the first 30 minutes but activity stabilises to  $\sim 50\%$  of its maximum for the remainder of the experiment. It is clear

that the Mnbpby complex is able to operate in the acidic environment as anticipated.<sup>9</sup> This is a significant result as it is recognised that operating the cathode at low pH overcomes the detrimental effects of  $\text{CO}_3^{2-}$ / $\text{HCO}_3^-$  formation that occurs in most reported devices<sup>22</sup> and few studies have achieved good selectivity since  $\text{H}_2$  production often dominates in the acidic environment. The FE for CO at  $50 \text{ mA cm}^{-2}$  of the Mnbpby GDE exceeds that of our previously reported system using a Ni cyclam derived catalyst ( $48 \pm 1 \%$ ) in a reverse biased BPM cell (using the same Fumasep BPM)<sup>46</sup> and for a benchmark Ag electrode ( $32 \pm 0.5 \%$ ) also at  $50 \text{ mA cm}^{-2}$  (figure S15) and compares well to the highest reported to date for CO production using a reverse biased BPM.<sup>24–26,47</sup> Further work is required to increase the achieved current densities and address the stabilities of these GDEs but these preliminary experiments indicate that Mnbpby is a promising electrocatalyst for use in electrolyzers where there is an acidic or neutral environment at the cathode.

## Conclusions

A GDE based on an earth abundant Mnbpby  $\text{CO}_2$  reduction catalyst requires a low overpotential to achieve higher partial current densities for CO than a GDE using a benchmark Ag catalyst in a flow electrolyser at a near neutral pH. The activity achieved here ( $j_{\text{CO}} = 13.7 \text{ mA cm}^{-2}$ ) at  $-0.98 \text{ V}_{\text{RHE}}$  under neutral pH conditions significantly exceeds that achieved in past studies with this class of catalysts but we do see a decrease in both partial current density for CO and selectivity towards  $\text{CO}_2$  reduction over a 5-hour period. This is proposed to be due to the loss of the catalyst from the GDE surface and future promising approaches to increasing stability in the flow electrolyser include optimisation of the electrode formulation and the potential modification of the Mn catalyst to decrease solubility and increase the strength of the interaction with the MWCNT. In a zero-gap configuration using an AEM we find that Mnbpby only shows low levels of activity. This observation is in-line with its known solution electrochemistry where protonation is critical in enabling initial  $\text{CO}_2$  binding. Promisingly, the Mnbpby GDE shows an excellent selectivity for CO when a reverse biased BPM configuration is used in preliminary studies. Such an approach is of particular interest as the BPM offers a way to overcome carbonate crossover losses but typically only low FEs for carbon products are achieved. Although

operational stabilities of these GDEs is relatively low and significant improvements are needed the work highlights the potential advantages of using selective molecular electrocatalysts such as Mnbp in reverse biased BPM zero-gap electrolyzers.

### **Acknowledgements**

CE thanks R&D Incubator, NSG Pilkington and the University of Liverpool for a PhD Studentship. This work was also supplied by UKRI-EPSC through grants EP/V011863/1, EP/P034497/1 and EP/N01053/1. The X-ray photoelectron (XPS) data collection was performed at the EPSC National Facility for XPS (“HarwellXPS”), operated by Cardiff University and UCL, under Contract No. PR16195.

## References

- 1 C. G. Vayenas, R. E. White and M. E. Gamboa-Aldeco, Eds., *Modern Aspects of Electrochemistry*, Springer New York, New York, NY, 2008, vol. 42.
- 2 J. P. Collin and J. P. Sauvage, *Coordination Chemistry Reviews*, 1989, **93**, 245–268.
- 3 O. N. Efimov and V. V. Strelets, *Coordination Chemistry Reviews*, 1990, **99**, 15–53.
- 4 M. R. Dubois and D. L. Dubois, *Accounts of Chemical Research*, 2009, **42**, 1974–1982.
- 5 Z. Jiang, Z. Zhang, H. Li, Y. Tang, Y. Yuan, J. Zao, H. Zheng and Y. Liang, *Advanced Energy Materials*, 2023, **13** (6), 2203603.
- 6 J. Hawecker, J.-M. Lehn and R. Ziessel, *Journal Chemical Society, Chemical Communication*, 1984, 328–330.
- 7 M. Bourrez, F. Molton, S. Chardon-Noblat and A. Deronzier, *Angewandte Chemie - International Edition*, 2011, **50**, 9903–9906.
- 8 J. J. Walsh, G. Neri, C. L. Smith and A. J. Cowan, *Chemical Communications*, 2014, **50**, 12698–12701.
- 9 J. J. Walsh, G. Neri, C. L. Smith and A. J. Cowan, *Organometallics*, 2019, **38**, 1224–1229.
- 10 C. L. Smith, R. Clowes, R. S. Sprick, A. I. Cooper and A. J. Cowan, *Sustainable Energy and Fuels*, 2019, **3**, 2990–2994.
- 11 T. E. Rosser, C. D. Windle and E. Reisner, *Angewandte Chemie - International Edition*, 2016, **55**, 7388–7392.
- 12 C. Sun, L. Rotundo, C. Garino, L. Nencini, S. S. Yoon, R. Gobetto and C. Nervi, *ChemPhysChem*, 2017, **18**, 3219–3229.
- 13 L. Rotundo, J. Filippi, R. Gobetto, H. A. Miller, R. Rocca, C. Nervi and F. Vizza, *Chemical Communications*, 2019, **55**, 775–777.
- 14 B. Siritanaratkul, C. Eagle and A. J. Cowan, *Accounts of Chemical Research*, 2022, **55**, 955–965.
- 15 R. Wiebe and V. L. Gaddy, *Solubility of Carbon Dioxide in Water The Solubility of Carbon Dioxide in Water at Various Temperatures from 12 to 40° and at Pressures to 500 Atmospheres. Critical Phenomena\**, 1940.
- 16 Y. Gu, J. Wei, X. Wu and X. Liu, *Scientific Reports*, 2021, **11**, 11136.
- 17 C.-T. Dinh, T. Burdyny, M. G. Kibria, A. Seifitokaldani, C. M. Gabardo, F. P. G. D. Arquer, A. Kiani, J. P. Edwards, P. D. Luna, O. S. Bushuyev, C. Zou, R. Quintero-Bermudez, Y. Pang, D. Sinton and E. H. Sargent, *Science*, 2018, **360**, 783–787.
- 18 F. P. G. de Arquer, C.-T. Dinh, A. Ozden, J. Wicks, C. McCallum, A. R. Kirmani, D.-H. Nam, C. Gabardo, A. Seifitokaldani, X. Wang, Y. C. Li, F. Li, J. Edwards, L. J. Richter, S. J. Thorpe, D. Sinton and E. H. Sargent, *Science*, 2020, **367**, 661–666.
- 19 S. Ren, D. Joulié, D. Salvatore, K. Torbensen, M. Wang, M. Robert and C. P. Berlinguette, *Science*, 2019, **365**, 367–369.

- 20 J. Filippi, L. Rotundo, R. Gobetto, H. A. Miller, C. Nervi, A. Lavacchi and F. Vizza, *Chemical Engineering Journal*, 2021, **416**, 147-160.
- 21 J. J. Walsh, C. L. Smith, G. Neri, G. F. S. Whitehead, C. M. Robertson and A. J. Cowan, *Faraday Discussions*, 2015, **183**, 147-160.
- 22 J. A. Rabinowitz and M. W. Kanan, *Nat Commun*, 2020, **11**, 5231.
- 23 M. A. Blommaert, D. Aili, R. A. Tufa, Q. Li, W. A. Smith and D. A. Vermaas, *ACS Energy Lett.*, 2021, **6**, 2539-2548.
- 24 D. A. Salvatore, D. M. Weekes, J. He, K. E. Dettelbach, Y. C. Li, T. E. Mallouk and C. P. Berlinguette, *ACS Energy Letters*, 2018, **3**, 149-154.
- 25 Y. C. Li, D. Zhou, Z. Yan, R. H. Gonçalves, D. A. Salvatore, C. P. Berlinguette and T. E. Mallouk, *ACS Energy Letters*, 2016, **1**, 1149-1153.
- 26 Z. Yan, J. L. Hitt, Z. Zeng, M. A. Hickner and T. E. Mallouk, *Nature Chemistry*, 2021, **13**, 33-40.
- 27 Y. Hori, H. Konishi, T. Futamura, A. Murata, O. Koga, H. Sakurai and K. Oguma, *Electrochimica Acta*, 2005, **50**, 5354-5369.
- 28 B. Reuillard, K. H. Ly, T. E. Rosser, M. F. Kuehnel, I. Zebger and E. Reisner, *Journal of the American Chemical Society*, 2017, **139**, 14425-14435.
- 29 S. Pal, S. Narayanaru, B. Kundu, M. Sahoo, S. Bawari, D. K. Rao, S. K. Nayak, A. J. Pal and T. N. Narayanan, *Journal of Physical Chemistry C*, 2018, **122**, 23385-23392.
- 30 C. Riplinger, M. D. Sampson, A. M. Ritzmann, C. P. Kubiak and E. A. Carter, *Journal of the American Chemical Society*, 2014, **136**, 16285-16298.
- 31 Y. C. Lam, R. J. Nielsen, H. B. Gray and W. A. Goddard, *ACS Catalysis*, 2015, **5**, 2521-2528.
- 32 G. Neri, J. J. Walsh, G. Teobaldi, P. M. Donaldson and A. J. Cowan, *Nature Catalysis*, 2018, **1**, 952-959.
- 33 D. C. Grills, M. Z. Ertem, M. McKinnon, K. T. Ngo and J. Rochford, *Coordination Chemistry Reviews*, 2018, **374**, 173-217.
- 34 K. Yang, R. Kas, W. A. Smith and T. Burdyny, *ACS Energy Letters*, 2021, **6**, 33-40.
- 35 Y. Wu, S. Garg, M. Li, M. N. Idros, Z. Li, R. Lin, J. Chen, G. Wang and T. E. Rufford, *Journal of Power Sources*, 2022, **522**, 230998.
- 36 L. C. Weng, A. T. Bell and A. Z. Weber, *Physical Chemistry Chemical Physics*, 2018, **20**, 16973-16984.
- 37 M. E. Leonard, L. E. Clarke, A. Forner-Cuenca, S. M. Brown and F. R. Brushett, *ChemSusChem*, 2020, **13**, 400-411.
- 38 Z. Zhang, L. Melo, R. P. Jansonius, F. Habibzadeh, E. R. Grant and C. P. Berlinguette, *ACS Energy Letters*, 2020, **5**, 3101-3107.
- 39 C. Kim, H. S. Jeon, T. Eom, M. S. Jee, H. Kim, C. M. Friend, B. K. Min and Y. J. Hwang, *Journal of the American Chemical Society*, 2015, **137**, 13844-13850.



- 40 T. Hatsukade, K. P. Kuhl, E. R. Cave, D. N. Abram and T. F. Jaramillo, *Physical Chemistry Chemical Physics*, 2014, **16**, 13814–13819.
- 41 S. Ma, R. Luo, J. I. Gold, A. Z. Yu, B. Kim and P. J. A. Kenis, *Journal of Materials Chemistry A*, 2016, **4**, 8573–8578.
- 42 W. H. Cheng, M. H. Richter, I. Sullivan, D. M. Larson, C. Xiang, B. S. Brunschwig and H. A. Atwater, *ACS Energy Letters*, 2020, 470–476.
- 43 J. Lim, H. Lim, B. Kim, S. M. Kim, J.-B. Lee, K. R. Cho, H. Choi, S. Sultan, W. Choi, W. Kim and Y. Kwon, *Electrochimica Acta*, 2021, **395**, 139190.
- 44 B. Endrődi, A. Samu, E. Kecsenovity, T. Halmágyi, D. Sebők and C. Janáky, *Nature Energy*, 2021, **6**, 439–448.
- 45 C. Riplinger and E. A. Carter, *ACS Catalysis*, 2015, **5**, 900–908.
- 46 B. Siritanaratkul, M. Forster, F. Greenwell, P. K. Sharma, E. H. Yu and A. J. Cowan, *Journal of the American Chemical Society*, 2022, **144**, 7551–7556.
- 47 K. Yang, M. Li, S. Subramanian, M. A. Blommaert, W. A. Smith and T. Burdyny, *ACS Energy Letters*, 2021, **6**, 4291–4298.