

Control of carrier transport in GaAs by longitudinal-optical phonon-carrier scattering using a pair of laser pump pulses

著者	Hase Muneaki, Hayashi Daisuke, Lee J. D.
journal or publication title	Journal of applied physics
volume	109
number	7
page range	073715
year	2011-04
権利	(C) 2011 American Institute of Physics
URL	http://hdl.handle.net/2241/110199

doi: 10.1063/1.3562188

Control of carrier transport in GaAs by longitudinal-optical phonon-carrier scattering using a pair of laser pump pulses

Muneaki Hase,^{1,a)} Daisuke Hayashi,¹ and J. D. Lee²

¹*Institute of Applied Physics, University of Tsukuba, 1-1-1 Tennodai, Tsukuba 305-8573, Japan*

²*School of Materials Science, Japan Advanced Institute of Science and Technology, Ishikawa 923-1292, Japan*

(Received 14 December 2010; accepted 9 February 2011; published online 7 April 2011)

We demonstrate optical control of the LO phonon-plasmon coupled (LOPC) modes in GaAs by using a femtosecond pump-pulse pair. The relaxation time of the plasmonlike LOPC mode significantly depends on the separation time (Δt) of the pump-pulse pair. Especially it is maximized when Δt becomes simultaneously comparable to the half period of the longitudinal optical (LO) phonon oscillation and resonant to the 3/4 period of the plasmonlike LOPC oscillation. We attribute these observations to the modification of carrier-LO phonon scattering and ballistic motion of the plasmonlike LOPC mode. © 2011 American Institute of Physics. [doi:10.1063/1.3562188]

I. INTRODUCTION

Ballistic transport of carriers in semiconductor devices, such as high electron mobility transistor (HEMT) and field-effect transistor (FET), possesses a potential issue to realize terahertz (10^{12} Hz) ultrahigh-speed operation in telecommunication and optical memory. To date intriguing efforts have been made to realize the ballistic regime in semiconductors,^{1,2} carbon nanotubes,³ and graphene.⁴ These studies in semiconductor nanostructures basically rely on the device structures to have the ballistic condition $\ell > L$, where ℓ is the carrier mean free path length and L is the length of the nanostructure,¹ while ballistic transport of carriers in graphene would be governed by ambipolar electric field effect.⁵

Since mobility (μ) of carrier transport in semiconductors is governed by inelastic scattering processes, such as electron-hole scattering, electron-phonon scattering, and scattering by defects and disorders,⁶ another direction to realize the ballistic regime in semiconductor is to manipulate those scattering processes in semiconductors without making nanostructure (Fig. 1). In fact, the ballistic regime for plasma wave propagation has been examined in a bulk GaAs,^{2,7} and in metal surfaces⁸ after the excitation of electron-hole plasma by femtosecond laser pulses, in which reduction of the electron-phonon scattering was significantly suggested. In a polar semiconductor, such as GaAs and InP, Fröhlich-type carrier-LO phonon scattering plays a major role at room temperature.^{6,9}

In doped semiconductors, such as n -type GaAs, it is well known that the plasmon and the longitudinal optical (LO) phonon form a new quasiparticle, the LO phonon-plasmon coupled (LOPC) mode, through Coulomb interactions.¹⁰ At the high doping levels ($n_{dop} \geq 1.0 \times 10^{18} \text{ cm}^{-3}$) the upper branch of the LOPC mode becomes plasmonlike, whose relaxation is dominated by the decay of carrier plasma.^{11,12}

One of the potential applications of femtosecond laser pulse sequences is controlling the amplitudes of coherent collective motions of atoms excited in condensed matters.^{13–15}

One can enhance the amplitude of a phonon mode by applying *in-phase* pulses, or suppress it by applying *out-of-phase* pulses, both of which are observed in real time-domain. Recently, it has been theoretically pointed out that coherent control of relaxation of carrier plasma is possible by the irradiation of THz-rate trains of laser pulses with *below-gap* excitation condition,^{16,17} while most of the pump-probe experiments and time-domain simulations have been made with *above-gap* excitation in GaAs,^{7,18–22} where the pump-pulse generates substantial nonequilibrium carriers in the conduction band with excess energy. In this condition, one expects that the firstly generated coherent LOPC modes may be always suppressed by the secondly pump-pulse if the separation time between the pump-pulses is several hundred femtoseconds.²³

In this paper, we report experimentally on the coherent control of the relaxation time of the plasma-relevant coherent LO phonon-plasmon coupled mode using a femtosecond pump-pulse pair in n -GaAs under nearly *below-gap* excitation condition. The relaxation time of the plasma-relevant LOPC mode is directly linked to the carrier transport,^{12,16,17} and therefore, our results are suggestive to a possibility of realization of near-ballistic regime as a consequence of the reduction of the electron-phonon scattering.

II. EXPERIMENTAL TECHNIQUE

To detect the plasmonlike LOPC modes in real time-domain, we used an electro-optic (EO) detection²⁴ combined with a fast scan pump-probe method utilizing a mode-locked Ti:sapphire laser with a pulse duration of 20 fs, and a center wavelength of 855 nm ($=1.45$ eV). The femtosecond pump-pulse pair was generated through a Michelson-type interferometer, in which a closed-loop piezo stage was installed to adjust the time separation (Δt) of the two pump-pulses to a precision of <0.1 fs. The average power of each pump-beam was fixed at 30 mW, while that of the probe was kept at 3 mW. The maximum photo-excited carrier density by the each pump-pulse was estimated to be $n_{exc} = 4 \times 10^{17} \text{ cm}^{-3}$ from the pump power density ($60 \mu\text{J}/\text{cm}^2$) and the absorption

^{a)}Electronic mail: mhase@bk.tsukuba.ac.jp.




FIG. 1. (Color online) (a) Schematic of the coherent control of the amplitude of the LO phonon and subsequent manipulation of the carrier transport in the case of the large amplitude LO phonon, in which the carrier mean free path length l satisfies $l \approx l_{th}$, with l_{th} the thermal mean free path length. (b) The case of the small amplitude LO phonon, in which l satisfies $l \geq l_{th}$. T_{LO} is the time period of the LO phonon.

coefficient. The sample used was Si-doped *n*-type GaAs with a doped carrier density of $n_{dop} = 1.0 \pm 0.3 \times 10^{18} \text{ cm}^{-3}$, which is larger than n_{exc} . Upon the doped carrier concentration of $n_{dop} = 1.0 \times 10^{18} \text{ cm}^{-3}$, the Burstein-Moss effect would shift the band-gap energy in *n*-GaAs to higher energy of $\approx 1.45\text{--}1.48 \text{ eV}$ from the original value (1.43 eV at 295 K) (Ref. 25). By this effect, our laser can stand at nearly *below-gap* excitation condition, although the phase-breaking scattering of virtual excitations can create the Urbach tail in the absorption line of an order of several meV,²⁶ generating




FIG. 2. (Color online) The $\Delta R_{eo}/R$ signals for *n*-GaAs obtained by each single pump (bottom) and pump-pulse pairs with two different Δt s. The inset shows the enlargement of the oscillation with $\Delta t = 60.2 \text{ fs}$ after subtraction of the exponentially decaying electronic background. The vertical arrows represent the temporal position of the pump-pulses.

small free-streaming current in the depletion region. The transient EO reflectivity change ($\Delta R_{eo}/R$) was recorded as a function of the time delay (τ) at room temperature (295 K).

III. EXPERIMENTAL RESULTS AND ANALYSIS

As shown in Fig. 2, the signal observed in *n*-GaAs with the single pump-pulse exhibits a beating oscillation, which has been commonly obtained by the similar pump-probe experiments^{19–21} and assigned to the coexistence of the LO phonon and the lower branch (LOPC-) of the LOPC modes. The coherent LO phonon is excited in the depletion region ($d = 0 - 100 \text{ nm}$), while the LOPC modes are excited in both depletion and bulk region.^{19–21} When the sample is excited with pump-pulse pair, the constructive and destructive generation of coherent phonons is observed. Especially, a high frequency coherent oscillation (see the inset of Fig. 2) becomes evident up to $\tau \sim 300 \text{ fs}$ when Δt is 60.2 fs, whose oscillation period is $\approx 70 \text{ fs}$ ($=14.3 \text{ THz}$). This mode appears to be the higher branch of the LOPC mode (LOPC+) as seen in the corresponding Fourier transformed (FT) spectra, Fig. 3, which is converted from the time-domain data just after the second pump-pulse excitation to exclude any coherent artifact originating from the period of the pump-pulse pair. The almost complete destructive interference of the coherent LO




FIG. 3. (Color online) The FT spectra obtained from the time-domain data in Fig. 2. With single pump excitation, the LO phonon (8.8 THz), the LOPC- mode (7.8 THz), and the very weak LOPC+ mode (13 THz) are observed. The black thick lines around the LOPC+ mode represent the fit of the data with the Lorentz function. The upper inset describes LOPC frequencies as a function of the total carrier density n_t . The solid curves are the frequencies of the LOPC+ and LOPC- modes calculated by the equilibrium model of Ref 10. The horizontal dashed lines are the frequencies of the bare LO (8.8 THz) and TO (8.0 THz) phonons, while the plasma frequency (ω_p) depends linearly on $n_t^{1/2}$.

phonon observed in Fig. 3 ($\Delta t = 60.2$ fs) may imply generating a similar condition to phonon cooling near the surface of the sample.²⁷ As shown in the inset of Fig. 3, the frequencies of the LOPC modes are in good agreement with the calculation within the experimental errors under the condition that the total carrier density n_t is the sum of the doped- and photoexcited-carriers ($n_t = n_{dop} + n_{exc}$) (Refs. 19 and 20).

Careful curve fitting with a Lorenz function to the FT data at various Δt s enables us to estimate the relaxation time of the LOPC+ mode by using the relation between the linewidth and the relaxation time,^{28,29} that changes from 180 ± 20 to 235 ± 20 fs, depending on the value of Δt . The relaxation time of the coherent LOPC+ mode in highly doped n -GaAs obtained under the *above-gap* excitation was 135 ± 15 fs at $n_t \approx 1.1 \times 10^{18} \text{ cm}^{-3}$,¹² and 130 ± 40 fs at $n_t \approx 1.2 \times 10^{18} \text{ cm}^{-3}$ (Ref. 30). Comparing these values with the relaxation time obtained in the present study indicates that the nearly *below-gap* excitation makes the relaxation slightly longer.

Figure 4 plots the relaxation time of the plasmonlike LOPC+ mode together with the FT intensity of the coherent LO phonon as the function of the separation time Δt . The relaxation time exhibits a maximum at $\Delta t \approx 64$ fs, while the amplitude of the LO phonon shows minimum at $\Delta t \approx 54$ fs. The latter effect can be understood in terms of the destructive interference of the coherent LO phonon as observed in GaAs¹⁴ and other materials.¹⁵ The value of $\Delta t \approx 64$ fs is significantly close to the characteristic time of $(3/4) T_{LOPC+}$ ($= 57.8$ fs), at which the LOPC+ oscillation reaches its maximum (when assuming the LOPC+ mode is a sinelike oscillation). To investigate the oscillatory phase of the LOPC+ mode, we fit the time-domain data of the single pump [labeled 1; bottom in Fig. 2] with damped harmonic oscillations




FIG. 4. (Color online) Relaxation time of the plasmonlike LOPC+ mode together with the peak intensity of the LO phonon as a function of the separation time Δt . The LOPC+ mode cannot be separately observed when $\Delta t \leq 40$ fs, and $\Delta t \geq 90$ fs due to the stronger spectral tail by the LO mode. The thick curve corresponds to the fit of the data with a Gaussian function to estimate the maximum position of the relaxation time, while that for the LO intensity is a guide for the eyes with a cosine function.

(not shown), and as the results, the sinelike phase was confirmed for the LOPC+ and LOPC- modes. On the contrary, the cosinelike phase was observed for the LO mode, being consistent with the previous result.³¹ According to Ref. 23, if Δt does not match a maximum of the oscillation of the LOPC modes, the oscillation is suppressed and the ballistic motion cannot be obtained. On the contrary, Δt matching a maximum of the oscillation would give long-surviving motion, suggesting $\Delta t = (3/4) T_{LOPC+}$ should be a necessary condition for ballistic motion of the LOPC+ mode. Thus, the enhancement of the relaxation time at $\Delta t \approx 64$ fs satisfies approximately both conditions; (i) minimum LO phonon amplitude ($\Delta t \approx T_{LO}/2$), and (ii) ballistic motion of the LOPC+ mode by coherent excitation with $\Delta t \approx (3/4) T_{LOPC+}$.

IV. DISCUSSION

A plausible reason for the enhancement of the relaxation time is reduction of the Fröhlich-type carrier-LO phonon scattering due to minimizing the LO phonon amplitude, which would occur at the value of $\Delta t \approx 57.5$ fs ($= T_{LO}/2$) (see Fig. 1). At room temperature (295 K), however, there is a substantial thermal population of LO phonons, which interact with the plasmonlike LOPC mode and would contribute to its relaxation. This contribution might be much stronger than the contribution of the coherent LO phonon generated and manipulated optically. In order to check these possibilities, we consider the ratio of the total number of the coherent LO phonons n_{coh} to the total number of the LO phonons as given by,³²

$$A(T) = \frac{n_{coh}}{n_{coh} + n_{incoh}(T)}, \quad (1)$$

where $n_{incoh}(T)$ is the number of thermal (incoherent) LO phonons expressed by $n_{incoh}(T) = n_0 / [\exp(\hbar\omega_{LO}/k_B T) - 1]^{-1}$. In the case of the GaAs-like LO phonon the ratio n_{coh}/n_0 was experimentally obtained to be 0.091 at $1 \mu\text{J}/\text{cm}^2$.³² Consequently we would expect $n_{coh}/n_0 \approx 1$ (maximum coherence) in our case ($60 \mu\text{J}/\text{cm}^2$). Then we found from Eq. (1) that the ratio of the coherent LO phonon is $A(T=295 \text{ K}) \approx 0.78$. It follows that the ratio of the thermal LO phonon is $1 - A(T=295 \text{ K}) \approx 0.22$. Although there is the constant thermal population of LO phonons as estimated above, the contribution of the coherent LO phonon is enough to affect the relaxation of the plasmonlike LOPC mode under our experimental condition.

Based on the above investigations, we argue overall understanding of the enhancement of the relaxation time of the LOPC+ mode in more details. In the case of the thermal LO phonon, high enough temperatures enable all LO phonons to participate in the Fröhlich-type carrier-LO phonon scattering process, which involves the absorption and emission of LO phonons; the interaction occurs very often at room temperature, and then reduces the mobility.^{6,9} To link this scenario with our case, we are controlling the amplitude of the coherent LO phonon [$A(T=295 \text{ K}) \approx 78\%$ in the maximum] by the optical means, instead of changing the lattice temperature, leading to the reduction of the probability of scattering events if the amplitude of the coherent LO

phonon becomes minimum, where A ($T = 295$ K) ≈ 0 . Additionally, the synchronization of free-streaming current by the second pump-pulse would lead to the condition of another ballistic motion of plasmons, leading to the subsequent formation of the ballistic motion of the plasmonlike LOPC+ mode, whose oscillation persists up to $\tau \sim 300$ fs, as uncovered in the inset of Fig. 2.

Note that other scattering processes than the Fröhlich-type carrier-phonon scattering cannot contribute to the “ Δt dependence” at room temperature because the arrival time of the second pump-pulse changes only the amplitude of the LO phonon, and not change carrier density, defect density, and amplitude of acoustic phonons within the time scale of a few hundred femtoseconds.

V. CONCLUSIONS

To summarize, we have obtained the enhancement of the relaxation time of the plasmonlike LOPC+ mode through the coherent control of the amplitude of both the LO phonon and plasmonlike LOPC modes in n-GaAs by use of the femtosecond pump-pulse pair. This effect would be attributed to the two possible origins, that is the minimum Fröhlich-type carrier-LO phonon scattering and ballistic motion of the plasmonlike LOPC+ mode, induced by coherent excitation with the ultimate condition of $\Delta t \approx T_{LO}/2 \approx (3/4) T_{LOPC+}$.

ACKNOWLEDGMENTS

This work was supported in part by PRESTO-JST, KAKENHI-22340076 and Special Coordination Funds for Promoting Science and Technology from MEXT, Japan.

- ¹J. Wang and M. Lundstrom, *IEEE Trans. Electron Devices* **50**, 1604 (2003).
²Y. D. Glinka, D. Maryenko, and J. H. Smet, *Phys. Rev. B* **78**, 035328 (2008).
³Y. -F. Chen and M. S. Fuhrer, *Phys. Rev. Lett.* **95**, 236803 (2005).

- ⁴X. Du, I. Skachko, A. Barker and E. Y. Andrei, *Nat. Nanotechnol.* **3**, 491 (2008).
⁵A. K. Geim and K. S. Novoselov, *Nat. Mater.* **6**, 183 (2007).
⁶P. Y. Yu and M. Cardona, *Fundamentals of Semiconductors* (Springer-Verlag, Berlin 1999), Chap. 3.
⁷M. D. Cummings, J. F. Holzman, and A. Y. Elezzabi, *Appl. Phys. Lett.* **78**, 3535 (2001).
⁸M. Lisowski, P. A. Loukakos, U. Bovensiepen, J. Stähler, C. Gahl, and M. Wolf, *Appl. Phys. A*, **78**, 165 (2004).
⁹R. Kersting, J. N. Heyman, G. Strasser, and K. Unterrainer, *Phys. Rev. B* **58**, 4553 (1998).
¹⁰A. Mooradian and G. B. Wright, *Phys. Rev. Lett.* **16**, 999 (1966).
¹¹F. Vallée, F. Ganikhanov, and F. Bogani, *Phys. Rev. B* **56**, 13141 (1997).
¹²M. Hase, *Appl. Phys. Lett.* **94**, 112111 (2009).
¹³A. M. Weiner, D. E. Leaird, G. P. Wiederrecht, and K. A. Nelson, *Science* **247**, 1317 (1990).
¹⁴T. Dekorsy, W. A. Kütt, T. Pfeifer, and H. Kurz, *Europhys. Lett.* **23**, 223 (1993).
¹⁵M. Hase, K. Mizoguchi, H. Harima, S. Nakashima, M. Tani, K. Sakai, and M. Hangyo, *Appl. Phys. Lett.* **69**, 2474 (1996).
¹⁶J. D. Lee and M. Hase, *Phys. Rev. Lett.* **101**, 235501 (2008).
¹⁷J. D. Lee, H. Gomi, and M. Hase, *J. Appl. Phys.* **106**, 083501 (2009).
¹⁸P. Saeta, J.-K. Wang, Y. Siegal, N. Bloembergen, and E. Mazur, *Phys. Rev. Lett.* **67**, 1023 (1991).
¹⁹G. C. Cho, T. Dekorsy, H. J. Bakker, R. Hövel, and H. Kurz, *Phys. Rev. Lett.* **77**, 4062 (1996).
²⁰M. Hase, K. Mizoguchi, H. Harima, F. Miyamaru, S. Nakashima, R. Fukasawa, M. Tani, and K. Sakai, *J. Lumin.* **76–77**, 68 (1998).
²¹Y. -M. Chang, *Appl. Phys. Lett.* **80**, 2487 (2002).
²²T. Dumitricá and R. E. Allen, *Phys. Rev. B* **66**, 081202(R) (2002).
²³M. I. Bakunov, A. V. Maslov, and S. N. Zhukov, *Phys. Rev. B* **67**, 153201 (2003).
²⁴G. C. Cho, W. Kütt, and H. Kurz, *Phys. Rev. Lett.* **65**, 764 (1990).
²⁵G. Borghs, K. Bhattacharyya, K. Deneffe, P. Van Mieghem, and R. Mertens, *J. Appl. Phys.* **66**, 4381 (1989).
²⁶A. Leitenstorfer, A. Lohner, T. Elsaesser, S. Haas, F. Rossi, T. Kuhn, W. Klein, G. Boehm, G. Traenkle, and G. Weimann, *Phys. Rev. Lett.* **73**, 1687 (1994).
²⁷M. Sheik-Bahae and R. I. Epstein, *Phys. Rev. Lett.* **92**, 247403 (2004).
²⁸A. Laubereau and W. Kaiser, *Rev. Mod. Phys.* **50**, 607 (1978).
²⁹M. Hase, K. Mizoguchi, H. Harima, S. Nakashima, and K. Sakai, *Phys. Rev. B* **58**, 5448 (1998).
³⁰M. Hase, S. Nakashima, K. Mizoguchi, H. Harima, and K. Sakai, *Phys. Rev. B* **60**, 16526 (1999).
³¹T. Pfeifer, T. Dekorsy, W. A. Kütt, and H. Kurz, *Appl. Phys. A* **55**, 482 (1992).
³²M. Nakayama, K. Mizoguchi, O. Kojima, T. Furuichi, A. Mizumoto, S. Saito, A. Syouji, and K. Sakai, *Phys. Status Solidi A* **204**, 518 (2007).