



The meaning of this research

Tyre compounds represent the most important application of rubber.

The higher **environmental impact of tyres** takes place **during their use** and is due to rolling resistance.

Silica has brought a **revolution** in the field of elastomer composites: it allows mechanical reinforcement and a **great reduction of hysteresis and rolling resistance**. A **chemical bond between silica and the rubber chains** is established: **this is the key strength of silica!**

A **coupling agent** is used: an organosilane containing sulphur atoms. However, **silica** has various **drawbacks**: the **release of ethanol** from the silica – silane reaction, the **corrosion** of compounding equipment, the **increase of compound viscosity**, the **reduction of the shelf life** of semifinished products.

It would be **highly desirable to substitute** or at least **partially replace silica** with an alternative filler, obviously without damaging the composites' properties.




The objectives

☞ **To prepare a CB-filled compound with the same performances of a silica-based compound**

Hence

☞ **To prepare a functionalized carbon black able to establish a chemical bond with rubber chains**


Thanks to the pyrrole methodology
for functionalizing carbon allotropes



How to achieve the objectives?




The selected pyrrole compound:



Thiol Pyrrole,
SHP


2-(2,5-dimethyl-1H-pyrrol-1-yl)ethane-1-thiol

Synthesis of SHP



The reaction was performed without catalysts and solvent

Preparation of CB-SHP adduct



Preparation and characterization of rubber composites





65 phr Silica vs 55 phr CB-SHP

Study of filler networking in shear

Dynamic rigidity and hysteresis from axial compressive tests

Recipies in phr	Silica 65 phr	CB-SHP 55 phr
S-SBR	70	70
NR	30	30
Silica	65	/
Silane	5.2	/
CB-SHP	/	55

Other ingredients used for each compound:
stearic acid, ZnO, 6PPD, TBBS, PVI, sulphur



Curves from axial and shear dynamic-mechanical analyses of S-SBR-based rubber composites filled with 65 phr of pristine silica (green) and 55 phr of CB-SHP (red). 55 phr of CB-SHP give similar results to 65 phr of silica.

Conclusions

- Composites with **functionalized CB, reactive with the rubber chains**, have the same or **even better dynamic mechanical properties with respect to silica –based composites**
- The **reactive CB** was prepared with the **pyrrole methodology**, through a simple and sustainable technology based on a pyrrole compound
- These results demonstrate that silica is not the only possible filler for the preparation of green elastomeric composites for tyre applications.

References:

- Galimberti, M., Barbera, V., Guerra, S., & Bernardi, A. Rubber Chemistry and Technology, 2017, 90(2), 285-307
- M. Galimberti, V. Barbera, S. Guerra, L. Conzatti, C. Castiglioni, L. Brambilla, A. Serafini, RSC Adv., 2015, 5, 81142-81152
- Barbera, V., Bernardi, A., Palazzolo, A., Rosengart, A., Brambilla, L., & Galimberti, M., Pure and Applied Chemistry, 2018, 90(2), 253-270.
- Barbera, V., Brambilla, L., Milani, A., Palazzolo, A., Castiglioni, C., Vitale, A., ... & Galimberti, M. (2019). Domino reaction for the sustainable functionalization of few-layer graphene. Nanomaterials, 9(1), 44.
- Maurizio Stefano Galimberti, Vincenzina Barbera, Gea Prioglio, Luca Giannini, Publication of WO2020225595A1: 12 November 2020

Acknowledgments:

We thank Pirelli Tyre S.p.A. for financial support

