

VTT Technical Research Centre of Finland

Mixing of high-consistency fiber-foam suspensions

Prakash, Barani; Viitala, Janika; Kiiskinen, Harri; Koponen, Antti I.

Published: 01/06/2023

Link to publication

Please cite the original version: Prakash, B., Viitala, J., Kiiskinen, H., & Koponen, A. I. (2023). *Mixing of high-consistency fiber-foam suspensions*. Abstract from 11th World Congress of Chemical Engineering, WCCE11, Buenos Aires, Brazil.



VTT http://www.vtt.fi P.O. box 1000FI-02044 VTT Finland By using VTT's Research Information Portal you are bound by the following Terms & Conditions.

I have read and I understand the following statement:

This document is protected by copyright and other intellectual property rights, and duplication or sale of all or part of any of this document is not permitted, except duplication for research use or educational purposes in electronic or print form. You must obtain permission for any other use. Electronic or print copies may not be offered for sale.



WCCE11 - 11th WORLD CONGRESS OF CHEMICAL ENGINEERING

IACCHE - XXX INTERAMERICAN CONGRESS OF CHEMICAL ENGINEERING CAIQ2023 - XI ARGENTINIAN CONGRESS OF CHEMICAL ENGINEERING CIBIQ2023 - II IBEROAMERICAN CONGRESS OF CHEMICAL ENGINEERING Buenos Aires - Argentina - June 4-8, 2023

"The global chemical engineering working for a better future world"

Mixing of high-consistency fiber-foam suspensions

Prakash, B., Viitala, J., Kiiskinen, H., Koponen, A.I.

VTT Technical Research Centre of Finland Ltd, P.O. Box 1603, 40101 Jyväskylä, Finland. Corresponding author email: Baranivignesh.Prakash@vtt.fi

Foam-forming has been gaining attention recently to manufacture sustainable packaging and cushioning products in various sectors, including food, automobile and construction [1]. Conventionally, foam suspension is made in a mixing tank at a lower fibre consistency, < 2% resulting in large volumes of water consumption. Besides, the excess moisture from the final foam-formed product needs to be removed by drying. Replacing the current foaming methods with Highconsistency foam (HCF) can reduce water consumption, drying energy and equipment footprint. However, increasing the fibre consistency makes the rheology of fibre-foam suspension complex [2], posing challenges in mixing. The present work focuses on mixing this complex suspension to generate a homogeneous HCF by selecting proper impeller geometry, mixing time and surfactant dosage. The lab-scale testing facility consisted of a 0.43 m tall and 0.16 m wide transparent acrylic tank equipped with a top-mount impeller assembly. Three impeller geometries, namely bend-disc, Bakker turbine and high solidity pitched blade turbine, and four impeller combinations were used. Chemithermomechanical pulp (CTMP) with a mean fibre length of 2.0 mm, a width of 39 µm and Canadian standard freeness (CSF) of 600 ml was used as the fibre material. The consistency varied from 5% to 15%. An 80/20 mol% mixture of sodium dodecyl sulphate (SDS) and Tween 20 (T 20) was used as the surfactant. The surfactant dosage was varied from 0.5 g/l to 2.0 g/l based on fibre consistency. The quality of the HCF was assessed in terms of air content, foaming time and X-ray microtomography. Preliminary results indicated that the used impeller combination should be selected on the base of fibre consistency. No improvement in the air content was noticed beyond 1.2 g/l surfactant dosage. However, increasing the surfactant dosage reduced foaming time at higher consistencies. Currently, experiments are carried out to understand the role of fibre length and the addition of binders such as guar gum in the mixing. In summary, this work provides an understanding of the mixing geometry and foam chemistry that enables the manufacturing of sustainable packaging products at a much lower water consumption.

Reference

- 1. Hjelt, T., Ketoja, J., Kiiskinen, H., Koponen, A. I. & Pääkkönen, E. (2022). Foam forming of fiber products: a review, Journal of Dispersion Science and Technology, 43(10), 1462–1497.
- Prakash, B., Jäsberg, A., & Koponen, A. I. (2021). Experimental investigation on the effect of fibre consistency on the rheology of aqueous foams in pipe flow, Annual Transactions of the Nordic Society of Rheology, (29), 27-34.

