

## Optical characteristics of single InAs/InGaAsP/InP(100) quantum dots emitting at 1.55 $\mu\text{m}$

**Citation for published version (APA):**

Cade, N. I., Gotoh, H., Kamada, H., Nakano, H., Anantathanasarn, S., & Nötzel, R. (2006). Optical characteristics of single InAs/InGaAsP/InP(100) quantum dots emitting at 1.55  $\mu\text{m}$ . *Applied Physics Letters*, 89(18), 181113-1/3. Article 181113. <https://doi.org/10.1063/1.2378403>

**DOI:**

[10.1063/1.2378403](https://doi.org/10.1063/1.2378403)

**Document status and date:**

Published: 01/01/2006

**Document Version:**

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

**Please check the document version of this publication:**

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

**General rights**

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

[www.tue.nl/taverne](http://www.tue.nl/taverne)

**Take down policy**

If you believe that this document breaches copyright please contact us at:

[openaccess@tue.nl](mailto:openaccess@tue.nl)

providing details and we will investigate your claim.

## Optical characteristics of single InAs/InGaAsP/InP(100) quantum dots emitting at 1.55 $\mu\text{m}$

N. I. Cade,<sup>a)</sup> H. Gotoh, H. Kamada, and H. Nakano  
*NTT Basic Research Laboratories, NTT Corporation, Atsugi, 243-0198 Japan*

S. Anantathanasarn and R. Nötzel  
*eiTT/COBRA Inter-University Research Institute, Eindhoven University of Technology, 5600 MB Eindhoven, The Netherlands*

(Received 4 April 2006; accepted 20 September 2006; published online 1 November 2006)

The authors have studied the emission properties of individual InAs quantum dots (QDs) grown in an InGaAsP matrix on InP(100) by metal-organic vapor-phase epitaxy. Low-temperature microphotoluminescence spectroscopy shows emission from single QDs around 1550 nm with a characteristic exciton-biexciton behavior and a biexciton antibinding energy of more than 2 meV relative to the exciton. Temperature-dependent measurements reveal negligible optical phonon induced broadening of the exciton line below 50 K, and emission from the exciton state clearly persists above 70 K. These results are encouraging for the development of a controllable photon source for fiber-based quantum information and cryptography systems. © 2006 American Institute of Physics. [DOI: 10.1063/1.2378403]

There is currently considerable interest in the development of self-assembled quantum dot (QD) structures for novel telecommunication applications, such as low-threshold lasers<sup>1</sup> and nonclassical light sources for quantum cryptography.<sup>2</sup> In the latter case, an optical fiber-based system requires the development of an efficient single photon source operating in the fiber transmission bands above 1260 nm. QD structures grown by metal-organic vapor-phase epitaxy (MOVPE) are very attractive commercially due to the high growth rates achievable and the potential for monolithic integration into existing devices. Recently we have reported on the photoluminescence (PL) characteristics of MOVPE grown InAs/InGaAs single QDs emitting at 1.3  $\mu\text{m}$ .<sup>3</sup> For longer wavelength applications InAs/InP QDs are normally used; however, due to the small lattice mismatch careful control of the growth conditions is required to realize emission around 1.55  $\mu\text{m}$ .<sup>4–6</sup> To date, there have been only a few investigations into single QDs emitting in the important C-band region between 1.53–1.57  $\mu\text{m}$ ; these have used selective area chemical-beam epitaxy<sup>7</sup> and MOVPE techniques.<sup>8–10</sup> However, in the latter cases the QDs were not optimized for low temperature device applications, producing a broad luminescence spectrum and low emission intensity at 1.55  $\mu\text{m}$  relative to that at shorter wavelengths.

Here, we report on the emission properties of InAs QDs embedded in an InGaAsP matrix by MOVPE. Wavelength tuning has been achieved via the insertion of ultrathin GaAs interlayers. We present low-temperature PL spectra from a single QD with an emission wavelength around 1550 nm. Power-dependent measurements clearly reveal the formation of an exciton-biexciton system; the biexciton is found to be antibinding with an emission energy of more than 2 meV relative to the exciton. The exciton linewidth shows negligible optical phonon induced broadening up to 50 K. In addition, emission from discrete electronic states is seen clearly above 70 K, which suggests that these QDs may be used as a

single photon source operating at liquid-nitrogen temperatures.

The QD sample was grown at 500 °C by low-pressure MOVPE on an InP (100) substrate misoriented 2° toward (110). A 100 nm InP buffer layer and a 100 nm lattice-matched InGaAsP layer ( $\lambda_0=1.25 \mu\text{m}$ ) were deposited, followed by 2 MLs of GaAs (growth rate 0.16 ML/s). The QDs were formed from 3 ML of InAs, with a 5 s growth interruption and an upper 100 nm InGaAsP layer. On top of this second InGaAsP layer, the growth of the GaAs interlayer and InAs QDs was repeated at the same conditions for atomic force microscopy measurements; from these we obtain a QD sheet density of  $\sim 10^{10} \text{ cm}^{-2}$ . The GaAs interlayer suppresses an As/P exchange during the QD growth, thus reducing the QD height and blueshifting the emission wavelength by a controllable amount. A detailed description of the sample growth procedure and the macroscopic optical characteristics are published elsewhere.<sup>11</sup>

To obtain single dot spectroscopy, mesa structures were fabricated by electron-beam lithography and dry etching with lateral sizes between 200 nm and 2  $\mu\text{m}$ . Micro-PL measurements were taken using a continuous-wave (cw) Ar<sup>+</sup> laser (488 nm) focused on a  $\sim 3 \mu\text{m}$  spot; the luminescence was dispersed in a 0.5 m spectrometer and detected with a nitrogen cooled InGaAs photodiode array (instrument resolution  $\Gamma_{\text{res}} \approx 65 \mu\text{eV}$ ). The sample temperature was controlled using a continuous-flow He cryostat.

PL spectra from a 500 nm mesa at 5 K are shown in Fig. 1 for various excitation powers. At the lowest power there is a single sharp emission line X in the spectral window between 1525–1580 nm. With increasing power additional lines appear in the spectrum; in particular, the line 2X develops superlinearly at 2.3 meV above the emission energy of X. The lines X and 2X are attributed to the recombination from the neutral exciton and biexciton states, respectively, of a single QD. This assignment has been confirmed by plotting the integrated intensities of these lines as a function of laser power, as shown in Fig. 2: fits to the data give almost ideal linear and quadratic behaviors for the X and 2X lines, respec-

<sup>a)</sup>Present address: Department of Physics, King's College London, WC2R 2LS, UK; electronic mail: nicholas.cade@kcl.ac.uk




FIG. 1. (Color online) PL spectra from a single QD in a 500 nm mesa at different excitation powers. Peaks X and 2X are attributed to neutral exciton and biexciton emission, respectively. (Inset) X emission resolved into horizontally (H) and vertically (V) polarized components. The solid and dashed lines are Lorentzian fits.

tively, which suggests a low scattering rate by impurities and defects for this particular dot.<sup>12</sup> The other spectral lines observed at higher powers most likely originate from charged- and multiexciton states.<sup>13</sup> From a study of other QDs on the sample, we find a similar exciton-biexciton behavior with 2X recombination energies in the range of 2–5 meV above the X line. This “antibinding” of the biexciton state has been observed previously in InAs/GaAs dots by Rodt *et al.*<sup>14</sup> and results from a reduction in exchange and correlation effects between the two localized excitons relative to the repulsive direct Coulomb interaction. This effect is consistent with the small dot aspect ratio (height/base diameter) of 0.09 expected from the growth conditions.<sup>11</sup>

The inset in Fig. 1 shows the X line resolved into horizontally and vertically polarized components. Lorentzian fits to the data suggest a fine-structure splitting of  $7 \pm 3 \mu\text{eV}$ , which is much smaller than the instrument precision. Inter-




FIG. 2. Integrated intensities of the X and 2X peaks in Fig. 1, as a function of the cw laser power. Solid lines are linear fits to the data.




FIG. 3. PL spectra from the same QD as in Fig. 1, normalized to the X integrated intensity, as a function of temperature. The laser power was  $P_0$ , indicated in Fig. 2.

mediate linear orientations and circularly polarized components give consistent results. Furthermore, these dots show a very similar emission intensity under pulsed (80 MHz) excitation from a Ti:sapphire laser which is necessary for controlled generation of single photons.

Figure 3 shows temperature-dependent PL spectra from the same QD studied in Fig. 1, normalized to the integrated intensity of the X line. The exciton emission intensity and linewidth<sup>15</sup> determined from these spectra are plotted in Fig. 4; the exciton line appears thermally stable over the measured temperature range, with the intensity at 70 K only dropping to approximately half of the maximum value. A fit to the data gives a thermal activation energy of 14 meV. We have observed a similar behavior in other QDs on the sample, with well resolved emission from the exciton state at 77 K.

At low temperatures the exciton–optical phonon interaction is negligible and the X linewidth  $\Gamma$  has a linear tempera-




FIG. 4. (Color online) (Bottom-left axes) Temperature dependence of the corrected exciton PL linewidth  $\Gamma$  (triangles) (Ref. 15). The solid line is a linear fit over low temperatures. (Top-right axes) Temperature dependence of the exciton PL integrated intensity (squares). A data fit (dashed line) gives an activation energy of 14 meV. Note that the two horizontal axes do not correspond exactly.

ture dependence due to acoustic phonon scattering:  $\Gamma(T) = \Gamma_0 + \alpha T$ , where  $\Gamma_0$  is the linewidth at 0 K. A linear fit of the data in Fig. 4 gives  $\alpha = 0.9 \pm 0.2 \mu\text{eV/K}$  and  $\Gamma_0 \approx 50 \mu\text{eV}$ . The value of  $\alpha$  is similar to those previously reported for other QD systems<sup>16,17</sup> and significantly smaller than that of a quantum well system due to the absence of final states for scattering. Above 50 K there is a sharp increase in linewidth due to optical phonon scattering, and the line shape strongly deviates from a Lorentzian profile.<sup>16</sup> From different QDs we find similar values for  $\alpha$ , but large variations in  $\Gamma_0$ ; this latter effect is most likely due to the influence of charge fluctuations on the mesa sidewalls when using nonresonant laser excitation.<sup>18</sup>

In conclusion, we have studied the emission properties of individual InAs/InGaAs P QDs grown on InP(100) by MOVPE; the insertion of a thin GaAs interlayer has enabled tuning of the QD emission wavelength to 1.55  $\mu\text{m}$  for telecom applications. We observe almost an ideal exciton-biexciton behavior at low temperatures, with a biexciton antibinding energy of more than 2 meV. The exciton line shows negligible broadening from optical phonon scattering up to 50 K and appears thermally stable at higher temperatures with clearly resolvable emission above 70 K. These results suggest that QDs fabricated with this growth technique may be suitable as an on-demand single photon source at liquid nitrogen temperatures for fiber-based quantum information and cryptography systems.

The authors are grateful to T. Segawa at NTT Photonics Laboratories for etching the mesa structures. This work was partly supported by the National Institute of Information and Communications Technology (NICT).

- <sup>1</sup>M. Sugawara, N. Hatori, M. Ishida, H. Ebe, Y. Arakawa, T. Akiyama, K. Otsubo, T. Yamamoto, and Y. Nakata, *J. Phys. D* **38**, 2126 (2005).
- <sup>2</sup>P. Michler, A. Kiraz, C. Becher, W. V. Schoenfeld, P. M. Petroff, L. Zhang, E. Hu, and A. Imamoglu, *Science* **290**, 2282 (2000).
- <sup>3</sup>N. I. Cade, H. Gotoh, H. Kamada, T. Tawara, T. Sogawa, H. Nakano, and H. Okamoto, *Appl. Phys. Lett.* **87**, 172101 (2005).
- <sup>4</sup>C. Paranthoen, N. Bertru, O. Dehaese, A. Le Corre, S. Loualiche, B. Lambert, and G. Patriarche, *Appl. Phys. Lett.* **78**, 1751 (2001).
- <sup>5</sup>K. Kawaguchi, M. Ekawa, A. Kuramata, T. Akiyama, H. Ebe, M. Sugawara, and Y. Arakawa, *Appl. Phys. Lett.* **85**, 4331 (2004).
- <sup>6</sup>S. H. Pyun, S. H. Lee, I. C. Lee, H. D. Kim, Weon G. Jeong, J. W. Jang, N. J. Kim, M. S. Hwang, D. Lee, J. H. Lee, and D. K. Oh, *J. Appl. Phys.* **96**, 5766 (2004).
- <sup>7</sup>D. Chithrani, R. L. Williams, J. Lefebvre, P. J. Poole, and G. C. Aers, *Appl. Phys. Lett.* **84**, 978 (2004).
- <sup>8</sup>K. Takemoto, Y. Sakuma, S. Hirose, T. Usuki, and N. Yokoyama, *Jpn. J. Appl. Phys., Part 2* **43**, L349 (2004).
- <sup>9</sup>T. Miyazawa, K. Takemoto, Y. Sakuma, S. Hirose, T. Usuki, N. Yokoyama, M. Takatsu, and Y. Arakawa, *Jpn. J. Appl. Phys., Part 2* **44**, L620 (2005).
- <sup>10</sup>G. Saint-Girons, N. Chauvin, A. Michon, G. Patriarche, G. Beaudoin, G. Bremond, C. Bru-Chevallier, and I. Sagnes, *Appl. Phys. Lett.* **88**, 133101 (2006).
- <sup>11</sup>S. Anantathanasarn, R. Nötzel, P. J. van Veldhoven, T. J. Eijkemans, and J. H. Wolter, *J. Appl. Phys.* **98**, 013503 (2005).
- <sup>12</sup>M. Nakayama, K. Suyama, and H. Nishimura, *Phys. Rev. B* **51**, 7870 (1995).
- <sup>13</sup>N. I. Cade, H. Gotoh, H. Kamada, H. Nakano, and H. Okamoto, *Phys. Rev. B* **73**, 115322 (2006).
- <sup>14</sup>S. Rodt, R. Heitz, A. Schliwa, R. L. Sellin, F. Guffarth, and D. Bimberg, *Phys. Rev. B* **68**, 035331 (2003).
- <sup>15</sup>We plot the corrected linewidth  $\Gamma = (\Gamma_{\text{exp}}^2 - \Gamma_{\text{res}}^2)^{1/2}$ , where  $\Gamma_{\text{exp}}$  is the measured linewidth and  $\Gamma_{\text{res}}$  the instrument resolution.
- <sup>16</sup>L. Besombes, K. Kheng, L. Marsal, and H. Mariette, *Phys. Rev. B* **63**, 155307 (2001).
- <sup>17</sup>C. Kammerer, C. Voisin, G. Cassabois, C. Delalande, Ph. Roussignol, F. Klopff, J. P. Reithmaier, A. Forchel, and J. M. Gérard, *Phys. Rev. B* **66**, 041306(R) (2002).
- <sup>18</sup>M. Bayer and A. Forchel, *Phys. Rev. B* **65**, 041308 (2002).