

A versatile latex-based route furnishing polymer/carbon nanofiller composites

Citation for published version (APA):

Koning, C. E., Grossiord, N., Hermant, M. C., Loos, J., Lu, K., Yu, J., Meuldijk, J., Schoot, van der, P. P. A. M., Miltner, H. E., Van Mele, B., & Regev, O. (2011). A versatile latex-based route furnishing polymer/carbon nanofiller composites. In *Presentation at the First International Conference on Composites and Nanocomposites (ICNC 2011), 7-9 January 2011, Athirampuzha, Kerala, India*

Document status and date:

Published: 01/01/2011

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

A versatile latex-based route furnishing polymer/carbon nanofiller composites

C.E. Koning,^a N. Grossiord,^a M.C. Hermant,^a J. Loos,^a K. Lu,^a J. Yu,^a J. Meuldijk,^a P. v.d. Schoot,^a H. Miltner,^b B. Van Mele,^b O. Regev^c

^aEindhoven University of Technology, P.O. Box 513, 5600 MB Eindhoven, The Netherlands.

^bFree University of Brussels, PSSC, Pleinlaan 2, B-1050 Brussels, Belgium

^cBen-Gurion University of the Negev, 84105 Beer-Sheva, Israel

e-mail : c.e.koning@tue.nl

A versatile, latex-based concept for dispersing Single and Multi Wall Carbon Nanotubes (S/MWNTs) in a highly viscous polymer matrix is described [1]. The first, crucial step of the concept is the ultrasound-driven exfoliation of the as produced SWNT and MWNT bundles in water, containing surfactant for the stabilization of the obtained dispersion. By applying UV/Vis spectroscopy, the minimum required energy input for obtaining the maximum attainable degree of exfoliation of the nanotubes could be determined [2]. The exfoliation process was also directly visualized with cryo-TEM images, which were in agreement with the collected UV/Vis data.

The surface coverage of exfoliated carbon nanotubes with sodium dodecylsulfate (SDS) surfactant molecules was determined by thermogravimetric analysis, UV-Vis spectroscopy, surface tension measurements and a variant of Maron's titration [3]. All four methods, applied to aqueous mixtures of carbon nanotubes and the surfactant SDS, consistently yielded a surface coverage of approximately 2-3 SDS molecules per square nanometer, which is comparable to the known maximum packing density of SDS at the air-water interface and in agreement with the theoretical value calculated with the Gibbs equation for surface excess.

The second step of the concept is mixing the stable aqueous CNT dispersions with polymer latex, preferably stabilized by the same surfactant as the CNT dispersion. The third step implies freeze-drying, followed by melt processing of the obtained powder into a polymer film.

The extremely high aspect ratio of the CNTs, along with the very efficient way of dispersing them, generates a percolating network of the SWNTs in a highly viscous polystyrene (PS) matrix, which becomes semi-conductive for SWNT amounts as low as 0.2-0.3 wt %. For commercially available MWNTs, having a lower aspect ratio, the percolation threshold is around 1-2 wt%.

Depending on the molar mass distribution of the PS matrix in PS/SWNT nanocomposites, the well-dispersed CNTs significantly raise the T_g of the PS. A low molar mass PS fraction, probably acting as a wetting agent for the SWNTs and replacing SDS at the CNT surface during melt processing, seems to be required for an improved PS/SWNT interaction [4].

The versatility of the 'latex concept' is demonstrated for semi-crystalline polypropylene/CNT nanocomposites, prepared from aqueous PP emulsions. For this system, a very low percolation threshold was found, and the extremely well-dispersed CNTs proved to be excellent nucleation agents for PP, raising the crystallization temperature by ca. 15 °C.

Three attempts to enhance the conductivity properties of our polymer/CNT nanocomposites will be briefly described, viz. (1) the use of high quality, vertically grown MWNTs, (2) the replacement of SDS surfactant by conductive surfactants, lowering the contact resistivity, and (3) the manufacturing of conductive PS foams with reduced percolation thresholds.

Finally, the latex-concept was also successfully applied for the manufacturing of polymer/graphene nanocomposites.

[1] O. Regev et al., *Adv.Mater.* **2004**, *16*, 248

[2] N. Grossiord et al., *Anal. Chem.* **2005**, *77*, 5135

[3] N. Grossiord et al., *Langmuir*, **2007**, *23*, 3646

[4] N. Grossiord et al., *Chem.Mater.* **2007**, *19*, 3787