

Tissue substitute material

Citation for published version (APA):

Wijlaars, M. W., Huyghe, J. M. R. J., Donkelaar, van, C. C., & Stichting voor de Technische Wetenschappen (STW) (2005). Tissue substitute material.

Document status and date:

Published: 01/01/2005

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

WO2005004943

Publication Title:

TISSUE SUBSTITUTE MATERIAL

Abstract:

Fibre-reinforced material that substitutes for cartilage-like tissue, consisting of a hydrophilic, relatively elastic fibre structure and a matrix of polymerised hydrogel. The fibre/matrix bonding is increased by saturating the fibre in the monomer solution before polymerisation of the hydrogel. The fibre preferably consists of a material based on polyurethane. More particularly, this material contains 10-70 % (m/m) fibres (based on the dry matter) and 1-5 % (m/m) (based on the dry matter) of a substance that contains ionised groups has been added to said hydrogel.

Data supplied from the esp@cenet database - <http://ep.espacenet.com>

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
20 January 2005 (20.01.2005)

PCT

(10) International Publication Number
WO 2005/004943 A2

- (51) International Patent Classification⁷: A61L 27/52
- (21) International Application Number: PCT/NL.2004/000511
- (22) International Filing Date: 15 July 2004 (15.07.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 1023924 15 July 2003 (15.07.2003) NL
- (71) Applicant (for all designated States except US): STICHTING VOOR DE TECHNISCHE WETENSCHAPPEN [NL/NL]; Van Vollenhovenlaan 661, NL-3527 JP Utrecht (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): WIJLAARS, Marcel [NL/NL]; Baarlosestraat 25, NL-5921 EB Venlo (NL). HUYGHE, Jacques, Marie, René [NL/BE]; Sijssesstraat 3, B-2340 Beerse (BE). VAN DONKELAAR, Corrinus, Cornelis [NL/NL]; Atalantstraat 13, NL-5641 HJ Eindhoven (NL).
- (74) Agent: VAN WESTENBRUGGE, Andries et al.; Nederlandsch Octrooibureau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2005/004943 A2

(54) Title: TISSUE SUBSTITUTE MATERIAL

(57) Abstract: Fibre-reinforced material that substitutes for cartilage-like tissue, consisting of a hydrophilic, relatively elastic fibre structure and a matrix of polymerised hydrogel. The fibre/matrix bonding is increased by saturating the fibre in the monomer solution before polymerisation of the hydrogel. The fibre preferably consists of a material based on polyurethane. More particularly, this material contains 10-70 % (m/m) fibres (based on the dry matter) and 1-5 % (m/m) (based on the dry matter) of a substance that contains ionised groups has been added to said hydrogel.

Tissue substitute material

The present invention relates to a tissue substitute material, comprising a fibre-reinforced polymerised hydrogel. A tissue substitute material of this type is disclosed in:
5 "High-strength, ultra-thin and fiber-reinforced pHE-MA artificial skin," in Biomaterials 19 (1998) pp. 1745-1752. This publication discloses a skin substitute material consisting of a hydrogel that has been reinforced with fibres, such as Spandex fibres.

For replacement of cartilage-like tissue, such as, for example, the intervertebral disc or joint cartilage, the swelling behaviour of the abovementioned tissue substitute material is
10 relatively weak and the strength and toughness are inadequate. When put into the body, the properties of these tissues that are inherent to the body are not sufficiently simulated. This applies in particular in respect of the characteristic of these cartilage-like tissues of being able to swell when the composition of the fluid (water/salt) surrounding the tissues changes. Consequently, optimum adaptation to the environment cannot be provided.

15 The aim of the present invention is to provide a tissue substitute material that does have these properties, that is to say does have an ability to swell, it furthermore being important that the material has adequate strength and is relatively compliant.

Said aim is achieved with a tissue substitute material as described above in that the tissue substitute material simulates cartilage-like tissue and contains 10 - 70 % (m/m) fibres
20 (based on the dry matter) and in that 1 - 5 % (m/m) (based on the dry matter) of a substance that contains ionised groups has been added to said hydrogel.

The ionised groups provide a Donnan osmotic pressure in the hydrogel that pretensions the fibres. This phenomenon is analogous to the Donnan osmotic pressure of the ionised glycosaminoglycans in cartilage-like tissue that pretensions the collagen fibres
25 in the tissue. The choice of a relatively weak fibre ensures that forces along the hydrogel-fibre interface are sufficiently low. The tougher mechanical properties can be obtained by adding much more fibre compared with the known state of the art. However, in this context it is important that the swelling ability is retained and this is achieved by adding a substance that contains ionised groups. One example of such a substance is sodium methacrylate. The diameter and the form thereof are chosen depending on the properties
30 desired. The form can be, for example, knitted, wound, chopped fibres or non-woven. A diameter of 20 μm is given as an example. The length of the fibre can range from millimetres to kilometres.

An example of such a fibre is a fibre based on polyurethane. Lycra (Dupont de Nemours) and Spandex are examples of such fibres. It has been found that such materials are not hydrophilic for pure water. However, in combination with one or more monomers that create the hydrogel matrix on polymerisation hydrophilic properties are obtained and in
5 combination with the particularly elastic behaviour thereof a particularly robust bond to the matrix is obtained.

The volume of the fibre increases (up to 50 %) as a result of the penetration of the monomer solution into the fibre. As a result of the use of such fibres the mechanical properties and more particularly the elastic properties can be improved to such an extent
10 that the properties of cartilage are more closely approached.

The monomers from which the hydrogel can be obtained by polymerisation can comprise HEMA (hydroxyethyl methacrylate) and/or sodium methacrylate. Other monomers, optionally in combination with one another and with one of the substances mentioned above, are also possible. The hydrophilic character of these monomers can be
15 either based on adsorption or based on electrostatic attraction of hydrophilic cations by a fixed charge.

It has been found that a tissue substitute material obtained in this way has properties that approach the properties of cartilage or are even better than these. An appreciable percentage of pre-stretch is possible, whilst a high compressive strength (of the order of 10
20 MPa) is achievable. The tissue substitute material obtained in this way is compressible under long-term loading. The material is not compressible under short-term peak loads.

Polymerisation can be achieved with the aid of a chemical initiator, thermal initiation and/or initiation with the aid of light (UV).

It has been found that the tissue substitute material thus obtained swells to a greater
25 or lesser extent depending on the conditions of the fluid surrounding it. For instance, it is possible to immerse the material in a solution with a relatively high salt concentration, as a result of which this material assumes a relatively small volume. After putting into, for example, a living being, the salt concentration will fall and more water will be absorbed, as a result of which the volume of the tissue substitute material increases and clasping is
30 provided between the parts in which this tissue substitute material is used.

The amount of fibre compared with the polymerised hydrogel will be chosen depending on the desired strength. A value of approximately 60 % of the dry weight of fibre material is mentioned as an example.

The tissue substitute material described above can be produced by immersing the polyurethane-based fibre in an aqueous solution of one or more of the abovementioned monomers. The monomer solution is sucked up during immersion. The strength and rigidity of the material can be promoted by orienting the fibres. The polymerisation
5 described above then takes place. It is possible to provide the fibres with an orientation during immersion or, respectively, winding or knitting, so as to be able to influence the properties of the tissue substitute material in various directions.

From preliminary studies it is anticipated that the tissue substitute material produced in the manner described above is biocompatible.

10 In Figure 1 a comparison is made between the mechanical properties on compression of a hydrogel sphere without fibre reinforcement and a hydrogel sphere in which the outer millimetre has been reinforced according to the invention with 60 % (m/m) (based on the dry matter) fibres. The hydrogel without fibre reinforcement is shown in Figure 1a and the hydrogel with fiber reinforcement is shown in Figure 1b.

15 Although the invention has been described above on the basis of particular embodiments, obvious variants that fall within the scope of the appended claims will be apparent to those skilled in the art after reading the above.

Claims

1. Material for cartilage-like material substitution comprising a fibre-reinforced
from monomers polymerised hydrogel, whereby this contains 10 - 70 % (m/m) swellable
5 fibres (based on the dry matter) and whereby 1 - 5 % (m/m) (based on the dry matter) of a
substance that contains ionised groups has been added to said hydrogel.

2. Material for cartilage-like material substitution according to Claim 1, wherein
said hydrogel comprises a polymer based on hydroxyethyl methacrylate (HEMA).

10

3. Material for cartilage-like material substitution according to Claim 1 or 2,
wherein said substance containing ionised groups comprises methacrylic acid.

4. Material for cartilage-like material substitution according to Claim 3,
15 comprising 1 - 5 % (m/m) methacrylate.

5. Material for cartilage-like material substitution according to one of the
preceding claims, wherein said fibre comprises a fibre saturated in liquid.

20 6. Material for cartilage-like material substitution according to one of the
preceding claims, wherein said fibre comprises a fibre based on polyurethane material.

7. Prosthesis consisting of a material for cartilage-like material substitution
according to one of the preceding claims.

Fig 1a




Fig 1b

