

# Step wise mode I crack propagation in HEMA-NaMA hydrogels

**Citation for published version (APA):**

Pizzocolo, F., Ito, K., & Huyghe, J. M. R. J. (2011). *Step wise mode I crack propagation in HEMA-NaMA hydrogels*. Poster session presented at Mate Poster Award 2011 : 16th Annual Poster Contest.

**Document status and date:**

Published: 01/01/2011

**Document Version:**

Accepted manuscript including changes made at the peer-review stage

**Please check the document version of this publication:**

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

**General rights**

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

[www.tue.nl/taverne](http://www.tue.nl/taverne)

**Take down policy**

If you believe that this document breaches copyright please contact us at:

[openaccess@tue.nl](mailto:openaccess@tue.nl)

providing details and we will investigate your claim.

# Step wise mode I crack propagation in HEMA-NaMA hydrogels

Francesco Pizzocolo, Jacques Huyghe, Keita Ito



## Introduction

Hydrogels are used in many applications in the biomedical field, due to their peculiar properties such as good mechanical stability, permeability and bio- and blood- compatibility.



Fig. 1: Some hydrogel applications: skin layers, contact lenses, artificial intervertebral disc.

Performing experiments on HEMA-NaMA hydrogels, we want to investigate the behavior of the gel during crack opening and propagation.

## Aim of the study

New advances necessitate a better understanding of the mechanical behavior of the hydrogels.

## Results

We performed a standard single-edge notch test for 16 samples of 4 different stiffness. In each experiment the hydrogel showed a step-wise behavior of the crack during propagation.

E [Mpa]	ΔX [mm]		
	min	max	average
0.112	2.1	2.7	2.35
0.256	3.01	3.55	3.26
0.588	4.38	4.97	4.67
0.817	5.9	6.5	6.2

Fig. 2: Length of the steps for different stiff-ness of the hydrogel.




Fig. 3: Stepwise scheme for Mode I at each time step.





Fig. 4: Top: linear relation between the stiffness of the hydrogel and the average length of the steps. Bottom: hyperbolic relation between the stiffness and the time span during which the crack propagation pauses.

## Discussion

The cracking surface has a toothed appearance (fig. 5) as a consequence of the step-wise propagation coupled to some extent of plastic deformation. Both the distance of propagation in one step as the time span during which the propagation pauses between the steps depend on the Young's modulus of the gel (fig. 4). The former is positively correlated with the Young's modulus while the latter is negatively correlated with the Young's modulus.



Fig. 5: Tooth shape repeating along the lip of the crack .

## Conclusions

We showed that in HEMA – NaMA hydrogels a cracks does not propagate smoothly, but following a step wise scheme. This result also support numerical simulations of crack propagation in porous materials .