

Looking for a relation between sensory and instrumental data

Citation for published version (APA):

Jeurissen, P. C. J. (1991). *Looking for a relation between sensory and instrumental data*. Eindhoven University of Technology.

Document status and date:

Published: 01/01/1991

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

Eindverslag van de ontwerpersopleiding
WISKUNDE VOOR DE INDUSTRIE

Final report of the postgraduate programme
MATHEMATICS FOR INDUSTRY

**LOOKING FOR A RELATION BETWEEN
SENSORY AND INSTRUMENTAL DATA**

Ir P.C.J. Jeurissen

University supervisor: Dr ir N.H. Linssen,
Technische Universiteit, Eindhoven

Industrial supervisor: Mr P.T. Whitthall,
Unilever Research, Bebington (UK)

February 1991

CIP data, Koninklijke Bibliotheek, Den Haag

Jeurissen, P.C.J.

Looking for a relation between sensory and instrumental data /
P.C.J. Jeurissen; [ill. by the author]. - Eindhoven: Instituut Vervolg-
opleidingen, Technische Universiteit Eindhoven. - Ill.
Final report of the postgraduate programme Mathematics for industry.
With index, ref.
ISBN 90-5282-118-6 bound

Subject headings: linear regression / empirical models.

© P.C.J. Jeurissen, Eindhoven

Niets uit deze uitgave mag worden vermenigvuldigd en/of openbaar
gemaakt door middel van druk, fotokopie, microfilm of op welke
andere wijze dan ook zonder voorafgaande schriftelijke toestemming
van de auteur.

No part of this publication may be reproduced or transmitted in any
form or by any means, electronic or mechanical, including photocopy,
recording, or any information storage and retrieval system, without
permission from the copyright owner.

ISBN 90 5282 118 6

Contents

1	Introduction	3
1.1	Objective of the report	3
1.2	Description of the Data	3
1.2.1	Sensory Data	3
1.2.2	Mechanical Data	5
2	Warp and weft measurements	8
2.1	Introduction	8
2.2	Results from the Plots	8
2.2.1	BEND	8
2.2.2	RIGID, flexural rigidity	11
2.2.3	EMT, tensile	11
2.2.4	RT, tensile	11
2.2.5	WT, tensile	11
2.2.6	G, shear stiffness	11
2.2.7	2HG, shear hysteresis at 0.5°	11
2.2.8	2HG5, shear hysteresis at 5°	11
2.3	Conclusion	11
3	Linear Regression Modelling	18
3.1	Modelling details	18
3.2	Felting	19
3.3	Thick	19
3.4	Stretchiness	22
3.5	Bounciness	22
3.6	Greasiness	25
3.7	Flexiness	25
3.8	Smoothness	29
3.9	Warmth	29
3.10	Softness	31
3.11	Man-made feel	34
3.12	Conclusion	34
4	Transformed Linear Modelling	36
4.1	Looking for optimal transformations	36
4.2	Estimating the optimal transformations	38
4.3	Estimating the nonlinear model	39
4.4	A second model	39
4.5	Looking for optimal transformations again	39
4.6	Estimating the optimal transformations again	41
4.7	Estimating the nonlinear model again	41
4.8	Conclusions	41

List of Figures

1.1	A typical stress/strain curve with tensile parameters indicated	6
1.2	A typical shear hysteresis curve with shear parameters indicated	6
1.3	A typical compression hysteresis curve	7
2.1	Plots for bend	9
2.2	Plots for rigid	10
2.3	Plots for emt	12
2.4	Plots for rt	13
2.5	Plots for wt	14
2.6	Plots for g	15
2.7	Plots for 2hg	16
2.8	Plots for 2hg5	17
3.1	Plots of FELTING against predicted value and against residual	20
3.2	Plots of thick against predicted value and against residual	21
3.3	Plots of STRETCHINESS against predicted value and against residual	23
3.4	Plots of BOUNCINESS against predicted value and against residual	24
3.5	Plots of BOUNCINESS against predicted value and against residual, for interlocks	26
3.6	Plots of GREASINESS against predicted value and against residual	27
3.7	Plots of FLEXINESS against predicted value and against residual	28
3.8	Plots of SMOOTHNESS against predicted value and against residual	30
3.9	Plots of WARMTH against predicted value and against residual	32
3.10	Plots of SOFTNESS against predicted value and against residual	33
3.11	Plots of MM.FEEL against predicted value and against residual	35
4.1	Figure with some nonlinear transformations	37
4.2	Predicted value and residuals, using all the data	40
4.3	Predicted value and residual using 2/3rd of the data	42

Chapter 1

Introduction

1.1 Objective of the report

The objective of this report is to have a valid relation between sensory assessment and instrumental measurements. The answer is desirable for several reasons. If a particular sensory property is of interest, only the relevant instrumental properties have to be measured. Secondly the expected sensory score may be predicted from measured instrumental data. Thirdly, an understanding of the mechanical basis of a sensory property should allow the design of systems which would influence this particular physical basis. Similar research is reported in [3] and [5].

The data used for this research were not gathered specifically for this purpose, but to improve the understanding of the effects of washing product formulations, and wash process variables, on the properties of a selection of 'consumer relevant' fabric types.

1.2 Description of the Data

We have three types of fabric construction, interlocks (I), poplins (P), and terry towels (T), and several different fibres within the interlocks, cotton, acrylic, polyester and nylon. These fabrics are washed and dried a number of times, in water or in a product. Water washed fabrics are line dried or tumble dried, all fabrics washed in product are tumble dried. There are no repeated observations.

It is reasonable to believe that the influence of different fabric constructions can be obviated within the instrumental measurements.

1.2.1 Sensory Data

The sensory evaluation was done by a trained panel. The descriptors used in fabric evaluation are:

FELTING	THICK	STRETCHINESS	BOUNCINESS	GREASINESS
FLEXIBILITY	SMOOTHNESS	WARMTH	SOFTNESS	MAN-MADE FEEL

Felting

Felting appears differently according to the construction of the fabric. We can identify:

on rib knits and interlocks Felting is most obvious on rib knits, particularly wool which may start to felt after only one wash. There are a number of physical changes associated with felting. The fabric shrinks and becomes thicker, goes progressively stiffer and loses suppleness, and develops a noticeable 'fuzz' of matted fibres on the surface which gives the fabric a greyish appearance and obscures the grooves in the rib. The amount of felting on the sample

is judged by assessing how much surface fuzz is present, and ignoring all other associated physical changes.

on terry towelling felting appears as matted 'fuzz' inside the loops, and also as matted tufts 'sitting' on the loops. The more fuzz there is blocking up and sitting on the loops, the higher the level of felting.

Thick

Thick is defined as the distance between the upper and lower surfaces. On terry towelling the loops are also taken into consideration so that thick is considered from the loop tip on the upper surface to the loop tip in the under surface.

Stretchiness

Stretchiness is defined as the ease of distortion by stretching fabric outwards. The further out the fabric stretches, the more stretchiness it has. For most fabrics, assessment for stretchiness is made by taking firm hold of either side of the fabric and pulling outwards to maximum stretch. This is done first in one direction and then the fabric is turned through 90° and repeated in the other direction. The fabric is not stretched on the diagonal as this gives a very false impression of overall stretch.

Bounciness

Bounciness is defined as the rate and degree of success with which the fabric 'bounces back' after having been crumpled in the palm. A very bouncy fabric will spring quickly back to shape and will leave less surface indentations, returning much more successfully to its original shape.

Greasiness

Greasiness, on all fabric types, is defined as the degree to which the surface of the fabric feels as though it has a greasy coating which gives a slip-slide greasy feel.

Flexibility

Flexibility is defined as 'floppiness', and absence of rigidity or stiffness. The more floppiness the fabric has the more flexibility it has.

Smoothness

Smoothness is defined as the lack of roughness experienced when moving the flat of the hand across the fabric; an absence of surface friction. The more smoothly and easily the hand glides across the surface and the less roughness is detected, the more smoothness the fabric has.

Warmth

Warmth is defined as 'the degree of apparent warmth given off by the fabric'.

Softness

Softness is very simply defined as how soft the fabric feels to the touch. This is often described as a lack of stiffness or hardness.

Man-made feel

Man-made feel is described as a synthetic feel to the fabric. As there is a very wide range of synthetic fabric types, this is a subjective measurement. Another way to describe this is as a 'lack of natural feel for that fabric type'.

1.2.2 Mechanical Data

The following measurements were made on all new fabrics , and then after 1, 10, 25, and 50 wash/dry cycles:

AREA_SHRINKAGE	THICKNESS	WEIGHT	
WARP_BEND	WEFT_BEND	WARP_RIGID	WEFT_RIGID
WARP_EMT	WEFT_EMT	WARP_RT	WEFT_RT
WARP_WT	WEFT_WT	WARP_G	WEFT_G
WARP_2HG	WEFT_2HG	WARP_2HG5	WEFT_2HG5
COMP_INT	COMP_LOOP	CROSS_MOVE	

AREA_SHRINKAGE

A 10cm-10cm square was marked on the new fabric and this was measured after 1, 10, 25 and 50 washes.

THICKNESS

This was measured using a Shirley micro gauge.

WEIGHT

A 20cm-20cm piece of fabric was weighted and this was transformed to mg/cm².

WARP_BEND, WEFT_BEND, WARP_RIGID, WEFT_RIGID

The bending length of fabric, c , is the length of fabric that will bend under its own weight to a definite angle. It is a measure of the stiffness that determines draping quality. The flexural rigidity, G , is a measure of stiffness associated with handle, i.e. whether the fabric can be handled easily. G is calculated from the bending length c and the weight per unit area of the fabric w as $G = w \times c^3$. The bending length and flexural rigidity are measured in both warp and weft directions, giving WARP_BEND, WEFT_BEND WARP_RIGID and WEFT_RIGID.

WARP_EMT, WEFT_EMT, WARP_RT, WEFT_RT, WARP_WT, WEFT_WT

These tensile properties on all fabrics were obtained from tensile hysteresis curves for both warp and weft directions A typical tensile hysteresis curve is illustrated in figure 1.1, from which the following tensile parameters are obtainable:

1. WARP_EMT and WEFT_EMT, the percentage extension at a specified load (500 gf/cm for poplins or towels or 50 gf/cm for interlocks).
2. WARP_RT and WEFT_RT, the percentage resilience or recovery of the fabric from extension.
3. WARP_WT and WEFT_WT, the work done in extending fabric to this specified load.




Figure 1.1: A typical stress/strain curve with tensile parameters indicated




Figure 1.2: A typical shear hysteresis curve with shear parameters indicated




Figure 1.3: A typical compression hysteresis curve

WARP_G, WEFT_G, WARP_2HG, WEFT_2HG, WARP_2HG5, WEFT_2HG5

These shear properties were obtained from the shear hysteresis curves. A similar procedure to tensile measurements was followed. A typical shear hysteresis loop is illustrated in figure 1.2. Shear variables are

1. WARP_G and WEFT_G, the shear stiffness or "elastic shear rigidity" given by the slope of the hysteresis curve between $\phi = 0.5^\circ$ and $\phi = 2.5^\circ$.
2. WARP_2HG and WEFT_2HG, the hysteresis at a deformation of 0.5° , and
3. WARP_2HG5 and WEFT_2HG5, the hysteresis at a deformation of 5° .

COMP_INT, COMP_LOOP, CROSS_MOVE

These compression properties were obtained from compression hysteresis curves for a maximum applied force of 5N. A typical hysteresis curve is shown in figure 1.3. Compression variables are:

1. COMP_INT, work done, to the 5N maximum.
2. COMP_LOOP, hysteresis loss, directly related to the loop area.
3. CROSS_MOVE, compression, the distance of cross-head movement (in mm) between 0.25 and 5 N.

Chapter 2

Warp and weft measurements

In most literature, for example in [3], the mean of the warp and weft measurements is used. The purpose of this chapter is to check whether this is a priori possible in our case.

2.1 Introduction

We have eight properties of the fabrics that are measured in warp and weft directions. These are

- WARP_BEND and WEFT_BEND, the bending length,
- WARP_RIGID and WEFT_RIGID, the flexural rigidity (weight per unit area \times bending length³),
- WARP_EMT and WEFT_EMT, the percentage extension at a specified load (500 gf/cm for woven fabrics or 50 gf/cm for fabrics with a knitted construction),
- WARP_RT and WEFT_RT, the percentage resilience or recovery of fabric form extension,
- WARP_WT and WEFT_WT, the work done in extending fabric to a specified load (500 gf/cm for woven fabrics or 50 gf/cm for fabrics with a knitted construction),
- WARP_G and WEFT_G, shear stiffness or elastic shear rigidity,
- WARP_2HG and WEFT_2HG, hysteresis at $\phi = 0.5^\circ$,
- WARP_2HG5 and WEFT_2HG5, hysteresis at $\phi = 5^\circ$.


We have plotted warp, weft and mean value in one graph, and also the mean value against the difference between warp and weft values. If warp and weft values are equal or a linear relation between the mean and the difference is obvious from the graph, it is useless to differentiate between warp and weft value.

2.2 Results from the Plots

2.2.1 BEND

We have one outlier. (See figure 2.1.) The differences within the constructions are small, but the relationship between mean and difference is different for the different constructions. So if we want a model for all fabrics, we cannot a priori use the mean.

RELATION BETWEEN WARP AND WEFT VALUES BENDING



RELATION BETWEEN MEAN AND DIFFERENCES WARP AND WEFT, BENDING





Figure 2.1: Plots for bend

RELATION BETWEEN WARP AND WEFT VALUES RIGID



RELATION BETWEEN MEAN AND DIFFERENCES WARP AND WEFT, RIGID




Figure 2.2: Plots for rigid

2.2.2 RIGID, flexural rigidity

Again we find one outlier, which is the same as with bending. We expected this, because of the way the flexural rigidity is calculated. (See figure 2.2.) The group in the lower-right corner are all towels. If we excluded the towels, it seems a fairly good relationship, but since the scale of the differences is similar to that of the means, I am not sure we could use just the mean in that case. If we include the towels, we cannot use the mean.

2.2.3 EMT, tensile

We have three fabrics with warp larger than weft. (See figure 2.3.) We can see no special relations, so we need both warp and weft values, even if we consider just one fabric. There are 7 interlocks higher than all the other interlocks, these are all nylons.

2.2.4 RT, tensile

All the towels are close together, no specific relation; it seems that the poplins are almost on one line. (See figure 2.4.) The interlocks are widely spread and we can identify four groups. The first one is a group with a difference of around 10, which are the nylons. The next group are the cotton interlocks, with means between 28 and 38 and differences between -10 and +5. The polyesters are almost on one line, with means from 42 to 54 and differences from -8 to -2. The acrylics are below this group, with means from 44 to 50 and differences from -20 to -8. Clearly we need to try both warp and weft values, except maybe for the poplins.

2.2.5 WT, tensile

The three groups are clearly interlocks, poplins and towels. (See figure 2.5.) For the interlocks the means would be enough, but for the other two groups we need to try both warp and weft values.

2.2.6 G, shear stiffness

We have one outlier, a towel. (See figure 2.6.) We also see 4 poplins with large MEAN_G. We need to try both warp and weft values.

2.2.7 2HG, shear hysteresis at 0.5°

Again we can identify three groups. (See figure 2.7.) Four poplins are a long way from the rest of the fabrics. These are the same as we found with MEAN_G. We also find the outlying towel again.


2.2.8 2HG5, shear hysteresis at 5°

Again we find the three groups. (See figure 2.8.) One towel is far from the other towels, at the far end of the poplins. This is again the same towel. Just below this are the four extreme poplins again.

2.3 Conclusion

Since we are interested in a general model accros different fabrics and constructions, we have to try both warp and weft measurements, instead of just the mean value.

RELATION BETWEEN WARP AND WEFT VALUES
EMT



RELATION BETWEEN MEAN AND DIFFERENCES
WARP AND WEFT, EMT





Figure 2.3: Plots for emt

RELATION BETWEEN WARP AND WEFT VALUES

RT



RELATION BETWEEN MEAN AND DIFFERENCES

WARP AND WEFT, RT





Figure 2.4: Plots for rt

RELATION BETWEEN WARP AND WEFT VALUES

WT



RELATION BETWEEN MEAN AND DIFFERENCES

WARP AND WEFT, WT





Figure 2.5: Plots for wt

RELATION BETWEEN WARP AND WEFT VALUES



RELATION BETWEEN MEAN AND DIFFERENCES

WARP AND WEFT, G





Figure 2.6: Plots for g

RELATION BETWEEN WARP AND WEFT VALUES
2HG



RELATION BETWEEN MEAN AND DIFFERENCES
WARP AND WEFT, 2HG





Figure 2.7: Plots for 2hg

RELATION BETWEEN WARP AND WEFT VALUES

2HG5



RELATION BETWEEN MEAN AND DIFFERENCES

WARP AND WEFT, 2HG5




Figure 2.8: Plots for 2hg5

Chapter 3

Linear Regression Modelling

3.1 Modelling details

We assume a linear model with p terms

$$y = \beta_0 + \sum_{i=1}^p \beta_i x_i + e_i \quad e_i \sim N(0, \sigma^2).$$

The p terms are chosen using a stepwise linear regression procedure. A stepwise linear regression procedure starts with an empty model (i.e. no x_i 's), and searches for that variable that gives the biggest improvement in the model. Then the resulting model is tested, on whether we can drop one of the variables. The search is then repeated, until no more variables can be added to the model, either because all variables are in the model, or because the influence of the remaining variables is too low.

We choose the variables from all instrumental measurements, untransformed and not taking cross products. This gives 22 possible predictors, while we have 71 observations.

The coefficient of determination

$$R^2 = 1 - \frac{\sum (y_i - \hat{y}_i)^2}{\sum (y_i - \bar{y})^2}$$

is a measure of the proportion of variation in the variable y explained by the model. Since the R^2 increases as the number of predictors in the model increases, we adjust the coefficient of determination to:

$$R^2 = 1 - \left(\frac{n-1}{n-p} \right) (1 - R^2).$$

More information on linear regression is available in [4].

As we have a number of explaining variables, and we do not know whether we need all of them, a stepwise regression is a good first start of the analysis.

In the remainder of this chapter we will discuss the results of a stepwise linear regression for all sensory measurements on all fabrics and on the subgroup of interlocks. We will only consider the model for interlocks if the coefficient of determination for this model is higher, since we are mainly interested in models for all fabrics. Regression for other subgroups (poplins and towels) was not possible because a lack of data in these groups. On all graphs the groups are separated (I=interlocks, P=poplins, T=towels).

3.2 Felting

A stepwise linear regression of the sensory measurement FELTING and all instrumental measurements on all fabrics gives the following model

$$\text{FELTING} = -26.95 - 27.44*\text{THICKNESS} + 5.265*\text{WEIGHT} - 0.0103*\text{COMP_INT} - 4.117*\text{WARP_EMT}$$

This model has an $R^2 = 0.754$ and two outliers.

Looking at the plots of FELTING against the predicted value and against the residuals, see figure 3.1, we see that the residuals for the poplins are smaller than those for the interlocks or the towels. Also FELTING is low for the poplins and high for the towels. This is as we would expect, since felting is not significant for poplin cottons. It is of course very significant for towels. The interlocks are intermediate.

Another thing we can notice is that there are some very large positive residuals, larger than the corresponding predicted value. Therefore we try a stepwise linear regression on the interlocks alone.

The model we get from this analysis is

$$\text{FELTING} = -35.13 - 113.9*\text{THICKNESS} + 7.11*\text{WEIGHT}$$

This model has an $R^2 = 0.430$ and one outlier. The R^2 of this model is fairly low so we will not consider this model any further.

The significance of all parameters is as follows:

Independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	-26.95	11.62	-2.3188	0.0235
THICKNESS	-27.44	17.32	-1.5842	0.1179
WEIGHT	5.265	0.849	6.2022	0.0000
COMP.INT	-0.0103	0.00233	-4.4080	0.0000
WARP.EMT	-4.117	1.414	-2.9111	0.0049

From this table we can see that the most significant variables in this model are WEIGHT and COMP.INT. A higher weight and a lower compression integral are associated with higher felting. The higher WEIGHT is associated with towels, which have a much higher chance of felting. The lower compression integral means that it is easier to compress the fabric, or that the fabric is less washed. The variable WARP.EMT is also a significant variable. A higher value of WARP.EMT gives a lower value of felting. THICKNESS is not that important.

3.3 Thick

The second sensory measurement is THICK. Linear regression on all fabrics gives

$$\text{THICKNESS} = -34.70 + 1.706*\text{WEIGHT} + 0.0167*\text{COMP_LOOP} + 46.31*\text{WEFT_BEND} - 3.045*\text{WARP_WT} - 5.165*\text{WEFT_2HG5}$$

This model has an $R^2 = 0.929$ and no outliers.

If we look at the plots of THICK against predicted value and residual (see figure 3.2), we see a reasonable relation between these values. On the plot of THICK against residual, we can see a relation between THICK and residual within the poplins.

The significance of all parameters is as follows

independent variable	coefficient	std. error	t-value	sig. level
INTERCEPT	-34.70	12.56	-2.7625	0.0075
WEIGHT	1.706	0.330	5.1628	0.0000
COMP_LOOP	0.0167	0.00307	5.4539	0.0000
WEFT_BEND	46.31	9.056	5.1143	0.0000
WARP_WT	-3.045	0.580	-5.2467	0.0000
WEFT_2HG5	-5.165	1.794	-2.8785	0.0054

Note that the instrumental measurement THICKNESS is not part of the model for the sensory measurement THICK, because THICKNESS is highly correlated with WEIGHT and




Figure 3.1: Plots of FELTING against predicted value and against residual




Figure 3.2: Plots of thick against predicted value and against residual

COMP_LOOP. High values of THICK are associated with high values of WEIGHT, COMP_LOOP and WARP_BEND and low values of WARP_WT and WEFT_2HG5.

3.4 Stretchiness

A stepwise linear regression for the sensory measurement STRETCHINESS and all instrumental measurements on all fabrics gives the following model

$$\text{STRETCHINESS} = 172.2 - 1.239*\text{WEIGHT} - 0.0256*\text{COMP_INT} + 122.8*\text{CROSS_MOVE} + 5.53*\text{WEFT_EMT} - 1.651*\text{WEFT_RT} - 7.703*\text{WEFT_WT}$$

This model has an $R^2 = 0.888$ and one outlier.

Looking at the plots of STRETCHINESS against the predicted value and against the residuals, see figure 3.3, we see that the model does not predict stretchiness very well. The high coefficient of determination is explained by the difference between fabric constructions. The model separates the fabrics in woven (poplins and towels) and knitted (interlocks) fabrics. All interlock predicted values of stretchiness are around 120. The plot of residuals showed a clear linear relation between value and residual for the woven fabrics. The dispersion of the residuals for the woven values is also very high compared to the value of stretchiness. The above linear relation does not predict stretchiness, but separates woven and knitted fabrics.

Trying a stepwise linear regression on the interlocks alone we find the following model:

$$\text{STRETCHINESS} = 105.0 + 15.06*\text{WARP_WT}$$

This model has an $R^2 = 0.045$. This model can hardly be called a model. A possible explanation of this phenomenon is that the interlocks have a very high stretchiness. This result indicates that the procedure for assessing stretchiness is not good enough for interlocks. If we are interested in stretchiness for interlocks, the panel, or another one, should be trained on interlocks for measuring stretchiness. A further analysis of these values does not seem useful.

If we consider the first model for STRETCHINESS again, we can test for significance. We get

independent variable	coefficient	std. error	t-value	sig. level
INTERCEPT	172.22	21.87	7.8753	0.0000
WEIGHT	-1.239	0.5385	-2.3010	0.0247
COMP.INT	-0.0256	0.01010	-2.5356	0.0137
CROSS_MOVE	122.80	31.818	3.8595	0.0003
WEFT.EMT	5.529	1.3208	4.0866	0.0001
WEFT_RT	-1.651	0.3368	-4.9009	0.0000
WEFT.WT	-7.7030	0.4276	-18.0151	0.0000

The three most significant variables are three weft tensile measurements, the percentage extension with a positive parameter, the percentage recovery and the work done in extension with negative parameters. Two compression parameters are also in the model. We have variables in the model that we would expect to be in the model.

3.5 Bounciness

A stepwise linear regression of the sensory measurement BOUNCINESS and all Instrumental measurements on all fabrics gives the following model

$$\text{BOUNCINESS} = 70.85 + 0.00427*\text{COMP_INT} - 39.99*\text{WARP_BEND} + 0.0354*\text{WARP_RIGID} + 4.126*\text{WARP_EMT} + 0.7636*\text{WEFT_RT} + 8.397*\text{WARP_2HG}$$

This model has an $R^2 = 0.408$ and two outliers.

Looking at the plots of BOUNCINESS against the predicted value and against the residuals, see figure 3.4, we see a group of 6 poplins with large negative residuals, the towels with approximately the same predicted value, 110-120, and a reasonable distribution of the residuals of the interlocks. The six poplins are the two new poplins and the four poplins washed 1 time in water. Washing the poplins in product increases the bounciness to values found with other fabrics. The product has a definite influence here.




Figure 3.3: Plots of STRETCHINESS against predicted value and against residual




Figure 3.4: Plots of BOUNCINESS against predicted value and against residual

Because the above model seems best for the interlocks, we try a stepwise linear regression on the interlocks alone. The model we get from this analysis is

$$\text{BOUNCINESS} = -9.365 - 48.63 \cdot \text{CROSS_MOVE} + 2.146 \cdot \text{WEFT_RT} + 12.35 \cdot \text{WARP_2HG} - 7.433 \cdot \text{WEFT_2HG5}$$

This model has an $R^2 = 0.617$ and two outliers. This model is better than the above model for all fabrics. If we look at the plots for this analysis, see figure 3.5 we see no linear relation on the plot for residuals.

As the second model is better than the first one, we test the parameters of the second model. We get

Independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	-9.364	21.444	-0.4367	0.6652
CROSS.MOVE	-48.629	26.115	-1.8620	0.0715
WEFT_RT	2.1457	0.3939	5.4474	0.0000
WARP_2HG	12.349	4.5209	2.7316	0.0100
WEFT_2HG5	-7.4239	3.4279	-2.1683	0.0374

The most significant variable is the warp tensile percentage recovery measurement. The next significant variable is the shear hysteresis measurements at 0.5° . The intercept is not significant at all.

3.6 Greasiness

A stepwise linear regression of the sensory measurement GREASINESS and all instrumental measurements on all fabrics gives the following model

$$\text{GREASINESS} = 104.9 - 0.8033 \cdot \text{WEFT_RT} - 4.417 \cdot \text{WARP_2HG5}$$

This model has an $R^2 = 0.381$ and no outliers. Looking at the plots of GREASINESS against the predicted value and against the residuals, see figure 3.6, we see two horizontal bands of points. In the lower band are all the poplins and one towel, the towel washed 50 times in water at 60°C and line dried, in the higher band are all the interlocks and the other towels.

A stepwise linear regression on the interlocks alone gives the following model.

$$\text{GREASINESS} = 114.9 - 4.690 \cdot \text{WEIGHT} + 76.37 \cdot \text{CROSS_MOVE} + 14.33 \cdot \text{WARP_WT} + 1.446 \cdot \text{AREA_SHRINKAGE}$$

This model has an $R^2 = 0.247$ and one outlier. The R^2 of both models is too low so we will not consider them any further.

One possible explanation for the bad models is that greasiness is a surface property. At this moment no surface measurements are in the database. These will be available in the future, at that time the analysis can be repeated.

3.7 Flexiness

A stepwise linear regression of the sensory measurement FLEXINESS and all instrumental measurements on all fabrics gives the following model

$$\text{FLEXINESS} = 269.2 + 23.72 \cdot \text{WARP_BEND} - 138.7 \cdot \text{WEFT_BEND} + 0.1055 \cdot \text{WEFT_RIGID} + 14.78 \cdot \text{WEFT_G}$$

This model has an $R^2 = 0.703$ and one outlier.

Looking at the plots of FLEXINESS against the predicted value and against the residuals, see figure 3.7, we see that this model is a fairly good description of the flexiness, with no apparent discrepancies. In the plot of the residuals a slight linear relation still exists between the flexiness and the residual. Therefore we also try a stepwise linear regression on the interlocks alone.

The model we get from this analysis is

$$\text{FLEXINESS} = 50.85 - 0.8366 \cdot \text{WEFT_RIGID} + 1.089 \cdot \text{WARP_RT} + 30.46 \cdot \text{WARP_2HG5} + 1.192 \cdot \text{AREA_SHRINKAGE}$$

This model has an $R^2 = 0.659$ and one outlier. The R^2 of this model is lower than that of the model calculated from all fabrics, so we will not consider this model any further.




Figure 3.5: Plots of BOUNCINESS against predicted value and against residual, for interlocks




Figure 3.6: Plots of GREASINESS against predicted value and against residual




Figure 3.7: Plots of FLEXINESS against predicted value and against residual

The significance of all parameters of the first model are as follows:

Independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	296.33	16.14	16.6910	0.0000
WARP_BEND	23.72	6.946	3.4153	0.0011
WEFT_BEND	-138.73	14.45	-9.6028	0.0000
WEFT_RIGID	0.1055	0.0150	7.0523	0.0000
WEFT_G	14.78	5.270	2.8046	0.0066

From this table we can see that the most important variables in this model are WEFT_BEND and WEFT_RIGID. A lower WEFT_BEND, and a higher WEFT_RIGID are associated with higher flexiness. These two values are related via

$$\text{WEFT_RIGID} = \text{WEIGHT} * (\text{WEFT_BEND})^3.$$

Other important values are WARP_BEND and WEFT_G, the shear stiffness or 'elastic shear rigidity'. All these measurements are measurements of flexiness.

3.8 Smoothness

A stepwise linear regression of the sensory measurement SMOOTHNESS and all Instrumental measurements on all fabrics gives the following model

$$\text{SMOOTHNESS} = 211.5 - 55.23 * \text{THICKNESS} - 0.01603 * \text{COMP_INT} + 67.5 * \text{CROSS_MOVE} - 1.581 * \text{WARP_RT} - 5.425 * \text{WARP_G}$$

This model has an $R^2 = 0.620$ and one outlier.

This model is a fairly good description of the smoothness of towels, judging from plots of smoothness, see figure 3.8, but does not give any information on the smoothness of poplins and interlocks. The plot of the residuals gives the same view, reasonable for towels, but a clear relation left for other fabrics.

Therefore we try a stepwise linear regression on interlocks. This gives the following result

$$\text{SMOOTHNESS} = 14.6 + 109.6 * \text{CROSS_MOVE} + 36.18 * \text{WEFT_BEND}$$

This model has an $R^2 = 0.088$ and two outliers. This model gives no useful information.

The significance of all parameters of the first model is as follows:

independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	211.49	27.30	7.7441	0.0000
THICKNESS	-55.23	10.14	-5.4447	0.0000
COMP_INT	-0.01603	0.009453	-1.6957	0.0947
CROSS_MOVE	67.50	31.89	2.1164	0.0381
WARP_RT	-1.581	0.5737	-2.7556	0.0076
WARP_G	-5.425	3.645	-1.4884	0.1415

The most important variable is THICKNESS, with a negative coefficient. This means that a thicker fabric is less smooth. This is a understandable variable, since the thinnest fabrics in the experiment are poplins, these are the smoothest fabrics too. Also the thickest fabrics are towels, which are not very smooth. The next important variable is WARP_RT. This is the warp value of percentage recovery from tensile extension. Again a lower percentage recovery is associated with a smoother fabric. This is also understandable; if a fabric is very smooth, it does not have much elasticity, and the recovery from a tensile extension is lower. The variable CROSS_MOVE is significant with a positive parameter. This variable is also a measurement of elasticity of the fabric. Again, as soon as surface measurements are available, this analysis should be repeated.

3.9 Warmth

A stepwise linear regression of the sensory measurement WARMTH and all instrumental measurements on all fabrics gives the following model




Figure 3.8: Plots of SMOOTHNESS against predicted value and against residual

$$\text{WARMTH} = 176.4 + 0.02485 * \text{COMP_LOOP} - 11.73 * \text{WARP_BEND} - 1.965 * \text{WEFT_EMT} \\ - 1.383 * \text{WARP_RT} - 2.558 * \text{WEFT_WT}$$

This model has an $R^2 = 0.862$ and one outlier.

Looking at the plots of WARMTH against the predicted value and against the residuals, see figure 3.9, we see that this model is a fairly good description of the warmth, with no apparent discrepancies. We can test the significance of all parameters. We get

independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	176.41	22.30	7.9099	0.0000
COMP_LOOP	0.02485	0.00179	13.8770	0.0000
WARP_BEND	-11.73	3.868	-3.0327	0.0035
WEFT_EMT	-1.965	0.7285	-2.6969	0.0089
WARP_RT	-1.3829	0.3429	-4.0326	0.0001
WEFT_WT	-2.5594	0.2522	-10.1473	0.0000

From this table we can see that the most important variables in this model are COMP_LOOP and WEFT_WT. A higher compression loop and a lower weft value of work done in tensile extension are associated with higher warmth. Other important values are WARP_RT, WARP_BEND and WEFT_EMT,

3.10 Softness

A stepwise linear regression of the sensory measurement SOFTNESS and all Instrumental measurements on all fabrics gives the following model

$$\text{SOFTNESS} = 394.6 - 44.23 * \text{WEIGHT} + 0.04558 * \text{COMP_LOOP} - 82.88 * \text{WEFT_BEND} \\ + 0.1433 * \text{WEFT_RIGID} - 1.624 * \text{WARP_RT} - 2.712 * \text{WEFT_WT} \\ + 0.7219 * \text{AREA_SHRINKAGE}$$

This model has an $R^2 = 0.728$ and two outliers.

Looking at the plots of SOFTNESS against the predicted value and against the residuals, see figure 3.10, we see that all the poplins have a predicted value lower than 80, whether SOFTNESS is as low as 35 or as high as 95. The residuals of the towels are also very high for low values of softness. Also a linear relation on the residuals plot exists for the interlocks.

Therefore we try a stepwise linear regression on the interlocks alone. The model we get from this analysis is

$$\text{SOFTNESS} = 281.3 - 135.5 * \text{WEFT_BEND} - 0.04052 * \text{WARP_RIGID} - 24.07 * \text{WEFT_2HG} \\ + 53.63 * \text{WARP_2HG5}$$

This model has an $R^2 = 0.611$ and one outlier. The R^2 of this model is lower than that of the above model, so we will not consider this model any further.

The significance of all parameters of the first model are as follows:

independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	394.6	49.89	7.9100	0.0000
WEIGHT	-5.5503	1.097	-5.0586	0.0000
COMP_LOOP	0.0456	0.00625	7.2960	0.0000
WEFT_BEND	-82.88	19.27	-4.3008	0.0001
WEFT_RIGID	0.1433	0.04991	2.8715	0.0056
WARP_RT	-1.624	0.5845	-2.7780	0.0072
WEFT_WT	-2.7116	0.8106	-3.3454	0.0014
AREA_SHRINKAGE	0.7219	0.4261	1.6942	0.0952

From this table we can see that the most important variables in this model are WEIGHT and COMP_LOOP. A lower weight and a higher compression loop are associated with higher softness. The higher weight is associated with towels, which have a much lower chance of softness, unless they are new. The higher compression loop means that the fabric does not recover immediately when the force decreases, but more slowly. Other important variables are the weft bending length




Figure 3.9: Plots of WARMTH against predicted value and against residual




Figure 3.10: Plots of SOFTNESS against predicted value and against residual

and flexural rigidity, the first with a negative coefficient and the second with a positive coefficient, and two tensile measurements, WARP_RT and WEFT_WT, both with negative coefficients.

We will try to find a transformed linear model for SOFTNESS in the next chapter.

3.11 Man-made feel

A stepwise linear regression of the sensory measurement MM_FEEL and all instrumental measurements on all fabrics gives the following model

$$\begin{aligned} \text{MM_FEEL} = & -32.57 - 32.96*\text{WEFT_BEND} + 3.262*\text{WARP_EMT} \\ & + 3.927*\text{WEFT_EMT} + 2.536*\text{WARP_RT} - 1.1671*\text{WEFT_RT} \\ & - 4.8954*\text{WEFT_WT} + 3.14*\text{WARP_2HG} + 0.5531*\text{AREA_SHRINKAGE} \end{aligned}$$

This model has an $R^2 = 0.800$ and one outlier.

Looking at the plots of MM_FEEL against the predicted value and against the residuals, see figure 3.11, we see a group of seven interlocks on a very high constant predicted value, 150. These are the nylon interlocks, a synthetic fabric with a high man-made feel. The model separates these from all other values. The other fabrics also have their predicted value of man-made feel close together, for example the group with predicted values between 82 and 102 are all cotton interlocks. We can see the same on the plot of residuals as parallel vertical lines.

Therefore we try a stepwise linear regression on the interlocks alone. The model we get from this analysis is

$$\text{MM_FEEL} = 108.8 - 0.05094*\text{COMP_INT} + 8.498*\text{WARP_EMT}$$

This model has an $R^2 = 0.779$, $\bar{R}^2 = 0.776$ and one outlier, the cotton interlock 50 wash, product 40°C. The R^2 of this model is lower than that of the above model, so we will not consider this model any further.

If we look again at the model for MM_FEEL we got from the first analysis, we can test the significancy of all parameters. We get

Independent variable	coefficient	std.error	t-value	sig.level
INTERCEPT	-33.57	30.47	-1.1061	0.2749
WEFT_BEND	32.96	12.43	2.6516	0.0102
WARP_EMT	3.262	1.401	2.3285	0.0232
WEFT_EMT	3.927	1.015	3.8682	0.0003
WARP_RT	2.536	0.4169	6.0821	0.0000
WEFT_RT	-1.671	0.3251	-5.1390	0.0000
WEFT_WT	-4.895	0.5044	-9.7037	0.0000
WARP_2HG	3.140	1.686	1.8620	0.0673
AREA_SHRINKAGE	-0.5531	0.2418	-2.2869	0.0256

From this table we can see that the most important variables in this model are the tensile measurements, WARP_RT, WEFT_RT and WEFT_WT, the first with a positive coefficient and the last two with negative coefficients. The tensile measurement weft.emt is the next significant, with a positive coefficient. This shows that tensile measurements are very important in this model. Whether this is because they are related to man-made feel or because they separate different fabrics is not clear. It is very well possible that surface characteristics are important in man-made feel. Therefore this analysis should be repeated when surface measurements are available.

3.12 Conclusion

Most sensory variables can not be predicted from instrumental data using these linear models. The exceptions are THICKNESS, see section 3.3 and WARMTH, see section 3.9. One would expect better models using separate intercepts for the three fabrics. Analysis showed us that this is not the case.




Figure 3.11: Plots of MM_FEEL against predicted value and against residual

Chapter 4

Transformed Linear Modelling

As we saw in chapter 3, a simple linear model is not very satisfying. Therefore we shall look at optimal transformations of our data. We will concentrate our efforts on SOFTNESS. After we have found optimal transformations, we will test our model with some other measurements.

Warning: The transformations found using an optimal transformations technique should never be used for hypothesis testing with the same data. If hypothesis testing is required, separate data sets should be used for finding optimal transformations and hypothesis testing. Otherwise a great risk is finding a significant relation where non exists.

4.1 Looking for optimal transformations

In order to find optimal transformations, we used the SAS procedure TRANSREG, an alternating least-squares algorithm. This procedure extends the ordinary general linear model by providing optimal variable transforms that are iteratively derived. The ordinary regression model assumes that the variables are all measured on an equal interval scale and, therefore, can be represented as vectors in an n (the number of observations) dimensional space. Nominal variables, as for example in analysis of variance, cannot be treated as single vectors. These are expanded to design matrices, each column of which can be treated as a vector.

A ordinary general linear model analysis can be described as taking a set of interval and nominal variables, expanding the nominal variables to a set of variables that can be treated as vectors, then fitting a regression or other model to the expanded set of vectors. The alternating least-squares algorithm adds one additional capability to the general linear model; it allows variables whose *full* representation is a matrix consisting of more than one vector to be represented by a single vector, which is an optimal linear combination of the columns of the matrix. For any type of linear model, an alternating least-squares program can solve for an optimal vector representation of any number of variables simultaneously. PROC TRANSREG iterates until convergence, alternating these two steps: finding the least-squares estimates of the parameters of the model (given the current scoring of the data, that is, the current set of vectors), and finding least-squares estimates of the scoring parameters, that is, the estimates of the optimal vectors (given the current set of model parameters). (A description of this algorithm can be found in [2].)

For a monotonic continuous transformation we can use the monotonic spline option. In the procedure the data are handled by first creating a B-spline basis, of the specified kind, and then regressing the variable onto the basis. A B-spline basis is a way of expressing such a continuous function, which is easy to use in computing. For more information on splines, see [1]. The plot 4.1 gives an example of the kind of output we get from transreg.

After we found transformations, we have to estimate the functions. Because of discussions with experts on fabric handle, we choose to allow for three possibilities, a logarithmic, a linear and an exponential transformation. We choose the following transformations:




Figure 4.1:

variable	transform	variable	transform
SOFTNESS	EXPONENTIAL	WARP_RT	LOGARITHMIC
THICKNESS	LINEAR	WEFT_RT	LOGARITHMIC
WEIGHT	EXPONENTIAL	WARP_WT	EXPONENTIAL
COMP_INT	EXPONENTIAL	WEFT_WT	LOGARITHMIC
COMP_LOOP	LINEAR	WARP_G	LOGARITHMIC
CROSS_MOVE	EXPONENTIAL	WEFT_G	LOGARITHMIC
WARP_BEND	EXPONENTIAL	WARP_2HG	EXPONENTIAL
WEFT_BEND	LOGARITHMIC	WEFT_2HG	LINEAR
WARP_RIDIG	EXPONENTIAL	WARP_2HG5	LOGARITHMIC
WEFT_RIGID	EXPONENTIAL	WEFT_2HG5	EXPONENTIAL
WARP_EMT	LOGARITHMIC	AREA_SHRINKAGE	LINEAR
WEFT_EMT	LOGARITHMIC		

Two possible ways are open now. The first one is taking these transformations and making one large formula for softness. The problem with this is that we get 43 parameters, while we have only 71 observations. Furthermore, this is a very complicated formula, and it is very difficult to make correct initial estimations for the parameters to get the program to converge. After a few trails on this method I abandoned it in favour of the easier, but theoretically less sound procedure. First we estimate all transformations in the above form from the original and transformed values. Then we do a regression on the calculated transformations. This gives a linear model in the calculated transformed values. Then we use the transformations found to get the final formula.

4.2 Estimating the optimal transformations

All transformations were estimated using the nonlinear least squares estimator of SAS, with the Gauss-Newton method. We get the transformations:

```

TSOFTNESS = 29.850 * EXP(0.01129*SOFTNESS)
TTHICKNESS = THICKNESS
TWEIGHT = 10.477*EXP(0.030807*WEIGHT)
TCOMP_INT = 667.56*EXP(0.000319*COMP_INT)
TCOMP_LOOP = COMP_LOOP
TCROSS_MOVE = 0.2055*EXP(1.0777*CROSS_MOVE)
TWARP_BEND = 0.9225*EXP(0.3925*WARP_BEND)
TWEFT_BEND = 2.311*LN(WEFT_BEND + 0.4111)
TWARP_RIGID = 218.12*EXP(0.001321*WARP_RIGID)
TWEFT_RIGID = 119.49*EXP(0.002138*WEFT_RIGID)
TWARP_EMT = 3.3945*LN(WARP_EMT - 0.2950)
TWEFT_EMT = 4.857*LN(WEFT_EMT - 1.932)
TWARP_RT = 14.123*LN(WARP_RT - 22.034)
TWEFT_RT = 14.346*LN(WEFT_RT - 21.314)
TWARP_WT = 1.4866*EXP(0.17136*WARP_WT)
TWEFT_WT = 5.9696*LN(WEFT_WT - 0.000134)
TWARP_G = 2.2821*LN(WARP_G + 0.5216)
TWEFT_G = 2.2623*LN(WEFT_G + 0.5271)
TWARP_2HG = 1.8265*EXP(0.1896*WARP_2HG)
TWEFT_2HG = WEFT_2HG
TWARP_2HG5 = 4.0873*LN(WARP_2HG5 - 0.7975)
TWEFT_2HG5 = 2.2119*EXP(0.15886*WEFT_2HG5)
TAREA_SHRINKAGE = AREA_SHRINKAGE.

```

4.3 Estimating the nonlinear model

The next step is taking the transformations we found and doing a linear regression on transformed value of SOFTNESS on the transformed values of the instrumental variables. This is done with a linear regression procedure. The optimal model is

$$\begin{aligned}
 &29.849 * \exp(0.0113 * \text{SOFTNESS}) = \\
 &360.0 - 66.45 * \text{THICKNESS} - 38.573 * \text{EXP}(0.031 * \text{WEIGHT}) \\
 &- 17.56 * \text{EXP}(0.00735 * \text{COMP_INT}) + 0.109 * \text{COMP_LOOP} \\
 &- 91.84 * \text{LN}(\text{WEFT_BEND} + 0.411) + 11.0 * \text{EXP}(0.00214 * \text{WEFT_RIGID}) \\
 &- 16.81 * \text{LN}(\text{WARP_RT} - 22.03) - \text{LN}(\text{WEFT_WT} - 0.000134) \\
 &- 117.4 * \text{LN}(\text{WARP_G} + 0.521) + 123.9 * \text{LN}(\text{WEFT_G} + 0.5271) \\
 &+ 39.9 * \text{EXP}(0.1896 * \text{WARP_2HG}) - 21.79 * \text{WEFT_2HG} \\
 &+ 112.1 * \text{LN}(\text{WARP_2HG5} - 0.797) - 62.45 * \text{EXP}(0.159 * \text{WEFT_2HG5}) \\
 &+ 0.927 * \text{AREA_SHRINKAGE}
 \end{aligned}$$

This is a very complicated model and it is not clear what it means in a physical sense. To find out whether it is a useful model we will test it with some other data, partly from part 3 of the experiments, see section 1.2, partly from other experiments on textiles. In figure 4.2 are the plots of the predicted value and the residuals against the transformed value of softness. The legend is:

I Interlocks J Jeans P Poplins R Ribknits
 S Shirts T Towels U Underwear

We can see that the model fits interlocks, poplins and towels, as expected, because these data were used to calculate the model, is reasonable for most of the jumpers, except for two woolen ones, and for most of the underwear, but does not fit the ribknits at all.

The conclusion is that this model is not useful for predicting.

4.4 A second model

As we saw in the last section, the model derived from all of the data did not predict the softness of other fabrics. In order to be able to test the model with data from the experiment, the data set was split in approximately 1/3 and 2/3 at random. The largest part will be used to derive the model, then we can use the rest of the data to test the model.

4.5 Looking for optimal transformations again

Running the procedure TRANSREG again with the smaller dataset we find the following transformations. The figures are very similar to the plots before, therefore we will not give the plots again. The optimal transformations are:

variable	transform	variable	transform
SOFTNESS	EXPONENTIAL	WARP_RT	LOGARITHMIC
THICKNESS	LINEAR	WEFT_RT	LOGARITHMIC
WEIGHT	EXPONENTIAL	WARP_WT	LOGARITHMIC
COMP_INT	LINEAR	WEFT_WT	LINEAR
COMP_LOOP	LINEAR	WARP_G	EXPONENTIAL
CROSS_MOVE	EXPONENTIAL	WEFT_G	EXPONENTIAL
WARP_BEND	LINEAR	WARP_2HG	LINEAR
WEFT_BEND	LINEAR	WEFT_2HG	LINEAR
WARP_RIDIG	LINEAR	WARP_2HG5	LOGARITHMIC
WEFT_RIGID	LOGARITHMIC	WEFT_2HG5	EXPONENTIAL
WARP_EMT	LOGARITHMIC	AREA_SHRINKAGE	EXPONENTIAL
WEFT_EMT	LOGARITHMIC		

Notice that in this case more variables are not transformed.




Figure 4.2: Predicted value and residuals, using all the data

4.6 Estimating the optimal transformations again

Again we estimate the transformations

```

TSOFTNESS = 31.039 * EXP(0.010899*SOFTNESS)
TTHICKNESS = THICKNESS
TWEIGHT = 10.314*EXP(0.03126*WEIGHT)
TCOMP_INT = COMP_INT
TCOMP_LOOP = COMP_LOOP
TCROSS_MOVE = 0.2140*EXP(1.0523*CROSS_MOVE)
TWARP_BEND = WARP_BEND
TWEFT_BEND = WEFT_BEND
TWARP_RIGID = WARP_RIGID
TWEFT_RIGID = 66.036*LN(WEFT_RIGID - 40.0876)
TWARP_EMT = 3.3625*LN(WARP_EMT - 0.2279)
TWEFT_EMT = 4.9160*LN(WEFT_EMT - 1.8731)
TWARP_RT = 14.338*LN(WARP_RT - 22.637)
TWEFT_RT = 14.348*LN(WEFT_RT - 21.153)
TWARP_WT = 4.379*LN(WARP_WT + 0.4742)
TWEFT_WT = WEFT_WT
TWARP_G = 0.6634*EXP(0.5070*WARP_G)
TWEFT_G = 0.6523*EXP(0.5187*WEFT_G)
TWARP_2HG = WARP_2HG
TWEFT_2HG = WEFT_2HG
TWARP_2HG5 = 4.0895*LN(WARP_2HG5 - 0.7930)
TWEFT_2HG5 = 2.1757*EXP(0.16086*WEFT_2HG5)
TAREA_SHRINKAGE = 2.8028*EXP(0.07802*AREA_SHRINKAGE)

```

4.7 Estimating the nonlinear model again

We will do a linear regression procedure again to estimate the new model, and we get

$$\begin{aligned}
 &31.0 * \text{EXP}(0.0109 * \text{SOFTNESS}) = \\
 &795.3 - 75.2 * \text{EXP}(0.031 * \text{WEIGHT}) + 0.028 * \text{COMP_LOOP} - 1.56.7 * \text{WARP_BEND} \\
 &+ 0.20 * \text{WARP_RIGID} + 100.7 * \text{LN}(\text{WARP_EMT} - 0.228) - 67.5 * \text{LN}(\text{WEFT_EMT} - 1.87) \\
 &- 72.8 * \text{LN}(\text{WARP_RT}) - 148.5 * \text{LN}(\text{WARP_WT} + 0.474) + 10.6 * \text{WEFT_WT} \\
 &+ 34.4 * \text{WARP_2HG} - 29.0 * \text{WEFT_2HG} + 121.6 * \text{LN}(\text{WARP_2HG5}) \\
 &- 55.5 * \text{EXP}(0.161 * \text{WEFT_2HG5})
 \end{aligned}$$

A physical interpretation of this model is again difficult to give. However, if we look at the plots of predicted value and residual against the transformed value of softness, see figure 4.3, we see that this model is better than the last. In this plot are only that part of the data set that was not used to estimate the model. Most values fit reasonably well, but there are some outliers, for example the terry towel washed 50 times in product at 15°C and tumble dried. This model is better than the previous one, and could be used for a preliminary test of formulations for detergents. It must not be used for ribknits, the last model showed that these are very different.

4.8 Conclusions

We have found a model for SOFTNESS which is not very good, but usable. Recommendations are:

1. Try to do more experiments, and repeat some of the experiments to get an idea of how much noise is in the data.
2. Repeat the analysis according to the second way using surface measurements too.




Figure 4.3: Predicted value and residual using 2/3rd of the data

Acknowledgements

I thank Unilever Research Laboratory Port Sunlight for giving me the opportunity to work in the laboratory for seven months, and giving me access to the data used in this report.

I thank Mr. Philip Whittall for his support on the statistical aspects of the research, and Mr Dave Bishop, Mr Don Cox, and Miss Colina Mackay for their information on the experiments done in the 'Fabric Care' group.

I thank the people of the section Operations Techniques for their hospitality and friendship during my stay in their group.

I thank the European Community for their financial support which enabled me to stay in the United Kingdom for this period.

Bibliography

- [1] Boor, C. de, *A Practical Guide to Splines*, New York, (1978).
- [2] Breiman, Leo and Jerome H. Friedman. Estimating Optimal Transformations for Multiple Regression and Correlation, with discussion, *Journal of the American Statistical Association*, **80**, (1985), pages 580–619.
- [3] Kawabata, S, The Development of the Objective Measurement of Fabric Handle, in: Kawabata, S, R. Postle, and Masako Niwa (ed.). *Objective Specification of Fabric Quality, Mechanical Properties and Performance*, The Textile Machinery Society of Japan, (1982), pages 31–59.
- [4] Montgomery, Douglas C. and Elizabeth A. Peck. *Introduction to Linear Regression Analysis*. John Wiley and Sons, New York, (1982).
- [5] Pierce, F.T., The “handle” of cloth as a measurable quantity, *The Journal of the Textile Institute Transactions*, **21** (1930), pages T377–T416.