

Synthesis and Characterization of New phenolic Schiff bases Derivatives Based on Terephthaladehyde

*Eman M. Mohammed **

Received 18, September, 2012

Accepted 9, December, 2012

Abstract

A variety of new phenolic Schiff bases derivatives have been synthesized starting from Terephthaladehyde compound, all proposed structures were supported by FTIR, ¹H-NMR, ¹³C-NMR, Elemental analysis, some derivatives evaluated by Thermal analysis (TGA).

Key words: Terephthaladehyde ,Fused epoxy ,Phenolic Schiff bases

Introduction

The development of simple synthetic routes to widely used organic compound using readily available reagent is one of the main objectives of organic synthesis.

The use of Schiff base covered a wide area application in industry and biological field [1,2], the industry phenolic Schiff bases were used as a rubber accelerators [3], antioxidants and corrosion inhibitors [4], they have a wide industrial application as photo stabilizer's for poly ethylene, in analytical chemistry Schiff bases were used for uptake metal ion[5] some Schiff bases are used in the accurate determination for trace elements in the dilute solution, which is often hindered due to the sensitivity[6] limites of the equipment used for the purpose[6] in the study number of epoxy Schiff bases[7] were prepared.

Material and Methods

General

Melting points were determined on Gallen kamp, melting point apparatus and were uncorrected, FTIR spectra of the compounds were recorded on a (SHIMADZU) FTIR – 8300 spectrometer as KBr-disc, ¹H-NMR, ¹³C-NMR spectra were recorded at 200.13 – 50.32MHz, respectively using tetra methyl Silane (TMS) as an internal standard (DMSO) as solvent Elemental analyses were run using aperkin-Elmer, RE-2400 (C.H.N) analyzer, Thermal stability (TGA).

All analyses were formed in Center of Consultation / University of Jordan.

Materials

All the chemicals used were supplied by (Merk, Fluka and BDH) chemicals, the solvent purified by distillation and dries with calcium chloride .

Measurement and Techniques

The purity of products were investigated by (T.L.C) technique by using a mixture of benzene – ethanol (5:5 v/v) as eluate and Iodine champer for spot location

Thermal gravimetric analysis (:TGA)⁽⁸⁾

Curing of the prepared epoxy Schiff bases resin were evaluated by using (NETZCH-ESTA) / 409-PG/PC Mod/Type of Meas (DTA-TGA).

*Department of Chemistry, college of Science for women University of Baghdad, Iraq

The programmed heating rate of 20°C/min from (25-1000)°C under atmosphere (N₂ gas), so that heat lost or absorbed were recorded Fig.s (15-20) and analyzed Table (4).

Synthesis of[(1E,1E)-2-2-(2E-2E)-2-2-(1,4-phenylenen bis(methanylylidene))bis(hydrazine-1-yl-2-ylidene))diethenamine(1)[9]:

A mixture of (0.02 mol, 2.068gm) terephthalaldehyde with (0.04 mol, 3.64gm) thiosemi carbazide in (25ml) abs. ethanol was refluxed for (6hrs), the solid formed and recrystallized from ethanol and used directly at the next step.

Synthesis 5,5-(1,4-phenylene)bis(1,3,4-thiadiazol-2-amine) compound with compound with ethane(1:1) (2)[10]:

A stirring solution (0.01mol, 2.86gm) of compound(1) with (0.02mol, 9.6gm) Ammonium Iron III sulfate dehydrate (NH₄Fe (SO₄)₂. 12H₂O) in (30ml) dis. Water was added and the refluxed continued for (4hrs) After cooling, the precipitate was collected by filtration and washed with dis. Water to give compound [2]. Recrystallizer by ethanol.

Synthesis (E)-4-(((1,3,4-thiadiazol-2-yl)imino)methyl)phenol compound with phenol and(E)-N—ethylidene-1,3,4-thiadiazol-2-amine and p-xylene and ethane(1:1:1:1)(3)[9]:

A mixture of (0.01mol, 2.76gm) compound [2] with (0.02mol, 2.44gm) p-hydroxy benzaldehyde in (25ml) abs. ethanol with (1-2) drops glacial acetic acid. Refluxing (6hrs) then cooled the precipitate and crystallized in THF.

Synthesis 5,5(E)-4-(((1,3,4-thiadiazol-2-yl)imino)methoxy)oxarinc compound with oxarine and(E)-N-ethoxye-1,3,4-thiadiazol-2-amine and p-xylene and ethane(1:1:1:1)(4)[6]:

To a mixture of an appropriate (0.01 mol, 4.46gm) phenolic Schiff bases with (0.12mol, 11.1ml) eipchlorohydrine to (50°C) for (15min) was added gently alcoholic sodium hydroxide (0.14mol, 5.6gm) in two portions to keep the temperature below 65°C. The stirring was continued for (2h), after first addition the


aqueous layer was separated from the organic layer, then the second portion of (NaOH) added and stirred for (1h) and left the mixture at the same temperature for 50min, and also the aqueous was separated, the organic layers were dried and excess of eipchlorohydrine and solvent distilled of under reduced pressure, the formed resins were purified by dissolving it in THF the filterization and evaporation of excess solvent at (50°C), the purified by thin layer chromatography (TLC).

Synthesis of epoxy phenolic Schiff bases with unstitched Ring (5-9)[8]:

A mixture of an appropriate (0.01mol, 5.96gm) compound [4] in (30ml) cold methanol and (0.02mol) secondary amine (piperidine, morpholine, 4-morpholine piperidine, 4-piperidino piperdine, 4-methyl piperdine, 1-methyl piperazine) respectively, refluxing for (72h), after cooling the solvent continued was avapourated and the residue purified by thin layer chromatography (TLC).

Results and Discussion :


Considerable interests have been expressed in Synthesis of Schiff bases in recent year due to their industrial and biological importance starting from.



Scheme – 1 – Synthetic path ways for preparation of Compound (1)

In Scheme -1- out Line the Synthetic sequences employed in our laboratories for preparation of intermediate thiosemicarbazide, The FTIR Spectrum ⁽¹¹⁾ showed the strong stretching vibration (3320)cm⁻¹ due to (NH₂) , (3200)cm⁻¹ for (NH), (1610)cm⁻¹ for (C=N) , (1250)cm⁻¹ for (C=S) , (3065)cm⁻¹ for (Ar-H), ¹H-NMR (DMSO-d₆) δ: (7-


7.9) ppm due to (Ar-H), (3.5-3.6)ppm due to (2H, NH₂), ¹³C-NMR (DMSO-d₆) δ: (123-127)ppm due to aromatic carbones, (133)ppm due to(C=N), (162-169)ppm due to(C=S) , compound [2] prepared by the condensation of the corresponding compound [1] with Iron III ammonium sulfate NH₄Fe(SO₄).12H₂O. Refluxing in dis. Water



Scheme – 2 – Synthetic path ways for preparation of Compound (2)

The FTIR spectra showed strong stretching vibration ($3400-3295\text{cm}^{-1}$) for (NH_2) , (3060cm^{-1}) for (Ar-H) ; ^{13}C -NMR (DMSO- d_6) δ : (4.1-3.5)ppm due to $(2\text{H},\text{NH}_2)$, (7.1-7.4)ppm for (Ar-H) ;


NMR(DMSO- d_6): (131.4-135.1)ppm for aromatic carbon.(140)ppm due to (Ar-NH_2) , Phenolic Schiff bases prepared by condensation compound [2] with p-hydroxy benzaldehyde refluxing in abs. ethanol



Scheme – 3 – Synthetic path ways for preparation of Compound (3)

FTIR spectra for compound (3) showed strong stretching vibration ($1609-1612\text{cm}^{-1}$) for $(\text{C}=\text{N})$, ($3410-3380\text{cm}^{-1}$) for (OH) , and (3100cm^{-1}) for (Ar-H) ; ^1H -NMR (DMSO- d_6) δ : (7.15-7.4)ppm for


(Ar-H) , (10.1-10.3)ppm (H,OH) , ^{13}C -NMR (DMSO- d_6) δ : (134-136)ppm for aromatic carbones. (164-165.2)ppm due to $(\text{C}=\text{N})$, (148.2-149.1)ppm due to (C,OH) .



Scheme – 4 – Synthetic path ways for preparation of Compound (4)

FTIR spectra for compound [4] obtained sharp band for (oxarine) absorption at $(948-995)\text{cm}^{-1}$, and strong

bands $(2931-2873)\text{cm}^{-1}$ for CH_2 , $(1130-1090)\text{cm}^{-1}$ for (C-O-C).



Scheme – 5 – Synthetic path ways for preparation of Compound (5-10)

Finally compound [4] react with secondary amines (piperidine, morpholine, 4-morpholine piperidine, 4-piperidino piperidine, 4-methylpiperidine, 1 – methylpiperazine to gave unstitched ring (5-10). The FTIR spectrum of compound (5-10) obtained increasing in stretching vibration of alcoholic(OH) at $(3350-3280)\text{cm}^{-1}$ and $(1190)\text{cm}^{-1}$ for (C-O); $^1\text{H-NMR}$ (DMSO- d_6) δ : (6.7-7.4)ppm due to (Ar-H), (10.5)ppm for (H,OH); $^{13}\text{C-NMR}$ (DMSO- d_6) δ :(12.1-119)ppm due to aromatic carbones, (148-149)ppm for

(C,OH)). All these steps were summarized in schemes (1-5).. physical properties and major FTIR absorption of all mentioned and other details [FTIR, Elemental analysis, TGA analysis; $^1\text{H-NMR}$, $^{13}\text{C-NMR}$] data are listed in table (1-4) respectively.Curing thermal stability of some compounds were evaluated by using (TGA) Table (4) clearly show the temperature rate belong to different type dissociated for derivatives Figs(15-20).

Table (1) Depicted physical properties and major (FTIR) absorption for (1-10) compounds

Comp No	Compound Structure	M.P °C	Colour	%yield	Major FTIR absorption		
					V _{OH}	V _{C=N}	other
1		<300	pale yellow	82	-	1610	V _{NH₂} (3320) V _{NH} (3200) V _{C=S} (1250) V _{Ar-H} (3065)
2		269-271	pale green	80	-	1646	V _{NH₂} (3400) 3295 V _{Ar-H} (3060)
3		113-115	Orange	86	3410 3380	1609 1612	V _{Ar-H} (3100)
4		Oily	Brown	75	-	-	V _{CH₂} (2931) 2873 V _{???} (948) 995 V _{C-O-C} (1130) 1090
5		Oily	Brown	85	3350 3200	1635	V _{C-O} (1190) V _{C-O-C} (1109) V _{C-N} (1200)
6		Oily	Brown	85	3300 3290	1625	V _{C-O} (1160) V _(C-N) (1195) V _{C-O-C} (1220)
7		Oily	Brown	80	3310 3291	1632	V _{O-C-O} (1200) V _{C-N} (1230)
8		Oily	Brown	70	3306 3290	1630	V _{O-C-O} (1111) V _{C-N} (1235)
9		Oily	Brown	70	3300 3287	1627	V _{C-O} (1182) V _{C-N} (1238)


10		Oily	Brown	70	3309 3280	1631	V _{C-O} (1163) V _{C-N} (1250)
----	---	------	-------	----	--------------	------	--

Table (2) Depacited, ¹H-NMR , ¹³C-NMR for some compounds





comp No	compound Structure	¹ H-NMR	¹³ C-NMR
1		δ: 7-7.9 (Ar-H) δ: 3.5-3.6 (2H,NH ₂)	δ: 123-127 (aromat. carb) δ: 133 (C=N) δ: 162-169 (C=S)
2		δ: 4.1-3.5 (2H,NH ₂) δ: 7.1-7.4 (Ar-H)	δ: 1314-135.1 (aromat. carb) δ: 140 (Ar-NH ₂)
3		δ: 7.15-7.4 (Ar-H) δ: 10.1-10.3 (H,OH)	δ: 134-136 (aromat. carb) δ: 164-165.2 (C=N) δ: 148.2-149.1 (C,OH)
5		δ: 6.7-7.4 (Ar-H) δ: 10.5 (H,OH)	δ: 124-129 (aromat. carb) δ: 148-149 (C,OH)

Table (3) Elemental analysis for some compounds

comp No	(C.H.N) analysis Calculated (Found)			comp No	(C.H.N) analysis Calculated (Found)		
	%C	%H	%N		%C	%H	%N
1	42.86 (43.86)	4.29 (5.27)	30 (30.9)	6	59.22 (60.02)	5.45 (6.23)	14.55 (15.50)
2	43.48 (44.45)	2.90 (3.89)	23.19 (24.19)	7	61.41 (62.32)	6.61 (7.40)	14.93 (15.71)
3	63.72 (64.70)	3.52 (4.50)	14.16 (15.16)	8	64.24 (65.20)	7.07 (7.90)	15.00 (15.75)
4	56.93 (57.93)	4.43 (5.40)	15.50 (16.32)	9	63.64 (64.40)	6.06 (7.02)	14.14 (14.98)
5	65.40 (66.32)	6.27 (7.19)	15.26 (16.24)	10	62.42 (63.21)	6.24 (7.11)	18.21 (18.96)

Table (4) Show Curing temperature of some compounds

comp No	primary dissociated	Finally dissociated	50% dissociated	maximum dissociated	average dissociated	% char content
4	220	380	350	310	0.25	93.77
5	210	475	350	275	0.16	83.97
6	190	525	370	325	0.96	79.44
8	180	750	612	325	0.069	61.63
9	120	700	647	425	0.054	59.94
10	165 260	700	660	360	0.050	50.70




Fig (1) FTIR Spectrum of Compound (6)
Compound (4)




Fig (2) FTIR Spectrum of




Fig (3) FTIR Spectrum of Compound (6)
Compound (8)




Fig (4) FTIR Spectrum of




Fig (5) FTIR Spectrum of Compound (9)
Compound (10)




Fig (6) FTIR Spectrum of




Fig (11) ¹³CNMR Spectrum of Compound (1)




Fig (12) ¹³CNMR Spectrum of Compound (2)




Fig (13) ¹³CNMR Spectrum of Compound (3)




Fig (14) ¹³CNMR Spectrum of Compound (5)




Fig (15) Curing Thermogram of Compound (4)




Fig (16) Curing Thermogram of Compound (5)




Fig (17) Curing Thermogram of Compound (6)




Fig (18) Curing Thermogram of Compound (8)




Fig (19) Curing Thermogram of Compound (9)




Fig (20) Curing Thermogram of Compound (10)

References :

1. Hardman. J. G; Limbird. L. E; Molinoff. P. B and Gilman's. G. M; 2006. "The pharmacological Basis of Therapeutics"; 11ed, Mc – Graw. Hill, New York; 1155
2. Verandas. L. Sand Fraga. C. A. M; 2005; "Letter in Drug Design & Discovery"; J. Braz;Vol.(2):62-67.
3. El Sayed. H; El Ashry. E and kassem. A. A; 2006, "Account of Microwave Irradiation for accelerating organic reactions"; ARKIVOC, (ix); 1-16.
4. Martin. R.W; 1956; "The Chemistry of Phenolic Resins"; Wiley. New York .
5. Samal. S; Dey. R.K; Acharya. S and Mohaptra. N. K; 1999; "Metal Ion Adsorption Studies of Chelating Resins Derived from Formaldehyde Condensed Schiff Base of 2,6 – Diaminopyridine and Salicyldehyde Immobilized on Silica Gel International Surnposium on Polymers Beyond (AD, 2000)"; 12-15 : 235-238, proceeding, Indian of Institute of Technology.
6. Adam. G. A; 2001; "Chemistry and Technology of Methylolic Resins and their Derivative"; IPN_s; J. Nat. Chem;Vol (1): 31-157.
7. Rebek. J. 1980,"Experimental Methods in Polymer Chemistry"; by John Wiley and Sons, , chapter 24.
8. Jeilenek. H. H. G; 1949, "Synthesis of High Moleculer weight linear polyamine"; J. Poly. Sci, 413.
9. Wadher. S.J; Puranik. M.P; karande. N. A and Yeole. P.G; 2009, "Synthesis and Biological Evaluation of Schiff Bases of Dapsone and Their Derivatives as Auticrobial Agents"; J. Phar. Tech, 1(1): 22-33.
10. Hudizadeh. F and Vosooghi. R; 2008, "Synthesis of α -[5-(5-Amino-1,3,4-thiadiazole-2-YL)-2- imidazolthio] acetic acid"; J. Heter.Chem, Vol (45),1-3.
11. Silverstein. R.M; 1981,"Spectrometric Identification of Organic compound," 4th. Ed. Part2.

تحضير وتشخيص مشتقات قواعد شيف الفينولية ابتداءً من التيرفثالديهايد

ايمان مهدي محمد *

*كلية العلوم للنبات /جامعة بغداد/قسم الكيمياء

الخلاصة :

تم تحضير مجموعة من الراتنجات لقواعد شيف الفينولية ابتداءً من المركب الاساسي (التيرفثالديهايد). شخّصت جميع المركبات المحضرة باستخدام تقانة مطيافية الاشعة تحت الحمراء (FTIR) وطيف الرنين المغناطيسي ($^1\text{H-NMR}$) و ($^{13}\text{C-NMR}$) والتحليل الدقيق للعناصر (C.H.N) مع قياس الثبات الحراري باستخدام تقانة التحليل الحراري الوزني (TGA) للبعض منها.