



Nanoparticles

Nanoscience opportunities in environmental remediation

Prashant V. Kamat *, Dan Meisel

Notre Dame Radiation Laboratory, Notre Dame, IN 46556–0579, USA

Received 18 March 2003; accepted 17 June 2003

Abstract

Semiconductor nanostructures play an important role in developing smart materials that can simultaneously sense and destroy harmful chemical contaminants from our environment. This review article highlights some recent advances of nanoscience in the area of environmental remediation. The potential for improving the effectiveness of photocatalytic processes by means of semiconductor–metal nanocomposites and merits of combining two advanced oxidation processes are discussed. **To cite this article:** P.V. Kamat, D. Meisel, C. R. Chimie 6 (2003).

© 2003 Published by Éditions scientifiques et médicales Elsevier SAS on behalf of Académie des sciences.

1. Scope of nanoscience in environmental chemistry

In this new millennium, we are faced with the challenge of cleaning our natural water and air resources. While we enjoy the comforts and benefits that chemistry has provided us, from composites to computer chips, from drugs to dyes, we are faced with the task of treating wastes generated during manufacturing processes and the proper disposal of various products and byproducts. Nanotechnology can provide us ways to purify the air and water resources by utilizing semiconductor nanoparticles as catalysts and/or sensing systems. Furthermore the utilization of light and ultrasound to activate such nanoparticles opens up new ways to design green oxidation technologies for environmental remediation.

The size and shape dependent optical and electronic properties of nanoparticles make an interesting case for environmental chemists to exploit their role in environmental remediation processes [1–5]. Of particular interest is their application in advanced oxidation processes [6]. TiO₂ nanoparticles have been extensively studied for oxidative and reductive transformation of organic and inorganic species present as contaminants in air and water. Technological advances in this area have already led to product development for a variety of day-to-day operations. Commercialization of products such as self-cleaning glasses, disinfectant tiles and filters for air purification demonstrates the early successes of nanosystems for environmental applications [7].

Maximizing the efficiency of photoinduced charge separation in semiconductor systems remains to be a major challenge to the scientific community. Obtaining insight into charge transfer processes is important to improve the photoconversion efficiencies in semiconductor-based nanoassemblies. Earlier reviews [8–10] have focused on the principles and mechanism

* Corresponding author.

E-mail addresses: pkamat@nd.edu (P.V. Kamat), dani@nd.edu (D. Meisel).

of photocatalytic reactions in advanced oxidation processes. We present here some of the recent developments related to semiconductor nanoparticles in advanced oxidation processes.

2. Semiconductor nanoparticles as photocatalysts

The participation of a semiconductor nanoparticle in a photocatalytic process can be either direct or indirect as illustrated in Fig. 1a and b respectively.

Charge separation in semiconductor particles occurs when they are subjected to bandgap excitation. The photogenerated electrons and holes are capable of oxidizing or reducing the adsorbed substrates (Fig. 1a). Alternatively the semiconductor nanoclusters also promote a photocatalytic reaction by acting as mediators for the charge transfer between two adsorbed molecules (Fig. 1b). This process, which is commonly referred to as photosensitization, is extensively used in photoelectrochemistry and imaging science. In the first case, the bandgap excitation of a semiconductor particle is followed by the charge transfer at the semiconductor/electrolyte interface. However, in the second case, the semiconductor nanoparticle quenches the excited state by accepting an electron and then transfers the charge to another substrate or generates photocurrent. In the present context, the contaminant dye itself acts as a sensitizer and undergoes oxidative degradation. Such an approach (Fig. 1b) was found to be useful in discoloration of the textile dye on TiO₂ nanoparticles [11, 12]. The energy of the conduction

and valence bands of the semiconductor and redox potential of the adsorbed molecule control the reaction course of the photochemical process.

The TiO₂ photocatalyst has been the popular choice of much of the published photocatalysis work. Its large bandgap energy (3.2 eV) necessitates UV excitation to induce charge separation within the particle. In a pioneering article of 1955, Markham pointed out the photocatalytic properties of zinc oxide, titanium oxide and antimony trioxide under UV irradiation [13]. In aqueous solutions, the holes are scavenged by surface hydroxide groups to generate •OH radicals, which then induce the oxidation of organics [14–18]. The •OH radical mediated oxidation has been successfully employed in the mineralization of many chemical contaminants. Interestingly, electron scavenging becomes the rate-limiting factor in such oxidation processes [19–25]. Alternative methods have also been suggested to promote the charge separation by applying an electrochemical bias to a TiO₂ particulate film electrode [23]. On the other hand both reductive and oxidative steps can be beneficially used to degrade aromatic compounds such as trinitrophenol [26].

Several research groups have attempted to extend the photoresponse into the visible by doping the TiO₂ with transition metal ions. In many instances, such doping procedure directly influences the intrinsic properties of the semiconductor and extends its photoresponse into the visible [27–29]. Nitrogen doped into substitutional sites of TiO₂ has shown bandgap narrowing as well as photocatalytic activity in the visible [30]. Films and powders of TiO_{2-x}N_x have shown an




Fig. 1. Photoinduced charge transfer processes in semiconductor nanoclusters. (a) Under bandgap excitation and (b) sensitized charge injection by exciting adsorbed dye molecules. CB and VB refer to conduction and valence bands of the semiconductor.

improvement over TiO_2 under visible light (up to 500 nm) irradiation. Arakawa and coworkers have synthesized a photocatalyst that produces stoichiometric amounts of oxygen and hydrogen under visible light irradiation [31]. The bandgap change in these Ni-doped indium tantalum oxide compounds was attributed to internal transitions in a partly filled Ni d shell and is characterized by the absorption band at 420–520 nm.

Another approach to utilize the visible light for inducing a charge transfer process in a large bandgap semiconductor system is to modify the surface with a sensitizing dye such as Ru(II) polypyridyl complex [32]. The electron injected into the semiconductor is transferred for the reductive transformation of a pollutant such as CCl_4 [33]. However, if one is interested in making use of the dye molecule as an active sensitizer, one needs to address the stability issues related to dye regeneration. While charge injected from excited Ru(II) polypyridyl complex into TiO_2 can be efficiently utilized for the reduction of an organic molecule such as carbon tetra chloride [33], it is necessary to regenerate the oxidized sensitizer with another sacrificial electron donor. Failure to regenerate the sensitizer will eventually cause the degradation of the sensitizer [34].

3. Semiconductor-metal nanocomposites for improving the efficiency of photocatalytic processes

By designing semiconductor–metal composite nanoparticles, it is possible to improve the catalytic properties of photocatalysts (Fig. 2). Contact of metal with the semiconductor indirectly influences the energetics and interfacial charge transfer processes in a favorable way. The deposition of a noble metal on semiconductor nanoparticles is an essential factor for maximizing the efficiency of photocatalytic reactions [35]. It is commonly assumed that the noble metal (e.g., Pt) acts as a sink for photoinduced charge carriers and promotes interfacial charge transfer processes.

Metal islands or nanoparticles deposited on a semiconductor surface undergo Fermi level equilibration following the charging with photogenerated electrons. The effect of Fermi level equilibration is predominantly seen when the metal deposits consists of small islands or small particles. Unlike bulk metals, the nanoparticles do not often exhibit ohmic contact with




Fig. 2. Charge-transfer and Fermi-level equilibration in a metal–semiconductor nanocomposite. E'_F and E_F refer to Fermi levels before and after equilibration.

the semiconductor surface which retain the charge before transferring them to the redox species. During extended UV photolysis, electron capture by metal islands of Ag, Au and Cu becomes inhibited as their Fermi-level shifts close to the conduction band of the semiconductor. Pt on the other hand acts as an electron sink and fails to achieve Fermi-level equilibration. Based on the photoelectrochemical study a Fermi-level shift of about ~ 150 mV was observed for the TiO_2/Au composite film [36, 37]. The metal nanoparticles deposited on TiO_2 films thus proved beneficial for improving the photoelectrochemical and photocatalytic performance (Fig. 3).

Photoelectrochemical studies [36, 39] carried out by depositing gold nanoparticles on nanostructured TiO_2 films exhibit enhanced photocurrent generation. Improved interfacial charge transfer at the semiconductor/electrolyte interface resulted in nearly three-time enhancement of photocurrent generation and a shift in the apparent flat band potential. Although the $\text{TiO}_2@Au$ interface may offer many complex scenarios, the photoelectrochemical and photocatalytic measurements support the argument that the metal nanoparticle deposition facilitates charge (electron) stabilization in nanostructured TiO_2 films and promote interfacial hole-transfer processes.

3.1. Sensing the chemical environment with semiconductor nanostructures

A variety of sensors for environmental applications have been developed in recent years, including SnO_2 -based semiconductor systems that have been used as




Fig. 3. Energy-level diagram illustrating the role of A. Pt and B. Au in dictating Fermi level equilibration of ZnO–Metal composite system (from [38]).

conductometric gas sensors [40, 41] and a TiO₂ electrode for determining the chemical oxygen demand (COD) of water [42]. The system that has drawn attention in recent years *vis-à-vis* its potential to be used as chemical sensors is semiconductor nanostructures. Prompted by the discovery of photoluminescence from porous Si and subsequent observation that many organic and inorganic molecules quench this emission, has led to their exploitation as chemical sensors [43, 44]. The photoluminescence in porous Si arises from charge carrier recombination in the quantum confined nanosized environments [45, 46]. Both energy- and electron-transfer mechanisms have been proposed to explain the quenching by organic molecules. Sailor et al have attributed the quenching of the PL by aromatic molecules such as anthracene, pyrene, benzantracene etc. to energy transfer to the triplet state of the organic substrate [47]. El-Shall and coworkers [48] have shown that the emission from silicon nanocrystals is quenched by aromatic nitrocompounds via electron transfer from the conduction band of the silicon nanocrystal to the vacant orbitals of the quenchers.

The feasibility of using porous silicon nanocrystals as sensors has been demonstrated for detecting nerve gas agents [49] and nitroorganics [48, 50]. Using detection based on electrical conductivity [51], photoluminescence [49, 50], or interferometry [49], researchers have achieved sensitivity in the range of ppb–ppm levels.

3.2. Simultaneous detection and degradation of low-level organic contaminants

A desirable feature for the detoxification of air and water is to develop methodologies that can simulta-

neously sense and destroy toxic chemicals. Such a catalyst system is especially useful when it triggers the photocatalytic operation on demand, i.e., photocatalysis becomes operational only when the system senses the presence of an aromatic compound in the immediate surrounding. Semiconductor nanoclusters such as ZnO and CdSe have an added advantage that they emit quite strongly in the visible region. Size-dependent emission properties of these semiconductor systems have been explored in earlier photochemical studies [52–56]. The size-dependence properties of these nanoparticles and the ability to tailor the sizes of the nanoassemblies find ready application in chemical sensors. The thermal conductivity of metal oxide semiconductors is often used to sense organic vapors and gases [57]. The visible emission of nanosized ZnO, which usually arises from anionic vacancies, is very sensitive to hole scavengers [56].

ZnO is a promising candidate for such a specialized environmental application (Fig. 4). The visible emission of ZnO, which usually arises from anionic vacancies, is very sensitive to hole scavengers. The emission is quantitatively quenched by hole scavengers such as iodide ions or phenols [59]. The feasibility of employing nanostructured ZnO films for simultaneous sensing and degradation of organic contaminants has been demonstrated recently in our laboratory [58]. The ZnO emission is very sensitive to the presence of aromatic compounds such as chlorinated phenols in water. The observed emission quenching is quantitative as the extent of quenching by the organics is determined by the adsorption equilibrium. A detection sensitivity of the order of 1 ppm can be achieved in these systems. A




Fig. 4. Principle of simultaneous detection and degradation approach in photocatalysis. The emission response of ZnO film to the presence of 4-chlorocatechol is shown on the right. (From [58]).

major feature of the ZnO semiconductor system is its ability to degrade the organic contaminant under high-intensity UV illumination.

Experiments illustrating the emission increase during photocatalytic degradation (Fig. 5) show that the emission recovery parallels the degradation of aromatic intermediates from the aqueous solution. Thus, emission from ZnO films can be used to monitor the course of a photocatalytic reaction. Though not selective, ZnO emission quenching serves as a probe to sense the presence of aromatic intermediates in water.




Fig. 5. Emission recovery during the degradation of 4-chlorophenol at an UV-irradiated ZnO film (from reference [58]).

ZnO film-based nanosensors should be useful in applications such as monitoring the quality of drinking water, or assessing the contamination in underground water. Design engineering of fiber optic probes can miniaturize the sensor for environmental applications.

3.3. Combining photocatalysis with other advanced oxidation processes (AOP)

Combining photocatalysis with another AOP such as sonolysis could be an effective approach to improve the mass transfer of reactants and products to and from the catalytic surface in photocatalytic reactions [60–64]. While hydroxyl radicals play a role in TiO₂ photocatalysis, direct hole induced oxidation on the catalyst surface opens up an alternative route in the degradation mechanism [65]. Many organic compounds are readily broken down, but others are not readily transformed by this heterogeneous oxidation system. The TiO₂ photocatalysis process is most useful in its ability to rapidly degrade polar compounds. When highly polar compounds are formed during the oxidation of organic contaminants, complete breakdown to CO₂ and H₂O (mineralization) is quickly realized.

Since the strengths of sonolysis and photocatalysis are complimentary, a system that employs them together seems a worthwhile endeavor. We tested a combination of sonolysis and photocatalysis in both a simultaneous and a sequential manner using the dye naphthol blue black as the model pollutant [66]. In




Fig. 6. **A.** Degradation of 2,4-D. **B.** Decrease in total organic carbon (TOC) during (a) photocatalytic, (b) sonolytic and (c) combined photocatalytic and sonolytic degradation of 2,4-D in aqueous solution (from [67]).

addition to increasing the rate of degradation and mineralization of environmental contaminants, the combinative approaches are implemented to solve the problem of toxic intermediates that often accumulate as chemical intermediates during the degradation process.

The merits of combining sonolysis and photocatalysis were evaluated by investigating the degradation of an azo dye, naphthol blue black (NBB) [66] and an herbicide, 2,4-dichlorophenoxyacetic acid [67]. Experiments were carried out by employing a high-frequency ultrasonic generator and UV photolysis simultaneously. Fig. 6 shows the degradation of 2,4-D and the decrease in TOC observed during the sonolysis, photocatalysis and combined sonolysis and photocatalysis experiments. An additive effect on the degradation rate of the parent compound was observed when the sonolysis and photocatalysis experiments were carried out together. Whereas sonolysis was effective in the initial degradation of 2,4-D, photocatalysis was more efficient in decreasing the TOC. Moreover, the combined approach also minimizes the production of chemical intermediates such as chlorinated phenols

[67]. The combination approach overcomes the deficiencies of the individual techniques and makes the overall remediation process more effective. The added benefit of sonication on photocatalysis also stems from several other sources. For example, during combined sonolysis and photocatalysis experiment we expect the photocatalyst to be well dispersed and its surface constantly refreshed. This mass transport of reactants and products to and from the catalyst surface improves as the slurry is constantly agitated.

One of the major concerns in any Advanced Oxidation Process is the formation of undesirable reaction intermediates. It is not unusual to observe several intermediates with toxicity greater than the parent compound itself. Rapid mineralization of an organic contaminant should be the goal. Minimizing the survival time of toxic intermediates is prerequisite to obtain fast mineralization. A combinative AOP approach could serve as a solution to tackle such an issue. While analyzing the merits and deficiencies of sonolysis and photocatalysis, several complimentary aspects of these two processes were noted. Table 1 summarizes the salient features of the two advanced oxidation pro-

Table 1

Comparison of salient features of different advanced oxidation processes[†]

Feature	Sonolysis	Photocatalysis	Combined Sonolysis and Photocatalysis
Degradation of non-polar compounds	good	variable	very good
Degradation of polar compounds	poor	good	very good
Mineralization	poor	good	very good
Avoidance of toxic intermediate	good	poor	very good
Need for a catalyst	no	yes	yes, in smaller quantity

[†] From reference [67]

cesses and highlights the benefits of the combined approach in the mineralization of 2,4-dichlorophenoxyacetic acid. Quick degradation and mineralization of the chlorinated organic compounds is induced by carrying out sonolysis and photocatalysis simultaneously. More importantly, no build-up of toxic intermediates such as chlorinated phenols is detected in the combination experiment.

4. Scope of future research

In recent months concerns have been raised regarding the adverse impact of nanotechnology on environment [68]. It should be noted that most of the nanotechnological advances are based on known chemicals and materials that are already employed in various applications. The novel aspect of nanotechnology has been to organize the molecules into clusters or assemblies so that the properties of the produced nanomaterials are tailored to the desired application. A recent thrust in this area has been the exploration of size and shape dependent properties of semiconductor and metals. While the contamination caused during manufacture and/or application of nanomaterials is a major concern, it should not be difficult to devise environmentally friendly protocols similar to those regulating the manufacture and use of other chemicals and materials.

On a positive note, semiconductor nanostructures can play an important role in developing smart materials that can simultaneously sense and destroy harmful chemical contaminants from the environment. Such an application seems to be important as the concern over chemical contamination of drinking water and air needs to be addressed. Application of semiconductor nanoparticles as photocatalysts is still limited by the fact that they respond only to UV-excitation. Continued efforts to extend the response to the visible range have met with limited success. Semiconductor–metal nanocomposites that improve the selectivity and efficiency of the photocatalytic process are expected to draw the attention of future research.

Acknowledgements

This work is supported by the US Department of Energy (DOE), Office of Science, Basic Energy Sciences. This is contribution NDRL No. 4443 from the Notre Dame Radiation Laboratory.

References

- [1] M.L. Steigerwald, L.E. Brus, Semiconductor crystallites: a class of large molecules, *Acc. Chem. Res.* 23 (1990) 183.
- [2] A. Henglein, Physicochemical properties of small metal particles in solution: 'microelectrode' reactions, chemisorption, composite metal particles, and the atom-to-metal transition, *J. Phys. Chem.* 97 (1993) 5457.
- [3] P. Alivisatos, Perspectives on the physical chemistry of semiconductor nanocrystals, *J. Phys. Chem.* 100 (1996) 13226.
- [4] P.V. Kamat, D. Meisel (Eds.), *Semiconductor Nanoclusters – Physical, Chemical and Catalytic Aspects*, Elsevier Science, Amsterdam, 1997.
- [5] P.V. Kamat, Photophysical, photochemical and photocatalytic aspects of metal nanoparticles, *J. Phys. Chem. B* 106 (2002) 7729.
- [6] P.V. Kamat, D. Meisel, Nanoparticles in Advanced Oxidation Processes, *Curr. Opin. Colloid Interface Sci.* 7 (2002) 282.
- [7] A. Fujishima, K. Hashimoto, T. Watanabe, *TiO₂ photocatalysis. Fundamentals and Applications*, Bkc, Inc. Tokyo, Japan, 1999.
- [8] P.V. Kamat, Photochemistry on nonreactive and reactive (semiconductor) surfaces, *Chem. Rev.* 93 (1993) 267.
- [9] M.R. Hoffmann, S.T. Martin, W. Choi, D.W. Bahnemann, Environmental applications of semiconductor photocatalysis, *Chem. Rev.* 95 (1995) 69.
- [10] N. Serpone, Relative photonic efficiencies and quantum yields in heterogeneous photocatalysis, *J. Photochem. Photobiol. A: Chem.* 104 (1997) 1.
- [11] K. Vinodgopal, D. Wynkoop, P.V. Kamat, Environmental Photochemistry on semiconductor surfaces: a photosensitization approach for the degradation of a textile azo dye, *Acid Orange 7*, *Environ. Sci. Technol.* 30 (1996) 1660.
- [12] C. Nasr, K. Vinodgopal, S. Hotchandani, A. Chattopadhyaya, P.V. Kamat, Environmental photochemistry on semiconductor surfaces. Visible light-induced degradation of a textile diazo dye, naphthol blue black on TiO₂ particles, *J. Phys. Chem.* 100 (1996) 8436.
- [13] S.M.C. Markham, Photocatalytic properties of oxides, *J. Chem. Ed.* 32 (1955) 540.
- [14] B. Kraeutler, C.D. Jaeger, A.J. Bard, Direct observation of radical intermediates in the radical formation by electron spin resonance, *J. Am. Chem. Soc.* 100 (1978) 4903.
- [15] M. Anpo, T. Shima, Y. Kubokawa, ESR and photoluminescence evidence for the photocatalytic formation of OH radicals on small TiO₂ particles, *Chem. Lett.* (1985) 1799.
- [16] R.F. Howe, M. Grätzel, EPR observation of trapped electrons in colloidal TiO₂, *J. Phys. Chem.* 89 (1985) 4495.
- [17] O.I. Micic, Y. Zhang, K.R. Cromack, A.D. Trifunac, M.C. Thurnauer, Photoinduced hole transfer from TiO₂ to methanol molecules in aqueous solution studied by electron paramagnetic resonance, *J. Phys. Chem.* 97 (1993) 13284.
- [18] O.I. Micic, Y. Zhang, K.R. Cromack, A.D. Trifunac, M.C. Thurnauer, Trapped holes on TiO₂ colloids studied by electron paramagnetic resonance, *J. Phys. Chem.* 97 (1993) 7277.

- [19] H. Gerischer, A. Heller, The role of oxygen in photooxidation of organic molecules on semiconductor particles, *J. Phys. Chem.* 95 (1991) 5261.
- [20] C.M. Wang, A. Heller, H. Gerischer, Palladium catalysis of O₂ reduction by electrons accumulated on TiO₂ particles during photoassisted oxidation of organic compounds, *J. Am. Chem. Soc.* 114 (1992) 5230.
- [21] H. Gerischer, A. Heller, Photocatalytic oxidation of organic molecules at TiO₂ particles by sunlight in aerated water, *J. Electrochem. Soc.* 139 (1992) 113.
- [22] M.W. Peterson, J.A. Turner, A.J. Nozik, Mechanistic studies of the photocatalytic behavior of TiO₂. Particles in a photoelectrochemical slurry cell and the relevance to photodetoxification reactions, *J. Phys. Chem.* 95 (1991) 221.
- [23] K. Vinodgopal, S. Hotchandani, P.V. Kamat, Electrochemically assisted photocatalysis. TiO₂ particulate film electrodes for photocatalytic degradation of 4-chlorophenol, *J. Phys. Chem.* 97 (1993) 9040.
- [24] J.M. Kesselman, A. Kumar, N.S. Lewis, in: D.F. Ollis, H. Al-Ekabi (Eds.), *Photocatalytic Purification and Treatment of Water and Air*, Elsevier Science Publishers B.V. Amsterdam, 1993, p. 19.
- [25] J.M. Kesselman, G.A. Shreve, M.R. Hoffmann, N.S. Lewis, Flux-matching condition at TiO₂ photoelectrodes: is interfacial electron transfer to O₂ rate-limiting in the TiO₂-catalyzed degradation of organics?, *J. Phys. Chem.* 98 (1994) 13385.
- [26] D. Schmelling, K.A. Gray, P.V. Kamat, Role of reduction in the photocatalytic degradation of trinitrotoluene, *Environ. Sci. Technol.* 30 (1996) 2547.
- [27] S.C. Martin, C.L. Morrison, M.R. Hoffmann, Photochemical mechanism of size-quantized vanadium-doped TiO₂ particles, *J. Phys. Chem.* 98 (1994) 13695.
- [28] M. Anpo, Y. Ichihashi, M. Takeuchi, H. Yamashita, Design of unique TiO₂ photocatalysts by an advanced metal ion-implantation method and photocatalytic reactions under visible light irradiation, *Res. Chem. Intermed.* 24 (1998) 143.
- [29] A. Di Paola, G. Marci, L. Palmisano, M. Schiavello, K. Uosaki, S. Ikeda, B. Ohtani, Preparation of polycrystalline TiO₂ photocatalysts impregnated with various transition metal ions: characterization and photocatalytic activity for degradation of 4-nitrophenol, *J. Phys. Chem. B* 106 (2002) 637.
- [30] R. Asahi, T. Morikawa, T. Ohwaki, K. Aoki, Y. Taga, Visible-light photocatalysis in nitrogen-doped titanium oxides, *Science* 293 (2001) 269.
- [31] Z. Zou, J. Ye, K. Sayama, H. Arakawa, Direct splitting of water under visible light irradiation with an oxide semiconductor photocatalyst, *Nature* 414 (2001) 625.
- [32] P.V. Kamat, K. Vinodgopal, in: V. Ramamurthy, K. Schanze (Eds.), *Organic and Inorganic Photochemistry*, Marcel Dekker, New York, 1998, p. 307.
- [33] Y.M. Cho, W.Y. Choi, C.H. Lee, T. Hyeon, H.I. Lee, Visible light-induced degradation of carbon tetrachloride on dye-sensitized TiO₂, *Environ. Sci. Technol.* 35 (2001) 966.
- [34] K. Vinodgopal, X. Hua, R.L. Dahlgren, A.G. Lappin, L.K. Patterson, P.V. Kamat, Photochemistry of Ru(bpy)₂(dcbpy)²⁺ on Al₂O₃ and TiO₂ surfaces. An insight into the mechanism of photosensitization, *J. Phys. Chem.* 99 (1995) 10883.
- [35] A.J. Bard, Design of semiconductor photoelectrochemical systems for solar energy conversion, *J. Phys. Chem.* 86 (1982) 172.
- [36] N. Chandrasekharan, P.V. Kamat, Improving the photoelectrochemical performance of nanostructured TiO₂ films by adsorption of gold nanoparticles, *J. Phys. Chem. B* 104 (2000) 10851.
- [37] V. Subramanian, E.E. Wolf, P.V. Kamat, Green emission to probe photoinduced charging events in ZnO–Au nanoparticles. Charge distribution and Fermi-level equilibration, *J. Phys. Chem. B* 107 (2003) 7479–7485.
- [38] M. Jakob, H. Levanon, P.V. Kamat, Charge distribution between UV-irradiated TiO₂ and gold nanoparticles. determination of shift in Fermi level, *Nano Lett.* 3 (2003) 353.
- [39] V. Subramanian, E. Wolf, P.V. Kamat, Semiconductor–metal composite nanostructures. To what extent metal nanoparticles (Au, Pt, Ir) improve the photocatalytic activity of TiO₂ films?, *J. Phys. Chem. B* 105 (2001) 11439.
- [40] G. Sberveglieri, Recent developments in semiconducting thin-film gas sensors, *Sens. Actuators B–Chem.* 23 (1995) 103.
- [41] N. Barsan, M. Schweizer-Berberich, W. Gopel, Fundamental and practical aspects in the design of nanoscaled SnO₂ gas sensors: a status report, *Fresenius J. Anal. Chem.* 365 (1999) 287.
- [42] Y.C. Kim, S. Sasaki, K. Yano, K. Ikebukuro, K. Hashimoto, I. Karube, Photocatalytic sensor for the determination of chemical oxygen demand using flow injection analysis, *Anal. Chim. Acta* 432 (2001) 59.
- [43] L. Brus, Model for carrier dynamics and photoluminescence quenching in wet and dry porous silicon thin films, *Phys. Rev. B* 53 (1996) 4649.
- [44] M.J. Sailor, J.L. Heinrich, J.M. Lauerhaas, in: P.V. Kamat, D. Meisel (Eds.), *Semiconductor Nanoclusters – Physical, Chemical and Catalytic Aspects*, Elsevier Science, Amsterdam, 1997, p. 209.
- [45] L. Brus, Luminescence of silicon materials: chains, sheets, nanocrystals, nanowires, microcrystals and porous silicon, *J. Phys. Chem.* 98 (1994) 3575.
- [46] W.L. Wilson, P.F. Szajowski, L.E. Brus, Quantum confinement in size-selected, surface-oxidized silicon nanocrystals, *Science* 262 (1993) 1242.
- [47] J.H. Song, M.J. Sailor, Quenching of photoluminescence from porous silicon by aromatic molecules, *J. Am. Chem. Soc.* 119 (1997) 7381.
- [48] I.N. Germanenko, S.T. Li, M.S. El-Shall, Decay dynamics and quenching of photoluminescence from silicon nanocrystals by aromatic nitro compounds, *J. Phys. Chem. B* 105 (2001) 59.
- [49] H. Sohn, S. Letant, M.J. Sailor, W.C. Troglter, Detection of fluorophosphate chemical warfare agents by catalytic hydrolysis with a porous silicon interferometer, *J. Am. Chem. Soc.* 122 (2000) 5399.

- [50] S. Content, W.C. Trogler, M.J. Sailor, Detection of nitrobenzene, DNT, and TNT vapors by quenching of porous silicon photoluminescence, *Chem. – Eur. J.* 6 (2000) 2205.
- [51] M. Benchorin, A. Kux, I. Schechter, Adsorbate effects on photoluminescence and electrical-conductivity of porous silicon, *Appl. Phys. Lett.* 64 (1994) 481.
- [52] S. Empedocles, M. Bawendi, Spectroscopy of single CdSe nanocrystallites, *Acc. Chem. Res.* 32 (1999) 389.
- [53] L. Li, J. Hu, W. Yang, A.P. Alivisatos, Bandgap variation of size- and shape controlled colloidal CdSe quantum rods, *Nano Lett.* 1 (2001) 349.
- [54] U. Koch, A. Fojtik, H. Weller, A. Henglein, Photochemistry of semiconductor colloids. 13. Preparation of extremely small ZnO particles, fluorescence phenomena and size quantization effects, *Chem. Phys. Lett.* 122 (1985) 507.
- [55] D.W. Bahneman, C. Kormann, M.R. Hoffmann, Preparation and characterization of quantum size zinc-oxide – a detailed spectroscopic study, *J. Phys. Chem.* 91 (1987) 3789.
- [56] P.V. Kamat, B. Patrick, Photophysics and photochemistry of quantized ZnO colloids, *J. Phys. Chem.* 96 (1992) 6829.
- [57] A.E. Varfolomeev, A.V. Eryshkin, V.V. Malyshev, A.S. Razumov, S.S. Yakimov, A study of the sensitivity of ZnO-based sensors to CO, H₂, NH₃, PH₃, and AsH₃, *J. Anal. Chem.* 52 (1997) 56.
- [58] P.V. Kamat, R. Huehn, R. Nicolaescu, A sense and shoot approach for photocatalytic degradation of organic contaminants in water, *J. Phys. Chem. B* 106 (2002) 788.
- [59] P.V. Kamat, B. Patrick, Photochemistry and photophysics of ZnO colloids, in: B. Levy, J. Deaton, P.V. Kamat, I. Leubner, A. Muentner, L. Slifkin, et al. (Eds.), *Symp. Electron. Ionic Prop. Silver Halides*, The Society for Imaging Science and Technology, Springfield, Va, 1991, p. 293.
- [60] A.J. Johnston, P. Hocking, Emerging technologies in hazardous waste management III, ACS Symposium Series, Washington, DC, 1993, pp. 106.
- [61] M. Stevenson, K. Bullock, W.-Y. Lin, K. Rajeshwar, Sonolytic enhancement of the bacterial activity of irradiated titanium dioxide suspensions in water, *Res. Chem. Intermed.* 23 (1997) 311.
- [62] N. Serpone, R. Trezian, H. Hidaka, E. Pelizzetti, Ultrasonic induced dehalogenation and oxidation of 2-, 3-, and 4-chlorophenol in air-equilibrated aqueous media. Similarities with irradiated semiconductor particulates, *J. Phys. Chem.* 98 (1994) 2634.
- [63] D.A. Szewczyk, Book of Abstracts, 213th American Chemical Society National Meeting, American Chemical Society, San Francisco, 1997.
- [64] E. Pernas, K. O'Shea, J. Saires, Prepr. Ext. Abstr. ACS National Meeting, American Chemical Society, Environ. Chem. Div. (1998) 18.
- [65] U. Stafford, K.A. Gray, P.V. Kamat, in: J. Roth, A. Bowers (Eds.), *Chemical Oxidation: Technologies for the 90s*, Technomic Publishing Co. Lancaster, Pennsylvania, 1996, p. 193.
- [66] N.L. Stock, J. Peller, K. Vinodgopal, P.V. Kamat, Combinative Sonolysis and Photocatalysis for Textile Dye Degradation, *Environ. Sci. Technol.* 34 (2000) 1747.
- [67] J. Peller, O. Wiest, P.V. Kamat, Synergy of combining sonolysis and photocatalysis in the degradation and mineralization of chlorinated aromatic compounds, *Environ. Sci. Technol.* 37 (2003) 1926.
- [68] A. Mnyusiwalla, A.S. Daar, P.A. Singer, Mind the gap: science and ethics in nanotechnology, *Nanotechnology* 14 (2003) R9.