



UNICA

UNIVERSITÀ
DEGLI STUDI
DI CAGLIARI



Università di Cagliari

UNICA IRIS Institutional Research Information System

This is the Author's preprint manuscript version of the following contribution:

Careddu, N., Cadeddu, D., Sitzia, F., 2023. Graffiti removal from granite cladding by abrasive water-jet. *Journal of Building Engineering* 78 (2023) 107626.

The publisher's version is available at:

<https://doi.org/10.1016/j.jobe.2023.107626>

When citing, please refer to the published version.

This full text was downloaded from UNICA IRIS <https://iris.unica.it/>

Graffiti removal from granite cladding by abrasive water-jet

N. Careddu^{a,b}, D. Cadeddu^a, F. Sitzia^{c,d}

^a Civil, Environmental Engineering and Architecture Department (DICAAR), University of Cagliari, Cagliari, Italy

^b Institute of Environmental Geology and Geoengineering, IGAG, CNR, Cagliari, Italy

^c HERCULES Laboratory, Institute for Advanced Studies and Research, University of Évora, Portugal

^d Geosciences Department, School of Sciences and Technology, University of Évora, Portugal

Abstract

This study focuses on the assessment of a graffiti removal system based on abrasive water-jet technology (AWJ). Spray paints were applied on samples of an important Italian granite commercially-named as “Rosa Limbara”. This granite has been used worldwide as dimension stone for paving and cladding. Two different commercial abrasives have been added in the high-pressure water-jet in order to clean the granite saw-plane surfaces from graffiti. After a check by the naked eye, different criteria have been chosen for assessing the effectiveness of the cleaning process: the similarity in roughness (R_a , R_z , and R_{max}) between the original surface and the one resulted after cleaning, the total colour difference (ΔE) and the depth of material removed by the AWJ action. The tests showed that excellent cleaning results can be achieved with both abrasives by correctly combining the operational parameters of the technology (i.e., water pressure, spacing between passes, stand-off distance, travel speed and abrasive flow-rate) without giving any damage to the stone material. The two abrasives showed good results in total colour difference although one of them gave better results in both roughness difference and material removal. Economic considerations on paint removal with AWJ technology are also offered.

Keywords

Granite; graffiti; spray paints; abrasive water-jet (AWJ); colourimetry; micro-topographic mapping.

1. Introduction

Since ancient times, stone has been widely used in art, urbanisation and construction all over the world: suffice it to think of the multitude of buildings dedicated to worship, monuments, and flooring constructed from natural stones such as marble, travertine, granite, basalt, etc. [1, 2]. The preservation, restoration and cleaning of these artefacts is now a socio-economic factor of great interest which, thanks to up-to-date studies, are making it possible to continuously improve the involved technologies [3, 4].

The cleaning of stone materials is an essential phase of conservation intervention aimed at reducing the effects of degradation phenomena and it represents a critical phase from both a technical and aesthetic point of view, considering the historical-artistic value of the surfaces on which one works [5].

One problem is graffiti. Due to this popular trend, buildings, squares, street furniture and historical monuments are now more an object of vandalism than of artistic expression: writing and drawings of all kinds can be seen everywhere, leading inexorably to a visible degradation of many cities or small urban areas [6, 7] (Fig.1). The removal of such graffiti is not always easy, particularly on natural stones, on which cleaning may cause surface damage and/or alter the colour of the rock [8].

Figure 1. Example of graffiti vandalism on external cladding with Ghiandone granite in Sardinia (photo courtesy of S. Cuccuru).

1 Many techniques have been studied and applied in graffiti removal. Chemical methods such as
2 solvents and paint strippers are efficient in dissolving or breaking down spray paint [9, 10]; however,
3 they can be used, if they do not further damage the stone substrate. Anti-graffiti coatings can be
4 applied on porous substrates including stone and granite, preventing the penetration of graffiti [11].
5 Eco-friendly solvents were found to be effective in removing graffiti from sandstones [12].
6 Sanmartín et al. [13] found good results in graffiti bioremoval from granite using *Comamonas*
7 *testosterone*. Soft mechanical methods have been used particularly on marbles and limestones.
8 Carvalhão and Dionísio [14] tested dry soft-abrasive blasting media to clean both limestone and
9 marble from graffiti. Careddu and Akkoyun [15] successfully used high-pressure pure water-jet to
10 remove graffiti from Carrara marble. Laser technology has been widely used in the cleaning of
11 graffiti paints made with spray on stone [16-18]. Laser ablation is also enhanced when used in
12 combination of solvents [19] or micro abrasives [20].

13 Protection from graffiti is provided via coatings which are specially applied to preserve polished
14 stone cladding; in this case, the use of a very thick prevents the spray used by vandals from bonding
15 to the stone surface [8]. In this way, the graffiti can be easily removed from a polished surface. It
16 should be also noted that tagger is typically attracted to a sound and polished surface rather than to
17 a raw [4]; however, this last is more difficult to be cleaned due to its porosity [21]. Unprocessed raw
18 granite is reportedly used in many different ways - i.e., as outdoor cladding and paving, curbs and
19 street furnishing. In fact, the rustic appearance, non-slip roughness and excellent durability of
20 granite means that such surfaces are preferred for outdoor use. The surface obtained with the
21 traditional pendulum-gang saw technology, is often applied in works that do not impose tight
22 geometric and dimensional tolerances, such as in paving squares, in pedestrian areas, in artefacts
23 placed at a great viewing distance, or with elements of large size (e.g. outdoor paving) [22]. For
24 these reasons, no preventive anti-graffiti treatment is required for granite raw surfaces.

25 The aim of this study is the evaluation of the abrasive water-jet (AWJ) technology in the cleaning
26 of stone surfaces and the removal of spray paint from the rough surface of granite. Currently, AWJ
27 technology is used for cutting and surface finishing of stone slabs; definitely, the novelty of this work
28 is to apply the same technology in graffiti cleaning and to prove its feasibility on granite.

29 To this end, surface cleaning tests were carried out to assess the operating parameters of AWJ
30 technology that could guarantee both the effectiveness of the paint removal process and the
31 preservation of the original condition of the stone material.

32 2. Materials and equipment

33 2.1 Stone material

34 The stone material used in this study is commercially known as Rosa Limbara, belonging to the
35 family of Ghiandone granite (Fig. 2a). This stone has been chosen because of its easy availability and
36 worldwide use; there are countless examples of use of Ghiandone granite throughout the whole
37 world [23]: see for instance the stairs of the Presidential Palace in Turkmenistan and the cladding of
38 some skyscrapers in Perth (Australia) as well as the many buildings, street paving and urban
39 furnishing in the towns of North Sardinia. Ghiandone granite represents a typical example of stone
40 relative to the vernacular architecture in Sardinia. Finally, the slabs of Ghiandone are sold with
41 almost all types of surface finishing.

42 Ghiandone granite is quarried nearby the town of Priatu in northern Sardinia, Italy. The slabs
43 from which the specimens were taken, have been produced by traditional pendulum-gang saw
44 sawing.

45 By the naked eye, the stone appears to have the characteristics of a medium to coarse grained
46 granitoid with the presence of “acorn-shaped”. These are referred to as both automorphic and

1 xenomorphic mega-crystals of K-feldspar. The size of these crystals varies from 1 cm to some
2 exceptional case of 8 cm. The most frequent size is around 2 cm.

3 Macro-crystals of plagioclase (from 0.5 to 2 cm) and quartz (from 0.5 to 3 cm) are well visible by
4 the naked eye, in addition to biotite agglomerates and opaques. Biotite crystals are from 0.2 to 1
5 cm in size.

6 In the 30 μm thin section (Fig. 2b) and according to the QAPF classification, the rock is
7 petrographically classified as Monzogranite with the following percentages of components Q = 33
8 %, A = 27 % and P = 40 %. In addition to the QAPF phases, the rock has a biotite percentage of about
9 6% and an opaque percentage of 2%.

10 The rock's ensemble of macro and microscopic traits are recognized as "Lovia Avra" lithotype of
11 the monzogranites from the area of Gallura [24].

12
13
14
15
16 Figures 2. a: Rosa Limbara granite (polished). b: thin section (crossed nicols) from Rosa Limbara granite. Legend: Qz =
17 Quartz, Kf = K-feldspar, Plg = plagioclase, Bt = Biotite.

18
19
20 Some of the physical and mechanical properties of Rosa Limbara granite given in Table 1. The
21 physical and mechanical properties were determined by a whole range of laboratory tests, which
22 were carried out in accordance with both UNI-EN and ASTM standards.

23
24
25 Table 1. Stone properties of Rosa Limbara granite according to UE and ASTM standards.

26 27 28 2.2 Abrasive water-jet equipment

29 The equipment used for the cleaning test is the model Waterline 1620, which is a numerical
30 control water-jet cutting robot (Fig. 3).

31 The high-pressure system includes the pump, cutting head and plumbing. The pump is equipped
32 with three linear intensifiers with 35 kW installed power, which supplies a working water pressure
33 ranging from 100 to 380 MPa at a flow rate of 7 L/min.

34 The cutting head is provided with a 0.3 mm diameter sapphire nozzle and a 7.6 cm long focusing
35 tube, made of tungsten carbide, with an internal diameter of 1 mm. The cutting head can be moved
36 along its X and Y axis (numerically controlled) on the working area (1.6 m x 2.0 m). The Z-axis is
37 manually moved. In order to carry out the cleaning tests, the cutting head has been modified to
38 allow a change of the angle of the jet inclination.

39 The control module, which governs the whole system, is interfaced to the machine via an
40 automatic programming system CAD-CAM. The abrasive particles are sucked in dry by the Venturi
41 effect into the mixing chamber (through a dosing device), in which they are introduced into a
42 primary jet issuing from a nozzle. The water-jet has the function of accelerating and transporting
43 the abrasive particles which work on the stone [25, 26].

44
45
46
47
48
49
50
51 Figure 3. Abrasive water-jet equipment. a: pressure intensifier; b: CNC-controlled working area; c: cutting head.

52 53 54 2.3 Abrasives

55 Two abrasives (hereafter called A and B) have been used in the experimental tests; both have
56 been chosen because they are the most used abrasives in the stone-cutting industry. Abrasive A
57 consisted of almandine garnet, while abrasive B came from metal slag deriving from copper
58 metallurgic process. Due to the distribution of the grain size of this latter product (Fig. 3) - which
59 ranged $45 \mu\text{m} < B < 1 \text{ mm}$ -, it was necessary to cut the particle size distribution by screening to
60
61
62
63
64
65

bring the abrasive B to the same class of abrasive A: $105 \mu\text{m} < A < 300 \mu\text{m}$. Figures 5a and 5b show the results of X-ray diffractometer tests on the two abrasives.

Figure 4. Particle-size distribution curves of abrasives A and B.

Figures 5. XRD analysis of the two abrasives

3. Methods

The aim of the experimental tests was to remove graffiti from the stone by limiting variations in the technical and aesthetic characteristics of the treated surface as much as possible. The method applied in this study is given in Fig. 6 and it is explained in the next sub-sections.

Figure 6. The methodology followed in this study.

To reproduce the granite surface that is commonly used in paving, cladding or other urban furnishing, the saw-plane surface of the specimen has been considered as the original surface. The granite specimens were painted by using spray paints in red (acrylic paint), orange and blue (synthetic paints). A piece of confectionery chewing gum was applied on one of the specimens, and they were left to weather for seven days. This time allowed for complete absorption of the paint and drying of the chewing gum. The idea behind this experiment originated from the consideration that littered chewing-gum is typically a frequent environmental problem in many countries.

3.1. Cleaning test

During the study, several different operation conditions of the abrasive water-jet plant were set to use it as a cleaner tool onto the different painted parts of stone surfaces. The different operational condition features of the water-jet plant are given in Table 2; twenty different combinations have been tested in the study.

Fig. 7a shows the process of paint removal by abrasive water-jet. Based on the results obtained from earlier investigations [27, 28], a finishing program for parallel rectilinear passes of the jet was adopted. The operating parameters as the nozzle diameter ϕ (0.3 mm) and water-jet inclination γ (30° with respect to the horizontal plane) were kept constant. The stand-off distance D , the inter-distance between passes i (spacing), travel speed v_t , water pressure P and abrasive flow-rate Q_a were varied as listed in Table 2.

Figure 7b can help to summarize the geometrical operating parameters.

Figures 7. a: view from the cleaning process by abrasive water-jet plant in the test laboratory. b: example of cleaning program for parallel passes indicating spacing (i) between passes, stand-off distance (D) and water-jet inclination (γ).

Table 2. The operating parameter ranges of the abrasive water-jet machine.

3.2. Colour measurements

Since the objective of the experimental tests is to restore the stone surface to the appearance it had before being vandalized, the color of the specimen had to be assessed, so as to compare the stone surface before painting and after cleaning. The colour of the specimen was measured with a bench-top spectrophotometer CM-3610A provided by Konica-Minolta and equipped with Spectra Magic NX PRO software. The measuring conditions set in the device were: illuminant D65, and observer 2° [29] with a $d=8^\circ$ illumination viewing geometry (following [30]). The diameter of the

1 target mask has been set at 25.4 mm diameter in order to allow an average of the stone colour to
2 be measured, simulating viewing from a distance [31]. Fig. 8 shows the target masks on the cleaned
3 area of a textured sample.
4

5 Figure 8. The 25.4 mm diameter target masks used in this study.
6

7 Colour was assessed by taking 9 random readings on some zones of the surface for each one of
8 the specimens both before painting (original stone surface) and after the cleaning process.
9

10 Due to the fact that the surface of the samples is not entirely reflective or matte, inclusion or
11 exclusion of the specular component may be important for colour measurements [32].
12

13 The technique of colour measurement, which excludes the specular reflectance, is named SCE
14 (Specular Component Excluded). When the specular reflectance is included in the colour
15 measurement by completing the sphere with a specular plug, we refer to it as SCI (Specular
16 Component Included). In SCE mode, the specular reflectance is excluded from the measurement
17 and only the scattered reflectance is measured. This gives a colour evaluation which correlates to
18 the way the observer perceives the colour of an object. Stone surfaces characterized by matte
19 colour and irregularities induce the light diffusion in many directions, thus reducing the SCE [32]:
20 for this reason, measurements have been carried out in SCE mode. When using the SCI mode, the
21 specular reflectance is included with the scattered reflectance during the measurement process.
22 This type of colour assessment measures the entire appearance in spite of the surface condition.
23

24 For these reasons, the measurements were carried out in both SCI and SCE modes.
25

26 Regarding the choice of CIE colour space, the CIE L*a*b* coordinates are recommended for
27 achromatic colours, whereas the CIE L*C*h* coordinates are preferred for stronger colours [33].
28 Because the objective of this study was to try to assess the possible difference in the colour of the
29 stone before painting and after cleaning, both sets of colour space coordinates were used.
30

31 To better assess the colour differences between the original surface and the ones obtained after
32 graffiti removal, the classical CIEL*a*b* formulation (1) [34] was used, as supported by Prieto et al.
33 [35] especially when textured surfaces are to be studied:
34

$$35 \Delta E_{ab} = \sqrt{(\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2} \quad (1)$$

36 3.3. Roughness test

37 The data which have been obtained with the spectrophotometer analysis have to be updated
38 with the information about roughness. In fact, a cleaned surface, which shows similar colours
39 compared to an unpainted surface, it may have completely different roughness features, due to an
40 excessive excavation caused by the water-jet during the cleaning process.
41

42 The purpose of roughness measurements is to determine which one of the treated surfaces has
43 similar roughness to the original surface. For this reason, the roughness profile of the cleaned
44 samples was carefully analysed using a mechanical comparator. Parameters R_a (mean roughness),
45 R_z (average distance between the highest peak and lowest valley in each sampling length) and R_{max}
46 (maximum roughness depth) were determined in accordance with EN ISO 21920-3 [36].
47
48
49
50
51
52
53

54 3.4. Measurement of average excavation depth

55 It is very important to assess how much stone material was removed during the cleaning
56 operation. This was calculated according to three cross sections of stone surface perpendicular to
57 the transition line between the painted area and the area subjected to the water-jet.
58
59
60
61
62
63
64
65

1 A 3D micro-topographic map (3x3 cm) has been performed by an HIROX-01 microscope equipped
2 with a nano point scanner (NPS-NP3, working range $0 < R < 1400 \mu\text{m}$). The 3D micro-topographic
3 map consists of 200 scanning lines realized through a speed of $3000 \mu\text{m/s}$.

4 The crossing section profiles have been extracted by the 3D micro-topographic map with the help
5 of the software Mountain Map Imaging topographic version 7.4

6 In any cross section, the difference (ΔY) between the average elevation in the painted area and
7 average elevation in the area subject to water-jet was measured by means of the processing
8 software. The average amount of material removed during the cleaning operation is then calculated
9 as the arithmetic average of the ΔY s of each of the three profiles.

13 4. Results and discussion

14 After the cleaning process and before the colorimetric study, the granite samples were checked
15 by the naked eye for macroscopic control. Graffiti removal was observed on all samples subjected
16 to the cleaning process. However, some tests were excluded from subsequent measurements
17 because the jet removed an excessive amount of material, which was not ideal.

18 The cleaning tests that passed this initial screening were subjected to the subsequent
19 measurements.

20 As general considerations, we can say that the best results, from a technical point of view, are
21 obtained with the following combinations of water-jet operating parameters:

- 22 - When using abrasive A:
 - 23 ○ $P = 300 \text{ MPa}$, $v_t = 40 \text{ m/s}$, $i = 10 \text{ mm}$, $D = 100 \text{ mm}$, $Q_a = 202,1 \text{ g/min}$
- 24 - When using abrasive B:
 - 25 ○ $P = 300 \text{ MPa}$, $v_t = 20 \text{ m/s}$, $i = 10 \text{ mm}$, $D = 100 \text{ mm}$, $Q_a = 211,2 \text{ g/min}$
 - 26 ○ $P = 200 \text{ MPa}$, $v_t = 35 \text{ m/s}$, $i = 10 \text{ mm}$, $D = 100 \text{ mm}$, $Q_a = 58,6 \text{ g/min}$ (chewing-gum test)

27 In fact, the tests which was carried out with these combinations resulted in perfectly clean
28 specimens, with a surface similar to the original one (before painting).

29 The high-pressure water-jet causes the removal of layers of variable thickness on the stone. In
30 monomineralic stones, water-jet abrasion capacity depends on the porosity of the rock especially
31 in the pore range $0.01 < \phi < 1 \mu\text{m}$ [37].

32 In multi-mineralogic rocks, as Ghiandone granite, surface removal takes place according to
33 differential erosion. By the latter, minerals with higher hardness and absence of microfractures or
34 layers of inclusions resist the action of the water-jet better. Conversely, softer or micro-fractured
35 minerals will exhibit low strength.

36 In our test, removal craters were often deeper and thinner when the water-jet was directed
37 parallel to micropertitic layers [38].

38 Following our test and based on bibliographic observations, the removal craters on macrocrystals
39 of K-feldspar are deeper than plagioclase.

40 Additionally in this latter, it has been statistically observed that the volume of the erosion crater
41 is not proportional to the pressure of the water-jet flow but shows significant oscillations [39].

42 Plagioclase shows the highest strength among all phases due to its compactness and absence of
43 fractures.

44 In K-feldspars the action of the water-jet is favoured by the presence of spatial discontinuities in
45 terms of cleavage planes. The K-feldspar removal capacity by the water-jet changes according to the
46 orientation of the water-jet with respect to the cleavage planes [38].

47 Conversely, in quartz the presence of spatial discontinuities favours its easy removal. As reported
48 in the biography, quartz is the most sensitive mineral to the action of the water-jet, showing a good
49 proportionality between the volume of the crater produced by the erosion and the pressure of the
50 flow [39]. On quartz crystal, the water-jet mainly produces irregular cavities irrespective to the
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1 mineral form. The biotitic phases from the granites show a good resistance due to their plastic
2 deformability [37].
3

4 4.1 Colour

5 Fig. 9a shows a comparison of the colour coordinates between the $L^*a^*b^*$ values of the surfaces
6 studied. The cleanings, obtained with both abrasives, show similar values in the Cartesian plane a -
7 b ; the colours of the cleaned surfaces move more towards the natural colours of the stone
8 (represented by the polished surface, POL) than the colours of the starting surface (SPG).
9

10
11 Figures 9. a: Values of the a^* , b^* CIELAB coordinates and L^* CIELAB lightness for the different surface. b: Values of the
12 CIELAB chroma C^* , L^* and CIELAB hue angle h for the different surface. CLA = surface cleaned by abrasive A; CLB =
13 surface cleaned by abrasive B; POL = polished surface; SPG = gang-saw-plane surface. Lightness L^* is shown in two
14 different scales to facilitate reading.
15

16
17 These results are also confirmed in the L^*C^*h colour space as shown in Fig. 9b. It should be noted
18 that the hue values (h) of the cleaned surfaces move towards to the values of the starting surface
19 (SPG), particularly in the samples in which abrasive B was used. However, when evaluated over
20 360° , the hue values are very close to each other, showing that the difference between the values
21 is very small.
22

23 As was to be expected, in each sample, the SCI and SCE values are very close to each other with
24 the only exception of the polished samples, where the difference is magnified for the reasons
25 already explained in section 3.2.
26
27

28
29 Table 3. Partial colour differences (ΔL^* , Δa^* , Δb^*) and total colour difference (ΔE^*) between the original saw-plane
30 surface and each of the other cleaned surface finishes, in SCI and SCE modes. Polished surface values are also reported.
31

32
33 Although the two abrasives restore a very similar surface to the original one, as can be seen from
34 the ΔE^* values in the Table 3, abrasive A seems to have a better result. In fact, when considering
35 observing the ΔE^* values with respect to the "just noticeable difference" (JND) it is known that an
36 unexperienced observer notices the difference when $2 < \Delta E < 3.5$ [40].
37
38

39 4.2 Roughness

40
41 Table 4 shows that the roughness of the samples subjected to paint removal is similar to that of the
42 original surface (SPG), particularly when abrasive A is used.
43

44 Table 4. Roughness values, measured in μm , for the different surfaces (R_a = Mean roughness; R_z = Average distance
45 between the highest peak and lowest valley in each sampling length; R_{max} = Maximum roughness depth).
46
47

48 The small differences with the original surface (before painting) are related to what was described
49 earlier: the 'selective' action produced by the AWJ on the different crystals of the granite implies a
50 greater 'excavation' at the more sensitive crystals (i.e. quartz) and lesser at the more resistant
51 crystals (i.e. plagioclase).
52

53 These values, taken together with the colorimetric parameters, show how abrasive water-jet
54 cleaning can restore the stone surface to its original appearance.
55
56

57 4.3 Material removal

58
59 Figures 10A and 10B show both the 2D orthophoto of sample surface subjected to AWJ cleaning (by
60 using abrasives A and B respectively). The scanning surface (3x3 cm) includes the transition line
61 between painted and cleaned area and the 3D micro-topographic map with cross section positions.
62
63
64
65

1 In Figs. 10, two 3D micro-topographic maps are illustrated by coloured thematic areas where red
2 and white topographically represent prominent areas while green and blue areas represent
3 depressions. As already explained in the methods, three cross-section profiles A-A', B-B', C-C' were
4 made from these surfaces and are exhibited in the corresponding photos. On the right of both the
5 figures, the 3 cross sections are present with the relative ΔY . It is easy to identify how the area
6 subject to cleaning is always less elevated than the painted area. This is due to the removal of a thin
7 layer of material following the passage of the abrasive water-jet.

8
9 In Fig. 10A, showing the sample cleaned by A abrasive, it can be seen that in profile 1, a difference
10 $\Delta Y = 33.6 \mu\text{m}$ between painted and cleaned area is identified. In profiles 2 and 3, a ΔY of $78.2 \mu\text{m}$
11 and $74.2 \mu\text{m}$ are respectively recorded. The average thickness of removed material in the sample is
12 therefore considered the arithmetic mean of the three ΔY , in this case $62 \mu\text{m}$.

13 In Figs. 10B, showing the sample cleaned by B abrasive, the first profile identifies a difference $\Delta Y =$
14 $114.8 \mu\text{m}$. In profiles 2 and 3, a ΔY of $119.7 \mu\text{m}$ and $159.2 \mu\text{m}$ are respectively recorded. The average
15 thickness of removed material in the sample is therefore $131.2 \mu\text{m}$.

16 In the sample cleaned through B abrasive a layer of material thicker than the abrasive A was
17 therefore removed. This is essentially due to a higher Q value.

18
19
20
21
22
23 Figures 10A: (a) 2D orthophoto of sample surface subjected to A abrasive cleaning. The scanning surface (3x3 cm)
24 includes the transition line between painted and cleaned area, (b) 3D micro-topographic map with cross section
25 positions.

26
27
28 Figures 10B: (a) 2D orthophoto of sample surface subjected to B abrasive cleaning. The scanning surface (3x3 cm)
29 includes the transition line between painted and cleaned area, (b) 3D micro-topographic map with cross section
30 positions.

31
32 The chewing gum was easily removed from the surface together with the paint (see Fig. 11).

33
34
35 Figure 11. Result of chewing-gum removal: a) vandalized condition, b) after cleaning.

36 37 5. Economic consideration

38
39 The economical features and operational costs of stone slabs surface finishing with water-jet were
40 stated in a previous study in detail [41]; so that, it can be said that: considering both technical and
41 economic parameters as the surface finishing velocity, the ownership costs of the plant, the
42 operating costs and labour cost (in the Italian market), we have obtained the total unit cost (C_t)
43 ranging from 2.59 €/m^2 , when abrasive A is used, to 4.56 €/m^2 when abrasive B is used. The main
44 parameters which affect C_t are both the inter-distance between passes i (smaller i value gives
45 higher C_t value) and the travel speed (faster v_t value gives lower C_t value). However, it should be
46 noted that this range allows a very good gain when compared with the current unit price in
47 European market for paint removing (from 13 to 60 €/m^2) from paving and cladding.

50 51 52 6 Conclusion

53
54 The assessment of abrasive water-jet technology on spray-paint graffiti removal from granite was
55 analyzed and discussed considering two different commercial abrasives.

56
57 Colorimetric investigations performed on the samples both previous painting and after cleaning
58 revealed that this method is effective in paint removal, restoring the surface aesthetic like the
59 original one. The total color difference (ΔE^*) after cleaning shows values lower than 4 units for both
60 abrasives; although these results are a bit higher than the JND, the surface aesthetic appearance is
61 surely acceptable.

Moreover, the micro-photographic mapping demonstrated that abrasive water-jet cleaning produces very low damage on the granite when the operative parameters (as abrasive flow-rate, water pressure) were well-chosen, especially when abrasive A is used.

This is also confirmed by roughness measurements that show the roughness parameters (R_a , R_z and R_{max}) very close to those of the original saw-plane surface.

Although presented here as an accessory experiment, it can be stressed that the abrasive water-jet removed easily the chewing-gum from the stone.

The study demonstrated the economic feasibility of the AWJ technology in removing graffiti from Ghiandone granite. We must highlight the importance of calibrating the operating parameters according to the material and the desired results: it should be borne in mind that a different typology of granite is expected to give different results in terms of paint removal.

Other stone surfaces (e.g. flamed and bush-hammered) will be considered in future research developments; the mechanism of graffiti removal by AWJ will be studied as well. Weathered surfaces will also continue to be included in the research.



References

- [1] O'Neill, H., Stone for building, W. Heinmann Ltd, London, 1965.
- [2] Careddu, N., Grillo, S.M., 2019. Sardinian Basalt—an Ancient Georesource Still *En Vogue*. *Geoheritage* (2019) 11:33-45. <https://doi.org/10.1007/s12371-018-0285-0>.
- [3] R. Snethlage, K. Sterflinger, Stone Conservation, in: S. Siegesmund and R. Snethlage (Eds.), *Stone in Architecture – Properties, Durability* (fourth ed.), Springer, Berlin, 2011, pp. 411-544.
- [4] Pozo-Antonio, J.S, Rivas, T., López, A.J., Fiorucci, M.P., Ramil, A., 2016. Effectiveness of granite cleaning procedures in cultural heritage: A review. *Science of The Total Environment*, Vol. 571, 2016, Pages 1017-1028. <https://doi.org/10.1016/j.scitotenv.2016.07.090>.
- [5] E. Doehne, C.A. Price, *Stone Conservation – An overview of current research* (second ed.), Getty Conservation Institute (Pub.), Los Angeles, 2010.
- [6] J. Ashurst, *Cleaning masonry buildings*, in: J. Ashurst and F.G. Dimes (Eds.), *Conservation of Building and Decorative Stone* (second ed.), Butterworth-Heinemann, Elsevier, Burlington, 2006.
- [7] Gomes, V., Dionísio, A., Pozo-Antonio, J.S., 2017. Conservation strategies against graffiti vandalism on Cultural Heritage stones: Protective coatings and cleaning methods, *Progress in Organic Coatings*, Vol. 113, 2017, Pages 90-109. <https://doi.org/10.1016/j.porgcoat.2017.08.010>.
- [8] P. Loughran, *Failed Stone - Problems and Solutions with Concrete and Masonry*. Birkhäuser – Publishers for Architecture, Basel, Switzerland, 2007.
- [9] Sanmartín, P., Cappitelli, F., Mitchell, R., 2014. Current methods of graffiti removal: A review. *Construction and Building Materials* 71, pp. 363-374. <https://doi.org/10.1016/j.conbuildmat.2014.08.093>.
- [10] Baglioni, M., Poggi, G., Jaidar Benavides, Y., Martínez Camacho, F., Giorgi, R., Baglioni, P., 2018. Nanostructured fluids for the removal of graffiti – A survey on 17 commercial spray-can paints. *Journal of Cultural Heritage* 34, pp. 218-226. <https://doi.org/10.1016/j.culher.2018.04.016>.
- [11] Amrutkar, S., More, A., Mestry, S., Mhaske, S.T., 2022. Recent developments in the anti-graffiti coatings: an attentive review. *Journal of Coatings Technology and Research* 19(3), pp. 717-739. <https://doi.org/10.1007/s11998-021-00580-z>.
- [12] Bartman, M., Balicki, S., Wilk, K.A., 2021. Formulation of environmentally safe graffiti remover containing esterified plant oils and sugar surfactant. *Molecules* 26(15),4706. <https://doi.org/10.3390/molecules26154706>.
- [13] Sanmartín, P., Bosch-Roig, P., Gulotta, D., Bosch, I., Cappitelli, F., 2021. *Klebsiella aerogenes* and *Comamonas testosteroni* as bioremoval agents on graffiti-coated concrete and granite: Impact assessment through surface analysis. *International Biodeterioration and Biodegradation* 161, 105244. <https://doi.org/10.1016/j.ibiod.2021.105244>.
- [14] Carvalhão, M., Dionísio, A., 2015. Evaluation of mechanical soft-abrasive blasting and chemical cleaning methods on alkyd-paint graffiti made on calcareous stones. *Journal of Cultural Heritage* 16(4), pp. 579-590. <https://doi.org/10.1016/j.culher.2014.10.004>.
- [15] Careddu, N., Akkoyun, O., 2016. An investigation on the efficiency of water-jet technology for graffiti cleaning. *Journal of Cultural Heritage* 19 (2016) 426-434. <https://doi.org/10.1016/j.culher.2015.11.009>.

- 1 [16] V. Atanassova, V., Laser cleaning of graffiti spray paints on marble, limestone and granite. In: X. Paradis and M.
2 Matthew (eds), *Graffiti: Vandalism, Street Art and Cultural Significance*, Nova Science Pub Inc, 2018, pp. 117-144.
3 ISBN-10: 1536134996.
- 4 [17] Penide, J., Quintero, F., Riveiro, A., Sánchez-Castillo, A., Comesaña, R., Del Val, J., Lusquiños, F., Pou, J., 2013.
5 Removal of graffiti from quarry stone by high power diode laser. *Optics and Lasers in Engineering* 51(4), pp. 364-370.
6 <https://doi.org/10.1016/j.optlaseng.2012.12.002>.
- 7 [18] Pozo-Antonio, J.S., Papanikolaou, A., Melessanaki, K., Rivas, T., Pouli, P., 2018. Laser-assisted removal of graffiti
8 from granite: Advantages of the simultaneous use of two wavelengths. *Coatings* 8(4),124.
9 <https://doi.org/10.3390/coatings8040124>.
- 10 [19] Ricci, C., Gambino, F., Nervo, M., Piccirillo, A., Scarcella, A., Zenucchini, F., Ramil, A., Pozo-Antonio, J.S., 2020.
11 Enhancement of graffiti removal from heritage stone by combining laser ablation and application of a solvent mixture.
12 *Construction and Building Materials* 262, 119934. <https://doi.org/10.1016/j.conbuildmat.2020.119934>.
- 13 [20] Gomes, V., Dionísio, A., Pozo-Antonio, J.S., Rivas, T., Ramil, A., 2018. Mechanical and laser cleaning of spray graffiti
14 paints on a granite subjected to a SO₂-rich atmosphere. *Construction and Building Materials* 188, pp. 621-632.
15 <https://doi.org/10.1016/j.conbuildmat.2018.08.130>
- 16 [21] Masieri, M., Lettieri, M., 2017. Influence of the Distribution of a Spray Paint on the Efficacy of Anti-Graffiti Coatings
17 on a Highly Porous Natural Stone Material. *Coatings* 2017, 7, 18. <https://doi.org/10.3390/coatings7020018>.
- 18 [22] P. Primavori, Surface finishes on stone materials. In: *Directory 2010*, Marmomacchine Servizi s.r.l. (Pubs.), Milano,
19 Italy.
- 20 [23] Careddu, N., Cuccuru, S., Grillo, S.M., 2021. Sardinian granitoids: 4000 years of geoheritage and dimension stones.
21 *Resources Policy* 74 (2021) 102339. <https://doi.org/10.1016/j.resourpol.2021.102339>.
- 22 [24] G.P. Cherchi, G. Musumeci, Il complesso granitoide della Sardegna settentrionale, in Carmignani, L., Pertusati, C.,
23 and Barca, S., eds, *Struttura della catena Ercinica in Sardegna – Guida all’escursione*, Pisa, Italy, Pacini Pub., 1992,
24 pp. 157–163 (in Italian).
- 25 [25] Careddu, N., 2006. Developments in the surface finishing of ornamental rocks by high-pressure water jet without
26 abrasive and proposal for an official name for the process. *Diamante – Applicazioni e Tecnologia*, suppl. n. 46, Anno
27 12, Settembre 2006, pagg. 65-77. Also published in *Diamante – Applicazioni e Tecnologia*, n. 47, Anno 12, Dicembre
28 2006, pagg. 65-77. Ed. G & M Associated Sas. ISSN 1824-5765.
- 29 [26] Careddu N., 2010. Surface treatment of ornamental stones by high-pressure, water-jet technology. *Mining*
30 *Engineering*, vol. 62, n. 7, July 2010, SME, pp. 44-50
- 31 [27] Careddu, N., 2009. Working granite surfaces with a high-pressure water-jet: a comparison of abrasives and
32 economic considerations. *Marmomacchine*, n. 208, 4° Bim. 2009 – Anno 39°, pagg. 50-68. Ed. Promorama, Milan,
33 Italy.
- 34 [28] Careddu, N., 2020. Chromaticism differentiations: A study of the diversified aesthetic appeal of the Ghiandone
35 granite range. *Journal of Building Engineering* 30 (2020) 101300. <https://doi.org/10.1016/j.jobe.2020.101300>.
- 36 [29] CIE. Colorimétrie, Resolutions 1–4. *Recueil des travaux et compterendu des séances*, Hutième Session Cambridge-
37 Septembre 1931. Bureau Central de la Commission, The National Physical Laboratory Teddington: Cambridge
38 University Press; p 19–29.
- 39 [30] Biscotin, G., Bakolas, A., Bertoncetto, R., Longega, G., Moropoulou, A., Tondello, E., Zendri, E., 1995. Investigation
40 of the effect of the cleaning procedures applied to stone surfaces, *Mater. Res. Soc. Symp. Proc.* 352 (1995) 857–864,
41 1995. <https://doi.org/10.1557/PROC-352-857>.
- 42 [31] Careddu, N., Aru, W., 2023. Chromaticism differentiations: How variegated homogeneous stones used in buildings
43 can gain diversified aesthetic appeal. *Journal of Building Engineering* 63 (2023) 105452.
44 <https://doi.org/10.1016/j.jobe.2022.105452>.
- 45 [32] Sanmartín, P., Silva, B., Prieto, B., 2011. Effect of surface finish on roughness, color, and gloss of ornamental
46 granites. *Journal of Materials in Civil Engineering*, vol. 23 (8), 2011, 1239–1248.
47 [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0000285](https://doi.org/10.1061/(ASCE)MT.1943-5533.0000285)
- 48 [33] Catalina, F., and Bruna, J. M., 1997. Principios de colorimetría práctica. *Sistema CIE de medida diferencial de color*.
49 *Rev. Plast. Mod.*, 73(488), 164–171 (in Spanish).
- 50 [34] CIE S014-4/E:2007, Colorimetry Part 4: CIE 1976 L*a*b* Colour Space, Commission Internationale de l’éclairage,
51 CIE Central Bureau, Vienna, 2007.
- 52 [35] Prieto, B., Ferrer, P., Sanmartín, P., Cárdenes, V., Silva, B., 2011. Color characterization of roofing slates from the
53 Iberian Peninsula for restoration purposes. *Journal of Cultural Heritage* 12 (2011) 420–430.
54 <https://doi.org/10.1016/j.culher.2011.02.001>.
- 55 [36] EN ISO 21920-3:2022. Geometrical product specifications (GPS) - Surface texture: Profile - Part 3: Specification
56 operators (ISO 21920-3:2021). International Organization for Standardization, January, 2022.
- 57 [37] M. Agus, A. Bortolussi, R. Ciccu, W.M. Kim, P.P. Manca, The influence of rock properties on waterjet performance.
58 In: M. Hashish (ed.), *Proc. 7th American Water Jet Conference*, Vol. 1, Seattle, Washington, 1993, pp. 427-442.
- 59
60
61
62
63
64
65

- 1 [38] Careddu, N., Mazzella, A., Dessì, S., 2017. Surface processing of stone by water-jet: assessment of the minerals'
2 luster and comparison with traditional technologies. *Episodes* Vol. 40, No. 4, 305-314.
3 <https://doi.org/10.18814/epiiugs/2017/v40i4/017031>.
- 4 [39] M. Agus, A. Bortolussi, R. Ciccu, W.M. Kim, P.P. Manca, G. Massacci, M. Bosu, Jet impingement tests on mineral
5 crystals. In: J.S.Y. Tan (ed.), *Proc. First Asian Conference on Recent Advances in Jetting Technology*, 7-8 May, 1991,
6 Singapore, pp. 1-9.
- 7 [40] Mokrzycki, W.S., Tatol, M., 2011. Colour difference ΔE - a survey, *Mach. Graph. Vis.* 20 (4) (2011) 383–411.
- 8 [41] Careddu, N., Akkoyun, O., Medda, P., Tilocca, C., 2014. Technical-economic assessment of stone slabs surface
9 finishing using water jet technology. *Int J Adv Manuf Technol* (2014) 71:1991–2001.
10 <https://doi.org/10.1007/s00170-014-5614-0>.
- 11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65













Figure 4


























A



B





Table 1. Stone properties of Rosa Limbara granite according to UE and ASTM standards.

Stone Properties - UE STANDARDS	UNIT	STONE
Denomination - UNI EN 12440:2008		Ghiandone Rosa Limbara
Petrographic denomination - UNI EN 12407:2007		Granite
Real density – UNI EN 1936:2007	kg/m ³	2,658
Apparent density – UNI EN 1936:2007	kg/m ³	2,626
Total porosity – UNI EN 1936:2007	%	1.20
Open porosity – UNI EN 1936:2007	%	0.90
Water absorption at atmospheric pressure - UNI EN 13755:2008	%	0.30
Flexural strength under concentrated load – UNI EN 12372:2007	MPa	15.10
Flexural strength under concentrated load (after 48 freeze-thaw cycles) – UNI EN 12372:2007 + UNI EN 12371:2003	MPa	15.20
Compressive strength – UNI EN 1926:2007	MPa	226
Compressive strength (after 48 freeze-thaw cycles) – UNI EN 1926:2007 + UNI EN 12371:2003	MPa	228
Resistance to ageing by thermal shock – UNI EN 14066:2004 + UNI EN 14146:2005	%	$\Delta m = 0.04$ $\Delta E_d = - 17.70$
Abrasion resistance – UNI EN 14157:2005	mm	15.50
Slip resistance by means of the pendulum tester – UNI EN 14231:2004		47 (polished and dry sample) 11 (polished and wet sample)
Linear thermal expansion coefficient – UNI EN 14581:2005	$\mu\text{m}/\text{m}/^\circ\text{C}$	9.48
Breaking load at dowel hole – UNI EN 13364:2003	mm (d_1 , b_A) kN (F)	$d_1 = 9.10$ $b_A = 43$ $F = 1.78$
Knoop hardness – UNI EN 14205:2004	MPa	HK25 = 5,536; H50 = 7,259; HK75 = 8.898
Stone Properties - ASTM STANDARDS	UNIT	STONE
Bulk specific gravity - C 97 - 02	kg/dm ³	2.63
Absorption – C 97 - 02	%	0.20
Modulus of rupture – C 99 - 00	MPa	R = 16.30
Flexural strength – C 880 - 98	MPa	$\sigma = 13$
Compressive strength – C 170 - 99	MPa	C = 172
Abrasion resistance of stone subjected to foot traffic – C 241 - 97		$H_a = 38.27$

Table 2. The different operational parameter of the abrasive water-jet machine.

Abrasive type	Spacing i [mm]	Stand-off distance D [mm]	Water pressure P [MPa]	Travel speed v_t [m/min]	Abrasive flow-rate Q_a [g/min]
A	10, 14, 20	100, 120	200, 300	20, 35, 40	90, 195, 202
B	10	100	200, 300	10, 20, 21, 30, 35, 40	58.6, 63, 146, 211

Table 3. Partial colour differences (ΔL^* , Δa^* , Δb^*) and total colour difference (ΔE^*) between the original saw-plane surface and each of the other cleaned surface finishes, in SCI and SCE modes. Polished surface values are also reported.

	SCI				SCE			
	$\Delta L^*(D65)$	$\Delta a^*(D65)$	$\Delta b^*(D65)$	$\Delta E^*(D65)$	$\Delta L^*(D65)$	$\Delta a^*(D65)$	$\Delta b^*(D65)$	$\Delta E^*(D65)$
SPG	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
POL	-4.11	2.32	2.83	5.50	-7.18	2.51	3.33	8.30
CLA	-2.75	1.06	1.97	3.54	-2.84	1.06	1.96	3.61
CLB	-2.78	0.46	2.41	3.71	-2.73	0.46	2.41	3.67

Table 4. Roughness values, measured in μm , for the different surfaces (R_a = Mean roughness; R_z = Average distance between the highest peak and lowest valley in each sampling length; R_{max} = Maximum roughness depth).

Type of surface	R_a	R_z	R_{max}
Sawplane	22,1	108,3	160,2
Cleaned (abrasive A)	24,8	125,8	169,9
Cleaned (abrasive B)	27,8	140,6	190,6

Declaration of interests

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

The authors declare the following financial interests/personal relationships which may be considered as potential competing interests:

CRediT author statement

Nicola Careddu: Conceptualization, Methodology, Validation, Resources, Writing - Original Draft, Supervision. **Diego Cadeddu:** Resources, Investigation. **Fabio Sitzia:** Resources, Writing - Review & Editing.