



岐阜大学機関リポジトリ

Gifu University Institutional Repository

Title	OS11(5)-21(OS11W0016) Effect of Ferritic-Austenitic Phase Fraction on Corrosion Fatigue Behavior in Stainless Steels(本文 (Fulltext))
Author(s)	AKITA, Masayuki; NAKAJIMA, Masaki; TOKAJI, Keiro
Citation	[Abstracts of ATEM : International Conference on Advanced Technology in Experimental Mechanics : Asian Conference on Experimental Mechanics] vol.[2003] p.[189]-[189]
Issue Date	2003-09-09
Rights	The Japan Society of Mechanical Engineers (日本機械学会)
Version	出版社版 (publisher version) postprint
URL	http://hdl.handle.net/20.500.12099/25728

この資料の著作権は、各資料の著者・学協会・出版社等に帰属します。

OS11 (5) - 21 (OS11W0016)

Effect of Ferritic-Austenitic Phase Fraction on Corrosion Fatigue Behavior in Stainless Steels

Masayuki Akita, Faculty of Engineering, Gifu Univ., Gifu, Japan

Masaki Nakajima, Dept. of Mechanical Engineering, Toyota National College of Tech., Toyota, Japan

Keiro Tokaji, Dept. of Mechanical and Systems Engineering, Gifu Univ., Gifu, Japan

Although stainless steels are generally used in aggressive environments, the corrosion resistance is different in each stainless steel, which would be affected by microstructure. On the other hand, the initiation and early growth of fatigue cracks are also influenced by microstructure. Based on such a viewpoint, in the present study, fatigue crack initiation and growth behavior of stainless steels with different volume fraction of ferritic (α) -austenitic (γ) phases were studied in 3 %NaCl solution.

Specimens with five different volume fractions of ferritic-austenitic phases, i.e. SUS304 (100 % γ), SUS329J4L (50 % γ , 28 % γ , 12 % γ) and SUS444 (100 % α), were prepared. After heat treatments, specimens were machined. Plate specimens were employed for small cracks (L-direction), which have a shallow notch to restrict the crack initiation site, and CT-Specimens (L-Tdirection) with 8~10 mm thickness were used for long cracks. Fatigue tests were conducted on electro-hydraulic testing machines operating at a frequency of 10~20 Hz in laboratory air and 1~3 Hz in 3% NaCl solution. Stress ratio was -1 for small cracks and 0.05 for long cracks. Crack length was measured using optical traveling microscope and replication technique for long cracks and small cracks, respectively. Crack closure for long cracks was measured by unloading elastic compliance method. Fracture surfaces were examined using a scanning electron microscope (SEM).

Cracks were generated predominantly from slip bands within γ grains for SUS304 and SUS329J4L, and within α grains for SUS444 in both environments. Both fatigue lives and fatigue limits in 3 %NaCl solution slightly decreased in all the materials compared to those in laboratory air. In early crack growth region, the crack growth rates solution were faster in 3 %NaCl than in laboratory air. Environmental effect was also found in high ΔK region for long cracks, where crack growth was enhanced in 3 %NaCl solution. Based on these results, relationships among crack growth rate, acceleration ratio and volume fraction of α/γ phase were discussed.