

## Evaluation of the color stability of different temporary restorative materials

## Avaliação da estabilidade de cor de diferentes materiais restauradores provisórios

DOI:10.34119/bjhrv6n3-168

Recebimento dos originais: 25/04/2023

Aceitação para publicação: 24/05/2023

### **Laura Cristina de Andrade Bubna**

Graduate in Dentistry

Institution: Universidade Estadual de Ponta Grossa

Address: Av General Carlos Cavalcanti, 4748, Ponta Grossa - PR

E-mail: laurabubna1999@gmail.com

### **Adriana Postiglione Buhrer Samra**

PhD in Integrated Practice

Institution: Universidade Estadual de Ponta Grossa

Address: Av General Carlos Cavalcanti, 4748, Ponta Grossa - PR

E-mail: adrianapbsamra@gmail.com

### **Fabiana Madalozzo Coppla**

Post-Doctorate in Dentistry

Institution: Universidade Estadual de Ponta Grossa

Address: Av General Carlos Cavalcanti, 4748, Ponta Grossa - PR

E-mail: fcoppla@hotmail.com

### **Heloisa Forville de Andrade**

Master of Science in Dentistry

Institution: Universidade Estadual de Ponta Grossa

Address: Av General Carlos Cavalcanti, 4748, Ponta Grossa - PR

E-mail: heloisafandrade@hotmail.com

### **Michael Willian Favoreto**

Master of Dentistry

Institution: Universidade Estadual de Ponta Grossa

Address: Av General Carlos Cavalcanti, 4748, Ponta Grossa - PR

E-mail: michaelfavoreto@hotmail.com

### **Lídia Olga Bach Pinheiro**

PhD in Dentistry

Institution: Universidade Estadual de Ponta Grossa

Address: Av General Carlos Cavalcanti, 4748, Ponta Grossa - PR

E-mail: bachpinheiro@hotmail.com

## ABSTRACT

This study aimed to evaluate the color stability of different temporary restorative materials in contact with staining solutions, as well as to verify which one presents the highest resistance to staining. In this laboratory study, five types of temporary restorative materials were evaluated: self-curing acrylic resin, bis-acrylic resin, light-curing acrylic resin, CAD/CAM machinable, and 3D printed resin. Thirty samples of each material were produced in a circular mold measuring 10 mm diameter and 2 mm thickness. The materials were divided into subgroups ( $n=10$ ) and immersed in solutions: Coffee, Coca-cola®, and distilled water (control). Color measurements were carried out at baseline, 1, 7, and 14 days using a digital spectrophotometer and the color parameters were calculated according to the CIEDE00 system. The color change data were subjected to two-way ANOVA (temporary material vs time) and post-hoc Tukey test ( $\alpha = 0.05$ ). The materials showed a color change only comparing baseline vs. one day, according to acceptability standard  $\Delta E_{00} > 1.8$ . Thus, we concluded that there was a difference in color stability already on the first day of immersion. In addition, the coffee solution showed the highest color variation when compared to the other solutions. Clinical applicability: Temporary restorations are widely used in prosthetic treatments and can remain in the mouth for a considerable period. They are responsible for aesthetic and function maintenance along the rehabilitation process. In addition, they provide data for the definitive prosthesis and should assure comfort and confidence to the patient. Thus, it is necessary that these materials are resistant and present such color stability that does not compromise the aesthetics during the treatment phase.

**Keywords:** temporary dental restoration, color, prosthesis coloring.

## RESUMO

O estudo teve como objetivo avaliar a estabilidade de cor de diferentes materiais restauradores provisórios em contato com soluções pigmentantes e verificar qual apresenta maior resistência ao manchamento. Neste estudo laboratorial, foram testados 5 tipos de materiais provisórios: resina acrílica autopolimerizável, resina bisacrílica, resina acrílica fotopolimerizável, blocos de resina acrílica usinados por CAD/CAM e resina impressa em 3D. Trinta corpos de prova de cada material foram produzidos em uma matriz circular com 10 mm de diâmetro e 2 mm de espessura. Os materiais foram divididos em subgrupos ( $n=10$ ) e imersos nas soluções: Café, Coca-cola® e água destilada (controle). As medições foram feitas no baseline, 1, 7 e 14 dias com um espectrofotômetro digital e os parâmetros de cor foram calculados de acordo com o sistema CIEDE<sub>00</sub>. Os dados de mudança de cor ( $\Delta E_{00}$ ) foram submetidos a ANOVA two-way (material temporário vs tempo) e teste post-hoc de Tukey ( $\alpha = 0,05$ ). Os materiais apresentaram mudança de cor apenas comparando os dados de baseline vs. primeiro dia de imersão, de acordo com os limites de aceitabilidade  $\Delta E_{00} > 1,8$ . Concluiu-se que houve diferença na estabilidade de cor já no primeiro dia de imersão. Além disso, a solução de café apresentou a maior variação de cor em relação às demais soluções. Aplicabilidade clínica: As restaurações temporárias são amplamente utilizadas em tratamentos protéticos e podem permanecer na boca por um período considerável. As restaurações provisórias são responsáveis pela manutenção da estética e função durante o processo de reabilitação. Além disso, provem dados para a confecção das próteses definitivas e devem assegurar conforto e confiança ao paciente. Assim, é necessário que esses materiais sejam resistentes e apresentem uma estabilidade de cor que não comprometa a estética durante a fase de tratamento.

**Palavras-chave:** restauração dentária provisória, cor, coloração de próteses.

## 1 INTRODUCTION

Temporary restorations are used in prosthesis treatments to reach pulp protection, marginal integrity, aesthetics, health, comfort, and mainly to restore the masticatory function over a period of time. [1] In addition, they are of great importance for diagnostic evaluation, planning of final restorations and insertion of the definitive prosthesis. [1,2] The material life span in the mouth is variable and can be extend beyond the time expected, it is also relevant to consider adequate biomechanics and aesthetic aspects. [2] Another factor to be considered is the stability of the material in the buccal environment.

These materials are exposed to an environment where various chemical substances, food and dying solutions pass through and may undergo changes in their characteristics. [3] Residual polymers can absorb liquids that enter the oral cavity and tend to change their color over time, and this can influence patients' satisfaction with the treatment.[2] The intensity of color change is affected by endogenous factors including initiator systems, polymerization, matrix composition, particle size, hardness, water sorption, hydrolysis, oxidation of unreacted carbon double bonds and surface roughness, and the intensity of color change usually depends on the staining substances and the material involved.[3]

Many temporary dental materials are available, from materials with easy-to-handle techniques to digital computer-aided materials. All of those have different characteristics and indications, as well as production costs. [1,4] They are widely used in dental routine and although there are several studies that cover the issue of color stability of temporary restorations over time, the results are still contradictory. [5] The results of color change can be measured by visual scales, being a subjective measurement, or by colorimetric instruments, such as the digital spectrophotometer, which ensures greater accuracy and clarity in the analysis. However, we have not found studies reporting the use of such equipment.

The temporary material chosen needs to present aesthetic quality and should approximate every shape and color of natural teeth, being fundamental to ensure patients' satisfaction.[3] Thus, the objective of this study was to evaluate the color stability of acrylic resin, bis-acrylic, light-curing acrylic resin, and CAD/CAM when in contact with staining solutions. We also aimed to determine which resin demonstrates the highest stain resistance. The null hypothesis of the study was the non-pigmentation of the sample.

## 2 MATERIALS AND METHODS

### 2.1 TEMPORARY MATERIALS

Five types of temporary materials (Table 1) were evaluated. For each temporary material analyzed, a total of 30 specimens were manufactured. The acrylic, bis-acrylic and light-curing acrylic resin samples were manufactured according to the manufacturers' information using a stainless circular metal mold measuring 10 mm diameter and 2 mm thickness. Polymerization was performed according to the manufacturers' recommendations.

Two glass plates were placed over the steel mold to promote the removal of excess material and ensure a parallel surface to facilitate the reading of the samples. The specimens of the EVOLUX resin (Evolux, Curitiba, Brazil) were milled in a Ceramill Motion 2 (Amann Girrbach, Curitiba, Brazil) milling machine using the Ceramill Mind software, and those of the Cosmos TEMP resin (Yllor, Pelotas, Brazil) were printed on the FlashForge Hunter 3D Printer (FlashForge, São Paulo, Brazil).

After the samples were prepared, they were manually polished using silicon carbide abrasive discs (3M ESPE, St. Paul, MN, USA), in descending order of grains # 320, # 600, # 800, and #1200. Polishing was performed for 30 seconds on each abrasive paper, under water cooling. The samples were washed for 30 seconds between each sandpaper to remove possible residues present on the surface.

All specimens were immersed in distilled water at 37 °C for 24 hours before baseline color measurement. This measurement was taken after washing and drying the specimens and performed on a white background with a digital spectrophotometer (VITA Easyshade Advance 4.0 Model DEASYAS4). After that, the specimens were placed in their respective staining solutions.

### 2.2 STAINING SOLUTIONS

The specimens were randomized and immersed in three different solutions (three subgroups n=10): distilled water (Cinoad Sudeste, Serrana, Brazil); cola soft drink (Coca-cola®, São Paulo, Brazil); and coffee (Pilão Tradicional, São Paulo, Brazil) - 90g powder to 1 liter of water. The solutions were replaced after each measurement.

### 2.3 COLOR CHANGE ASSESSMENT

The color assessment was carried out at baseline, and after 1, 7 and 14 days of immersion using a digital spectrophotometer (VITA Easyshade Advance 4.0 Model DEASYAS4). Before the measurements, the specimens were manually cleaned with a P-40 soft bristle brush (ORAL-

B) for 30 seconds followed by washing in water to remove sediment remaining from immersion solutions. The color change ( $\Delta E$ ) calculations were performed using the CIEDE<sub>00</sub> System, established by the “Commission Internationale de l’Eclairage” (International Illumination Commission) CIE,  $\Delta E_{00} = [(\Delta L/kLSL)^2 + (\Delta C/kCSC)^2 + (\Delta H/kHSH)^2 + RT(\Delta C*\Delta H/SC*SH)]^{1/2}$ . [7] Color changes were considered significant when the differences at baseline and the period of evaluation present  $\Delta E_{00} > 1.8$ . [8]

## 2.4 STATISTICAL ANALYSIS

Data were analyzed using the Kolmogorov-Smirnov test to assess the normality and the Barlett test for equality of variance (data not shown). As the data showed normality, the color change data in ( $\Delta E_{00}$ ) in each solution were subjected to two-way ANOVA (temporary material vs time) and Tukey' post-hoc test to compare different materials and different times. Statistical significance was fixed at ( $\alpha = 0.05$ ).

## 3 RESULTS

Table 2 presents the data of the temporary materials immersed in distilled water. In these materials, there was no significant difference in the intersection of factors ( $p = 0.61$ ). However, there was a difference between the times alone ( $p = 0.003$ ) and also for the different materials ( $p > 0.0001$ ). Only the materials Light-curing acrylic resin, Acrylic-resin, and 3D Printed resin showed color changes. However, it is important to observe that these changes already happened on the first day (24h) of measurement, being higher than acceptability standard ( $\Delta E_{00} > 1.8$ ). Regarding the other periods, the color was still higher than the acceptability threshold in comparison to the baseline for both of materials, however, without statistically significant difference between the periods (24h, 7 days, and 14 days).

The results of the temporary materials submitted to the Coca-cola® solution did not show significant difference in the intersection of the factors ( $p = 0.99$ ). There was no difference between the times alone ( $p = 0.94$ ), but a difference was observed for different materials ( $p > 0.0001$ ). In addition, all materials showed color changes already occurred on the first day (24h) of measurement, which were higher than the acceptability standard ( $\Delta E_{00} > 1.8$ ) (Table 3). As regards the other periods, the color was still higher than the acceptability threshold when compared to the baseline, however, without statistically significant difference between the periods (24h, 7 days, 14 days).

When the temporary materials were subjected to coffee solution, there was no significant difference in the intersection of the factors ( $p = 0.99$ ). There was no difference

between the times alone ( $p = 0.94$ ), but a difference was observed for the different materials ( $p > 0.0001$ ). All materials showed changes already on the first day (24h) of measurement (Table 4), being also higher than the acceptability standard ( $\Delta E_{00} > 1.8$ ). When considering the other periods, the color was still higher than the acceptability threshold in comparison to the baseline, however, without statistically significant difference between the periods (24h, 7 days, 14 days).

#### 4 DISCUSSION

In dentistry, color is an important aesthetic parameter, being responsible for the harmony of the smile and patients' satisfaction with the treatment.[9,20] Since the oral cavity and temporary restorations are subject to different staining solutions, this study aimed to evaluate the main temporary materials in contact with commonly consumed and used solutions, not only subjectively, but with the use of a spectrophotometer.[1]

There are two thresholds for evaluating color, namely the perceptibility threshold (PT) and the acceptability threshold (AT). These thresholds are tools that can be used as a quality control to guide the selection of dental materials.<sup>8</sup> The acceptability threshold is the most common value used to evaluate color in dentistry, and refers to a broader value describing the acceptability difference of color in a situation according to clinical acceptance, where the standard value is  $\Delta E_{00} > 1.8$ . [10] In this study, we evaluated color change according to acceptability parameters.

Although there are studies in the literature that evaluate the color stability of temporary materials, no studies were found that evaluated all these materials together. [11] The joint evaluation of these materials is important because each one has its different characteristics, advantages and disadvantages concerning material and clinical applicability. Therefore, this is an interesting comparison for providing an overview of another factor in the clinicians' choice. [12] Some studies evaluated different resins, such as Structor (bis-acrylic) in comparison to Revotek (light-cure resin)[13], or in comparison to Dencorlay (acrylic resin)[1], and they had already found differences in color stability. However, no color stability studies were found for CAD/CAM resin or Printed 3D resin (EVOLUX and Cosmos TEMP).

Given the hypothesis of the study, the non-pigmentation of the samples was rejected, since there was variation in the color assessment of the specimens. In this study, the comparison between the liquids showed that the staining solution influenced the color change of the specimens, and it seems relevant to mention that the change occurred already on the first contact between the staining solution and temporary material.

Regarding the color variation of specimens in distilled water, some studies reported that water absorption can be influenced by factors such as unreacted monomers, inclusion of air, and incomplete polymerization. [5,14,15,16] For this reason, it might provoke decrease in the material physical properties, increased microleakage and solubility, and color change. [5,14,15,16] In the distilled water, bis-acrylic and CAD/CAM resins did not reach  $\Delta E_{00} > 1.8$ , while the other materials showed significant color variation. Therefore, they may be more susceptible to changes due to their composition and other interactions.

When analyzing the behavior of resins in Coca Cola, we could conclude that all the resins were influenced by the staining liquid, being more affected on the first day of measurement. The acrylic resin was the less affected among all. Among the materials tested, the one that showed the best color stability in the Coca Cola solution was the acrylic resin, followed by light-cured resin, bis-acrylic resin, 3D Printed, and CAD/CAM.

However, the coffee solution showed higher color variation of the specimens when compared to the Coca Cola solution. Previous studies already showed higher variation in the color of the temporary materials exposed to this solution. [2,4,17] Regarding the coffee solution, the light-cured resin showed the highest resistance to the color change, followed by the milled CAD/CAM. The bis-acrylic and 3D Printed showed the highest vulnerability.

Despite the lower color stability shown by the 3D Printed version, it has advantages over bis-acrylic, such as the elimination of traditional molding steps, reducing possible inaccuracies resulting from contraction, expansion or deformation of the material. In addition, it promotes greater patient comfort and reduced chair time for the dentist. It also has the advantages of low consumption and economical use of the material. [18,19] Besides that, even though acrylic resin, light-cured and CAD/CAM showed less color change in different staining solutions, they present less favorable characteristics for the agility of the clinical procedure.

This study demonstrated that both staining solutions interfere with the staining of the resins since the first day of contact, decreasing the intensity from the second day onwards to the end of the study, but still clinically significant and visible. Because of these characteristics, it is very important to consider the function and application of the material in the clinical routine, and properly analyze the characteristics of the materials and their advantages and disadvantages to achieve a successful treatment.

## **5 CONCLUSIONS**

Within the limitations of this study, we concluded that there was a difference in the color stability of the materials, but some remained within the acceptability limit. In addition, the coffee solution showed the highest color variation when compared to the other solutions.

## **ACKNOWLEDGMENTS**

The authors are grateful for the content contributions provided by Lidia Olga Bach Pinheiro for developing the idea, Laura Cristina de Andrade Bubna and Michael Willian Favoreto for the practical development of the research. We are also thankful to Adriana Postiglione Buhner Samra, Fabiana Madalozzo Coppla, Heloisa Forville de Andrade, Lidia Olga Bach Pinheiro, Michael Willian Favoreto for their critical review of the manuscript and the support during the development and writing of this manuscript. The authors would like to acknowledge D'One 3D (Ribeirão Preto, SP, Brazil) for the manufacture and donation of 3D printed resin specimens and COD-UEPG for milling of CAD/CAM milled resin specimens.



## REFERENCES

1. Mazaro JVQ, Minari LM, Zavanellin AC, Mello CC, Lemos CAA. Avaliação da estabilidade de cor de diferentes materiais restauradores provisórios. *Rev Odontol UNESP*. 2015 Sept-Oct; 44(5): 262-267. Doi: 10.1590/1807-2577.0017
2. Maciel LC, et al. Avaliação da Alteração de Cor das Resinas Acrílica e Bisacrílica Após Imersão em Diferentes Soluções. *J Health Sci* 2020; 22(1):2-6. Doi: 10.17921/2447-8938.2020v22n1p2-6
3. Costa IAF, Lima EMCX. Effect of Colorant Solutions on the Color Stability of Provisional Prosthetic Materials. *Braz. J. Oral Sci.* 2018 jun; 17:e18153 Doi: 10.20396/bjos.v17i0.8652654
4. Peñate L, Mercade M, Arregui M, Roig M, Basilio J, Cedño R. Color Stability of CAD/CAM Interim Material for Long-Term Fixed Dental Prostheses vs. Conventional Materials after Immersion in Different Staining Solutions. *J. Compos. Sci.* 2021; 5:106. Doi: 10.3390/jcs5040106
5. Mann NS, Jhamb A, Bajaj S, Rahuk A. Color Stability in Temporization. *Dent. J. Adv. Stud.* 2010; 08(01):05-08. Doi: 10.1055/s-0040-1708076
6. Lee, Y. Powers, M. Comparison of CIE Lab, CIEDE 2000, and DIN 99 Color Differences Between Various Shades of Resin Composites. *Int J Prosthodont* 2005; 18:150–155. Doi:
7. Luo MR, Cui G, Rigg BJCR. The development of the CIE 2000 colour-difference formula: CIEDE2000. 2001; 26:340-350.
8. Paravina RD, et al. Color Difference Thresholds in Dentistry. *Wiley Periodicals, J Esthet Restor Dent.* 2015; 27(1):1-9. Doi: 10.1111/jerd.12149
9. Pavicic DK et al. A Cross-Sectional Study of the Influence of Tooth Color Elements on Satisfaction with Smile Esthetics. *Int J Prosthodont.* 2017; 30(2):156-159. Doi: 10.11607/ijp.5070
10. Paravina RD, Pérez MM, Ghinea R. Acceptability and perceptibility thresholds in dentistry: A comprehensive review of clinical and research applications. *J Esthet Restor Dent.* 2019; 31:103–112. Doi: 10.1111/jerd.12465
11. KUL, Esra et al. Evaluation of the color stability of temporary materials produced with CAD/CAM. *Dent. Med. Probl.* 2021; 58(2):187-191, Doi: 10.17219/dmp/126745
12. Sari, T., Usumez, A., Strasser, T., Şahinbas, A., & Rosentritt, M. (2020). Temporary materials: comparison of in vivo and in vitro performance. *Clin. oral invest.* 24: 4061-4068.
13. Rutkunas V, Sabaliauskas V. Effects of different repolishing techniques on colour change of provisional prosthetic materials. *Stomatologija.* 2009; 11:105-112.
14. Oysaed H, Ruyter IE. Sorção de água e características de preenchimento de compósitos para uso em dentes posteriores. *J Dent Res* 1986; 65:1315-1318.

15. Akashi A, Matsuya Y, Unemori M, Akamine A. A relação entre as características de absorção de água e a resistência mecânica de cimentos de ionômero de vidro modificados por resina em armazenamento de água a longo prazo. *Biomat* 1999; 20:1573-1578.
16. Braden M, Clarke RL. Características de absorção de água de materiais de obturação compósitos microfinos odontológicos. *Biomat*. 1984; 5:369-372.
17. Recio H, León L, Sanchez JCS. Efeito de diferentes tempos de polimento na estabilidade de cor de materiais provisórios: um estudo in vitro. *J. adv. clin. res. insights* 2019; 6:138–1434.
18. Favero R, et al. Precisão da modelagem digital 3D de arcos dentários. *Dental Press J. Orthod*. 2019 Jan-Fev; 24(1). Doi: 10.1590/2177-6709.24.1.38.e1-7.onl
19. Shin JW, et al. Avaliação da estabilidade de cor de materiais de coroa e ponte impressos em 3D contra várias fontes de descoloração: um estudo in vitro. *Materials* 2020; 13:53-59. Doi: 10.3390/ma13235359
20. Rocha CKF, Teixeira PR, Breda PLCL. Importância da estética do sorriso na autoestima. Importance of smile aesthetics in self-esteem. *Brazilian Journal of Health Review*. 2021; 4:25867-25876. Doi 10.34119/bjhrv4n6-182

## LISTA DE TABELAS

Table 1. Temporary materials used.

PRODUCT	MATERIAL	COMPOSITION
Dencôr Lay (Clássico/ São Paulo – SP, Brazil)	Self-curing acrylic resin	Copolymer, methyl ethyl
STRUCTUR 2 SC (Voco/ Cuxhaven, Germany)	Bis-acrylic resin	Methacrylate, peroxide, pigment
REVOTEK™ LC (GC Dental Products, Aichi, Japan)	Light-curing acrylic resin	Urethane Dimethacrylate
Cosmos TEMP (Yllor, Pelotas, Brazil)	3D printed resin	Oligomers, monomers, photoinitiators, stabilizer, pigment.
EVOLUX (Evolux, Curitiba, Brazil)	CAD/CAM machinable blocks	PMMA and biocompatible components

Table 2. Means  $\pm$  standard deviations of different temporary materials submitted to distilled water at times of 1, 7, and 14 days in CIEDE units ( $\Delta E_{00}$ ).

Material	Time		
	Baseline vs. 1 day	Baseline vs. 7 days	Baseline vs. 14 days
Light-curing acrylic resin	2.6 $\pm$ 1.6 Ad	3.0 $\pm$ 1.4 ABd	3.8 $\pm$ 1.2 Bd
Bis-acrylic resin	1.2 $\pm$ 0.6 Ab	1.2 $\pm$ 0.5 ABb	1.5 $\pm$ 0.5 Bb
Acrylic resin	1.9 $\pm$ 0.5 Ac	2.3 $\pm$ 0.6 ABc	2.3 $\pm$ 0.9 Bc
3D Printed resin	2.2 $\pm$ 0.9 Acd	2.9 $\pm$ 1.2 ABcd	3.1 $\pm$ 1.1 Bcd
CAD/CAM machinable resin	0.5 $\pm$ 0.3 Aa	0.4 $\pm$ 0.2 ABa	0.7 $\pm$ 0.4 Ba

Two-way ANOVA  $p = 0.61$ . Same small letters in the same individual column indicate no significant difference ( $P > 0.05$ ).

Same capital letters within individual rows indicate no significant difference ( $P > 0.05$ ).

Table 3. Means ± standard deviations of different temporary materials subjected to Coca-Cola® at times of 1, 7, and 14 days in CIEDE units ( $\Delta E_{00}$ ).

Material	Time		
	Baseline vs. 1 day	Baseline vs. 7 days	Baseline vs. 14 days
Light-curing acrylic resin	3.8 ± 1.2 Aab	3.9 ± 1.1 Aab	3.9 ± 1.2 Aab
Bis-acrylic resin	4.2 ± 1.5 Abc	4.1 ± 0.9 Abc	4.2 ± 1.0 Abc
Acrylic resin	2.9 ± 0.7 Aa	2.7 ± 0.9 Aa	2.5 ± 1.0 Aa
3D Printed resin	4.3 ± 0.6 Abc	4.5 ± 1.1 Abc	4.7 ± 0.7 Abc
CAD/CAM machinable resin	4.8 ± 2.0 Ac	5.1 ± 3.1 Ac	5.2 ± 2.9 Ac

Two-way ANOVA  $p = 0.99$ . Same small letters in the same individual column indicate no significant difference ( $P > 0.05$ ).

Same capital letters within individual rows indicate no significant difference ( $P > 0.05$ ).

Table 4. Means ± standard deviations of different temporary materials subjected to coffee at times of 1, 7, and 14 days in CIEDE units ( $\Delta E_{00}$ ).

Material	Time		
	Baseline vs. 1 day	Baseline vs. 7 days	Baseline vs. 14 days
Light-curing acrylic resin	5.0 ± 1.7 Aa	5.2 ± 1.7 ABa	5.1 ± 1.4 Ba
Bis-acrylic resin	14.9 ± 4.0 Ac	14.8 ± 4.2 ABc	15.9 ± 3.8 Bc
Acrylic resin	6.4 ± 1.9 Aa	6.6 ± 2.5 ABa	7.5 ± 2.3 Ba
3D Printed resin	7.8 ± 2.0 Ab	8.7 ± 2.8 ABb	12.7 ± 3.3 Bb
CAD/CAM machinable resin	6.0 ± 3.9 Aa	6.1 ± 4.2 ABa	6.5 ± 4.4 Ba

Two way-ANOVA (materials vs time)  $p = 0.37$ , time  $p = 0.033$  material  $p > 0.0001$ . Same small letters in the same

individual column indicate no significant difference ( $P > 0.05$ ). Same capital letters within individual rows indicate

no significant difference ( $P > 0.05$ ).