The Serbian Ceramic Society Vinča Institute of Nuclear Sciences, University of Belgrade Institute for Multidisciplinary Research, University of Belgrade Institute of Physics, University of Belgrade

PROGRAM AND THE BOOK OF ABSTRACTS

1st Conference of the Serbian Ceramic Society March 17-18. 2011. Belgrade, Serbia 1CSCS-2011

> Edited by: Snežana Bošković Zorica Branković Jasmina Grbović Novaković

Publisher:

The Serbian Ceramic Society Vinča Institute of Nuclear Sciences, University of Belgrade Institute for Multidisciplinary Research, University of Belgrade Institute of Physics, University of Belgrade

For Publisher: Snežana Bošković Jovan Nedeljković Sonja Veljović-Jovanović Aleksandar Belić

Editors: Snežana Bošković Zorica Branković Jasmina Grbović Novaković

Technical editor: Nikola Novaković

Design: Nikola Novaković

ISBN: 978-86-7306-107-8

Print: "ALTA NOVA" Printing Comp.: 120 copies Copyright © 2011 by The Serbian Ceramic Society and others contributors. All rights reserved. No part of this publication may be reproduced, in any form or by any means, without permission in writing from the publisher.

Društvo za Keramičke Materijale Srbije Institut za nuklearne nauke Vinča, Univerzitet u Beogradu Institut za multidisciplinarna istraživanja, Univerzitet u Beogradu Institut za fiziku, Univerzitet u Beogradu

PROGRAM I KNJIGA APSTRAKATA Prva konferecija Društva za Keramičke Materijale Srbije 17-18. Mart 2011, Beograd, Srbija 1CSCS2011

Urednici: Snežana Bošković Zorica Branković Jasmina Grbović Novaković

Gd_{9.33}(SiO₄)₆O₂ OXYAPATITE SYNTHESIZED BY SOL-GEL COMBUSTION METHOD

<u>Slavica Zec</u>, Svetlana Ilić, Marija Stojmenović, Dušan Bučevac, Branko Matović, Snežana Bošković

Department of material science, INN Vinča, Serbia

Investigations of Ln-silicates with the apatite type of structure have shown high oxide-ion conductivity and therefore can be used as new solid electrolytes. In this study synthesis of $Gd_{9.33}(SiO_4)_6O_2$ oxyapatite was performed from ethanol-water solution of gadolinium nitrate, tetraethyl orthosilicate (TEOS) and glycine by sol-gel combustion method. X-ray diffraction (XRD) analyses confirmed that the nanocrystalline structure of $Gd_{9.33}(SiO_4)_6O_2$ was formed during combustion reaction at the molar ratio glycine:nitrate ion=0.4. Produced $Gd_{9.33}(SiO_4)_6O_2$ powder was calcined at 600 °C, then uniaxialy pressed and sintered at 1550 °C for 4 h. Relative density of sintered material was 83%.

SYNTHESIS AND CHARACTERIZATION OF ANODIC SUBSTRATES FOR IT-SOFCs BASED ON PROTON CONDUCTORS

Milan Zunic¹, Aleksandar Radojkovic¹, Zorica Brankovic¹, Goran Brankovic¹

¹Institute for Multidisciplinary Research, Belgrade, Serbia

Cermet anode substrates based on high temperature proton conductors Ni-BaCe $_{0.9}Y_{0.1}O_{3.5}$ (Ni-BCY10) were prepared using wet chemical method. The microstructural properties of sintered pellets were investigated using X-ray diffraction analysis and field emission scanning electron microscopy. Impedance spectroscopy measurements were used for evaluation of electrical properties of the anode pellets. The high conductivity values of reduced anodes confirmed the percolation through Ni particles even for anode with reduced amount of nickel. Fuel cell tests were carried out and fuel cells with the cermet anode showed higher power output comparing to the fuel cells with platinum electrode.