

# Chemistry & Chemical Technology

*Editor-in-Chief*  
*Michael Bratychak*



Lviv Polytechnic  
National University

EFFICIENCY STUDY OF NEEM SEEDS-BASED  
NANOBIOPESTICIDES*Elika Joeniarti<sup>1</sup>, Achmadi Susilo<sup>1</sup>, Noer Rahmi Ardiarin<sup>2</sup>,  
Nindayu Indrasari<sup>3</sup>, Mochamad Zakki Fahmi<sup>3,\*</sup>*<https://doi.org/10.23939/chcht13.02.240>

**Abstract.** An innovative nanosized natural pesticide based on neem seeds was developed. The resulting nanobiopesticide (NBP) was synthesised by entangling neem seed extract on chitosan cross-linked with succinic anhydride *via* ultrasonic treatment following purification. Fourier-transform infrared (FTIR), ultraviolet-visible (UV-Vis) and dynamic light scattering (DLS) spectrophotometers were used to characterise the resulting NBP, and its stability was observed against changes in pH, temperature and UV radiation.

**Keywords:** nanobiopesticide, neem seed extract, chitosan, succinic anhydride.

## 1. Introduction

In Indonesia, the agriculture sector plays an important role in the overall national economy, and it is the sector that contributes the most to the labour force. According to the Statistical Bureau, in 2013 the agricultural sector hired up to 40 million people from a workforce of 114 million [1]. Crop failure is the thing most feared by farmers, and it is usually caused by pests that attack crops. The use of synthetic pesticides is regarded as the best solution for overcoming this problem, although, in reality, it has many negative impacts on the environment and the animals who reside in and around agricultural land. An alternative solution is the use of natural pesticides or biopesticides, such as neem seeds, even though some modification is needed to improve the performance and quality of these types of pesticides. Nanoencapsulation is a new, attractive technology that has been extensively developed; it covers active pesticides with a polymer coating to produce nanosized particles.

The most widely used polymer layer is chitosan. Chitosan is a biodegradable [2], bio-adhesive material [3]. Under specific conditions [4], it forms a gel and it will expand the polymer solubility and control the release of active substances, which cover most of the pores [5, 6].

The development of nanotechnology has benefited a wide range of sectors, including health [7, 8], electronics [9], sustainable energy [10], the environment [11], and many others. In the agriculture sector, nanotechnology has had a significant impact in terms of enhancing the agricultural process [12]. The present study focused on developing a nanoencapsulated extract of neem seeds with chitosan modified (cross-linked) by succinic anhydride using ultrasonication. The resulting nanobiopesticide (NBP) was determined to be an improvement over synthetic pesticides by studying its stability against various pH and temperature ranges, and under UV radiation along with the controlled release study of the active ingredient. The resulting product was characterised using Fourier-transform infrared (FTIR), ultraviolet-visible (UV-Vis) and dynamic light scattering (DLS) spectrophotometers to determine the success of the generating process. The efficiency of the encapsulation process was accessed by investigating the toxicity of the prepared NBP against *Spodoptera litura* (*S. litura*).

## 2. Experimental

### 2.1. Synthesis of Chitosan Modified with Succinic Anhydride

About two grams of chitosan is dissolved in 40 ml of 10% acetic acid and 160 ml of methanol. On the other part, about one gram of succinic anhydride is dissolved in 30 ml of acetone. Both solutions are subsequently mixed simultaneously and then stirred for 24 h until a gel is formed, following with deionized water (DI) addition as much as 200 ml when the mixture has successfully formed the gel. The next process is the conditioning mixture at pH 10 with the addition of NaOH dropwise. The next

<sup>1</sup> Agrotechnology Study Program, Faculty of Agriculture, Wijaya Kusuma University, Surabaya 60225, Indonesia

<sup>2</sup> Department of Agronomy, Faculty of Agriculture, University of Brawijaya, Malang 65145, Indonesia

<sup>3</sup> Department of Chemistry, Faculty of Science and Technology, Universitas Airlangga, Mulyorejo-Surabaya 60115, Indonesia

\* [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)

© Joeniarti E., Susilo A., Ardiarin N., Indrasari N., Fahmi M., 2019

process is dialysis of resulted crosslinked chitosan using 50 kDa MWCO membrane for 24 h agitation.

## 2.2. Synthesis of NBP

The study followed the encapsulation process used by Fahmi *et al.* [13], with some modifications, to meet the desired goals. Experimentally, about 10 ml of chitosan modified with succinic anhydride were mixed with 0.5 ml of neem seed extract dissolved in *n*-hexane. Mixing these two solutions produced two phases. The mixture was then ultrasonicated for 2 min with a power of 5 % (25 Hz) at room temperature to obtain a homogeneous solution and to let the neem seed extract be encapsulated with the chitosan modified with succinic anhydride. During the ultrasonication process, the encapsulated extract that was successfully covered by chitosan will move to the water phase. The results obtained from the water phase were further analysed using 50 kDa molecular weight cut-off (MWCO) membrane in DI water, and stirred for 24 h. The resulting mixture was called NBP.

## 2.3. Rearing Armyworms in a Laboratory

Larvae of *S. litura* were collected from a brassica field in Batu, East Java. Then, the larvae were reared in plastic jars with brassica leaves as feed. The hatch eggs developed into stage 1 larvae, stage 2 larvae, *etc.* At stage 3, the larvae were used in an insecticidal bioassay.

## 2.4. Neem Seed Extraction

The neem seeds were initially oven-dried at 333 K until a constant weight was obtained; then they were finely grounded. Ethanol was added to the powder and the mixture was stirred for 2 days until it became uniform. It was then subjected to filtration. The obtained solid mass was washed with chloroform, which was then evaporated. The resulting powder was the neem seed extract.

## 2.5. Encapsulation of the Neem Seed Extract

The neem seed extract was dissolved in hexane and the chitosan was dissolved in acetic acid solution. After these two solutions were mixed, the neem seed extract was inserted into the interspace of the chitosan nanoparticle through ultrasonic wave for 2 min to homogenise the mixture. The wave treatment produces cavitation (hexane-in-water) bubbles in the medium via a series of compression and relaxation waves. The high dimension of the crosslink-chitosan results in the encapsulation of small molecules, even when present in a difference phase. The sample was cured for 24 h and then centrifuged (6000 rpm, 20 min) to separate the water

phase containing the neem seed extract. This step was followed by dialysis using a dialysis membrane (MWCO 50 kDa, 24 h).

## 2.6. Repellent Activity Test of the Nanoencapsulated Neem seed extract towards Armyworms (*S. litura*)

The larvae that were of the same age as a result of the rearing were used to conduct the repellent activity test. Complete randomized design (CRD) was used for the treatment of nanoencapsulated neem seed extract at various concentrations: 0 % (using only aquadist), 10 %, 20 % and 30 % (v/v). Each treatment was repeated six times for total of 24 treatments. The experiment was conducted in the laboratory using plastic jars that were covered with gauze. In every treatment unit, 20 tested larvae were infested in the jars and *Brassica chinensis* var. *parachinensis* leaves were used as a feed. The observed parameter is the percentage of tested larvae that stayed away from the feed due to the nanoencapsulated neem seed extract treatment. After the treatment was applied, the samples were observed for seven days. The repellent activity percentage (% RA) was adjusted using the following equation:

$$\% RA = \frac{LF}{LT} \cdot 100 \%$$

where LF refers to the number of larvae which stay away from feed and LT refers to the total number of tested larvae.

## 2.7. Data Analysis

The collected data were statistically analysed by using ANOVA (Analysis of Variance). Comparison of treatment means was performed using LSD (Least Significant Difference) test at  $p < 0.05$  probability level.

## 2.8. Characterizations

Zetasizer ZS 90 (Malvern, USA) was used to perform the size distribution and zeta potential value of resulted NBP. The concentration of neem seed extract adjusted by calibration curve based on light adsorption measured by UV spectrophotometer UV-1800 (Shimadzu, Japan). The standard solution of neem seed extract was initially a concentrated blackish brown diluted one in ethanol at a concentration of  $6 \cdot 10^2$ ;  $8 \cdot 10^2$ ;  $10 \cdot 10^2$ ;  $12 \cdot 10^2$  and  $14 \cdot 10^2$  M. The maximum wavelength of NBP can be observed by UV-Vis spectrophotometer, where a maximum wavelength of neem seed extract is around 276 nm. The maximum wavelength that has been obtained can be used to find the concentration of the standard solution through the absorbance value. Vibration spectra of a sample are performed using FTIR spectroscopy (Shimadzu, Japan).

### 3. Results and Discussion

#### 3.1. Crosslinking and Nanoencapsulation Process

The present study used the nanoencapsulation process found in [13], by modifying some parts in order to meet the desired objectives. The process of inserting the neem seed extract into the chitosan modified with succinic anhydride was done under the ultrasonic wave [14]. This wave breaks the particles into smaller sizes; it also accelerates the presence of a bubble-shaped bubble. This results in an *n*-hexane bubble containing the neem seed extract in water containing chlorine modified with succinic anhydride because the *n*-hexane contains fewer neem seed extracts than the water containing chitosan modified with succinic anhydride. The bubbles form an emulsion from the non-mixing phase. The ability of harmonic waves to suppress and attract bubbles causes the *n*-hexane bubbles in water to shrink so the wave cannot be harmonized. In this condition, there is only the neem seed extract surrounded by chitosan modified with succinic anhydride so that the neem seed extract is trapped in the anhydride-modified chitosan and driven into the water phase. Encapsulation of the neem seed extract is still at random sizes, so further treatment is needed using a membrane dialysis of MWCO 50 kDa. The 50 kDa MWCO value means that the membrane can withstand a molecule weighing 50000 Da at least 90 % or more [15]. The Zetasizer Nano ZS (Malvern Instruments) was used to determine whether the results are within the nanosize characterisation. This instrument utilises a DLS. The DLS

results showed that the particle size was 271.6 nm. Thus, it can be concluded that the encapsulation process of the neem seed extract was successfully performed.

#### 3.2. The Stability of NBP

The stability of NBP was first observed against various pH ranges because pH is one of the important parameters of the product. This pH stability analysis was performed by adjusting the pH range from 3 to 12 (by adding HCl or NaOH solutions). The photographs (Fig. 1) show that the post-pH treatment changes were only slight, and almost no changes on its appearance and its UV absorbance at pH 3 and pH 4. Moreover, most of the changes occurred in the form of turbidity at higher pH value.

From the results of this study, it can be concluded that the nanoencapsulation product of neem seed extract can be stable at a pH range of 5–12. The results reveal that the proposed NBP will maintain its stability in the natural environment or soil that is slightly acidic to neutral (pH 5.0–7.5).

The stability of the proposed NBP under various temperatures was also assessed. The results (Fig. 2) of the nanoencapsulation neem seed extracts with a temperature treatment show that the colour or the turbidity of the extracts did not change (based on each UV maximum absorbance). It can be concluded that nanoencapsulation neem seed extracts with chitosan modified with succinic anhydride can survive in an environment with temperatures ranging from 303 to 333 K. These data prove that the NBP meets the requirements for agricultural application (average temperature 308–323K).



**Fig. 1.** Photos of NBP under various pH ranges (from pH 3 to pH 12). The UV absorbance maximum of each sample is showed in the lower series



**Fig. 2.** Photos of NBP under various temperatures: at room temperature (a), 303 K (b), 313 K(c), 323 K(d) and 333 K (e). The UV absorbance maximum of each sample is showed in the lower series



**Fig. 3.** Photos of NBP after UV exposure for different times (h):1 (a), 2 (b), 3 (c), 6 (d) and 12 (e). The UV absorbance maximum of each sample is showed in the upper series

Next, the stability of the proposed NBP was further assessed using UV radiation (Fig. 3). Qualitative and quantitative methods were used to analyse the stability of the nanoencapsulation neem seed extract with chitosan modified with succinic anhydride against UV radiation. The qualitatively visually observed changes are shown in Fig. 3 As seen, the NBP is stable against UV radiation because its turbidity or colour did not change. The same result was also found for the nanoencapsulation of neem seed extract without modification.

Quantitative methods are needed because qualitative testing does not give specific results. Adjusted NPB concentrations were based on the conversion results of their absorbance to calibration curve, whereas in this study, showed regression equation is  $y = 0.93x - 0.0372$  with a correlation or  $R^2$  value of 0.9951. Absorbance values obtained by irradiating a long time will be used to determine degradation reaction rate constants of the first order. It has been widely reported that most of the degradation of organic compounds has always followed the first order reaction [16].

If the absorbance and concentration values are known then we can find the  $k$  value or the rate of chemical reaction kinetics. Kinetics of chemical reactions can be expressed in an equation called the rate law that can be determined from the experimental data [17]. Value of kinetics rate commonly symbolized by " $k$ " can be obtained from the slope between the axis ( $x$ ) and the ordinate ( $y$ ) which is the value of the duration of the radiation and the value of  $\ln[A]$  where the value of  $A$  is the sum of concentrations after radiation. Regression values resulting from the three test materials are shown in Table 1.

The greater the value of the kinetics rate, the faster the substance will degrade. From the above data, the fastest sequence of degradation rates is the neem seed extract > nanoencapsulation of neem seed extracts without modification > nanoencapsulation of neem seed extracts with modification. Thus, neem seed extract without modifiers is less effective when used as a natural pesticide because it is easily degraded by sunlight. The similar statement is supported by a previous report, where one of the shortcomings of natural pesticides using neem seed extract is the nature that is not resistant to sunlight [18, 19].

Table 1

**Degradation rate of the samples after exposure with UV light**


Sample	Regression value	Kinetics rate, m/s
Neem seed extracts	$y = -0.021x + 0.749$	0.021
Nanoencapsulation of neem seed extracts without modification	$y = -0.013x - 0.207$	0.013
Nanoencapsulation of neem seed extracts with modification	$y = -0.008x - 0.282$	0.008

### 3.3. Release of Active Ingredients from Nanoencapsulation Neem Seed Extracts with Chitosan Modified Succinic Anhydride

The release of the NBP content was evaluated by measuring the absorbance obtained from neem seed extract released from encapsulation and successfully passing the dialysis membrane MWCO 50 kDa. The concentration of neem seed extract released at any given time can be calculated through the equation as follows [8]:

$$C_t' = C_t + \frac{u}{V} \sum_0^{i-t} C_t$$

where  $C_t'$  and  $C_t$  are the actual and apparent concentrations of neem seed extract at time  $t$ , respectively;  $u$  is the volume of the aliquots taken, ml;  $V$  is the total volume of the buffer, ml.



**Fig. 4.** Release pattern of the neem seed extract from NBP for various pH

The concentration of the extract is determined by UV adsorption of the extract comparing with a calibration curve of standard. The releases of active ingredient from nanoencapsulation neem seed extract was treated at varied values, namely at pH 4, 7 and 10.


Based on the release observations (Fig. 4), it can be seen that the maximum active substance released from NBP occurred at pH 7, followed by pH 10 and then pH 4. It is assumed that at pH 7 (neutral) the molecule is formed in the neutral charge so the interaction of the van der Waals force between the COOH group and NH<sub>2</sub> is weak. The weak bond increases the absorption power of the water so the index expands and causes the active substance in the nanoencapsulation to be more easily released or disengaged. In an alkaline medium (pH 10), ionization of carboxylic groups (–COOH) into a carboxylate ion (–COO<sup>–</sup>) occurs. This ion site has a stronger attraction to any potential electropositive group, including amino groups (NH<sub>2</sub>), that exist on chitosan, resulting in a stronger van der Waals bond between them. This attractive force affects the release of the nanoencapsulation neem seed extract from chitosan modified with succinic anhydride. The stronger bond results in a denser nanoencapsulate, so it is difficult to release the active substances that are inside. However, with an acid medium (pH 4), the amount of dissolved chitosan with soluble succinic anhydride is relatively decreased. This is because the acidic pH range is an isoelectric point of succinic anhydride-modified chitosan, which results in the balance of NH<sub>3</sub><sup>+</sup> and COO<sup>–</sup> in the molecule [20]. This condition makes it more difficult to release the active substance in the nanoscale formation due to the ion balance in the molecule. Thus, it can be concluded that NBP has a maximum discharge occurring at pH 7 (neutral). This also corresponds to the good pH criteria required for crops when released into an agricultural environment.

### 3.4. Characterization of NBP

FTIR was used to find out whether a chitosan was successfully modified with succinic anhydride. The result of several FTIR tests is shown in Fig. 5, with a description of the [i] line showing the extract of the neem seeds. The [ii] line is chitosan. The [iii] line indicates a modified chitosan and [iv] line indicates the nanoencapsulation neem seed extracts with chitosan modified with succinic anhydride.

Strong band of chitosan is observed at wavelength of 3600–3335 cm<sup>–1</sup> referring to OH and NH functional groups. The CH stretching band appears on chitosan at 2852.81 cm<sup>–1</sup> and shifts to 2920.32 cm<sup>–1</sup> after the modification. Functional groups of NH primer of chitosan are clearly observed at 1639 cm<sup>–1</sup>, which is slightly shifted

to 1641.48 cm<sup>–1</sup> on the modified chitosan (Fig. 5a). Ester and ether functional groups formed *via* the modification process of chitosan are shown at 1151.54 cm<sup>–1</sup> (Fig. 5b). When comparing several peaks above, it can be concluded that chitosan was successfully modified with succinic anhydride. Successful encapsulation process of neem seed extract is proved by existing NH band of chitosan on NBP at 1558.48 cm<sup>–1</sup> (Fig. 5c) and the existence of neem seed extract band on NBP is also confirmed by the shift of C=O aliphatic esters band from 1710.92 cm<sup>–1</sup> to 1633.71 cm<sup>–1</sup> (Fig. 5d).



**Fig. 5.** FTIR pattern of neem seed extract [i], chitosan [ii], cross-linked chitosan [iii] and NBP [iv]

The characterization on using UV-Vis spectrophotometer was further done to know that the neem seed extract was successfully encapsulated by chitosan. The maximum absorbance value of neem seed extract is 276 nm, where similar one on NBP – 275 nm. Thus, it strongly reveals that neem seed extract is successfully encapsulated in the product because the maximum wavelength is almost the same.

*Table 2*

#### Size distribution and zeta potential of sample

Sample	Size, nm	Zetta potential, mV
Neem seed extract	320	35.6
Chitosan modified succinic anhydride	319	0.02
NBP before dialysis	518.8	–
NBP after dialysis	271.6	20.3

Characterization using the DLS further aims to measure the size of the particles formed and its zeta potential (Table 2). The size of neem seed extract of

320 nm and chitosan modified with succinic anhydride of 317.9 nm then showed that the extract of neem seeds was successfully encapsulated by increasing the size of 518.8 nm in the product prior to dialysis. After dialysis, the size becomes 271.6 nm. Both of these proved that the neem seed extract was successfully encapsulated in the chitosan modified with succinic anhydride and also successfully made in nanosize. Zeta potential is the parameter of electrical charge between colloidal particles. The higher zeta potential values the better is preventing the occurrence of flocculation. The potential zeta value indicates that the resulting product is relatively stable and flocculated with a relatively long time. In addition, the

potential zeta value of NBP is 20.3 mV, where there are zeta potentials of neem seed extract (35.6 mV) and succinic anhydride modified chitosan (0.02 mV). This founding also reveal the successful encapsulation process of neem seed extract.

Assessment of NBP toxicity against *Spodoptera litura* is presented in Table 3. The data showed that neem seed was quite efficient on pressing *S. litura* living. Compared with untreated leaf, mortality amount of *S. litura* significantly increases (up to 82 %). Moreover compared with bare neem seed extract, the encapsulation process enhances ability of neem seed to be an excellent pesticide, where mortality can efficiently kill *S. litura*.

Table 3

Mortality investigation of *S. litura* after treated with specific samples

Concentration of neem seed extract to total NBP, w/w	Mortality		
	Number	Percentage dead <i>S. Litura</i> from the total	Average
Control	120	0.00	0.00
Bare neem seed extract	98	81.67	16.33
0.1	117	97.50	19.50
0.2	119	99.20	19.83
0.3	120	100.0	20.00

#### 4. Conclusions

The effort to produce nanobiopesticides from neem seed extract with chitosan modified succinic anhydride can be done through the process of encapsulation with ultrasonication. NBP performs excellent stability at pH 5–12, temperature of 303–333 K and exposure to UV radiation for 12 h. Treating the leaf with NBP can increase mortality of NBF perfectly. This founding can initiate further development of agricultural aspect based on nanotechnology.

#### Acknowledgments

Authors thank the Ministry of Research, Technology and Higher Education for research funding program on scheme PUPT funding and Universitas Airlangga for facilities support.

#### References

- [1] Badan Pusat Statistik, Berita Resmi Statistik 2013.
- [2] Singh B., Kaur T., Kaur S. *et al.*: Pestic. Biochem. Phys., 2016, **131**, 46. <https://doi.org/10.1016/j.pestbp.2016.01.004>
- [3] Mathiowitz E., Chickering III D., Lehr C.-M.: Bioadhesive Drug Delivery Systems: Fundamentals, Novel Approaches, and Development. CRC Press 1999. <https://doi.org/10.1201/b14099>
- [4] Chenite A., Chaput C., Wang D. *et al.*: Biomater., 2000, **21**, 2155. [https://doi.org/10.1016/S0142-9612\(00\)00116-2](https://doi.org/10.1016/S0142-9612(00)00116-2)
- [5] Mello K., Bernusso L., Pitombo R., Polakiewicz B.: Braz. Arch. Biol. Techn., 2006, **49**, 665. <https://doi.org/10.1590/S1516-89132006000500017>

- [6] Chang R., Yang J., Ge S. *et al.*: Food Hydrocolloid., 2017, **67**, 14. <https://doi.org/10.1016/j.foodhyd.2016.12.023>
- [7] Fahmi M., Chen J.-K., Huang C.-C. *et al.*: J. Mater. Chem. B, 2015, **3**, 5532. <https://doi.org/10.1039/C5TB00289C>
- [8] Fahmi M., Chang J.-Y.: RSC Adv., 2014, **4**, 56713. <https://doi.org/10.1039/C4RA11582A>
- [9] Dou Q., Rengaramchandran A., Selvan S. *et al.*: Sci. Report., 2015, **5**, 8252. <https://doi.org/10.1038/srep08252>
- [10] Zhao Y., Burda C.: Energ. Environ. Sci., 2012, **5**, 5564. <https://doi.org/10.1039/C1EE02734D>
- [11] Permana A., Haris A., Setyawati H., Fahmi M.: J. Chem. Technol. Metallurg., 2017, **52**, 1101.
- [12] Servin A., White J.: NanoImpact, 2016, **1**, 9. <https://doi.org/10.1016/j.impact.2015.12.002>
- [13] Fahmi M., Ou K.-L., Chen J.-K. *et al.*: RSC Adv., 2014, **4**, 32762. <https://doi.org/10.1039/C4RA05785F>
- [14] Bousbia-Salah M., Redjati A., Fezari M., Bettayeb M.: ICSPC 2007. IEEE Int. Conf., 2007, 1003. <https://doi.org/10.1109/ICSPC.2007.4728491>
- [15] Mulder J.: Basic Principles of Membrane Technology. Springer Science & Business Media 2012.
- [16] Modestov A., Glezer V., Marjasin I., Lev O.: J. Phys. Chem. B, 1997, **101**, 4623. <https://doi.org/10.1021/jp970132n>
- [17] Atkins P., de Paula J.: Elements of Physical Chemistry. Oxford University Press, Oxford 2013.
- [18] Sandahl M., Mathiasson L., Jönsson J.: J. Chromatogr. A, 2000, **893**, 123. [https://doi.org/10.1016/S0021-9673\(00\)00697-X](https://doi.org/10.1016/S0021-9673(00)00697-X)
- [19] Smital T., Luckenbach T., Sauerborn R. *et al.*: Mutat. Res.-Fund. Mol. M, 2004, **552**, 101. <https://doi.org/10.1016/j.mrfmmm.2004.06.006>
- [20] Yan C., Chen D., Gu J. *et al.*: Yakugaku zasshi, 2006, **126**, 789. <https://doi.org/10.1248/yakushi.126.789>

Received: November 10, 2017 / Revised: May 12, 2018 / Accepted: June 27, 2018



**ЕФЕКТИВНІСТЬ НАНОБІОПЕСТИЦИДІВ  
НА ОСНОВІ НАСІННЯ НІМУ ПРОТИ  
*SPODOPTERA LITURA***

**Анотація.** Розроблено нанорозмірний інноваційний натуральний пестицид на основі насіння німу. Новий нанобіопестицид (НБП) синтезовано нанесенням екстракту насіння німу на хітозан, зшитий янтарним ангідридом, в результаті

оброблення ультразвуком з подальшим очищенням. З використанням Фур'є-спектроскопії, УФ-спектроскопії та динамічного світлорозсіювання визначено основні характеристики НБП. Встановлено залежність стабільності НБП від зміни рН, температури і ультрафіолетового випромінювання.


**Ключові слова:** нанобіопестицид, екстракт насіння німу, хітозан, янтарний ангідрид.



## Editorial Board

1. Prof. Michael Bratychak, D.Sc., Lviv Polytechnic National University – Editor-in-Chief, Ukraine
2. Prof. Volodymyr Starchevskyy, D.Sc., Lviv Polytechnic National University – Deputy Editor-in-Chief, Ukraine
3. Dr. Olena Shyshchak, Lviv Polytechnic National University – Executive Secretary, Ukraine
4. Prof. Zoryan Pikh, D.Sc., Lviv Polytechnic National University, Ukraine
5. Prof. Stanislav Voronov, D.Sc., Lviv Polytechnic National University, Ukraine
6. Prof. Volodymyr Skorokhoda, D.Sc., Lviv Polytechnic National University, Ukraine
7. Prof. Myroslav Malyovanyy, D.Sc., Lviv Polytechnic National University, Ukraine
8. Prof. Vira Lubenets, D.Sc., Lviv Polytechnic National University, Ukraine
9. Prof. Iosyp Yatchyshyn, D.Sc., Lviv Polytechnic National University, Ukraine
10. Prof. Roman Gladyshevskii, D.Sc., Ivan Franko National University of Lviv, Ukraine
11. Prof. Borys Zimenkovsky, D.Sc., Danylo Halytsky Lviv National Medical University, Ukraine
12. Prof. Anatolii Starovoit, D.Sc., Ukrainian Scientific-Industrial Association Ukrkoks, Dnipro, Ukraine
13. Prof. Witold Brostow, D.Sc., University of North Texas, Doctor Honoris Causa of Lviv Polytechnic National University, USA
14. Prof. Victor Castano, D.Sc., National Autonomous University of Mexico, Mexico
15. Prof. Elizabete Lucas, D.Sc., Federal University of Rio de Janeiro, Brazil
16. Prof. Maria Waclawek, D.Sc., University of Opole, Poland
17. Prof. Oleh Suberlyak, D.Sc., Lviv Polytechnic National University, Ukraine
18. Prof. Cemil Ibis, D.Sc., Istanbul University, Turkey
19. Prof. Omari Mukbaniani, D.Sc., Ivane Javakhishvili Tbilisi State University, Georgia
20. Prof. Radomir Jasinski, D.Sc., Cracow University of Technology, Poland
21. Dr.Sc. Maryna Stasevych, Lviv Polytechnic National University, Ukraine

## Chemistry and Chemical Technology

COUNTRY	SUBJECT AREA AND CATEGORY	PUBLISHER	H-INDEX
<a href="#">Ukraine</a>  Universities and research institutions in Ukraine	<a href="#">Chemical Engineering</a> Chemical Engineering (miscellaneous)  <a href="#">Chemistry</a> Chemistry (miscellaneous)	Lviv Polytechnic National University	<b>11</b>
PUBLICATION TYPE	ISSN	COVERAGE	INFORMATION
Journals	19964196	2012-2020	<a href="#">Homepage</a> <a href="#">How to publish in this journal</a> <a href="mailto:mbratych@polynet.lviv.ua">mbratych@polynet.lviv.ua</a>

### SCOPE

The journal is currently accepting articles in such field as analytical, general, inorganic, organic and physical chemistry; chemical kinetics and catalysis; biotechnology; chemistry of high molecular compounds; materials science and engineering; technology of inorganic substances and organic synthesis products; chemical technology of processing of combustible minerals; ecology of chemical processes. We are publishing results of scientific works carried out by the leading universities and institutes of Europe, America and Asia.

 Join the conversation about this journal

 Quartiles

FIND SIMILAR JOURNALS 

1 Arabian Journal of Chemistry

2 Asian Journal of Chemistry

3 Chemical Papers

4

5 Revue Roumaine de Chimie

SAU

**38%**  
similarity

IND

**36%**  
similarity

CHE

**36%**  
similarity


Journal of the Chemical  
PAK

**36%**  
similarity

ROU


**35%**  
similarity

SJR




Total Cites

Self-Cites




Citations per document




External Cites per Doc

Cites per Doc




% International Collaboration





Citable documents

Non-citable documents



Cited documents

Uncited documents



Show this widget in your own website

Just copy the code below and paste within your html code:

```
<a href="https://www.scimagojr.com" style="float: right; font-size: 0.8em; color: #ccc; text-decoration: none;">

```

Metrics based on Scopus® data as of April 2020

T **Tamar kanchaveli** 3 months ago

Please, tell me how much it costs to publish an article in your journal. Probably written about it, but I could not find this information. Thank you.

Best regards

Tamar kanchaveli

reply



**Melanie Ortiz** 3 months ago

Dear Tamar,  
thank you for contacting us.

We are sorry to tell you that SClmago Journal & Country Rank is not a journal. SJR is a portal with scientometric indicators of journals indexed in Elsevier/Scopus. Unfortunately, we cannot help you with your request, we suggest you visit the journal's homepage or contact the journal's editorial staff, so they could inform you more deeply.  
Best Regards, SClmago Team

SCImago Team

D **Dauren Baiseitov** 6 months ago

Hello, Dear Sir or Madam

I have a question: is this journal open access or not? There is no orange sign in this site, but in Scopus some articles in this journal are shown by open access

reply



**Melanie Ortiz** 6 months ago

SCImago Team

Dear Dauren,  
thank you for contacting us.  
Unfortunately, we cannot help you with your request, we suggest you visit the journal's homepage or contact the journal's editorial staff, so they could inform you more deeply.  
Best Regards, SCImago Team

**K** **Kwenzekile Bhengu** 6 months ago

Hi please help me, I had a Bachelor of Science- Chemical and Chemistry Technology, I looking for internship/ learnership

reply



**Melanie Ortiz** 6 months ago

SCImago Team

Dear Kwenzekile,  
Thank you for contacting us. Could you please expand a little bit on your comment?  
Best Regards, SCImago Team

**M** **Muhabbat Honkeldieva** 1 year ago

I am Muhabbat Honkeldieva and I work at the Institute of Bioorganic Chemistry of Uzbek Academy of Sciences. I am research worker in the field bioorganic and physical chemistry. I want to publish an article in your journal called "Chemistry and Chemical technology". So, how I can get instruction of guideline for authors.

Can you send me all instruction of journal.

The best regards  
Muhabbat Honkeldieva  
PhD of Chemistry  
Institute of Bioorganic Chemistry  
Uzbek Academy of Sciences

reply



**Melanie Ortiz** 1 year ago

SCImago Team

Dear Muhabbat,  
thank you for contacting us.  
We are sorry to tell you that SCImago Journal & Country Rank is not a journal. SJR is a portal with scientometric indicators of journals indexed in Elsevier/Scopus.  
Unfortunately, we cannot help you with your request, we suggest you to visit the journal's homepage (See submission/author guidelines) or contact the journal's editorial staff, so they could inform you more deeply.  
Best Regards, SCImago Team

**N** **Nanik AR** 2 years ago

Warm regards

How to register in Journal Chemistry and Chemical Technology?

Thank you

Best regards  
Nanik AR

reply



**Elena Corera** 2 years ago

SCImago Team

Please, contact Chemistry and Chemical Technology, you are contacting Scimago Journal and Country Rank.

Best,

SCImago Team

#### Leave a comment

Name

Email

(will not be published)

I'm not a robot

reCAPTCHA  
Privacy - Terms

Submit

The users of Scimago Journal & Country Rank have the possibility to dialogue through comments linked to a specific journal. The purpose is to have a forum in which general doubts about the processes of publication in the journal, experiences and other issues derived from the publication of papers are resolved. For topics on particular articles, maintain the dialogue through the usual channels with your editor.

Developed by:



Powered by:



Follow us on @ScimagoJR

Scimago Lab, Copyright 2007-2020. Data Source: Scopus®

EST MODUS IN REBUS

Horatio (Satire 1.1.106)



# Source details

## Chemistry and Chemical Technology

Scopus coverage years: from 2012 to 2022

Publisher: Lviv Polytechnic National University

ISSN: 1996-4196

Subject area: Chemistry: General Chemistry Chemical Engineering: General Chemical Engineering

Source type: Journal

[View all documents >](#)[Set document alert](#)[Save to source list](#)

CiteScore 2021

**1.5**

SJR 2021

**0.304**

SNIP 2021

**0.667**[CiteScore](#) [CiteScore rank & trend](#) [Scopus content coverage](#)

### i Improved CiteScore methodology



CiteScore 2021 counts the citations received in 2018-2021 to articles, reviews, conference papers, book chapters and data papers published in 2018-2021, and divides this by the number of publications published in 2018-2021. [Learn more >](#)

CiteScore 2021

$$1.5 = \frac{443 \text{ Citations 2018 - 2021}}{293 \text{ Documents 2018 - 2021}}$$

Calculated on 05 May, 2022

CiteScoreTracker 2022

$$1.6 = \frac{466 \text{ Citations to date}}{286 \text{ Documents to date}}$$

Last updated on 05 April, 2023 • Updated monthly

## CiteScore rank 2021

Category	Rank	Percentile
Chemistry		
General Chemistry	#265/409	35th
Chemical Engineering		
General Chemical Engineering	#184/280	34th

[View CiteScore methodology >](#) [CiteScore FAQ >](#) [Add CiteScore to your site](#)

---

## About Scopus

[What is Scopus](#)

[Content coverage](#)

[Scopus blog](#)

[Scopus API](#)

[Privacy matters](#)

## Language

[日本語版を表示する](#)

[查看简体中文版本](#)

[查看繁體中文版本](#)

[Просмотр версии на русском языке](#)

## Customer Service

[Help](#)

[Tutorials](#)

[Contact us](#)

---

## ELSEVIER

[Terms and conditions](#) ↗ [Privacy policy](#) ↗

Copyright © Elsevier B.V. ↗. All rights reserved. Scopus® is a registered trademark of Elsevier B.V.

We use cookies to help provide and enhance our service and tailor content. By continuing, you agree to the use of cookies ↗.





---

## doi number for your articles in Ch&ChT (V.13, No.2)

2 messages

---

**Olena Shyshchak** <oshyshchak@gmail.com> Sat, May 11, 2019 at 1:39 PM

To: fatma oğuz erdoğan <foerdogan@gmail.com>, Farzaneh Mohamadpour <mohamadpour.f.7@gmail.com>, Svit Lana <sval\_kov@ukr.net>, Анна Еремина <annerem2012@gmail.com>, Prabal Pratap Singh <prabal.singh@gla.ac.in>, Ирина Цихановская <cikhanovskaja@gmail.com>, Jimsher Aneli <jimaneli@yahoo.com>, Waed Rasmi Alahmad <w.alahmad@uoh.edu.sa>, Kasim Al-Musawi <kasimhello@gmail.com>, vahab ghalandari <ghalandari.v@gmail.com>, Юра Демчук <yuriy\_demchuk@ukr.net>, Марія Швед <mari4ka.ved@ukr.net>, Myroslav Malovanyy <myroslav.mal@gmail.com>, "j. Zelenko" <j.v.zelenko@gmail.com>, Nita Aryanti <nita.aryanti@gmail.com>, sarafi@uk.ac.ir, imir aliyev <aliyevimir@rambler.ru>, Mochamad Zakki <m.zakki.fahmi@fst.unair.ac.id>, zelenskii.ukhin@gmail.com, Вікторія Воробйова <vorobyovavika1988@gmail.com>, Ирина Курмакова <i.kurmakova@gmail.com>, Jalal Nasser Jeber <jalalanalyticalchemistry@scbaghdad.edu.iq>

Dear authors,

Here you can see doi numbers assigned for your articles in the journal Chemistry&Chemical Technology (V.13, No.2, 2019)

Best regards,

Olena Shyshchak

Executive secretary



Вірусів немає. [www.avast.com](http://www.avast.com)



**-Dodatok\_02\_2019\_DOI.docx**

19K

---

**Mochamad Zakki Fahmi** <m.zakki.fahmi@fst.unair.ac.id>

Sun, May 12, 2019 at 10:07 AM

To: Olena Shyshchak <oshyshchak@gmail.com>

Thank you very much

[Quoted text hidden]

--

Best Regards,

-----  
Mochamad Zakki Fahmi, Ph.D (張家其)

Assistant Professor, Departement of Chemistry

Airlangga University

Phone : +62-838-32901697

Email : [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)

---

## proofs fromCh&ChT

3 messages

---

**Olena Shyshchak** <oshyshchak@gmail.com>  
To: Mochamad Zakki <m.zakki.fahmi@fst.unair.ac.id>

Wed, Apr 17, 2019 at 6:53 PM

Dear authors,

See in attach proofs of your article and send me your corrections **in 5 days**. Please, pay attention to the symbols, especially in equations or reactions because they may be changed during paper was formed by the publishing house. After the mentioned term no changes will be possible.

Best regards,

Olena Shyshchak

Executive secretary

journal Ch&ChT

P.S. You already may use pages for citation of your publication. I will inform you additionally the doi number of the article after its assignment



Вірусів немає. [www.avast.com](http://www.avast.com)

---

**Joeniarti.pdf**  
248K

---

**Mochamad Zakki Fahmi** <m.zakki.fahmi@fst.unair.ac.id>  
To: Olena Shyshchak <oshyshchak@gmail.com>

Thu, Apr 18, 2019 at 12:43 PM

Thank you for your previous email. Please find the attached file for revised manuscript. All the change is marked with the red block. and the figures attached to fix the red number that error on the pdf file. Thank you

**Best Regards,**

-----  
**Mochamad Zakki Fahmi, Ph.D (張家其)**  
**Assistant Professor, Departement of Chemistry**  
**Universitas Airlangga**  
**Phone : +62-838-32901697**  
**Email : [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)**




[Quoted text hidden]


---

**4 attachments**


**Fig 1.jpg**  
13K



**Fig 3.jpg**  
10K



**Fig 2.jpg**  
13K

 **Joeniarti-103-edit (revised).doc**  
1730K

---

**Olena Shyshchak** <[oshyshchak@gmail.com](mailto:oshyshchak@gmail.com)>  
To: Mochamad Zakki Fahmi <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>

Thu, Apr 18, 2019 at 1:16 PM

Thank you, all corrections will be done  
Regards,  
Olena

чт, 18 квіт. 2019 о 08:43 Mochamad Zakki Fahmi <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)> пише:  
[Quoted text hidden]

---

## your article in Ch&ChT

9 messages

---

**Olena Shyshchak** <oshyshchak@gmail.com>  
To: Mochamad Zakki <m.zakki.fahmi@fst.unair.ac.id>

Fri, Jun 29, 2018 at 1:18 PM

Dear authors,

I am preparing now your article for the final acceptance and need some corrections. All my questions or incomprehensible places I marked with yellow or green (see attach). Please correct them in the same file and send me back also marked with the color.

Best regards,  
Olena Shyshchak  
Executive secretary  
journal Chemistry & Chemical Technology

---

 **Joeniarti-103-edit.doc**  
1111K

---

**Mochamad Zakki Fahmi** <m.zakki.fahmi@fst.unair.ac.id>  
To: Olena Shyshchak <oshyshchak@gmail.com>

Tue, Jul 3, 2018 at 3:51 PM

Dear Editor,  
Please find the attached file for my revised manuscript, also highlighted file. Thank You

**Best Regards,**  
-----


**Mochamad Zakki Fahmi, Ph.D (張家其)**  
**Assistant Professor, Departement of Chemistry**  
**Universitas Airlangga**  
**Phone : +62-838-32901697**  
**Email : [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)**



[Quoted text hidden]

---

### 2 attachments

 **Joeniarti-103-edit (revised).doc**  
1707K

 **Joeniarti-103-edit (highlighted).doc**  
2262K

---

**Mochamad Zakki Fahmi** <m.zakki.fahmi@fst.unair.ac.id>  
To: Olena Shyshchak <oshyshchak@gmail.com>

Tue, Jul 3, 2018 at 3:51 PM

Dear Editor,  
Please find the attached file for my revised manuscript, also highlighted file. Thank You

Best Regards,

-----  
Mochamad Zakki Fahmi, Ph.D (張家其)  
Assistant Professor, Departement of Chemistry  
Universitas Airlangga  
Phone : +62-838-32901697  
Email : [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)




2018-06-29 13:18 GMT+07:00 Olena Shyshchak <[oshyshchak@gmail.com](mailto:oshyshchak@gmail.com)>:

[Quoted text hidden]

---

**2 attachments**

 **Joeniarti-103-edit (revised).doc**  
1707K

 **Joeniarti-103-edit (highlighted).doc**  
2262K

---

**Olena Shyshchak** <[oshyshchak@gmail.com](mailto:oshyshchak@gmail.com)>  
To: Mochamad Zakki Fahmi <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>

Mon, Jul 9, 2018 at 5:47 PM

Thank you

[Quoted text hidden]

---

**Mochamad Zakki Fahmi** <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>  
To: elika joeniarti <[elika\\_joe@yahoo.co.id](mailto:elika_joe@yahoo.co.id)>

Fri, Aug 24, 2018 at 7:53 PM

[Quoted text hidden]

--

Best Regards,

-----  
Mochamad Zakki Fahmi, Ph.D (張家其)  
Assistant Professor, Departement of Chemistry  
Airlangga University  
Phone : +62-838-32901697  
Email : [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)

---

 **Joeniarti-103-edit.doc**  
1111K

---

**Olena Shyshchak** <[oshyshchak@gmail.com](mailto:oshyshchak@gmail.com)>  
To: Mochamad Zakki <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>

Mon, Aug 27, 2018 at 6:11 PM

Everything is ok now, thanks

вт, 3 лип. 2018 о 11:51 Mochamad Zakki Fahmi <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)> пише:

[Quoted text hidden]

---

**Mochamad Zakki Fahmi** <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>  
To: Olena Shyshchak <[oshyshchak@gmail.com](mailto:oshyshchak@gmail.com)>

Mon, Nov 5, 2018 at 8:41 AM

Dear Editor,

Is there an update process for our manuscript entitle "EFFICIENCY STUDY OF NEEM SEEDS-BASED NANOBIOPESTICIDES"? Thank you

Best Regards,


-----  
Mochamad Zakki Fahmi, Ph.D (張家其)  
Assistant Professor, Departement of Chemistry  
Universitas Airlangga  
Phone : +62-838-32901697  
Email : [m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)



[Quoted text hidden]

---

**2 attachments**

 **Joeniarti-103-edit (revised).doc**  
1707K

 **Joeniarti-103-edit (highlighted).doc**  
2262K

---

**Olena Shyshchak** <[oshyshchak@gmail.com](mailto:oshyshchak@gmail.com)>  
To: Mochamad Zakki <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>

Wed, Nov 7, 2018 at 6:54 PM

Dear Sir,  
The article is ok and it is in turn to be published.

Regards,  
Olena Shyshchak

пн, 5 лист. 2018 о 03:41 Mochamad Zakki Fahmi <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)> пише:  
[Quoted text hidden]

---

**Mochamad Zakki Fahmi** <[m.zakki.fahmi@fst.unair.ac.id](mailto:m.zakki.fahmi@fst.unair.ac.id)>  
To: elika joeniarti <[elika\\_joe@yahoo.co.id](mailto:elika_joe@yahoo.co.id)>

Thu, Nov 8, 2018 at 8:37 AM

assalamu'alaikum bu elika berikut saya forwardkan email dr jurnal yang meninfokan  
jurnal tersebut akan diterbitkan. maturnuwun  
[Quoted text hidden]