

Aalborg Universitet

Two distinct structural domains for sub-Tg relaxation in glass fibers

Zhang, Yanfei; Yue, Yuanzheng

Published in:

International Glass Fiber Symposia 2012: Proceedings of the first International Symposium on Glass Fiber

Publication date: 2012

Document Version Accepted author manuscript, peer reviewed version

Link to publication from Aalborg University

Citation for published version (APA):

Zhang, Y., & Yue, Y. (2012). Two distinct structural domains for sub-Tg relaxation in glass fibers. In *International Glass Fiber Symposia 2012: Proceedings of the first International Symposium on Glass Fiber* (pp. 38). Institut für Textiltechnik of RWTH Aachen University. http://www.ita.rwth-aachen.de/glassconf/

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- ? You may not further distribute the material or use it for any profit-making activity or commercial gain ? You may freely distribute the URL identifying the publication in the public portal ?

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Two distinct structural domains for sub- $T_{\rm g}$ relaxation in glass fibers

Yanfei Zhang^{1,2} and Yuanzheng Yue^{1,2}

¹Section of Chemistry, Aalborg University, Aalborg DK-9000, Denmark ²Key Laboratory of Processing and Testing Technology of Glass & Functional Ceramics of Shandong Province, Shandong Polytechnic University, Jinan 250353, China

Structural heterogeneity and its impact on structural relaxation during sub- T_g annealing provide a key to better understand the dynamic slowing down near the glass transition temperature (T_g). In this work we present our findings about sub- T_g relaxation of the hyperquenched glass fibers with the composition of 20CaO-22MgO-58SiO₂. This composition is highly unstable, since crystallization occurs slightly above T_g . The calorimetric curves show two separated relaxation peaks below T_g , and this implies that two distinct structural domains which are arrested in the supercooled liquid during hyperquenching. The first relaxation peak is much smaller than the second one. With increasing the annealing degree, the first one is vertically diminishing, while the second one shifts from lower to high temperature and is becoming smaller. This indicates that the two structural domains are correlated with each other. We also provide some insights into the relation between structural relaxation and nucleation.