

Abnormal phase transitions for tetragonal $(1-x)\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3-x\text{PbTiO}_3$ single crystals at low temperature

Xinming Wan^{a)}

The State Key Laboratory of High Performance Ceramics and Superfine Microstructure, Shanghai Institute of Ceramics, Chinese Academy of Sciences, Jiading, Shanghai 201800, China and Department of Applied Physics, The Hong Kong Polytechnic University, Hung Hom, Hong Kong, China

R. K. Zheng, H. L. W. Chan, and C. L. Choy

Department of Applied Physics, The Hong Kong Polytechnic University, Hung Hom, Hong Kong, China

Xiangyong Zhao and Haosu Luo

The State Key Laboratory of High Performance Ceramics and Superfine Microstructure, Shanghai Institute of Ceramics, Chinese Academy of Sciences, Jiading, Shanghai 201800, China

(Received 20 July 2004; accepted 30 August 2004)

Dielectric spectroscopy and ultrasonic sound velocity were investigated for tetragonal PMN- x PT single crystals over a wide range of temperature. In addition to the expected phase transition from the tetragonal ferroelectric phase to the cubic paraelectric phase at a high temperature, an abnormal ferroelectric phase transition below room temperature is observed. The low-temperature phase transition shows a relaxor behavior though tetragonal PMN- x PT single crystal is considered to be typical normal ferroelectrics. By comparing the dielectric constants of poled and depoled conditions and by analyzing $[\text{BO}_6]$ oxygen-octahedra units of perovskite structure, it is suggested that the low-temperature phase transition in poled tetragonal PMN- x PT single crystal could be tetragonal to rhombohedral ferroelectric phase transition. © 2004 American Institute of Physics.

[DOI: 10.1063/1.1808906]

I. INTRODUCTION

The complex perovskite $(1-x)\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3-x\text{PbTiO}_3$ (PMN- x PT) single crystals are well-known ferroelectrics. The solid solutions have a morphotropic phase boundary (MPB) near $x \sim 0.33$ to 0.35 ,¹ dividing the rhombohedral phase and the tetragonal one. For compositions with $x \geq 0.35$, the compounds have a tetragonal structure with symmetry of $P4mm$, for those with $x \leq 0.33$, the crystal symmetry is rhombohedral $R3m$. Normal ferroelectric behavior increases as a function of x , whereas relaxor behavior decreases.² PMN- x PT single crystals have come into prominence in the past few years due to their very high piezoelectric coefficients ($d_{33} > 2500$ pC/N), extremely large piezoelectric strains ($> 1.7\%$), and extrahigh electromechanical coupling factor in the longitudinal bar mode ($k_{33} \sim 94\%$).³⁻⁶ Such excellent properties point to a potential revolution in an electromechanical transduction for a broad range of applications. Recent studies show that the materials with tetragonal structure exhibit excellent optical properties,^{7,8} especially the electro-optic properties.^{9,10} The result shows that tetragonal PMN- x PT single crystals are also promising candidates for optical devices.⁸

Recently, an intensive theoretical and experimental research has been undertaken in order to understand the origin of these enhanced dielectric and piezoelectric properties. Fu and Cohen pointed out that a large piezoelectric response could be driven by a polarization rotation induced by an

external electric field.¹¹ At almost the same time, Noheda *et al.* revealed the existence of a monoclinic phase between the previously established tetragonal (FE_T) and rhombohedral (FE_R) regions in $\text{PbZr}_{0.52}\text{Ti}_{0.48}\text{O}_3$, which further supports the concept of polarization rotation.^{12,13} Subsequently, similar experiments were carried out on PMN- x PT single crystals, and it was found that monoclinic (FE_M) orthorhombic and (FE_O) phases can also be induced in a narrow range of compositions with an appropriate poling history.¹⁴ Based on the dielectric constants obtained on a poled $\langle 001 \rangle$ -oriented PMN-0.3PT single crystal, Viehland *et al.* suggested that the transition from a normal ferroelectric state (macrodomains) to a relaxor state (microdomains) with an increasing temperature is responsible for the secondary transformation near 90°C .¹⁵ For a poled $\langle 001 \rangle$ -oriented PMN-0.33PT single crystal, Lu *et al.* also found an additional ferroelectric phase transition ($\text{FE}-\text{FE}$) at 80°C using dielectric constant measurements. However, they were uncertain whether this phase change corresponds to a FE_O-FE_T or a FE_R-FE_O transition.¹⁶ From the dielectric constant measurements, the secondary phase transition below T_m (the temperature of the permittivity maximum) has been found for PMN- x PT single crystals by many groups.¹⁷⁻²¹ But all the investigations are limited to compositions near the MPB, and there is no report on tetragonal PMN- x PT single crystals.

The aim of this work is to investigate tetragonal PMN- x PT single crystals over a wide range of temperature using dielectric spectroscopy. In addition to a phase transition at T_m , an abnormal ferroelectric phase transition below room temperature is observed in all the main crystallo-

^{a)}Electronic mail: xmwan@citiz.net




FIG. 1. Temperature dependence of dielectric constants of $\langle 110 \rangle$ -oriented PMN-0.38PT single crystal (solid line: 100 Hz; dashed line: 1 kHz; dotted line: 10 kHz).

graphic directions $\langle 001 \rangle$, $\langle 110 \rangle$, and $\langle 111 \rangle$. The phase transition has been supported by an ultrasonic sound velocity measurement.

II. EXPERIMENTAL PROCEDURE

Large-size and high-quality PMN- x PT single crystals were grown directly from melt by the modified Bridgman technique.^{22,23} The crystals were oriented and cut along three main crystallographic directions $\langle 001 \rangle$, $\langle 110 \rangle$, and $\langle 111 \rangle$ by an x-ray diffractometer. Rectangular-shaped specimens ($6 \times 6 \times 1$ mm³) were prepared for property measurements.

Silver paste was painted and sintered at 580 °C for 30 min. Then, the samples were poled with an electric field of 10 kV/cm for 15 min at 160 °C in a silicone oil and then slowly cooled to room temperature with the half of the applied electric field.

In this work, dielectric spectroscopy was measured using a HP4194A impedance analyzer in the temperature range from -180 to 200 °C. The sample was placed inside a liquid-nitrogen bath cryostat (Oxford DN1704-type). The temperature of the sample was stabilized by a digital temperature controller (Oxford ITC 601-type). The longitudinal ultrasonic sound velocity was measured using the AUV-100 Advanced Ultrasonic Workstation with a 10-MHz LiNbO₃ transducer.

III. RESULTS AND DISCUSSION

Figure 1 shows the dielectric constants versus temperature curve of the $\langle 110 \rangle$ -oriented PMN- x PT single crystal. The dielectric constant exhibits a sharp change at 180 °C, so the PT content in the sample is about 0.38, which is deduced from the equation, $T_m = 5x - 10$ (where T_m is the temperature in Celsius scale and x is the PT content).⁷ PMN-0.38PT single crystal is known to possess the tetragonal structure at room temperature and shows a normal ferroelectric behavior. The sharp change corresponds to the phase transition from the tetragonal ferroelectric phase (FE_T) to the cubic paraelectric phase (PE_C), and the dielectric constants exhibit very little frequency dispersion at this range, as shown in the inset of Fig. 1. All the properties agree well with the previous reports.^{24,25}

The most remarkable result of our dielectric measurements is the second dielectric peak at about -120 °C, also




FIG. 2. Temperature dependence of longitudinal ultrasonic sound velocity of $\langle 110 \rangle$ -oriented PMN-0.38PT single crystal.

shown in Fig. 1, which has not been observed for the tetragonal PMN- x PT single crystal so far. Furthermore, as we know, PMN-0.38PT single crystal is considered to be typical normal ferroelectrics, while the dielectric constants near the second peak are frequency-dependent. It shows that this peak possesses relaxor behavior and demonstrates a “micro-to macrodomain” transition, similar to that previously reported PMN- x PT single crystals in the MPB region.¹⁵ After the first heating measurement to 220 °C, the sample was depoled. We also measured the dielectric spectroscopy for the depoled sample and found that the peak near -120 °C disappeared, which indicates that the abnormal dielectric peak only exists in the poled sample. From the theory of polarization rotation,¹¹ the dipoles will rotate along different paths under different poling directions. When the poling was done, the polar direction is expected to incline close to the electric field in each domain, possibly resulting in an increased tetragonal lattice distortion. However, the distortion doesn't result in the structure transformation at room temperature because there is no additional dielectric peak from room temperature to T_m . Decreasing the temperature may result in the collapse of the distortion and induce another phase transition at a low temperature.

The low-temperature phase transition has been supported by ultrasonic measurement. Figure 2 shows the temperature dependence of the longitudinal ultrasonic sound velocity propagated along the $\langle 110 \rangle$ direction for the PMN-0.38PT single crystal. With a decreasing temperature from 27 °C, the sound velocity softens smoothly and reaches a local minimum at about -60 °C, and then follows a slight stiffening with further cooling of the temperature. The broad softening of the sound velocity reflects that the acoustic phonon damps over a wide temperature range. As is known, the compositional fluctuations-induced random electric fields can suppress the development of a long-range ferroelectric order and give rise to order-parameter fluctuations in a wide temperature range.²⁶ The coupling between the elastic strain and the fluctuating order parameters, hence, leads to the smooth softening of the sound velocity in a wide temperature range from 27 to -30 °C. Similar acoustic anomalies have also been observed in PbMg_{1/3}Nb_{2/3}O₃ (PMN)^{27,28} and PbMg_{1/3}Ta_{2/3}O₃ (PMT)²⁹ by the measurements of micro-Brillouin scattering. In contrast to the smooth softening of the sound velocity at high temperatures, the sound velocity




FIG. 3. Pulse-echo patterns at (a) $-58\text{ }^{\circ}\text{C}$, (b) $-83\text{ }^{\circ}\text{C}$, and (c) $-143\text{ }^{\circ}\text{C}$.

shows a drastic softening with a decreasing temperature from -90 to $-120\text{ }^{\circ}\text{C}$, which has not yet been observed in similar PMN and PMT single crystals. Due to the increasing large attenuation with the decreasing temperature, the ultrasonic echo signal disappears completely below $-120\text{ }^{\circ}\text{C}$ (see Fig. 3), which possibly resulted from the scattering of another phase below $-120\text{ }^{\circ}\text{C}$. We note that with an increasing temperature from a low temperature (77 K) to room temperature, the ultrasonic echo signal appears again at about $-120\text{ }^{\circ}\text{C}$, which may correspond to a reverse structural phase transition. The large ultrasonic attenuation below $-120\text{ }^{\circ}\text{C}$ makes it impossible to measure the sound velocity below $-120\text{ }^{\circ}\text{C}$. We want to stress that such a large attenuation, together with a large softening of the sound velocity below $-90\text{ }^{\circ}\text{C}$, strongly implies a structural phase transition associated with the dielectric constants anomaly. Similar large softening of the sound velocity has been observed near the structural phase-transition points in $\text{Ba}_{1-x}\text{Sr}_x\text{TiO}_3$.³⁰

From the dielectric measurements, we observed an abnormal relaxor peak at about $-120\text{ }^{\circ}\text{C}$ for normal ferroelectric PMN-0.38PT single crystal. The peak was confirmed to be corresponding with a phase transition by ultrasonic sound velocity measurement. We know that the lattice distortions and the angles in different phases for the PMN- x PT single crystal differ only slightly, so they are very different to be detected,³¹ especially at such a low temperature. However, it is estimated that the low-temperature phase couldn't be the orthorhombic phase, which has been observed in PMN- x PT single crystals with rhombohedral structure or in the MPB region.¹⁶⁻²⁰ It is generally accepted that for PMN- x PT single crystals, the dielectric constant shows the minimum value




FIG. 4. Schematic diagram of ABO_3 perovskite structure composed of $[\text{BO}_6]$ oxygen octahedra by their vertices (A: Pb^{2+} ; B: Mg^{2+} , Nb^{5+} , or Ti^{4+}).

when the crystals are poled along the spontaneous polarization direction. For example, the dielectric constants at room temperature for tetragonal PMN-0.38PT single crystal are about 780, 6972, and 9784, respectively, for the samples poled along $\langle 001 \rangle$, $\langle 110 \rangle$, and $\langle 111 \rangle$ directions.²⁵ The dielectric constant of the spontaneous polarization direction $\langle 001 \rangle$ shows the minimum value. As shown in Fig. 1, the dielectric constants for the $\langle 110 \rangle$ -poled sample around the low-temperature phase-transition region are much larger than those of the depoled condition. Such evidence may be believed that the $\langle 110 \rangle$ direction is not the polarization direction. That is to say, the phase that appeared near $-120\text{ }^{\circ}\text{C}$ cannot be an orthorhombic phase.

The structure of PMN- x PT single crystals can be regarded as the one made of $[\text{BO}_6]$ ($[\text{TiO}_6]$, $[\text{NbO}_6]$, and $[\text{MgO}_6]$) coordination polyhedra linked by their vertices. Figure 4 shows the schematic diagram of the perovskite structure composed of $[\text{BO}_6]$ oxygen octahedra. Ferroelectric PMN crystals have rhombohedral phase and its T_m is about $-10\text{ }^{\circ}\text{C}$, ferroelectric PT crystals have tetragonal phase and its T_m is about $490\text{ }^{\circ}\text{C}$. It is in favor of the rhombohedral phase by adding PMN in the PMN- x PT solid solutions or decreasing temperature. Therefore, it is reasonable to think that the polarization in $[\text{TiO}_6]$ octahedra appears dominant along the $\langle 001 \rangle$ direction, it's dominant along $\langle 111 \rangle$ in $[\text{NbO}_6]$ or $[\text{MgO}_6]$ octahedra. In tetragonal single crystals, $[\text{NbO}_6]$ and $[\text{MgO}_6]$ octahedra are forced to distort along the $\langle 001 \rangle$ direction in the pressing of $[\text{TiO}_6]$ octahedral. When decreasing temperature or adding PMN, $[\text{NbO}_6]$ and $[\text{MgO}_6]$ octahedra slip the leash of $[\text{TiO}_6]$ octahedra, and simultaneously make $[\text{TiO}_6]$ octahedra distort along $\langle 111 \rangle$, resulting in the $\text{FE}_T\text{-FE}_R$ ferroelectric phase transition. The $\text{FE}_T\text{-FE}_R$ phase transition has been found in the other compositions. For example, the $\text{FE}_T\text{-FE}_R$ phase-transition temperature T_{RT} is about 89, 78, and $66\text{ }^{\circ}\text{C}$, respectively, for PMN-0.256PT, PMN-0.296PT, and PMN-0.324PT.¹⁷ One can draw the conclusion that the T_{RT} decreases with an increasing PT concentration. The T_{RT} of our sample, PMN-0.38PT, is about $-120\text{ }^{\circ}\text{C}$, which is consistent with the trend. Combined with its dielectric properties and ultrasonic sound velocity results, it is assume that the phase below $-120\text{ }^{\circ}\text{C}$ in the poled




FIG. 5. Temperature dependence of dielectric constants of poled (a) $\langle 001 \rangle$ and (b) $\langle 111 \rangle$ -oriented PMN- x PT single crystals (solid line: 100 Hz; dashed line: 1 kHz; dotted line: 10 kHz).

PMN-0.38PT single crystal could be the ferroelectric rhombohedral phase and the peak could be the FE_T - FE_R phase transition.

We note that the similar peaks also appear in the $\langle 001 \rangle$ and $\langle 111 \rangle$ direction of poled tetragonal PMN- x PT single crystals. Figure 5 shows the temperature dependence of dielectric constants of poled $\langle 001 \rangle$ and $\langle 111 \rangle$ -oriented PMN- x PT single crystals. They both have a sharp change and T_m is about 196 °C for the $\langle 001 \rangle$ direction and 199 °C for $\langle 111 \rangle$ one, indicating that the PT content for them is about 0.412 and 0.418, respectively. So they are both in tetragonal phase. As shown in the inset of Fig. 5, they also have an additional frequency-dependent peak at about -145 °C, as observed for the $\langle 110 \rangle$ direction. But they are much “evener” compared with the peak of the $\langle 110 \rangle$ direction. We should also mention here that accurate structure measurements for the low-temperature phases, such as high-resolution powder x-ray diffraction measurements, must be carried out to find out the nature of the phase. The authentic experimental evidences are still under investigation and more details will be discussed in later work.

IV. CONCLUSION

Dielectric spectroscopy and ultrasonic sound velocity were investigated for tetragonal PMN- x PT single crystals over a wide range of temperature. In addition to the expected phase transition from the tetragonal ferroelectric phase to the cubic paraelectric phase at T_m , an abnormal ferroelectric phase transition below room temperature is observed. Furthermore, the low-temperature phase transition shows relaxor behavior though tetragonal PMN- x PT single crystal is re-

garded as typical normal ferroelectrics. By comparing the dielectric constants of the poled and depoled conditions and by analyzing $[\text{BO}_6]$ oxygen-octahedra units of perovskite structure, it is suggested that the low-temperature phase transition in poled tetragonal PMN- x PT single crystal could be tetragonal to rhombohedral ferroelectric phase transition.

ACKNOWLEDGMENTS

One of the authors (R.K.Z.) thanks Professor Xiaoguang Li for his support in the ultrasonic measurements. This work is supported by the National Natural Science Foundation of China (Grant No. 50272075), the High Technology and Development Project of the People’s Republic of China (Grant No. 2002AA325130), Hong Kong Research Grants Council (Grant No. PolyU 5193/00P), and Center for Smart Materials of the Hong Kong Polytechnic University.

- ¹S. W. Choi, J. M. Jung, and A. S. Bhalla, *Ferroelectr., Lett. Sect.* **21**, 27 (1996).
- ²E. V. Colla, N. K. Yushin, and D. Viehland, *J. Appl. Phys.* **83**, 3298 (1998).
- ³R. F. Service, *Science* **275**, 1878 (1997).
- ⁴S.-E. Park and T. R. Shrout, *J. Appl. Phys.* **82**, 1804 (1997).
- ⁵K. Harada, S. Shimanuki, T. Kobayashi, S. Saitoh, and Y. Yamashita, *Key Eng. Mater.* **157**, 95 (1999).
- ⁶G. Xu, H. Luo, P. Wang, H. Xu, and Z. Yin, *Chin. Sci. Bull.* **45**, 491 (2000).
- ⁷X. Wan, H. Luo, J. Wang, H. L. W. Chan, and C. L. Choy, *Solid State Commun.* **129**, 401 (2004).
- ⁸X. Wan, J. Wang, H. L. W. Chan, C. L. Choy, H. Luo, and Z. Yin, *J. Cryst. Growth* **263**, 251 (2004).
- ⁹D.-Y. Jeong, Y. Lu, V. Sharma, Q. Zhang, and H. Luo, *Jpn. J. Appl. Phys., Part 1* **42**, 4387 (2003).
- ¹⁰X. Wan, H. Xu, T. He, D. Lin, and H. Luo, *J. Appl. Phys.* **93**, 4766 (2003).
- ¹¹H. Fu and R. E. Cohen, *Nature (London)* **281**, 403 (2000).
- ¹²B. Noheda, D. E. Cox, G. Shirane, J. A. Gonzalo, L. E. Cross, and S. E. Park, *Appl. Phys. Lett.* **74**, 2059 (1999).
- ¹³B. Noheda, D. E. Cox, G. Shirane, R. Guo, B. Jones, and L. E. Cross, *Phys. Rev. B* **63**, 014103 (1999).
- ¹⁴Z.-G. Ye, B. Noheda, M. Dong, D. E. Cox, and G. Shirane, *Phys. Rev. B* **64**, 184114 (2001).
- ¹⁵D. Viehland, J. Powers, L. E. Cross, and J. F. Li, *Appl. Phys. Lett.* **78**, 3508 (2001).
- ¹⁶Y. Lu, D.-Y. Jeong, Z.-Y. Cheng, Q. Zhang, H. Luo, Z. Yin, and D. Viehland, *Appl. Phys. Lett.* **78**, 3109 (2001).
- ¹⁷M. C. Shin, S. J. Chung, S.-G. Lee, and R. S. Feigelson, *J. Cryst. Growth* **263**, 412 (2004).
- ¹⁸J. P. Han and W. W. Cao, *Phys. Rev. B* **68**, 134102 (2003).
- ¹⁹X. Zhao, J. Wang, H. L. W. Chan, C. L. Choy, and H. Luo, *J. Phys.: Condens. Matter* **15**, 6899 (2003).
- ²⁰Y. Guo, H. Luo, K. Chen, H. Xu, X. Zhang, and Z. Yin, *J. Appl. Phys.* **92**, 6134 (2002).
- ²¹X. Zhao, B. Fang, H. Cao, and H. Luo, *Mater. Sci. Eng., B* **96**, 254 (2002).
- ²²Z. Yin, H. Luo, P. Wang, and G. Xu, *Ferroelectrics* **299**, 207 (1999).
- ²³H. Luo, G. Xu, P. Wang, and Z. Yin, *Ferroelectrics* **231**, 97 (1999).
- ²⁴H. Cao, B. Fang, H. Luo, Y. Sun, and J. Guo, *Ceram. Int.* **29**, 145 (2003).
- ²⁵H. Cao, B. Fang, H. Xu, and H. Luo, *Mater. Res. Bull.* **37**, 2135 (2002).
- ²⁶V. Westphal, W. Kleemann, and M. D. Glinchuk, *Phys. Rev. Lett.* **68**, 847 (1992).
- ²⁷S. G. Lushnikov, J. H. Ko, and S. Kojima, *Appl. Phys. Lett.* **84**, 4798 (2004).
- ²⁸C. S. Tu, V. H. Schmidt, and I. G. Siny, *J. Appl. Phys.* **78**, 5665 (1995).
- ²⁹J. H. Ko, S. Kojima, and S. G. Lushnikov, *Appl. Phys. Lett.* **82**, 4128 (2003).
- ³⁰V. V. Lemanov, E. P. Smirnova, P. P. Syrnikov, and E. A. Tarakanov, *Phys. Rev. B* **54**, 3151 (1996).
- ³¹B. Noheda, D. E. Cox, G. Shirane, J. Gao, and Z.-G. Ye, *Phys. Rev. B* **66**, 054104 (2002).

Journal of Applied Physics is copyrighted by the American Institute of Physics (AIP). Redistribution of journal material is subject to the AIP online journal license and/or AIP copyright. For more information, see <http://ojps.aip.org/japo/japcr/jsp>