

Contents lists available at ScienceDirect

Chinese Journal of Chemical Engineering

journal homepage: www.elsevier.com/locate/CJChE





A concise review on surface and structural modification of porous zeolite scaffold for enhanced hydrogen storage



B.A. Abdulkadir ¹, R.S.R. Mohd Zaki ², A.T. Abd Wahab ², S.N. Miskan ², Anh-Tam Nguyen ³, Dai-Viet N. Vo ³, H.D. Setiabudi ^{1, 2, *}

¹ Centre for Research in Advanced Fluid & Processes, Universiti Malaysia Pahang Al-Sultan Abdullah, Lebuh Persiaran Tun Khalil Yaakob, Gambang, Pahang 26300, Malaysia

² Faculty of Chemical & Process Engineering Technology, Universiti Malaysia Pahang Al-Sultan Abdullah, Lebuh Persiaran Tun Khalil Yaakob, Gambang, Pahang 26300, Malaysia

³ Center of Excellence for Green Energy and Environmental Nanomaterials (CE@GrEEN), Nguyen Tat Thanh University, 300A Nguyen Tat Thanh, District 4, Ho Chi Minh City 755414, Viet Nam

ARTICLE INFO

Article history: Received 23 December 2023 Received in revised form 21 February 2024 Accepted 1 March 2024 Available online 23 March 2024

Keywords: Zeolites Hydrogen storage Surface modification Adsorption Active metal

ABSTRACT

Investigating zeolites as hydrogen storage scaffolds is imperative due to their porous nature and favorable physicochemical properties. Nevertheless, the storage capacity of the unmodified zeolites has been rather unsatisfactory (0.224%–1.082% (mass)) compared to its modified counterpart. Thus, the contemporary focus on enhancing hydrogen storage capacities has led to significant attention towards the utilization of modified zeolites, with studies exploring surface modifications through physical and chemical treatments, as well as the integration of various active metals. The enhanced hydrogen storage properties of zeolites are attributed to the presence of aluminosilicates from alkaline and alkaline-earth metals, resulting in increased storage capacity through interactions with the charge density of these aluminosilicates. Therefore, there is a great demand to critically review their role such as well-defined topology, pore structure, good thermal stability, and tunable hydrophilicity in enhanced hydrogen storage. This article aimed to critically review the recent research findings based on modified zeolite performance for enhanced hydrogen storage. Some of the factors affecting the hydrogen storage capacities of zeolites that can affect the rate of reaction and the stability of the adsorbent, like pressure, structure, and morphology were studied, and examined. Then, future perspectives, recommendations, and directions for modified zeolites were discussed.

© 2024 The Chemical Industry and Engineering Society of China, and Chemical Industry Press Co., Ltd. All rights reserved.

1. Introduction

Recently, research into the search for alternative sources of energy, particularly for the transportation and industrial sectors, has increased tremendously owing to the rapid depletion of fossil fuels, the associated environmental effluence from their combustion, and the recent increase in crude oil prices globally [1,2]. The use of green energy, like solar, and wind has fascinated much consideration due to the rising concerns about the problem of fossil fuels and ecological damage. Unfortunately, the production of these green energies is periodic and has many downsides, including poor power output. Similarly, the energy supply needs to catch up with its demand. As a result, energy storage has emerged as one of the key topics that will improve the use of sustainable energies for high-power, environmentally friendly energy sources in the present and the future [3–5]. Among the available energy storage technologies, hydrogen storage holds great potential for different applications, including vehicles, and other heavy-duty devices. Due to its substantial benefits, including its lightweight, high-burning heat, and relatively minimal environmental pollution, the usage of hydrogen as an energy carrier in an automobile or aviation turbine is a possible field of application [6]. However, a tool for secure and convenient handling, storage, and transportation is required. For this objective, several methods have been put forth. Currently, hydrides (metals and non-metals) have been seen as a potential and suitable candidate to be used for hydrogen storage,

* Corresponding author.

E-mail address: herma@umpsa.edu.my (H.D. Setiabudi).

https://doi.org/10.1016/j.cjche.2024.03.001

1004-9541/© 2024 The Chemical Industry and Engineering Society of China, and Chemical Industry Press Co., Ltd. All rights reserved.