



## Data Article

# Dataset on infrared spectroscopy and X-ray diffraction patterns of Mg–Al layered double hydroxides by the electrocoagulation technique



Marena Molano-Mendoza <sup>a</sup>, Dayana Donneys-Victoria <sup>a</sup>,  
 Nilson Marriaga-Cabral <sup>a</sup>, Miguel Angel Mueses <sup>b</sup>,  
 Gianluca Li Puma <sup>c</sup>, Fiderman Machuca-Martínez <sup>a,\*</sup>

<sup>a</sup> Escuela de Ingeniería Química, Universidad del Valle, A.A. 25360 Cali, Colombia

<sup>b</sup> Department of Chemical Engineering, Universidad de Cartagena, A.A. 1382, Postal 195, Cartagena, Colombia

<sup>c</sup> Department of Chemical Engineering, Loughborough University, Loughborough LE11 3TU, United Kingdom

## ARTICLE INFO

## Article history:

Received 6 July 2019

Received in revised form 26 August 2019

Accepted 19 September 2019

Available online 25 September 2019

## Keywords:

Layered double hydroxides

Al and AZ31 magnesium alloy electrodes

Electrochemical synthesis

Electrocoagulation

## ABSTRACT

The XRD profiles and FTIR analysis of sludge aggregates, Mg–Al layered double hydroxides, produced during electrocoagulation processes are presented. The data describes the composition of materials (LDH) produced at different operations conditions (atmospheric conditions and  $Mg^{2+}/Al^{3+}$  ratio). The data show the diffraction peaks of (003), (006), (018) and (110) crystal planes for hydrotalcite structure.

© 2019 The Authors. Published by Elsevier Inc. This is an open access article under the CC BY license (<http://creativecommons.org/licenses/by/4.0/>).

## 1. Data

The electrochemical method for the synthesis of Layered Double Hydroxides (LDHs) by electrocoagulation is used as an alternative procedure [1]. The LDHs are a class of anionic clays which have observed increasing attention due to their applications in many research areas [2]. Therefore, physicochemical properties of HDL materials, mainly explored from X-ray diffraction and FTIR analysis,

\* Corresponding author.

E-mail addresses: [fiderman.machuca@correounivalle.edu.co](mailto:fiderman.machuca@correounivalle.edu.co), [fiderman@univalle.edu.co](mailto:fiderman@univalle.edu.co) (F. Machuca-Martínez).

## Specifications Table

Subject area	Chemical Engineering
More specific subject area	Lamellar materials
Type of data	Table, image, graph, figure
How data was acquired	X-ray diffraction (XRD) patterns were recorded using a X'pert PRO – PANalytical diffractometer under the following conditions: 45 kV, 40 mA, monochromatic CuK $\alpha$ radiation ( $\lambda = 0.1542$ nm) over a in the $2\theta$ range from of $4^\circ$ to $-90^\circ$ . The FTIR spectra was recorded with a JASCO FT/IR-4100 over a frequency in a range of 500–4000 cm $^{-1}$ . The samples were prepared by mixing the powdered solids with KBr.
Data format	Raw data are tabulated and analyzed
Experimental factors	The XRD and FTIR analysis were performed according to the LDHs typical characterization
Experimental features	The LDH materials were prepared by electrocoagulation method with varying operations conditions and M $^{2+}$ /M $^{3+}$ ratio
Data source location	Universidad del Valle, Cali, Colombia
Data accessibility	The data are presented in this article
Related research article	M. Molano-Mendoza, D. Donneys-Victoria, N. Marriaga-Cabral, M. A. Mueses, G. Li Puma and F. Machuca-Martinez, Synthesis of Mg–Al layered double hydroxides by electrocoagulation, MethodsX, Volume 5, pp. 915–923, 2018.

**Value of the Data**

- The data set shows the methodology to obtain *Layered Double Hydroxides* (LDHs) through electrocoagulation (EC) method varying atmospheric conditions and M $^{2+}$ /M $^{3+}$  ratio.
- X-ray characterization discloses a “classical” 2H-polypeptide (*Magnesite*) of LDHs as well as common LDHs impurities. FTIR analysis indicates some interesting stretching and bending bonds that can have an effect on the type of material.
- The EC method can guide other researchers toward designing multifunctional LDHs by using other metal electrodes (Zn, Fe, Co) for environmental applications such as water/ground remediation, solar energy storage or conversion and catalysis support.

disclose their more specific applications. The dataset presents LDH characteristics prepared by electrocoagulation varying atmospheric conditions and Mg $^{2+}$ /Al $^{3+}$  ratio. Figs. 1–6 show the diffraction peaks of (003), (006), (018) and (110) crystal planes for hydrotalcite structure. Tables 1–6 describe information on the phases and hkl -diffraction planes. Table 7 shows the band positions in the FTIR spectra. Figs. 7–12 displays the functional groups and bonding information. Table 8 exhibits the LDH-material specifications.

### 1.1. X-ray diffraction


X-ray diffraction (XRD) patterns of the materials were measured using an X'pert PRO-PANalytical diffractometer with CuK $\alpha$  radiation ( $\lambda = 0.1542$  nm). The data were collected in the  $2\theta$  range of 4–90°. Determination of the phases and diffraction planes were determined using X'pert PRO-PANalytical software [3]. In every case, hydrotalcite composite was showed. Some XRD and FTIR patterns of the composites were similar to those reported in the literature for hydrotalcite materials [4].

### 1.2. Infrared spectroscopy


The FTIR analysis was carried out in the spectral range (500–4000) cm $^{-1}$  by a Jasco FTIR-4100 spectrometer with a resolution of 4 cm $^{-1}$ . The Figs. 7–12 represent the FTIR spectrum of composites and different vibrations attribution of the composites are represented in Table 7.

## 2. Experimental design, materials and methods


The experimental procedure is described details by Molano-Mendoza [1]. Here the protocol is provided for nitrogen experiments, giving details that were omitted from previous research article.




**Fig. 1.** XRD pattern of the AZ31-AZ31-1 material.




**Fig. 2.** XRD pattern of the AZ31-Al-N2-1 material.




**Fig. 3.** XRD pattern of the AZ31-Al-N2-3 material.



**Fig. 4.** XRD pattern of the HTX3-1 material.



**Fig. 5.** XRD pattern of the MgHP-1 material.



**Fig. 6.** XRD pattern of the MgHP-2 material.

Electrocoagulation experiments were conducted in a batch mode, using synthetic chloride solutions as supporting electrolyte. A 5.000 mg L<sup>-1</sup> of Sodium Chloride solution was prepared by the dissolution of Sodium Chloride (AR grade) in deionized water giving an overall final conductivity of 8.4  $\mu\text{s}\cdot\text{cm}^{-1}$ . This solution was left to dissolve for 10 min. For nitrogen experiments, the beaker was covered and stirred with a speed of 100-rpm for 3.15 h. The sample was dried in a conventional oven for 2 h at 110 °C. The dried samples were then crushed into a fine powder using a ceramic mortar/bowl.

The electrocoagulation unit consisted on two plates that worked as anodes and cathodes, AZ31 magnesium alloy, Mg or aluminum, with an immersed area of 46.6 cm<sup>2</sup> each. The distance between electrodes was 5 mm, and the solution was mixing at 100 rpm using a hot magnetic plate mixer machine. Electrodes were connected to a DC power supply and the appropriate amount of the trivalent and divalent cations were carefully added to the beaker by a manual polarity inverter unit at an applied current of 0.36 and 0.15 mA. The Mg<sup>2+</sup>/Al<sup>3+</sup> ratio and the operating time were calculated based on Faraday's law, assuming that electro-dissolution only occurs at the anode. Before testing, electrodes were subjected to dry abrasion with emery paper No. 600 and then with abrasive paper No. 1000. Afterwards, the electrodes were rinsed with distilled water for approximately 5 min to remove traces (Table 8 describes the experimental conditions).

The following units were obtained beforehand and thoroughly cleaned:

- Digital scale
- Glass beaker (size: 1000 ml)
- Magnetic hotplate stirrer

**Table 1**

X-ray diffraction planes related to the AZ31-AZ31\_(1)\_MMH material.

Magnesium Aluminium Hydroxide Carbonate Hydrate (0.5%)	Hydrotalcite (0.5%)		Carbon (97.6%)		Magnesite (1.2%)		Doyleite (0.2%)	
JCPDS: 98-004-0937	JCPDS: 98-000-6183		JCPDS: 98-003-1976		JCPDS: 98-006-6643		JCPDS: 98-004-9607	
Lattice parameters (Å):	Lattice parameters (Å):							
a	3.0810	a	3.054	a	14.26	a	4.314	a
b	3.0810	b	3.054	b	14.26	b	4.314	b
c	23.784	c	22.81	c	14.26	c	12.775	c
2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	Hkl	2 Theta degree	Hkl	2 Theta degree
11.154	0 0 3	11.630	0 0 3	10.737	1 1 1	37.00	1 0 4	18.560
22.409	0 0 6	23.382	0 0 6	17.578	0 2 2	47.192	1 1 3	20.731
34.419	0 1 2	34.098	1 0 1	20.643	1 1 3	61.105	1 1 6	21.263
36.892	1 0 4	34.792	0 1 2	21.570	2 2 2	63.276	0 1 8	21.723
38.657	0 1 5	35.390	0 0 9	35.583	0 4 4			22.926
45.651	0 1 8	37.455	1 0 4	37.273	1 3 5			23.779
45.738	0 0 12	39.343	0 1 5	37.825	0 0 6			35.526
61.243	1 1 3	46.811	0 1 8	39.956	0 2 6			36.002
61.393	1 0 13	60.593	1 1 0	45.382	1 1 7			37.114
		60.868	0 0 15	45.850	0 4 6			37.637
		61.933	1 1 3	47.687	2 4 6			38.766
		63.596	1 0 13	60.893	4 6 6			46.031
				62.033	1 3 9			46.242
				63.910	4 4 8			60.163
								61.920
								63.865
								1 -1 -3

**Table 2**

X-ray diffraction planes related to the Al-AZ31\_N2 material.

Carbon dioxide (0.2%)	Hydrotalcite (0.3%)		Nitrogen oxide (0.2%)		Magnesium zinc (98.3%)		Sodium carbide (0.3%)		Magnesite (0.7%)		
JCPDS: 98-000-4494	JCPDS: 98-004-0936	Lattice parameters (Å):	JCPDS: 98-000-7431	Lattice parameters (Å):	JCPDS: 98-007-4545	Lattice parameters (Å):	JCPDS: 98-005-6296	Lattice parameters (Å):	JCPDS: 98-006-6646	Lattice parameters (Å):	
a	5.624	a	3.046	a	5.67	A	14.025	A	6.756	a	
b	5.624	b	3.046	b	5.67	B	14.083	B	6.756	b	
c	5.624	c	22.77	c	5.67	C	14.486	C	6.756	c	
2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	hkl	2 Theta degree	Hkl
27.447	1 1 1	11.646	0 0 3	27.220	1 1 1	12.210	0 0 2	22.777	1 1 1	27.947	0 1 2
35.668	0 2 1	23.421	0 0 6	31.531	0 0 2	12.562	0 2 0	37.626	0 2 2	37.540	1 0 4
39.206	1 1 2	34.194	1 0 1	35.368	0 2 1	12.611	2 0 0	61.312	0 2 4	47.716	1 1 3
48.525	1 2 2	34.882	0 1 2	38.875	1 1 2	21.674	2 2 2			62.015	1 1 6
61.657	1 2 3	35.447	0 0 9	48.105	1 2 2	23.201	1 2 3			64.469	0 1 8
		37.546	1 0 4	61.105	1 2 3	23.223	2 1 3				
		39.446	0 1 5			23.437	1 3 2				
		46.922	0 1 8			23.635	3 2 1				
		47.899	0 0 12			26.893	3 3 0				
		60.768	1 1 0			27.675	0 2 4				
		60.980	0 0 15			28.158	0 4 2				
		62.109	1 1 3			29.409	2 3 3				
		71.608	0 2 1			34.041	1 2 5				
		72.020	2 0 2			35.611	4 0 4				
		72.360	1 1 9			36.410	0 3 5				
						37.239	3 5 0				
						38.703	3 2 5				
						39.423	0 2 6				
						39.544	6 1 1				
						45.481	0 7 1				
						45.703	7 1 0				
						46.148	2 1 7				
						46.775	2 5 5				
						48.359	6 4 2				

**Table 3**

X-ray diffraction planes related to the AZ31-Al-N23 material.

Hydrotalcite (20.4%)		Carbon dioxide (15.0%)		Brucite (1.1%)		Sodium Carbonate (15.4%)		Magnesite (48.1%)	
JCPDS:98-000-6183		JCPDS: 98-001-3442		JCPDS: 98-004-4736		JCPDS: 98-003-6631		JCPDS: 98-006-6646	
Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):	
a	3.054	a		5.63	a		3.148	a	5.208
b	3.054	b		5.63	b		3.148	b	5.208
c	22.810	c		5.63	c		4.779	c	6.454
2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	Hkl	2 Theta degree	hkl	2 Theta degree	Hkl
11.630	0 0 3	27.414		1 1 1	18.549		0 0 1	27.619	
23.382	0 0 6	35.628		0 2 1	37.614		0 0 2	34.137	
34.098	1 0 1	39.160		1 1 2	37.967		0 1 1	34.413	
35.3900	0 0 9	61.588		1 2 3	62.027		1 1 1	39.945	
46.811	0 1 8							46.746	
60.593	1 1 0							49.252	
60.868	0 0 15							60.936	
61.933	1 1 3							61.468	
								61.644	
								0 3 0	

**Table 4**

X-ray diffraction planes related to the HTX3\_1 material.

Hydrotalcite (12.7%)		Halite (12.5%)		Brucite (0.7%)		Gibbsite (74.1%)	
JCPDS: 98-000-6183		JCPDS: 98-011-6223		JCPDS: 98-003-4961		JCPDS: 98-008-2783	
Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):	
<hr/>							
a	3.054	a		5.653	a	3.148	a
b	3.054	b		5.653	b	3.148	b
c	22.81	c		5.653	c	4.772	c
2 Theta degree	Hkl	2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	Hkl
11.630	0 0 3	27.303		1 1 1	18.577	0 0 1	18.675
23.382	0 0 6	31.632		0 0 2	37.671	0 0 2	22.393
34.792	0 1 2	45.341		0 2 2	37.979	0 1 1	27.054
35.390	0 0 9				62.040	1 1 1	27.736
37.455	1 0 4						27.819
39.343	0 1 5						28.669
46.811	0 1 8						34.984
47.810	0 0 12						35.509
60.593	1 1 0						36.989
60.868	0 0 15						37.871
61.933	1 1 3						38.269
							39.315
							60.580
							62.015
							62.493
							2 4 3

- Spatula
- Al, Mg and AZ31 alloy electrode plates
- Sodium Chloride, AR grade
- Nitrogen ( $N_2$ ) gas pipeline
- DI water
- Ceramic mortar/bowl
- Emery paper No. 600 and abrasive paper No. 1000

**Table 5**

X-ray diffraction planes related to the MgHP-1 material.

Zinc Aluminium Hydroxide Chloride Hydrate (7.6%)	Magnesite (12.3%)		Diamond (2.3%)		Sodium carbide (40.0%)		Hydrotalcite (5.2%)		Gibbsite (32.4%)		
JCPDS: 98-005-8141	JCPDS: 98-006-6646		JCPDS: 98-005-4252		JCPDS: 98-005-6291		JCPDS: 98-000-6183		JCPDS: 98-011-2963		
Lattice parameters (Å):	Lattice parameters (Å):										
a	3.083	a	4.278	a	4.591	a	6.778	a	3.054	a	8.675
b	3.083	b	4.278	b	4.591	b	6.778	b	3.054	b	5.069
c	23.47	c	12.546	c	4.591	c	12.74	c	22.81	c	12.508
2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	Hkl	2 Theta degree	Hkl
11.3	0 0 3	27.947	0 1 2	39.212	002	23.206	1 1 2	11.630	0 0 3	18.287	0 0 2
22.711	0 0 6	37.540	1 0 4	48.536	112	27.991	0 0 4	23.382	0 0 6	20.293	1 1 -1
34.363	0 0 9	47.716	1 1 3			36.387	1 2 3	34.792	0 1 2	22.618	1 1 -2
38.772	0 1 5	62.015	1 1 6			37.501	2 2 0	35.390	0 0 9	27.997	1 1 -3
45.920	0 1 8	64.469	0 1 8			38.766	0 2 4	37.455	1 0 4	28.091	2 1 -1
58.983	0 0 15					46.758	1 1 6	39.343	0 1 5	28.686	1 0 2
62.002	1 0 13					47.439	2 2 4	46.811	0 1 8	28.714	2 0 -4
						48.939	2 3 1	47.810	0 0 12	31.649	3 0 2
						50.697	0 2 6	60.593	1 1 0	35.159	1 1 4
						61.093	2 4 0	60.868	0 0 15	35.385	0 2 0
						61.224	2 3 5	61.933	1 1 3	35.809	3 1 3
						61.412	1 3 6	63.586	1 0 13	38.327	1 2 -2
						61.983	0 4 4			40.117	0 2 2
						64.610	0 2 8			40.249	2 1 -5
										45.440	0 2 -3
										47.175	1 0 4
										47.287	4 1 -5
										50.512	3 1 1
										58.612	2 3 -2
										60.468	4 2 -6
										64.616	6 0 -6
										72.237	1 1 -8


**Table 6**


X-ray diffraction planes related to the MgHP\_A1\_2 material.

Magnesium Zinc (98.5%)		Magnesium Aluminium Hydroxide Carbonate Hydrate (0.3%)		Hydrotalcite (0.3%)		Sodium Carbonate (0.9%)	
JCPDS: 98-007-4545		JCPDS: 98-004-0937		JCPDS: 98-00-61-83		JCPDS: 98-003-6621	
Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):		Lattice parameters (Å):	
a	14.025	a	3.045	a	3.054	a	9.015
b	14.083	b	3.045	b	3.054	b	5.209
c	14.48	c	22.701	c	22.81	c	6.405
2 Theta degree	Hkl	2 Theta degree	hkl	2 Theta degree	Hkl	2 Theta degree	Hkl
12.210	0 0 2	11.684	0 0 3	11.630	0 0 3	23.415	2 0 -1
12.562	0 2 0	23.492	0 0 6	23.382	0 0 6	23.762	1 1 -1
17.835	2 2 0	34.205	1 0 1	34.098	1 0 1	27.897	0 0 2
23.201	1 2 3	37.580	1 0 4	34.792	0 1 2	34.408	0 2 0
23.223	2 1 3	39.486	0 1 5	35.390	0 0 9	35.464	2 0 2
23.492	3 1 2	48.058	0 0 12	37.455	1 0 4	36.557	3 1 -1
27.675	0 2 4	60.786	1 1 0	39.343	0 1 5	38.070	3 1 1
28.413	4 2 0	61.193	0 0 15	47.810	0 0 12	47.893	4 0 -2
34.741	1 5 2	62.140	1 1 3	60.593	1 1 0	50.244	2 2 2
40.633	6 2 0	72.053	2 0 2	60.868	0 0 15	55.692	0 2 -3
45.335	4 5 3			61.933	1 1 3	58.6	2 2 -3
46.523	4 6 0			72.160	1 1 9	60.730	2 2 3
47.310	1 7 2					71.203	1 3 3
48.359	6 4 2						
50.238	5 1 6						


**Table 7**Positions of the bands (in cm<sup>-1</sup>) in the IR spectra (Figs. 7–12) [4,5].

Vibration/Assignment	Material						
		AZ31-AZ31-1	AZ31-Al-N2	AZ31AlN2-3	HTX3-1	MgHP-1	MgHP-2
Water and hydroxyl groups	<i>OH stretching</i>					3694.94	3693.01
	<i>Bending</i>	3459.67	3443.28	3443.28	3450.99	3216.68	3465.46
	<i>Adsorbed water</i>	1641.13	1639.2	1639.2	1641.13	1646.91	1642.09
	<i>N–H stretching</i>		2095.28	2095.28	2098.17	2100.1	2101.06
Nitrogen	<i>C = O</i>	1475.28	1501.31	1501.31			1508.06
	<i>v<sub>3</sub> asymmetric stretching</i>	1364.39	1363.43	1363.2	1364.39	1360.53	1365.35
Carbonates		1267					
		675.93					
	<i>V<sub>1</sub> symmetrical stretching</i>	1032.69	1069.33	1069.33	1073.19	1087.66	1075.12
	<i>Al–O and Mg–O deformation</i>	1188.9			1175.4		
Others	<i>Mg–O</i>		557.33	598.80	639.2	589.15	544.79
			447.40	452.22	452.22	412.692	
	<i>Mg–O</i>	378.94			367.37		


**Fig. 7.** IR Spectrum of the AZ31-AZ31-1 material.




**Fig. 8.** IR Spectrum of the AZ31-AL-N2-1 material.




**Fig. 9.** IR Spectrum of the AZ31-AL-N2-3 material.



**Fig. 10.** IR Spectrum of the HTX3-1 material.



**Fig. 11.** IR Spectrum of the MgHP-1 material.



**Fig. 12.** IR Spectrum of the MgHP-2 material.

**Table 8**  
Sample specifications.

Sample	Electrodes	Current (A)	Temperature (°C)	Sodium Chloride (ppm)	Nitrogen gas	Mg <sup>2+</sup> /Al <sup>3+</sup> ratio
AZ31-AZ31-1	AZ31-AZ31	0.51	50	5000	—	2/1
AZ31-Al-N2-1	AZ31-AZ31	0.51	50	5000	X	2/1
AZ31-Al-N2-3	AZ31-Al	0.51	50	5000	X	3/1
HTX3-1	AZ31-Al	0.51	50	5000	—	
MgAl-1	Mg-Al	0.51	50	5000	—	2/1
MgAl-2	Mg-Al	0.51	50	5000	—	2/1

## Acknowledgements

The authors would like to acknowledge the Universidad del Valle (Colombia) for supporting the study under Grant No. 2863: Electrocoagulation of textile industrial effluents using magnesium 'Case study of indigo carmine solutions'. The Royal Academy of Engineering -Newton Caldas Fund (United Kingdom) and Loughborough University (United Kingdom) for the financial support for the development of this research, framed in the project: Treatment of petroleum production wastewater by combined adsorption and oxidation process using double layer hydrotalcites under Grant No. IAPP1617~70.

## Conflict of Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

## References

- [1] M. Molano-Mendoza, D. Donneys-Victoria, N. Marraga-Cabralles, M.A. Mueses, G. Li Puma, F. Machuca-Martínez, Synthesis of Mg-Al layered double hydroxides by electrocoagulation, *MethodsX* 5 (2018) 915–923.
- [2] T. Hibino, A. Tsunashima, Characterization of repeatedly reconstructed Mg - Al hydrotalcite-like compounds: gradual segregation of aluminum from the structure, *Chem. Mater.* 20 (1998) 4055–4061.
- [3] T. Degen, M. Sadki, E. Bron, U. König, G. Nébert, The HighScore suite, *Powder Diffr.* 29 (Supplement S2) (2014) S13–S18.
- [4] F. Cavani, F. Trifirò, A. Vaccari, Hydrotalcite-type anionic clays: preparation, properties and applications, *Catal. Today* 11 (1991) 173–301.
- [5] J. Pérez-Ramírez, G. Mul, F. Kapteijn, J.A. Moulijn, A spectroscopic study of the effect of the trivalent cation on the thermal decomposition behaviour of Co-based hydrotalcites, *J. Mater. Chem.* 11 (2001) 2529–2536.