

Project Number:	86736			
Project Title:	Armored Enzyme Nanoparticles for Remediation of Subsurface			
Contaminants				
Publication Date:	September 2005			
DOE Report Numbe	er:			
Lead Principal Investigator:		Dr. Jay W. Grate		
-	0	Pacific Northwest National Laboratory		
		Box 999, Richland, WA 99352		
		509-376-4242 (voice); jwgrate@pnl.gov,		
Co-Investigator:		Dr. Jungbae Kim		
0		Pacific Northwest National Laboratory		
		Box 999, Richland, WA 99352		
		509-376-4621 (voice); jungbae.kim@pnl.gov		
Co-Principle Investigator:		Prof. Jon Dordick		
-	0	Department of Chemical and Biological Engin	eering	
		Rensselaer Polytechnic Institute	e	
		Troy, NY, 12180		
		(518) 276-2899 (voice); dordick@rpi.edu		
Number of Graduat	e Students Ao	ctively Involved in the Project:	2	
Number of Undergra	aduate Stude	nts Involved (part-time) in the Project:	1	
Number of Post-Doc	toral Scholar	s involved (part-time) in the Project:	2	

Number of Ph.D. degrees granted involved in the Project:	0
Number of M.S. degrees granted involved in the Project:	0

Research Objective

The remediation of subsurface contaminants is a critical problem for the Department of Energy, other government agencies, and our nation. Severe contamination of soil and groundwater exists at several DOE sites due to various methods of intentional and unintentional release. Given the difficulties involved in conventional removal or separation processes, it is vital to develop methods to *transform* contaminants and contaminated earth/water to reduce risks to human health and the environment. Transformation of the contaminants themselves may involve conversion to other immobile species that do not migrate into well water or surface waters, as is proposed for metals and radionuclides; or degradation to harmless molecules, as is desired for organic contaminants. Transformation of contaminated earth (as opposed to the contaminants themselves) may entail reductions in volume or release of bound contaminants for remediation.

Effective methods to carry out these transformations are required. One approach is microbial bioremedition, however this is not trivial. The microbes must be capable of living in the contaminated environment of concern, they must express the enzymes or enzyme systems of interest, and they must do so in competition with other microorganisms in the same subsurface environment. Highly contaminated soil and groundwater may be inhospitable to microorganisms, which would limit bioremediation to the periphery of the contamination and preclude bioremediation of the source. In addition, bacteria provide two barriers for uptake of organic contaminants: the cell wall and the inner cytoplasmic membrane.

An alternative approach is remediation with isolated enzymes instead of microorganisms. However, direct addition of the required enzymes to bioreactors, engineered landfills, or *in situ* is not feasible if the enzymes are too short-lived to be effective. Enzyme stability is a critical technical gap in the enzymatic alternative to bioremediation. Furthermore, stability is a significant component of the cost of using enzymes. The technical ability to produce enzymes on a large scale has progressed dramatically in the past two decades, and further advances can be expected as attention shifts from genomics to proteomics. However, methods to stabilize enzymes in suitable forms for practical use remain an important issue.

Thus, the most fundamental scientific challenges are two-fold: to develop new methods of increasing the stability of enzymes and to do so without sacrificing the effective activity of those enzymes by limiting mass transfer to the active sites. *We propose to address these issues by developing armored enzyme nanoparticles.* The nanometer scale dimensions of the "armor" will provide much less mass transfer limitation to enzymatic activity compared to other immobilization methods such as micron scale particles with entrapped or immobilized enzymes. The armored enzyme nanoparticles will be nano-bio-composites, combining the soft bio-organic enzyme core with an inorganic silicate-containing polymer network as the armor. This network will be porous to small or medium sized molecules.

Research Progress and Implications

This report summarizes work after 3 years of the 3 year program. The research effort is being directed at stabilization of enzymes as nanostructured enzyme-containing composites, and development of a dehalogenase enzyme composite as a stabilized enzyme form for the transformation of chlorinated organic contaminants. In addition, research is being performed on methods to modify enzymes for active and stable inclusion into these nanoscale composites.

The primary enzyme nanostructure developed was the armored enzyme nanoparticles. As these contain a single enzyme molecule, we also refer to them as single enzyme nanoparticles, or SENs. The preparation of SENs represents a new approach that is distinct from immobilizing enzymes on the surfaces of solids or encapsulating them in sol-gels, polymers, or bulk composite structures. Converting free enzymes to SENs can result in significantly more stable catalytic activity, as we have demonstrated for chymotrypsin as a model hydrolase enzyme. The nanoscale structure of the SEN does not impose a serious mass transfer limitation on substrates. At the same time, the synthesis of SENs is also different from conventional enzyme modifications such as surface amino acid modifications or polymer attachment, which generally do not provide as great a long-term enzyme stabilization. The process for the preparation of SENs begins from the surface of the enzyme molecule, with covalent reactions to anchor, grow, and crosslink a composite organic/inorganic network around each separate enzyme molecule. The reactions are carried out so that crosslinking is largely confined to individual enzyme surfaces, yielding discrete nanoparticles rather than the bulk solids that would result from interparticle reactions. SENs were observed using high resolution transmission electron microscopy (TEM). Individual nanoparticles with seemingly hollow centers and a contrasting outer structure could be resolved,. The dimensions of the transparent core containing the protein are consistent with the size and

shape of the enzyme. Kinetic measurements showed that the SENs were quite stable in contrast to their native free enzyme precursors, and that there was little mass tranfer limitation.

The development of stabilized enzymes as soluble individual enzyme particles provides the opportunity to further process these new nanomaterials, in contrast to enzymes entrapped in bulk solids. The SENs can be deposited as films or immobilized on solid supports. Given their small size, they can penetrate and be immobilized within nanostructured or nanoporous matrices, creating hiearchical architectures. They can potentially be linked with other nanoparticles or molecules as part of multifunctional nano-assemblies. Several other nanostructured enzyme systems have also been developed and investigated in the course of this project, using mesoporous silica and polymer nanofibers as supports. In each case, with proper synthetic conditions, significant enzyme stabilization has been achieved. Dehalogenase enzyme was produced but has not yet been stabilized as SENs. This work is now underway at the RPI subcontract site.

Planned activities

This project is complete. Given additional opportunity, the work would focus on developing stabilized enzyme systems for enzymes that are specifically relevant to contaminants on DOE sites.

Information Access

Lee J, Kim J, Kim J, Jia HF, Kim MI, Kwak JH, Jin SM, Dohnalkova A, Park HG, Chang HN, Wang P, Grate JW, Hyeon T Simple synthesis of hierarchically ordered mesocellular mesoporous silica materials hosting crosslinked enzyme aggregates SMALL 1 (7): 744-753, 2005

Herricks TE, Kim S-H, Kim J, Li D, Kwak JH, Grate JW, Kim SH, Xia Y (2005) "Direct Fabrication of Enzyme-Carrying Polymer Nanofibers by Electrospinning", JOURNAL OF MATERIAL CHEMISTRY 15: 3241-3245, 2005

Kim BC, Nair S, Kim J, Kwak JH, Grate JW, Kim SH, Gu MB Preparation of biocatalytic nanofibres with high activity and stability via enzyme aggregate coating on polymer nanofibres NANOTECHNOLOGY 16 (7): S382-S388, 2005

J. Kim and J. W. Grate "Single-Enzyme Nanoparticles Armored by a Nanometer-scale Organic/Inorganic Network" <u>NANO LETTERS</u>, 3:1219-1222, 2003

Jungbae Kim and Jay W. Grate, "Nano-Biotechnology in Using Enzymes for Environmental Remediation: Single-Enzyme Nanoparticles", in ACS Symposium Series 890: Nanotechnology and the Environment, Applications and Implications, Ed; B. Karn, T. Masciangioli, W.Zhang, V. Colvin, and P. Alivisatos, Chapter 29, pp220-225, 2005 Jay W. Grate and Jungbae Kim, "Single Enzyme Nanoparticles: A New Nanostructure for Enzyme Stabilization", Dekker Encyclopedia of Nanoscience and Nanotechnology, edited by James A. Schwarz, Cristian I. Contescu, and Karol Putyera Pages: 235 – 239, Print Published: 03/31/2004 | Online Published: 04/20/2004 Invited Chapter