

University of New Hampshire
University of New Hampshire Scholars' Repository

Division 09 – Finishes

Chapter 5 – Technical Construction and
Renovation Standards

1-25-2013

099600 - High-Performance Coatings

Sandra Hickey
sandra.hickey@unh.edu

Follow this and additional works at: https://scholars.unh.edu/pdch_5_09

Recommended Citation

Hickey, Sandra, "099600 - High-Performance Coatings" (2013). *Division 09 – Finishes*. 12.
https://scholars.unh.edu/pdch_5_09/12

This Article is brought to you for free and open access by the Chapter 5 – Technical Construction and Renovation Standards at University of New Hampshire Scholars' Repository. It has been accepted for inclusion in Division 09 – Finishes by an authorized administrator of University of New Hampshire Scholars' Repository. For more information, please contact nicole.hentz@unh.edu.

SECTION 09 9600 - HIGH-PERFORMANCE COATINGS

1.1 SUMMARY

- A. Section includes surface preparation and application of high-performance coating systems.

1.2 DEFINITIONS

- A. Gloss Level 6: 70 to 85 units at 60 degrees, according to ASTM D 523.
- B. Gloss Level 7: More than 85 units at 60 degrees, according to ASTM D 523.

1.3 SUBMITTALS

- A. LEED Submittals:
 - 1. Product Data for Credit EQ 4.2: For interior coatings, documentation including printed statement of VOC content.
- B. Product List: For each product indicated, include the following:
 - 1. Cross-reference to paint system and locations of application areas. Use same designations indicated on Drawings and in schedules.
 - 2. Printout of current "MPI Approved Products List" for each product category specified in Part 2, with the proposed product highlighted.
 - 3. VOC content.

1.4 MANUFACTURERS

- A. Manufacturers: Tnemec.

1.5 HIGH-PERFORMANCE COATINGS, GENERAL

- A. MPI Standards: Provide products that comply with MPI standards indicated and are listed in "MPI Approved Products List."
- B. Material Compatibility:
 - 1. Provide materials for use within each coating system that are compatible with one another and substrates indicated, under conditions of service and application as demonstrated by manufacturer, based on testing and field experience.
 - 2. For each coat in a coating system, provide products recommended in writing by manufacturers of topcoat for use in coating system and on substrate indicated.
 - 3. Provide products of same manufacturer for each coat in a coating system.

- C. VOC Content: Products shall comply with VOC limits of authorities having jurisdiction and, for interior coatings applied at project site, the following VOC limits, exclusive of colorants added to a tint base, when calculated according to 40 CFR 59, Subpart D (EPA Method 24).
1. Flat Paints and Coatings: 50 g/L.
 2. Nonflat Paints and Coatings: 150 g/L.
 3. Primers, Sealers, and Undercoaters: 200 g/L.
 4. Anti-Corrosive and Anti-Rust Paints Applied to Ferrous Metals: 250 g/L.
 5. Zinc-Rich Industrial Maintenance Primers: 340 g/L.
 6. Pre-Treatment Wash Primers: 420 g/L.
 7. Floor Coatings: 100 g/L.
 8. Shellacs, Clear: 730 g/L.
 9. Shellacs, Pigmented: 550 g/L.

1.6 EXTERIOR PAINTING SCHEDULE

- A. Steel Substrates: Polyurethane, Pigmented, Epoxy Zinc Rich Primer and High-Build Epoxy Coating System; MPI EXT 5.1G.
1. Primer Coat: Epoxy Zinc Rich Primer MPI #20.
 2. Intermediate Coat: High-performance, polyamide-epoxy coating; High-Build Epoxy Marine Coating, Low Gloss; MPI #108.
 3. Topcoat: Polyurethane, Two-Component, Pigmented, Gloss; MPI #72.

END OF SECTION 09 9600