

## §103. Synergistic Effects of Neutron (ion) and Plasma on Material in QUEST

Watanabe, H., Yoshida, N. (RIAM Kyushu Univ.), Muroga, T., Kurishita, H. (Tohoku Uni.)

### 1. Introduction

In a fusion reactor, plasma-facing materials are irradiated by 14MeV neutron and particles (hydrogen isotope, helium). It is known that high energy neutron causes displacement damage and nuclear reaction. Plasma particles also cause various phenomena in the plasma facing materials. In particular, helium atom is recognized that it has the strong effects on irradiated materials because helium can easily diffuse in materials and it has a strong interaction with radiation induced defects (interstitials and/or vacancies). In this study, therefore, the effects of implanted helium and hydrogen on heavy ions irradiation damage pure tungsten (W) and TFGR W-1.1TiC<sup>1)</sup> were studied. The 2.4 MeV Cu<sup>2+</sup> ion irradiations were performed in the temperature range of room temperature to 873K. After the ion irradiations up to 4 dpa, transmission electron microscope (TEM) and TDS experiments were conducted.

### 2. Results<sup>1-2)</sup>

In order to clarify the effect of radiation induced damage on D retention in W based materials with different microstructures, specimens of pure R-W (0.1mm thick sheet recrystallized at 2273K for 10 min,) and TFGR W-1.1TiC were employed. The pure W was electrolytically polished and TFGR W-1.1TiC was mechanically mirror polished followed by degassing at 1473 K for 5 min. The both specimens were irradiated with 2.4MeV-Cu<sup>2+</sup> at room temperature up to  $1 \times 10^{19}$  ions/m<sup>2</sup> for pure W and  $2 \times 10^{19}$  ions/m<sup>2</sup> for TFGR W-1.1TiC, which correspond to 2 and 4 dpa (displacement per atom), respectively. The position of the peak damaged zone is around 400-500 nm from the surface. After the ion irradiation, the specimens were irradiated with 2.0 keV-D<sup>2+</sup> at room temperature and higher temperature up to  $1 \times 10^{21}$  D<sup>2+</sup>/m<sup>2</sup> and subjected to TDS at temperatures from RT to 1023K in vacuum with an heating rate of 1 K/s. Fig. 1 and 2 show the microstructure of pure W and TFGR W-1.1TiC irradiated at room temperature. Fig. 1 and 2 show dislocation contrast images and void contrast images, respectively. By the irradiation, dislocation loops of interstitial type and a high density of nano-voids were observed in both materials. But, the microstructure of TFGR W-1.1TiC was almost same as the pure W. These results mean that the addition of 1.1TiC does not significant affects on the formation of dislocation loops and voids by the present irradiation conditions. Fig. 3 and 4 show the effects of displacement level (dpa) and irradiation temperature dependence of desorption rate of D<sub>2</sub> for pure W and TFGR W-1.1TiC, respectively. These results show that the sink density (dislocation loops and nano-voids) and resultant lattice defects due to 2.4MeV Cu<sup>2+</sup> irradiation have significant effects of the desorption of D<sub>2</sub> in both pure W and TFGR W-1.1TiC.

- 1) H. Kurishita, S. Matsuno, H. Arakawa, T. Sakamoto, S. Kobayashi, K. Nakai, H. Okano, H. Watanabe, N. Yoshida, Y. Tokitani, Y. Hatano, T. Takida, M. Kato, A. Ikegaya, Y. Ueda, H. Hatakeyama and T. Shikama, presented at PFMC14 .
- 2) H. Watanabe, N. Futagami, S.Naitou, N.Yoshida, J. Nucl. Materials, 455 (2014)51-55




Fig.1 Microstructure of pure W and TFGR W-1.1TiC irradiated at room temperature.




Fig.2 Void contrast image of pure W and TFGR W-1.1TiC irradiated at room temperature




Fig.3 Effects of Cu ion irradiation on desorption of D<sub>2</sub> for pure W and TFGR W-1.1TiC irradiated at room temperature




Fig. 4 Effects of higher temperature irradiation of on desorption of D<sub>2</sub> for pure W and TFGR W-1.1TiC