



University of HUDDERSFIELD

University of Huddersfield Repository

Nep, Elijah, Ghori, Muhammad U., Ngwuluka, Ndidi, Conway, Barbara R and Smith, Alan M.

Physicochemical characterization of polysaccharides extracted from sesame leaves: a potential matrix for sustained release tablets

Original Citation

Nep, Elijah, Ghori, Muhammad U., Ngwuluka, Ndidi, Conway, Barbara R and Smith, Alan M. (2014) Physicochemical characterization of polysaccharides extracted from sesame leaves: a potential matrix for sustained release tablets. In: The AAPS Annual Meeting and Exposition 2014, 2-6th November 2014, San Diego, USA. (Unpublished)

This version is available at <http://eprints.hud.ac.uk/30861/>

The University Repository is a digital collection of the research output of the University, available on Open Access. Copyright and Moral Rights for the items on this site are retained by the individual author and/or other copyright owners. Users may access full items free of charge; copies of full text items generally can be reproduced, displayed or performed and given to third parties in any format or medium for personal research or study, educational or not-for-profit purposes without prior permission or charge, provided:

- The authors, title and full bibliographic details is credited in any copy;
- A hyperlink and/or URL is included for the original metadata page; and
- The content is not changed in any way.

For more information, including our policy and submission procedure, please contact the Repository Team at: E.mailbox@hud.ac.uk.

<http://eprints.hud.ac.uk/>

Physicochemical Characterization of Polysaccharides Extracted from Sesame Leaves: A Potential Matrix for Sustained Release Tablets

E. I. Nep¹, M. U. Ghori¹, N. C. Ngwuluka², B. R. Conway¹, A. M. Smith¹

¹ University of Huddersfield, ² University of Jos

Purpose

In the developing world the pharmaceutical sector depends heavily on imported raw materials which elevate the cost of medicines beyond the reach of the majority of the local population; despite often being rich in renewable sources which could be used as excipients. In this study we have extracted and characterised a largely undeveloped polysaccharide, sesamum gum, with a view to application as an alternative pharmaceutical excipient.

Methods

Polysaccharide from the leaves of *Sesamum indicum* was extracted by maceration in distilled water followed by precipitation in absolute ethanol. The material was oven dried and milled to a particle size of 250 μ m. The resulting material was characterized using X-ray diffractometry (XRD), Fourier transform infra-red spectroscopy, differential scanning calorimetry and thermogravimetric analysis. The total carbohydrate content, protein content and intrinsic viscosity of the extracted gum were determined according to standard protocols. Constituent sugar analysis of the material was determined by high performance anion exchange chromatography after hydrolysis of the samples using 2M trifluoroacetic acid for 3 hours. Compaction studies were carried out using a Testometric materials testing machine and data analysed by Heckel analysis.

Results

The polysaccharide gum had a total carbohydrate content of 98.1% and protein content of 1.7%. XRD spectra were typical of an amorphous material with a maximum decomposition temperature of 266.7 °C. Intrinsic viscosity was determined to be approximately 3.31 and 4.40 dl/g in 0.1 M NaCl and deionized water respectively. Dispersions of the polysaccharide are viscoelastic and exhibit shear-thinning behaviour. The polysaccharide contains fucose (0.1%), rhamnose (1.1%), arabinose (2.8%), galactose (48.9%), glucose (2.7%), mannose (6.8%) and xylose (33.6%) as neutral sugars, and glucuronic acid (3.0%) and galacturonic acid (1.1%) as acid sugars. Heckel analysis indicates that sesamum consolidates plastically having mean yield pressure of 131.45 MPa.

Conclusion

Sesamum polysaccharide is typically amorphous with a low content of uronic acids. Results suggest it is a thermally stable, high molecular weight polymer which exhibits shear-thinning behaviour in the hydrated form. The polymer in the dry state is a highly compactable material which has the potential to be exploited as a matrix former in sustained release tablets.