

Intermittent origin of the large violations of the fluctuation-dissipation relations in an aging polymer glass

L. BUISSON, S. CILIBERTO and A. GARCIMARTÍN(*)

*Ecole Normale Supérieure de Lyon, Laboratoire de Physique, CNRS UMR5672
46 Allée d'Italie, 69364 Lyon Cedex 07, France*

(received 13 May 2003; accepted in final form 10 June 2003)

PACS. 75.10.Nr – Spin-glass and other random models.

PACS. 77.22.Gm – Dielectric loss and relaxation.

PACS. 64.70.Pf – Glass transitions.

Abstract. – The fluctuation-dissipation relation (FDR) is measured on the dielectric properties of a polymer glass (polycarbonate) in the range 20 mHz–100 Hz. It is found that after a quench below the glass transition temperature, the fluctuation-dissipation theorem is strongly violated. The amplitude and the persistence time of this violation are decreasing functions of frequency. At frequencies larger than 1 Hz it persists for about 3 h. The origin of this violation is a highly intermittent dynamics characterized by large fluctuations. The relevance of these results for recent models of aging dynamics is discussed.

When glassy materials are quenched from above their glass transition temperature T_g to a temperature lower than T_g , any response function of these materials depends on the time t_w elapsed from the quench: they are aging [1]. A widely studied question is how the temperature of these systems can be defined. Recent theories [2] based on the description of spin glasses by a mean-field approach propose to extend the concept of temperature using a fluctuation-dissipation relation (FDR) which generalizes for a weakly out-of-equilibrium system the fluctuation-dissipation theorem (FDT). (For a review see refs. [3,4].) At equilibrium, FDT relates the fluctuation spectral density of a variable V to the response $\chi_{Vq}(f)$ of V to a perturbation of its conjugated variable q at frequency f :

$$S(f) = \frac{2K_B T}{\pi f} \text{Im} [\chi_{Vq}(f)], \quad (1)$$

where $S(f) = \langle |V(f)|^2 \rangle$ is the fluctuation spectral density of V , K_B is the Boltzmann constant, T the temperature of the system and $\text{Im}[\chi_{Vq}(f)]$ is the imaginary part of $\chi_{Vq}(f)$. When the system is not in equilibrium, FDT, that is eq. (1), may fail. Because of the slow dependence

(*) Permanent address: Departamento de Física, Facultad de Ciencias, Universidad de Navarra - E-31080 Pamplona, Spain.

on t_w of the response functions, it has been proposed to use an FDR which generalizes eq. (1) and which can be used to define an effective temperature $T_{\text{eff}}(f, t_w)$ of the system [4]:

$$T_{\text{eff}}(f, t_w) = \frac{S(f, t_w)\pi f}{\text{Im}[\chi_{Vq}(f, t_w)]2K_B}. \quad (2)$$

It is clear that if eq. (1) is satisfied $T_{\text{eff}} = T$, otherwise T_{eff} turns out to be a decreasing function of t_w and f . The physical meaning of eq. (2) is that there is a time scale (for example, t_w) which allows to separate the fast processes from the slow ones. In other words, the low-frequency modes, such that $ft_w < 1$, relax towards equilibrium much more slowly than the high-frequency ones which rapidly relax to the temperature of the thermal bath. This striking behavior has been observed in several numerical models of aging [5–10], which show that eq. (2) is a good definition of temperature in the thermodynamic sense [4]. The experimental analysis of the dependence of $T_{\text{eff}}(f, t_w)$ on f and t_w is very useful to distinguish among different models of aging because the FDT violations are model dependent [4–10].

Recently, a few experiments have analyzed this problems in real materials [11–13]. The violation of FDT measured in an experiment on a spin glass [13] seems to be in agreement with theoretical predictions. The experiment on the dielectric measurements on glycerol [11] is a single-frequency experiment. Thus it cannot give insight on the time evolution of the spectrum. The experiment on colloidal glasses [12] presents only a qualitative agreement with theory. Specifically, it shows that the persistence time of the violation is very long and the amplitude of the violation is huge.

In order to give more insight into this problem, we have done wide-band (20 mHz, 100 Hz) measurements of the dielectric susceptibility and of the polarization noise in a polymer glass. In this letter we present results which show a strong violation of the FDT in a polymer glass quenched from the molten state to below its glass transition temperature. T_{eff} defined by eq. (2) slowly relaxes towards the bath temperature. The violation is observed even at $ft_w \gg 1$ and may last for more than 3 h for $f > 1$ Hz. The polymer used is Makrofol DE 1-1 C, a bisphenol A polycarbonate, with $T_g \simeq 419$ K, produced by Bayer in form of foils. This material has been chosen because it has a wide temperature range of strong aging [1] and is totally amorphous. Many studies of the dielectric susceptibility of this material exist, but no one had an interest on the problem of noise measurements. In our experiment polycarbonate is used as the dielectric of a capacitor. The capacitor is composed by 14 cylindrical capacitors in parallel in order to reduce the resistance of the sample and to increase its capacity. Each capacitor is made of two aluminum electrodes, 12 μm thick, and by a disk of polycarbonate of diameter 12 cm and thickness 125 μm . The 14 capacitors are sandwiched together and put inside two thick aluminum plates which contain an air circulation used to regulate the sample temperature within a few percent. This mechanical design of the capacitor is very stable and gives very reproducible (better than 1%) results even after many temperature quenches. The capacitor is inside two Faraday screens to insulate it from external noise. Fast quench of about 50 K/min are obtained by injecting nitrogen vapor in the air circulation of the aluminum plates. The electrical impedance of the capacitor is $Z(f, t_w) = R/(1 + i2\pi fRC)$, where C is the capacitance and R is a parallel resistance which accounts for the complex dielectric susceptibility. It is measured using a Novocontrol Dielectric Analyzer. The noise spectrum of this impedance $S_Z(f, t_w)$ is

$$S_Z(f, t_w) = \frac{4K_B T_{\text{eff}}(f, t_w)R}{1 + (2\pi fRC)^2}, \quad (3)$$

where T_{eff} is the effective temperature of the sample. The polarization noise of Z is sent to an amplifier whose input resistance is $R_i = 4 \text{ G}\Omega$. The output signal of the amplifier is directly




Fig. 1 – (a) Polycarbonate resistance R as a function of frequency measured at $T_i = 433$ K (\triangleleft) and at $T_f = 333$ K (\circ). The effect of the $4\text{G}\Omega$ input resistance is also shown at $T = 433$ K (\square) and at $T = 333$ K ($*$). b) Polycarbonate capacitance *vs.* frequency measured at $T_i = 433$ K (\triangleleft) and at $T_f = 333$ K (\circ).

acquired by a NI4462 card. The measured spectrum at the amplifier input is

$$S_V(f, t_w) = \frac{4K_B R R_i (T_{\text{eff}}(f, t_w) R_i + T_R R)}{(R + R_i)^2 + (2\pi f R R_i C)^2} + \frac{S_\xi(f) R R_i}{(R + R_i)^2 + (2\pi f R R_i C)^2} + S_\eta(f), \quad (4)$$

where T_R is the temperature of R_i and S_η and S_ξ are, respectively, the voltage and the current noise spectrum of the amplifier. The desired statistical accuracy of $S_V(f, t_w)$ is reached by averaging the results of many experiments. In each of these experiments the sample is first heated to $T_i = 433$ K. It is maintained at this temperature for 4 hours to reinitialize its thermal history. Then it is quenched from T_i to $T_f = 333$ K in about 2 minutes. The origin of aging time t_w is the instant when the capacitor temperature is at $T_g \simeq 419$ K, which, of course, may depend on the cooling rate. However, adjustment of T_g of a few degrees will shift the time axis by at most 30 s, without affecting our results.

At $T_f = 333$ K the main relaxation process of polycarbonate are well outside the frequency range of our measurements, specifically the α relaxation frequency is smaller than 10^{-10} Hz and the β relaxation frequency is larger than 10^6 Hz. Thus we are testing a frequency range which is far away from the two relaxation frequencies. In fig. 1(a) and (b), we plot the measured values of R and C as a function of f at T_i and at T_f for $t_w \geq 200$ s. We see that with lowering temperature R increases and C decreases. At T_f aging is small and extremely slow. Thus for $t_w > 200$ s, the impedance can be considered constant without affecting our results. From the data plotted in fig. 1(a) and (b), one finds that $R = 10^{10}(1 \pm 0.05)f^{-0.95 \pm 0.01} \Omega$ and $C = (21.5 \pm 0.05) \text{ nF}$. In fig. 1(a) we also plot the total resistance at the amplifier input which is the parallel of the capacitor impedance with R_i . We see that at T_f the input impedance of the amplifier is negligible for $f > 10$ Hz, whereas it has to be taken into account at slower frequencies.

Figure 2(a) represents the evolution of $S_V(f, t_w)$ after a quench. Each spectrum is obtained as an average in a time window starting at t_w . The time window increases with t_w so as to reduce errors for large t_w . Then the results of 7 quenches have been averaged. At longest time ($t_w = 1$ day) the equilibrium FDT prediction (continuous line) is quite well satisfied. FDT is strongly violated for all frequencies at short times. Then high frequencies relax on the FDT, but there is a persistence of the violation for lower frequencies. The amount of the violation




Fig. 2 – (a) Noise power spectral density $S_V(f, t_w)$ measured at $T_f = 333$ K and different t_w . The spectra are the average over seven quenches. The continuous line is the FDT prediction. Dashed lines are the fit obtained using eqs. (4) and (5) (see the text for details). (b) Effective temperature *vs.* frequency at $T_f = 333$ K for different aging times: $\triangleleft t_w = 200$ s, $* t_w = 260$ s, $\bullet t_w = 2580$ s, $\times t_w = 6542$ s, $\circ t_w = 1$ day. The continuous lines are the fits obtained using eq. (5). The horizontal straight line is the FDT prediction. The dot-dashed line corresponds to the limit where the FDT violation can be detected. In the inset the frequency $f_0(t_w)$, defined in eq. (5), is plotted as a function of t_w . The continuous line is not a fit, but corresponds to $f_0(t_w) \propto 1/t_w$.

can be estimated by the best fit of $T_{\text{eff}}(f, t_w)$ in eq. (4), where all other parameters are known. We start at very large t_w when the system is relaxed and $T_{\text{eff}} = T$ for all frequencies. Inserting the values in eq. (4) and using the S_V measured at $t_w = 1$ day, we find $T_{\text{eff}} \simeq 333$ K, within error bars for all frequencies (see fig. 2(b)). At short t_w , data show that $T_{\text{eff}}(f, t_w) \simeq T_f$ for f larger than a cut-off frequency $f_0(t_w)$ which is a function of t_w . In contrast, for $f < f_0(t_w)$, $T_{\text{eff}}(f, t_w) \propto f^{-A(t_w)}$, with $A(t_w) \simeq 1$. This frequency dependence of $T_{\text{eff}}(f, t_w)$ is quite well approximated by

$$T_{\text{eff}}(f, t_w) = T_f \left[1 + \left(\frac{f}{f_0(t_w)} \right)^{-A(t_w)} \right], \quad (5)$$

where $A(t_w)$ and $f_0(t_w)$ are the fitting parameters. We find that $1 < A(t_w) < 1.2$ for all the data set. Furthermore, for $t_w \geq 250$ s, it is enough to keep $A(t_w) = 1.2$ to fit the data within error bars. For $t_w < 250$ s, we fixed $A(t) = 1$. Thus the only free parameter in eq. (5) is $f_0(t_w)$. The continuous lines in fig. 2(a) are the best fits of S_V found inserting eq. (5) in eq. (4). In fig. 2(b) we plot the estimated $T_{\text{eff}}(f, t_w)$ as a function of frequency at different t_w . Just after the quench, $T_{\text{eff}}(f, t_w)$ is much larger than T_f in all the frequency interval. High frequencies rapidly decay towards the FDT prediction, whereas at the smallest frequencies $T_{\text{eff}} \simeq 10^5$ K. Moreover, low frequencies decay more slowly than high frequencies and the evolution of $T_{\text{eff}}(f, t_w)$ towards equilibrium is very slow. From the data of fig. 2(b) and eq. (5), it is easy to see that $T_{\text{eff}}(f, t_w)$ can be superposed onto a master curve by plotting them as a function of $f/f_0(t_w)$. The function $f_0(t_w)$ is a decreasing function of t_w , but the dependence is not a simple one, as can be seen in the inset of fig. 2(b). The continuous straight line is not a fit, it represents $f_0(t_w) \propto 1.0/t_w$ which seems a reasonable approximation for these data. For $t_w > 10^4$ s, we find that $f_0 < 1$ Hz. Thus we cannot follow the evolution of T_{eff} anymore because the contribution of the experimental noise on S_V is too big, as is shown in fig. 2(b) by the increasing of the error bars for $t_w = 1$ day and $f < 0.1$ Hz.




Fig. 3 – Typical noise signal of polycarbonate measured at $1500\text{ s} < t_w < 1900\text{ s}$ (a) and $t_w > 75000\text{ s}$ (b).

Before discussing these experimental results, we want to compare them to the single-frequency experiment performed on glycerol [11]. In this experiment, T_{eff} has been measured only at 7 Hz and nothing can be said on the dependence of T_{eff} on frequency. This is a crucial point in order to compare the observed dynamics to that of models [4] and to see whether there is a connection between T_{eff} and the concept of fictive temperature (see the discussion in ref. [4]). The strong frequency dependence of T_{eff} suggests that such a comparison will make sense only for $f \rightarrow 0$. Therefore, it would be interesting to check whether at shorter times and at lower frequencies large T_{eff} could be observed in glycerol too.

To compare with theoretical predictions [2,4] and recent spin glass experiment [13], we may plot the integrated response $R(t, t_w)$ as a function of the correlation $C(t, t_w)$. The latter is obtained by inserting the measured $T_{\text{eff}}(f, t_w)$ in eq. (3) and Fourier-transforming it. $R(t, t_w)$ can be computed by Fourier-transforming $\text{Real}[Z(f, t_w)]$. FDR now takes the form [4]

$$-C(t, t_w) + C(t_w, t_w) = K_B T_{\text{eff}}(t, t_w) R(t, t_w). \quad (6)$$

The study of the correlations functions will be the object of a longer reports [14]. Here we want only to stress that the self-similarity of T_{eff} for $t_w > 300\text{ s}$ (see eq. (5)) implies that also $C(t_w, t)$ can be scaled onto a single master curve by plotting $C(t_w, t)$ as a function $(t - t_w)/t_0(t_w)$, where $t_0(t_w)$ is an increasing function of t_w : approximately $t_0(t_w) \propto 1/f_0(t_w)$ for $t_w > 300\text{ s}$. The self-similarity of correlation functions, found on our dielectric data, is a characteristic of the universal picture of aging [3–5,15], which has also been observed in spin glass experiment [13] and in the structure function of the dynamic light scattering of colloidal gels [16]. Thus, our results show that this picture of aging applies also to the dielectric noise of a polymer. Furthermore, the study of $R(t, t_w)$ as a function $(-C(t, t_w) + C(t_w, t_w))/K_B$ confirms the spectral analysis of fig. 2, that is T_{eff} is huge for long $(t - t_w)$. This result is quite different to what has been observed in recent experiments on spin glasses where $T_{\text{eff}} \simeq 5T_g$ has been measured [13].

A large T_{eff} is not specific to our system, but it has been observed in domain growth models [4,8] and in models controlled by activation processes [3,17–19]. The question is whether these models may have some connections with our observations. In order to understand the origin of such large deviations in our experiment, we have analyzed the noise signal. We find that the signal is characterized by large intermittent events which produce




Fig. 4 – Typical PDF of the noise signal of polycarbonate measured at various t_w .

low-frequency spectra proportional to $f^{-\alpha}$ with $\alpha \simeq 2$. Two typical signals recorded at $1500\text{s} < t_w < 1900\text{s}$ and $t_w > 75000\text{s}$ are plotted in fig. 3. We clearly see that in the signal recorded at $1500\text{s} < t_w < 1900\text{s}$ there are very large bursts which are on the origin of the frequency spectra previously. In contrast, in the signal (fig. 3(b)), which was recorded at $t_w > 75000\text{s}$ when FDT is not violated, the bursts are totally disappeared. It is interesting to notice that this kind of dynamics could be a common feature of several aging systems (see also ref. [20]). Indeed intermittency has also been observed in dielectric local measurements of polymers [21] and in the diffusing wave spectroscopy measurements in gels [22].

To further characterize the observed dynamics, we have computed the probability density function (PDF) of the signals, which is plotted in fig. 4(a) for different t_w . We clearly see that the PDF, measured at small t_w , has very high tails which become smaller and smaller at large t_w . Finally, the Gaussian profiles is recovered after 24 h. In a more quantitative way we find that the Kurtosis Ku (which is 0 for a Gaussian) of the distribution is a decreasing function of time which can be roughly approximated by $Ku = (6 \pm 1)(t_w/1000)^{-(0.55 \pm 0.05)}$. The time interval τ between two successive pulses is power law distributed. In order to study the distribution $P(\tau, t_w)$ of τ , we have first selected the signal fluctuations with amplitude larger than a fixed threshold, which has been chosen between 3 and 4 standard deviations of the equilibrium noise, *i.e.* the noise predicted by FDT. We have then measured the time intervals τ between two successive large fluctuations. The PDF $P(\tau, t_w)$ computed for $t_w < 20\text{min}$ and for $20\text{min} < t_w < 3\text{h}$ is plotted in fig. 4(b). We clearly see that $P(\tau, t_w)$ is a power law, specifically $P(\tau) \propto \frac{1}{\tau^{1+\mu}}$ with $\mu \simeq 0.4 \pm 0.1$. This result agrees with one of the predictions of the trap model [17], which presents non-trivial violation of FDT associated to an intermittent dynamics. In the trap model τ is a power-law-distributed quantity with an exponent $1 + \mu$ that, in the glass phase, is smaller than 2. However, there are important differences between the dynamics of our system and that of the trap model. Indeed in this model one finds short and large τ for any t_w which is in contrast with our system because the probability of finding short τ seems to decrease as a function of t_w . But this effect could be a consequence of the imposed threshold. It seems that there is no correlation between the τ and the amplitude of the associated bursts. Finally, the maximum distance τ_{max} between two successive pulses grows as a function of t_w logarithmically, that is $\tau_{\text{max}} = [10 + 152 \log(t_w/300)]\text{s}$ for $t_w > 300\text{s}$. This slow relaxation of the number of events per unit time shows that the intermittency is related to aging.

In conclusion, we have observed a large violation of FDT in the dielectric thermal noise of an aging polymer glass. Such a large violation is produced by rare events of high amplitude. The important question is now to understand the physical origin of these big events in the electrical thermal noise of the sample. A possibility is the triboelectricity produced by the aging-induced stress relaxation in the sample. Mechanical and acoustical measurements performed in parallel with dielectric measurements could clarify this problem. Work is in progress.

* * *

We acknowledge useful discussions with L. BELLON, L. CUGLIANDOLO and J. P. BOUCHAUD. We thank P. METZ and F. VITTOZ for technical support. This work has been partially supported by the Région Rhône-Alpes contract “Programme Thématique: Vieillissement des matériaux amorphes”.

REFERENCES

- [1] STRUIK L. C., *Physical Aging in Amorphous Polymers and Other Materials* (Elsevier, Amsterdam) 1978.
- [2] CUGLIANDOLO L. and KURCHAN J., *Phys. Rev. Lett.*, **71** (1993) 173.
- [3] BOUCHAUD J. P., CUGLIANDOLO L. F., KURCHAN J. and MÉZARD M., in *Spin Glasses and Random Fields*, edited by YOUNG A. P. (World Scientific, Singapore) 1998.
- [4] CUGLIANDOLO L., KURCHAN J. and PELITI L., *Phys. Rev. E*, **55** (1997) 3898.
- [5] KOB W. and BARRAT J. L., *Europhys. Lett.*, **46** (1999) 637; *Phys. Rev. Lett.*, **78** (1997) 4581.
- [6] PARISI G., *Phys. Rev. Lett.*, **79** (1997) 3660.
- [7] BERTHIER L., BARRAT J. L. and KURCHAN J., *Phys. Rev. E*, **61** (2000) 5464.
- [8] BARRAT A., *Phys. Rev. E*, **57** (1998) 3629.
- [9] SELKITO M., *Eur. Phys. J. B*, **4** (1998) 135.
- [10] MARINARI E., PARISI G., RICCI-TERSENGHI F. and RUIZ-LORENZO J. J., *J. Phys. A*, **31** (1998) 2611.
- [11] GRIGERA T. S. and ISRAELOFF N., *Phys. Rev. Lett.*, **83** (1999) 5038.
- [12] BELLON L., CILIBERTO S. and LAROCHE C., *Europhys. Lett.*, **53** (2001) 511.
- [13] HERRISSON D. and OCIO M., *Phys. Rev. Lett.*, **88** (2002) 257702.
- [14] BUISSON L., BELLON L. and CILIBERTO S., to be published in *J. Phys. Condens. Matter*.
- [15] BERTHIER L. and BOUCHAUD J. P., cond-mat/0202069v1.
- [16] CIPELLETTI L., MANLEY S., BALL R. C. and WEITZ D. A., *Phys. Rev. Lett.*, **84** (2000) 2275.
- [17] BOUCHAUD J. P. and DEAN D. S., *J. Phys. I*, **5** (1995) 265; BERTIN E. and BOUCHAUD J. P., cond-mat/0112187.
- [18] FIELDING S. and SOLLICH P., *Phys. Rev. Lett.*, **88** (2002) 50603-1.
- [19] PEREZ-MADRID A., REGUERA D. and RUBI J. M., *Origin of the Violation of the Fluctuation-Dissipation Theorem in Systems with Activated Dynamics*, cond-mat/0210089.
- [20] CUGLIANDOLO L., *Heterogeneity and local fluctuations in glassy systems*, preprint 2003.
- [21] VIDAL RUSSEL E. and ISRAELOFF N. E., *Nature*, **408** (2000) 695.
- [22] CIPELLETTI L. *et al.*, to be published in *J. Phys. Condens. Matter* (2003).