


NASA TECH BRIEF



NASA Tech Briefs are issued to summarize specific innovations derived from the U. S. space program and to encourage their commercial application. Copies are available to the public from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

Corrosion of Metal Samples Rapidly Measured



50x MAGNIFICATION

The problem:

To devise a method for accurately and rapidly measuring the extent of corrosion of a large number of metal samples that have been exposed to controlled environments.

The solution:

A method of microexamination of wire samples of the metal before and after exposure to a controlled corrosive environment.

How it's done:

Cross sections of the wire samples are microexamined prior to exposure to the corrosive environment, in order to establish a reference. After exposure, the wires are embedded in a quick-curing clear plastic. The plastic matrix (with the embedded wires) is then cut into suitable lengths, leaving the ends of the wires flush with the plastic surface. Micromerements on the ends of the wires indicate the amount of corrosion penetration that has occurred.

(continued overleaf)

Note:

Inquiries concerning this innovation may be directed to:

Technology Utilization Officer
AEC-NASA Space Nuclear Propulsion
Office
U.S. Atomic Energy Commission
Washington, D.C., 20545
Reference: B66-10140

Patent status:

No patent action is contemplated by NASA.

Source: C. E. Maskell
of the Aerojet-General Corporation
under contract to
AEC-NASA Space Nuclear Propulsion Office
(NU-0041)