November 1966





# **AEC-NASA TECH BRIEF**



AEC-NASA Tech Briefs describe innovations resulting from the research and development program of the U.S. AEC or from AEC-NASA interagency efforts. They are issued to encourage commercial application. Tech Briefs are published by NASA and may be purchased, at 15 cents each, from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

# Crucible Cast from Beryllium Oxide and Refractory Cement is Impervious to Flux and Molten Metal

### The problem:

To cast a large crucible which will not deteriorate in the presence of fused salt-molten metal mixtures such as uranium-magnesium-zinc-halide salt systems. Large vessels made from pure BeO cannot be cast and fired because the BeO lacks strength before curing.

#### The solution:

Cast a large crucible from a mixture of a beryllium oxide aggregate and hydraulic refractory cement, and coat the vessel with an impervious refractory oxide. The cement gives high precure strength to the structure, and the oxide coating increases the crucible's resistance to fused salt and molten metal.

#### How it's done:

A mixture comprising 85%-93% by dry weight of BeO and 7%-15% hydraulic refractory cement is cast in the desired vessel shape and fired at 1200° F. The refractory cement, which contains 3 or 4 of the components alumina, magnesia, baria, strontia, or calcia, forms eutectic bonds with the BeO when fired at this temperature. These cement components are inert in the fused salt-molten metal environment. The cast and fired crucible has a 10%-20% porosity which is desirable for thermal shock resistance.

After the initial firing of the vessel, a coating of refractory oxides is applied to the vessel inner surfaces and fired to form eutectic phases with the BeO.

Two coating compositions found effective with BeO and resistant to attack by the fused salt and molten metal contain the following compounds, in percentage by weight:

	Coating #1	Coating #2
$\mathrm{Al}_2\mathrm{O}_3$	28%	55%
BeO	27.5%	
MgO	44.5%	
CaO		35%
SrO		10%

Large, impervious vessels with thick walls and high impact resistance, made of coarse economic grades of BeO, can be cast effectively by this method.

#### Notes:

- 1. Al<sub>2</sub>O<sub>3</sub> appears to be an essential component in the coating material.
- 2. Vessels cast by this process can be used in the flux reduction of oxides of thorium and uranium.
- 3. Additional information concerning this innovation is given in U.S. Patent No. 3,150,281, available from the U.S. Patent Office. Inquiries may also be directed to:

Office of Industrial Cooperation Argonne National Laboratory 9700 S. Cass Avenue Argonne, Illinois 60439 Reference: B66-10527

(continued overleaf)

This document was prepared under the sponsorship of the Atomic Energy Commission and/or the National Aeronautics and Space Administration. Neither the United States Government nor any person acting on behalf of the United States Government assumes any

liability resulting from the use of the information contained in this document, or warrants that the use of any information, apparatus, method, or process disclosed in this document may not infringe privately owned rights.

## Patent status:

Inquiries about obtaining rights for commercial use of this innovation may be made to:

Mr. George H. Lee, Chief Chicago Patent Group U.S. Atomic Energy Commission Chicago Operations Office 9800 S. Cass Avenue Argonne, Illinois 60439

Source: Z. D. Jastrzebski Chemical Engineering Division (ARG-22)