




AEC-NASA TECH BRIEF



AEC-NASA Tech Briefs describe innovations resulting from the research and development program of the U.S. AEC or from AEC-NASA interagency efforts. They are issued to encourage commercial application. Tech Briefs are published by NASA and may be purchased, at 15 cents each, from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

Plasma Jet Electrode Has Longer Operating Life



The problem:

Pure tungsten electrodes (cathodes) used in plasma jet generators have an average operating life of only 15 minutes at the extremely high heat fluxes and arc temperatures encountered.

The solution:

A water-cooled, silver-infiltrated tungsten electrode which has twice the lifetime of the pure tungsten electrode.

How it's done:

The assembly consists of the silver-infiltrated tungsten electrode core, a stainless steel retainer, and an O-ring sealed copper cap which holds the electrode core in the retainer. Annular passages are provided for water circulation to cool the electrode and thereby reduce the erosion rate. The high heat conductivity of the silver-infiltrated tungsten core ensures excellent heat transfer from the arc to the coolant. Pyramids on the surface of the electrode core reduce thermal stresses by concentrating the arc electrical energy on a small contact area.

Notes:

1. Replacement costs for this electrode are considerably below those of previous devices.
2. Inquiries concerning this invention may be directed to:

Technology Utilization Officer
 AEC-NASA Space Nuclear Propulsion Office
 U.S. Atomic Energy Commission
 Washington, D.C. 20545
 Reference: B67-10024

Patent status:

Inquiries about obtaining rights for the commercial use of this invention may be made to NASA, Code GP, Washington, D.C. 20546.

Source: Charles M. Gracey
 of Aerojet General Corp.
 under contract to
 AEC-NASA Space Nuclear Propulsion Office
 (NU-0098)

Category 02