

April 1967

Brief 67-10069

# NASA TECH BRIEF



NASA Tech Briefs are issued to summarize specific innovations derived from the U.S. space program, to encourage their commercial application. Copies are available to the public at 15 cents each from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

## Controlled Ferrite Content Improves Weldability of Corrosion-Resistant Steel

### The problem:

Experience has shown that 347 CRES has a tendency to develop cracks during welding, both in the fusion zone and the adjacent heat affected zone. This fault is most prevalent in materials containing less than 4% calculated ferrite. Welding rod with controlled ferrite content is available but has no effect where joints are made without filler metal.

### The solution:

An otherwise standard formulation of corrosion-resistant steel that incorporates additional restrictions on chemical composition to ensure a calculated ferrite content of from 5% to 9% in welded material. The equations restricting the chemical composition are based on the Schaeffler constitution diagram for stainless steel weld metal.

### Note:

Inquiries concerning this innovation may be directed to:

Technology Utilization Officer  
Marshall Space Flight Center  
Huntsville, Alabama 35812  
Reference: B67-10069

### Patent status:

No patent action is contemplated by NASA.

Source: Craig O. Malin  
of North American Aviation, Inc.  
under contract to  
Marshall Space Flight Center

(M-FS-568)

Category 03