## NASA TECH BRIEF

NASA Tech Briefs are issued to summarize specific innovations derived from the U.S. space program, to encourage their commercial application. Copies are available to the public at 15 cents each from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

## Evaluation of Lubricants for Ball Bearings at High Temperatures

Ball bearings fabricated from high-temperature alloys (Stellite 6B balls and races and Reńe 41 cages) were operated in air at temperatures up to 1500°F. The adherent oxides which formed on these alloys prevented bearing seizure and high wear on otherwise unlubricated bearings. However, bearing torque was high and erratic.

In previous basic studies of high temperature lubricants, new solid lubricants which had low friction coefficients and effective antiwear characteristics at elevated temperatures (1000°-1900°F) were formulated.

A test program was therefore begun to determine the feasibility of lubricating ball bearings with the solid lubricants which had appeared promising in the basic studies.

The solid lubricants were calcium fluoride-barium fluoride coatings which were applied to the bearing cages, or, in some cases, the cages were fabricated from self-lubricating composites consisting of porous, sintered nickel-chromium alloy impregnated with a calcium fluoride-barium fluoride eutectic filler. All tests were conducted in air.

The bearings (20-mm bore) were of the angular contact type. Under a 30-pound thrust load, which produced a Hertz stress of 93,000 psi at 1200°F, fluoride-lubricated bearings ran at 5000 rpm without failing for as long as 700 hours at 1200°F and 70 hours at 1500°F. The shortest lives under these conditions were of the order of 20 to 50 hours. Wear rates were very low until just prior to the onset of bearing failure.

## Notes:

- 1. The tests demonstrated that calcium fluoridebarium fluoride as coatings on bearing cages or as fillers in porous bearing cages could lubricate bearings successfully for operations in air at temperatures of 1200° to 1500° F.
- 2. Documentation is available from:

Clearinghouse for Federal Scientific and Technical Information Springfield, Virginia 22151 Price \$3.00 Reference: B69-10025

3. Technical questions may be directed to: Technology Utilization Officer Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135

## Patent status:

No patent action is contemplated by NASA.

Source: H. E. Sliney and R. L. Johnson (LEW-10578)

Category 03

This document was prepared under the sponsorship of the National Aeronautics and Space Administration. Neither the United States Government nor any person acting on behalf of the United States Government assumes any liability resulting from the use of the information contained in this document, or warrants that such use will be free from privately owned rights.



