

July 1969

Brief 69-10227

NASA TECH BRIEF



NASA Tech Briefs are issued to summarize specific innovations derived from the U.S. space program, to encourage their commercial application. Copies are available to the public at 15 cents each from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

Electrochemical Sintering Process for Producing Electrodes from Cadmium Felt and a Nickel or Silver Grid

Commercially fabricated cadmium felt electrodes are now available for testing and evaluation. The electrochemical sintering process for producing these electrodes is of interest to battery manufacturers and the electrochemical industry.

Cadmium felt is made by drawing off the solvent from a slurry of fine cadmium fibers by means of suction filtration. The layer of intertwined fibers on the fiber bed is then pressed to the desired thickness. Thermal sintering of the felt is impossible because heating at temperatures below the low melting point of cadmium does not result in permeation at contact points.

Two pieces of cadmium felt are sandwiched around a nickel screen or silver expanded metal grid, held together by mold compression, and electrochemically sintered by being put through several charge and discharge cycles at low current density (0.5–1.0 ma/cm² approximately). The pieces of felt grow together through the grid. A network of conductive current paths forms, gradually beginning at the grid and working out into the felt to more and more of active cad-

mium material. This causes the ampere-hour capacity of the electrode to increase. A strong finished product results.

The use of cadmium felt is a novel method of affixing active cadmium to electrode substrates. This felt serves a double function both as the active material and as the substrate. Advantages of the electrode production process are ease of quality control and speed.

Note:

No further documentation is available. Inquiries may be directed to:

Technology Utilization Officer
Goddard Space Flight Center
Greenbelt, Maryland 20771
Reference: B69-10227

Patent status:

No patent action is contemplated by NASA.

Source: T. J. Hennigan, N. Potter, W. Webster,
E. Colston, and J. T. Stemmler
Goddard Space Flight Center
(GSC-10764)

Category 05