

February 1970

Brief 70-10153

NASA TECH BRIEF



NASA Tech Briefs are issued to summarize specific innovations derived from the U.S. space program, to encourage their commercial application. Copies are available to the public at 15 cents each from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

Improved Alkaline Electrochemical Cell

The problem:

In the conventional rechargeable alkaline electrochemical cell employing a negative zinc electrode, the zinc oxide produced during discharge dissolves in the electrolyte to form zincate ions. During the charging cycle, zinc is plated out from the zincate ions in the form of dendrites, which can cause shorting, inconsistent performance, and early failure of the cell.

The solution:

Addition of lead ions to the electrolyte to suppress zinc dendrite formation during the charging cycle.

How it's done:

A soluble lead salt (e.g., lead nitrate or acetate) can be added directly to the electrolyte to introduce the lead ions, or metallic lead can be incorporated in the zinc electrode and allowed to dissolve (ionize) into the electrolyte. The concentration of lead dissolved in the electrolyte should be in the range of 0.2 to 2.0 grams per liter. Less lead is ineffective in preventing dendrite

growth, and more lead results in a mass of nonadherent dendrites containing lead.

Note:

No additional documentation is available. Specific questions, however, may be directed to:

Technology Utilization Officer

Goddard Space Flight Center

Greenbelt, Maryland 20771

Reference: B70-10153

Patent status:

Inquiries about obtaining rights for the commercial use of this invention may be made to NASA, Code GP, Washington, D.C. 20546.

Source: Harry G. Oswin, James E. Oxley, and

Charles W. Fleischmann of

Leesona Moos Laboratory

under contract to

Goddard Space Flight Center

(GSC-10792)

Category 01