

July 1971

Brief 71-10225

NASA TECH BRIEF

Marshall Space Flight Center




NASA Tech Briefs announce new technology derived from the U.S. space program. They are issued to encourage commercial application. Tech Briefs are available on a subscription basis from the National Technical Information Service, Springfield, Virginia 22151. Requests for individual copies or questions relating to the Tech Brief program may be directed to the Technology Utilization Office, NASA, Code KT, Washington, D.C. 20546.

Strain Gage Performance Above 1033 K

A study was conducted to determine the behavioral characteristics of strain gages at temperatures above 1033 K (1400° F). The study provides a compen-

After the thermal drift study was completed, the strain gages were mounted, as shown in the figure, on a constant strain beam of Inconel 750. The gage



dium of test methods and results which may be used in evaluating the performance of strain gages used in high temperature environments.

The tests were performed on strain gages developed through recent research on alloys that are stable to 1033 K, and through improvements in manufacturing and fabrication techniques. The gages were spotwelded to a section of turbine disk alloy and heated in an oven to the temperature desired. Two measurements were taken at each temperature, and the resistance to ground and the drift rate were observed over a 20 minute period.

factor variation as a function of temperature was then determined. This variation ranged from zero at room temperature (297 K) to 14.5% at 1083 K.

Note:

Requests for further information may be directed to:

Technology Utilization Officer
Code A&TS-TU
Marshall Space Flight Center
Huntsville, Alabama 35812
Reference: TSP71-10225

(continued overleaf)

Patent status:

No patent action is contemplated by NASA.

Source: D. W. Nichols of
North American Rockwell Corp.
under contract to
Marshall Space Flight Center
(MFS-18831)