NASA TECH BRIEF

Marshall Space Flight Center



NASA Tech Briefs announce new technology derived from the U.S. space program. They are issued to encourage commercial application. Tech Briefs are available on a subscription basis from the National Technical Information Service, Springfield, Virginia 22151. Requests for individual copies or questions relating to the Tech Brief program may be directed to the Technology Utilization Office, NASA, Code KT, Washington, D.C. 20546.

A New Intermediate for the Production of Flexible Stable Polymers

The problem:

A number of polyimides have been prepared and studied for use as high-temperature, solvent-resistant sealants. Some of the most promising candidates have included aryl-fluorocarbon groups to increase the solvent resistance of the polymer. Dianhydride intermediates of the form

have been used in the synthesis, but the resulting polymers are insufficiently flexible for use as sealants.

The solution:

A method of incorporating ether linkages into the perfluoroalkylene segment of dianhydride (I) above yields an intermediate that may be used in the synthesis of more stable polyimides having increased flexibility.

How it's done:

The synthesis yields ether-linked aryl tetracarboxy dianhydrides of the structure:

The synthesis steps are outlined below:

$$\begin{array}{c}
O & O \\
\parallel & \parallel \\
CF_3 & CF_2
\end{array}$$

$$OH + C1C (CF_2)_3CC1 \longrightarrow$$

$$CF_3 \longrightarrow OC (CF_2)_3 CO \longrightarrow CF_3 \longrightarrow SF_4$$

$$CF_3 \longrightarrow CF_3 \longrightarrow CF_3$$

$$\begin{array}{c} \text{CF}_3 \\ \text{CF}_3 \end{array} \begin{array}{c} \text{O (CF}_2)_5 \text{ O} \\ \text{CF}_3 \end{array} \begin{array}{c} \frac{\text{H}_2\text{SO}_4/\text{C1SO}_3\text{H}}{\text{C}} \end{array}$$

The acid chloride-hydroxyl group reaction and the SF_4 fluoridation are fairly straightforward. However, the preferential hydrolysis of the aryl- CF_3 to COOH without attack on the aryl- OCF_2 linkage, the essential feature of the synthesis, has not previously appeared in the literature.

The effect of the ether linkage on polymides incorporating structure II may be seen in the change in the glass transition temperature. Polyimides with structure I have transition temperatures in the range of 60 to 65° C; those with structure II in the range of 40 to 45° C.

(continued overleaf)

Note:

No further information is available. Specific questions, however, may be directed to:

Technology Utilization Officer Marshall Space Flight Center

Code A&PS-TU

Marshall Space Flight Center, Alabama 35812

Reference: B73-10080

Patent status:

Inquiries concerning rights for the commercial use of this invention should be addressed to:

Patent Counsel Marshall Space Flight Center Code A&PS-PAT Marshall Space Flight Center, Alabama 35812

> Source: J. A. Webster of Monsanto Research Corp. under contract to Marshall Space Flight Center (MFS-22355)