

Experimental Investigation of the Shuttle Transportation System Composite Overwrapped Pressure Vessels for Stress Rupture Life

Nathanael Greene, NASA WSTF

Regor Saulsberry, NASA WSTF

Tommy Yoder, NTEC WSTF

Brad Forsyth, NTEC WSTF

Marlene Carrillo, NTEC WSTF

John Thesken, OAI GRC

NASA White Sands Test Facility



Outline

- Introduction
- Purpose for Testing
- NASA WSTF COPV Test Program
- NASA WSTF Test Facilities
- COPV Impact Study
- Fluids Compatibility Testing
- Stress Rupture Testing
- COPV Lifing
- Conclusions



Introduction

- Composite overwrapped pressure vessel (COPV).
 - Typically a metallic liner overwrapped with a fiber epoxy matrix
- Weight advantage: Kevlar COPVs saved 752 lb in pressurized storage over an all metal design.



wsftf0106e00289



wsftf0106e00088



wsftf1004e9252

8/28/2006




Purpose for Testing

- Safe use of COPVs
- Two failure modes for a COPV
- Leak Before Burst (LBB) more benign failure mode
- Burst Before Leak (BBL) catastrophic failure mode with pressure wave and fragments
 - Stress rupture: sudden failure of the overwrap BBL
 - Composite Damage: impact or cuts can cause BBL
 - Liner Flaw: dump of load into composite can cause BBL
 - Manufacturing: defects can cause BBL




NASA-WSTF COPV Test Program



COPV Impact Study



- Understand COPV impact sensitivity
- Establish VDT, CIE
- Data to support impact control plan



8/28/2006



Fluids Compatibility Testing

- Effect of fluids on COPV strength¹
- MMH, NTO, LN₂, hydrazine, and unsymmetrical dimethylhydrazine
- Carbon not sensitive to fluids
- Kevlar very sensitive to NTO




wstf0396-0453



wstf0596-1318



wstf0496-1109



wstf0496-1111

8/28/2006

¹ Details of testing is in "Composite Overwrapped Pressure Vessels NASA/TP-2002-210769




Stress Rupture Testing

- Carbon and PBO Stress Rupture Test
- Thin overwraps similar to propellant tanks



wstf0403-0562




wstf0403-0559



Stress Rupture Testing

- Flight-qualified configurations
- COPVs in test for 9 years
- Nine impact-damaged COPVs
- Limited statistical population

Size (in)	Undamaged COPV Fiber Stress (% Ult)
9 Ø	62
6.6 Ø X 20 L	56
13 Ø X 25 L	58
10.25 Ø	60






Stress Rupture, Cycle and Burst Testing

- Thermal control for constant vessel pressure
- Backup power for data acquisition and thermal control
- Flight qualified Kevlar® COPV testing
 - Strain, FOBG, Volume Measurement, DIC, Eddie Current, AE, Raman Spectroscopy, Belly Bands and NDE¹



wstf1005e08438



wstf1105e08998




wstf0506e02679



COPV Lifting

- Establish the amount of liner load sharing¹
 - Evaluate through the composite compression
 - Liner residual stress after yield point
 - Place time at pressure and stress ratio into model²



- ¹ Details of how stress ratio calculation is in companion paper by Theksen
- ² Details of stress rupture lifing is given in a companion paper by Phoenix

8/28/2006



Conclusions

- COPVs are sensitive to composite damage and should have impact control plans
- Propellants and fuels exposure to carbon COPV composite does not immediately affect COPV burst strength
- Limited stress rupture test data for Carbon COPVs (difficulty in predicting stress rupture life)
- Testing to understand COPV mechanical response is important in estimating stress rupture life

Questions

