

drophilic property in addition to the antibacterial property.

Thermally conductive materials are fabricated and then treated to create the antibacterial and hydrophilic surface properties. The individual parts are assembled to create a condensing heat exchanger with antibacterial and hydrophilic surface properties and capillary geometry, which is capable of passive phase separation in a reduced gravity application.

The plasma processes for creating antibacterial and hydrophilic surface properties are suitable for applications where water is present on an exposed surface for an extended time, such that bacteria or biofilms could form, and where there is a need to manage the water on the sur-

face. The processes are also suitable for applications where only the hydrophilic property is needed. In particular, the processes are applicable to condensing heat exchangers (CHXs), which benefit from the antibacterial properties as well as the hydrophilic properties. Water condensing onto the control surfaces of the CHX will provide the moist conditions necessary for the growth of bacteria and the formation of biofilms. The antibacterial properties of the base layer (silver) will mitigate and prevent the growth of bacteria and formation of biofilms that would otherwise reduce the CHX performance. In addition, the hydrophilic properties reduce the water contact angle and prevent water droplets from bridging between control

surfaces. Overall, the hydrophilic properties reduce the pressure drop across the CHX.

This work was done by Chris Thomas and Yonghui Ma of Orbital Technologies Corporation, and Mark Weislogel for Johnson Space Center. Further information is contained in a TSP (see page 1).

In accordance with Public Law 96-517, the contractor has elected to retain title to this invention. Inquiries concerning rights for its commercial use should be addressed to:

*Orbital Technologies Corp.
1212 Fourier Drive
Madison, WI 53717*

Refer to MSC-24496-1/502-1, volume and number of this NASA Tech Briefs issue, and the page number.

Polyolefin-Based Aerogels

These aerogels can be used for thermal insulation and radiation shielding in apparel, aircraft, race car insulation, and military and recreation tents.

Lyndon B. Johnson Space Center, Houston, Texas

An organic polybutadiene (PB) rubber-based aerogel insulation material was developed that will provide superior thermal insulation and inherent radiation protection, exhibiting the flexibility, resiliency, toughness, and durability typical of the parent polymer, yet with the low density and superior insulation properties associated with the aerogels. The rubbery behaviors of the PB rubber-based aerogels are able to overcome the weak and brittle nature of conventional inorganic and organic aerogel insulation materials. Additionally, with higher content of hydrogen in their structure, the PB rubber aerogels will also provide inherently better radiation protection than those of inorganic and carbon aerogels. Since PB rubber aerogels also exhibit good hydrophobicity due to their hydrocarbon molecular structure, they will provide better performance reliability and durability as well as simpler, more economic, and environmentally friendly production over the conventional silica or other inorganic-based aerogels, which require chemical treatment to make them hydrophobic.

Inorganic aerogels such as silica aerogels demonstrate many unusual and useful properties. There are several strategies to overcoming the drawbacks associated with the weakness and brittleness of silica aerogels. Development of the flexible fiber-reinforced silica aerogel composite blanket has proven one prom-

ising approach, providing a conveniently fielded form factor that is relatively robust toward handling in industrial environments compared to silica aerogel monoliths. However, the flexible silica aerogel composites still have a brittle, dusty character that may be undesirable, or even intolerable, in certain applications. Although the cross-linked organic aerogels such as resorcinol-formaldehyde (RF), polyisocyanurate, and cellulose aerogels show very high impact strength, they are also very brittle with little elongation (i.e., less rubbery). Also, silica and carbon aerogels are less efficient radiation shielding materials due to their lower content of hydrogen element.

The present invention relates to maleinized polybutadiene (or polybutadiene adducted with maleic anhydride)-based aerogel monoliths and composites, and the methods for preparation. Hereafter, they are collectively referred to as polybutadiene aerogels. Specifically, the polybutadiene aerogels of the present invention are prepared by mixing a maleinized polybutadiene resin, a hardener containing a maleic anhydride reactive group, and a catalyst in a suitable solvent, and maintaining the mixture in a quiescent state for a sufficient period of time to form a polymeric gel. After aging at elevated temperatures for a period of time to provide uniformly stronger wet gels, the microporous maleinized polybu-

tadiene-based aerogel is then obtained by removing interstitial solvent by supercritical drying. The mesoporous maleinized polybutadiene-based aerogels contain an open-pore structure, which provides inherently hydrophobic, flexible, nearly unbreakable, less dusty aerogels with excellent thermal and physical properties. The materials can be used as thermal and acoustic insulation, radiation shielding, and vibration-damping materials.

The organic PB-based rubber aerogels are very flexible, no-dust, and hydrophobic organics that demonstrated the following ranges of typical properties: densities of 0.08 to 0.255 g/cm³, shrinkage factor (raerogel/rtarget) = 1.2 to 2.84, and thermal conductivity values of 20.0 to 35.0 mW/m-K.

This work was done by Je Kyun Lee and George Gould of Aspen Aerogels, Inc. for Johnson Space Center. Further information is contained in a TSP (see page 1).

In accordance with Public Law 96-517, the contractor has elected to retain title to this invention. Inquiries concerning rights for its commercial use should be addressed to:

*Aspen Aerogels, Inc.
30 Forbes Road, Building B
Northborough, MA 01532
Phone No.: (508) 691-1111
E-mail: info@aerogel.com*

Refer to MSC-24213-1, volume and number of this NASA Tech Briefs issue, and the page number.