

STRUCTURAL, OPTICAL AND MAGNETIC PROPERTIES OF SAMARIUM  
DOPED ZINC PHOSPHATE GLASSES EMBEDDED WITH NICKEL  
NANOPARTICLES

SITI AMLAH BINTI MOHAMAD AZMI

UNIVERSITI TEKNOLOGI MALAYSIA

STRUCTURAL, OPTICAL AND MAGNETIC PROPERTIES OF SAMARIUM  
DOPED ZINC PHOSPHATE GLASSES EMBEDDED WITH NICKEL  
NANOPARTICLES

SITI AMLAH BINTI MOHAMAD AZMI

A thesis submitted in fulfilment of the  
requirements for the award of the degree of  
Doctor of Philosophy (Physics)

Faculty of Science  
Universiti Teknologi Malaysia

AUGUST 2016

In the name of Allah, Most Gracious Most Merciful

All praise and thanks are due to Allah Almighty and  
peace and blessing be upon His Messenger

To my beloved parents, siblings and friends  
for their love and support

## ACKNOWLEDGEMENT

First and foremost, thanks to Allah SWT for giving me strength and opportunity to complete this study. I am heartily thankful to all my supervisors Prof Dr Md Rahim Sahar and Assoc. Prof. Dr. Ramli Arifin for their constant encouragement, supervision, supporting and guidance during my study. I would also to convey my deepest gratitude to all physics lecturers (UTM) especially to Assoc. Prof. Dr Sib Krishna Ghoshal, Assoc. Prof. Dr Karim Deraman Dr. Alam Saeed and Dr Amirruddin Shaari for the encouragement and immense knowledge during all these years.

I would also like to acknowledge the Ministry of Higher Education Malaysia for the scholarship under MyPHD program and all financial research support from UTM grants of Vote: 4L032, 4F319 and 05H45. My sincere thanks and appreciation extend to the laboratory assistants of Physics Department (UTM), Ibnu Sina Institute (UTM), Physics Department (UPM), Physics Department (UKM), School of Physics and Biology (USM) and who had helped me in many ways.

Deepest thanks and appreciation goes to my parents (Mohamad Azmi B. Nor and Mariyati Binti Mokhtar), family, and all my colleagues. I have been blessed with a friendly, cheerful and encouraging group of advance optical material research team members. Lastly, I offer my regards and blessings to all of those who supported me in any respect during the completion of this study.

## ABSTRACT

Two series of  $40\text{ZnO}-(60-x)\text{P}_2\text{O}_5-x\text{Sm}_2\text{O}_3$  and  $40\text{ZnO}-(59-y)\text{P}_2\text{O}_5-\text{Sm}_2\text{O}_3-y\text{NiO}$  glasses are prepared by melt-quenching technique with  $1.0 \leq x \leq 4.0$  mol% and  $0.5 \leq y \leq 2.0$  mol% respectively. The glass is characterized by X-Ray Diffractometer (XRD), Transmission Electron Microscope (TEM), High Resolution Transmission Electron Microscope (HRTEM), Fourier Transform Infrared (FTIR) spectrometer, Raman spectrometer, UV-Vis NIR spectrophotometer, Photoluminescence (PL) spectrometer, Vibrating Sample Magnetometer (VSM) and Electron Spin Resonance (ESR) spectrometer. The XRD pattern confirms the amorphous nature of the glass and the TEM image reveals the existence of nickel nanoparticles (Ni NPs) with average size  $\sim 8$  nm. Meanwhile, HRTEM reveals the lattice spacing of face centered cubic (FCC) structure of nickel is 0.35 nm at (100) plane. Four major IR absorption peaks are found to be at  $723\text{ cm}^{-1}$ ,  $916\text{ cm}^{-1}$ ,  $1081\text{ cm}^{-1}$  and  $1280\text{ cm}^{-1}$  corresponding to stretching vibration of symmetric (P-O-P), asymmetric (P-O-P), asymmetric (P-O $\cdot$ ) and asymmetric (P=O) respectively. Raman spectra display two significant peaks at  $708\text{ cm}^{-1}$  and  $1201\text{ cm}^{-1}$  attributed to the symmetric and asymmetric stretching vibrations of P-O-P, respectively. The Raman intensities for both peaks exhibit a rapid decrease with the increase of Ni NPs concentration. The absorption spectra of samarium ions consist of five bands attributed to absorption from the ground state  $^6\text{H}_{5/2}$  to the excited states  $^6\text{F}_{1/2}$ ,  $^6\text{F}_{3/2}$ ,  $^4\text{F}_{5/2}$ ,  $^4\text{F}_{7/2}$  and  $^6\text{F}_{9/2}$ . The surface plasmon resonance (SPR) peaks of Ni NPs are detected at 433 nm and 475 nm. Photoluminescence emission exhibits four peaks corresponding to  $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{5/2}$ ,  $^6\text{H}_{7/2}$ ,  $^6\text{H}_{9/2}$ , and  $^6\text{H}_{11/2}$  transitions. It is observed that all peaks experience significant quenching effect with increasing concentration of Ni NPs, suggesting that there is a strong energy transfer from excited samarium ions to the nickel ions. The glass magnetization and susceptibility in magnetic field up to 12 kOe at room temperature is found to be in the range of  $(0.11-2.02) \times 10^{-2}$  emu/g and  $(0.09-1.68) \times 10^{-6}$  emu/Oeg respectively. The obtained hysteresis curve and  $g$ -factor value of 1.99 to 2.34 indicate that the glass samples are superparamagnetic. It is concluded that samarium doped zinc phosphate glass embedded with nickel nanoparticles could be useful for magneto-optical and solid state devices.

## ABSTRAK

Dua siri kaca  $40\text{ZnO}-(60-x)\text{P}_2\text{O}_5-x\text{Sm}_2\text{O}_3$  dan  $40\text{ZnO}-(59-y)\text{P}_2\text{O}_5-\text{Sm}_2\text{O}_3-y\text{NiO}$  masing-masing dengan  $1.0 \leq x \leq 4.0$  mol% dan  $0.5 \leq y \leq 2.0$  mol% disediakan menggunakan teknik pelindapan leburan. Kaca tersebut dicirikan dengan pembelauan Sinar-X (XRD), Mikroskop Transmisi Elektron (TEM), Mikroskop Transmisi Elektron Beresolusi Tinggi (HRTEM), spektrometer Infra Merah Transformasi Fourier (FTIR), spektrometer Raman, spektrofotometer UV-Vis-NIR, spektrometer Fotoluminesen (PL), Magnetometer Getaran Sampel (VSM) dan spektrometer Resonans Putaran Elektron (ESR). Corak XRD mengesahkan sifat amorfus kaca tersebut dan imej TEM mendedahkan kewujudan zarah nano nikel (Ni NPs) dengan saiz purata  $\sim 8$  nm. Sementara itu, HRTEM mendedahkan jarak kekisi bagi struktur kubus berpusat muka (FCC) nikel ialah 0.35 nm pada satah (100). Empat puncak penyerapan utama IR ditemui pada  $723\text{ cm}^{-1}$ ,  $916\text{ cm}^{-1}$ ,  $1081\text{ cm}^{-1}$  dan  $1280\text{ cm}^{-1}$  masing-masing merujuk kepada getaran regangan bagi (P-O-P) simetri, (P-O-P) tak simetri, (P-O) tak simetri dan (P=O) tak simetri. Spektrum Raman memaparkan dua puncak yang ketara pada  $708\text{ cm}^{-1}$  dan  $1201\text{ cm}^{-1}$  yang masing-masing berpadanan dengan getaran regangan P-O-P simetri dan tak simetri. Keamatan kedua-dua puncak Raman tersebut mempamerkan penurunan yang mendadak dengan meningkatnya kepekatan Ni NPs. Spektrum penyerapan ion samarium terdiri daripada lima jalur yang berpadanan dengan penyerapan dari keadaan dasar  ${}^6\text{H}_{5/2}$  kepada keadaan teruja  ${}^6\text{F}_{1/2}$ ,  ${}^6\text{F}_{3/2}$ ,  ${}^4\text{F}_{5/2}$ ,  ${}^4\text{F}_{7/2}$  and  ${}^6\text{F}_{9/2}$ . Puncak resonans plasmon permukaan (SPR) bagi Ni NPs dicerap pada 433 nm dan 475 nm. Pancaran fotoluminesen memaparkan empat puncak yang berpadanan kepada peralihan  ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{5/2}$ ,  ${}^6\text{H}_{7/2}$ ,  ${}^6\text{H}_{9/2}$ , dan  ${}^6\text{H}_{11/2}$ . Diperhatikan bahawa semua puncak mengalami kesan penurunan dengan peningkatan kepekatan Ni NPs, yang mencadangkan bahawa berlakunya pemindahan tenaga yang kuat daripada ion samarium teruja kepada ion nikel. Kemagnetan dan kerentanan kaca dalam medan magnet sehingga 12 kOe di bawah suhu bilik ditemui masing-masing dalam julat  $(0.11-2.02) \times 10^{-2}$  emu/g dan  $(0.09-1.68) \times 10^{-6}$  emu/Oeg. Lengkok histerisis yang diperolehi dan nilai faktor-g antara 1.99 hingga 2.34 menandakan bahawa sampel kaca adalah superparamagnetik. Dapat disimpulkan bahawa kaca zink fosfat berdopkan samarium yang tertanam zarah nano nikel boleh digunakan sebagai peranti optik termagnet dan peranti keadaan pepejal.

## TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	<b>DECLARATION</b>	ii
	<b>DEDICATION</b>	iii
	<b>ACKNOWLEDGEMENTS</b>	iv
	<b>ABSTRACT</b>	v
	<b>ABSTRAK</b>	vi
	<b>CONTENTS</b>	vii
	<b>LIST OF TABLES</b>	xi
	<b>LIST OF FIGURES</b>	xiii
	<b>LIST OF SYMBOLS</b>	xviii
	<b>LIST OF ABBREVIATIONS</b>	xx
	<b>LIST OF APPENDICES</b>	xxii
<b>1</b>	<b>INTRODUCTION</b>	<b>1</b>
	1.1 Background of Study	1
	1.2 Problem Statement	5
	1.3 Objectives	6
	1.4 Scope of Study	7
	1.5 Significance of Study	7
	1.6 Organization of Study	8

<b>2</b>	<b>LITERATURE REVIEW</b>	<b>10</b>
2.1	Introduction	10
2.2	Phosphate Glass	10
2.3	Network Modifier of ZnO	13
2.4	Rare-earth (Samarium)	15
2.5	Structural Properties	18
2.5.1	X-Ray Diffraction (XRD)	19
2.5.2	Transmission Electron Microscopy (TEM)	20
2.5.3	Physical Properties of Phosphate Glass	23
2.6	Vibrational Spectroscopy	25
2.6.4	Fourier Transform Infra-Red (FTIR)	26
2.6.5	Raman Spectroscopy	27
2.7	Absorption Spectroscopy	29
2.7.1	Absorption and Energy Band Gap	29
2.7.3	Urbach Energy	32
2.7.4	Refractive Index	33
2.7.5	Bonding Characteristic	33
2.8	Photoluminescence (PL)	34
2.8.1	PL Conversion and Energy Diagram	35
2.6.1	Fluorescence Lifetime	37
2.9	Magnetic Properties	39
2.9.1	Magnetic Materials Classification	39
2.9.2	Electron Spin Resonance (ESR)	41
2.9.3	Magnetic Nanoparticles in Glasses	45
<b>3</b>	<b>METHODOLOGY</b>	<b>48</b>
3.1	Introduction	48
3.2	Samples preparation	48



3.3	Physical Properties	50
3.3.1	Density, Molar Volume and Ionic Packing Density	50
3.3.2	Molar Refractivity and Electronic Polarizability	51
3.3.3	Vickers Hardness	52
3.4	Sample Characterization	52
3.4.1	X-ray Diffraction (XRD)	52
3.4.2	Transmission Electron Microscopy (TEM)	53
3.4.3	Fourier Transform Infra-Red (FTIR)	55
3.4.4	Raman Spectroscopy	55
3.4.5	UV-Vis Spectroscopy	57
3.4.6	Photoluminescence Spectroscopy	57
3.4.7	Vibrating Sample Magnetometer (VSM)	58
3.4.8	Electron Spin Resonance (ESR)	60
3.5	Flow Charts of Sample Characterization	61
<b>4</b>	<b>RESULTS AND DISCUSSION</b>	<b>63</b>
4.1	Introduction	63
4.2	Glass Formation	63
4.3	Physical Properties	65
4.3.1	Density, Molar Volume and Ionic Packing Density	65
4.3.2	Molar Refractivity and Electronic Polarizability	68
4.3.3	Hardness Analysis	69
4.4	Glass Characterization	70
4.4.1	X-Ray Diffraction (XRD)	70
4.4.2	Image Analysis	71
4.4.3	FTIR Analysis	74

4.4.4	Raman Analysis	76
4.4.5	UV-Vis Analysis	79
4.4.5.1	Absorption Spectra	79
4.4.5.2	Absorption Properties	84
4.4.5.3	Bonding Properties	87
4.4.6	Luminescence Properties	88
4.5	Interpretation of Sm <sup>3+</sup> doped Glass due to Inclusion of Ni NPs	91
4.6	Magnetic Properties	93
4.6.1	Vibrating Sample Magnetometer Analysis	94
4.6.2	Electron Spin Resonance (ESR)	97
<b>5</b>	<b>CONCLUSIONS AND RECOMMENDATIONS</b>	<b>101</b>
5.1	Introduction	101
5.2	Conclusion	101
5.3	Recommendation for Future Work	103
	<b>REFERENCES</b>	<b>104</b>
	Appendices A-E	120-133

**LIST OF TABLES**

<b>TABLES NO</b>	<b>TITLE</b>	<b>PAGE</b>
2.1	The classification of phosphate glass as a function of O/P ratio(Carta <i>et.al.</i> , 2007).	12
2.2	The classification of Sm <sup>3+</sup> ions <i>f-f</i> transitions (Hasegawa <i>et.al.</i> , 2008).	16
2.3	The density, $\rho$ and molar volume, $V_m$ of various zinc phosphate glasses systems.	24
2.4	The main categories of vibration modes in molecules (Pavia <i>et.al.</i> , 2001).	25
3.1	The nominal composition of samarium doped zinc phosphate glasses embedded with magnetic nickel oxide nanopowder.	49
4.1	The nominal composition and remark of all glass system.	64
4.2	The density, $\rho$ molar volume, $V_m$ and concentration of rare-earth ions, $N$ of the ZPS glasses.	65

4.3	Calculated O/P ratio, Density, $\rho$ Molar Volume, $V_m$ Ionic Packing Density, $V_t$ Nickel Ion Concentration, $N$ Molar Refractivity, $R_M$ Polarizability, $\alpha_e$ and Hardness, $H_v$ properties of samarium doped zinc phosphate glass embedded with Ni NPs.	66
4.4	Position and assignments of FTIR absorption bands.	76
4.5	Calculated optical energy band gap, $E_g$ Urbach energy, $E_u$ and refractive index, $n$ properties of ZnO-P <sub>2</sub> O <sub>5</sub> :Sm <sup>3+</sup> .	84
4.6	Calculated optical energy band gap, $E_g$ Urbach energy, $E_u$ and refractive index, $n$ nephelauxetic ratio, $\bar{\beta}$ and bonding parameter, $\delta$ of the ZPSN glasses.	85
4.7	Band position in cm <sup>-1</sup> for different glass system. A comparison with Carnall <i>et.al.</i> , 1968 is also inserted.	87
4.8	Ni NPs concentration dependent $\tau$ value of <sup>4</sup> G <sub>5/2</sub> → <sup>6</sup> H <sub>11/2</sub> transition.	90
4.9	Magnetic properties of saturation magnetization, $M_s$ remanence, $M_r$ coercive force, $H_c$ squariness, $M_r/M_s$ and magnetic susceptibility, $\chi$ of ZPSN glasses.	95

**LIST OF FIGURES**

<b>FIGURE NO</b>	<b>TITLE</b>	<b>PAGE</b>
2.1	Phosphate glasses Q <sup>n</sup> groups model (Lu <i>et.al.</i> , 2015).	11
2.2	Raman spectra of ZnO raw material (Li <i>et.al.</i> , 2014).	13
2.3	Typical energy level of samarium ions (Rao and Jayasankar 2013).	17
2.4	The XRD of glass and glass ceramic of zinc phosphate samples containing iron ions (Pascuta <i>et.al.</i> , 2010).	19
2.5	The TEM image and average size distribution of Fe <sub>3</sub> O <sub>4</sub> NPs in zinc phosphate matrix (Anigrahawati <i>et.al.</i> , 2015).	21
2.6	The high resolution TEM image and the inset shows the selected area electron diffraction (SAED) of silver NPs in phosphate glass (Amjad, <i>et.al.</i> , 2012).	22
2.7	The FTIR spectra of (40-x)ZnO-xFe <sub>2</sub> O <sub>3</sub> -60P <sub>2</sub> O <sub>5</sub> (x=0-40 mol%) glass (Li <i>et.al.</i> , 2014).	27
2.8	A typical Raman spectra of (40-x)ZnO-xFe <sub>2</sub> O <sub>3</sub> -60P <sub>2</sub> O <sub>5</sub> (x=0-40 mol%) glass (Li <i>et.al.</i> , 2014).	28

2.9	Density of State (DOS) in an insulator (Ashcroft and Mermin 1981)	29
2.10	A typical Tauc plot of $(\alpha h\nu)^{1/2}$ versus $(h\nu)$ in phosphate glass sample (Anigrahawati <i>et.al.</i> , 2015).	31
2.11	The energy conversion process of photoluminescence.	35
2.12	The energy level diagram of $\text{Ni}^{2+}$ ions (Zannoni <i>et.al.</i> , 1999).	36
2.13	The decay rate of samarium doped glass (Rao and Jayasankar 2013).	38
2.14	The ferromagnetic hysteresis loop	40
2.15	The hysteresis loop of RE doped glasses containing $\text{Fe}_2\text{O}_3$ NPs (Anigrahawati <i>et.al.</i> , 2015).	41
2.16	The energy level splitting of a free electron in an external magnetic field.	42
2.17	The comparison of the (a) absorption spectrum and (b) first derivative ESR spectrum (Weckhuysen <i>et.al.</i> , 2004).	44
2.18	The ESR spectra of $\text{Ni}^{2+}$ zinc phosphate glass (Ravikumar <i>et.al.</i> , 2005).	45
2.19	Illustration of surface plasmon resonance for spherical nanoparticles with polarized light field (Zhang and Noguez 2008).	47
3.1	Bragg reflection from a particular parallel lattices planes, separated by a distance $d$ with path difference is $2d \sin \theta$ .	53

3.2	The schematic diagram of Raman scattering effect.	56
3.3	The Full Width at Half Maximum (FWHM) of emission peaks.	58
3.4	Block diagram of VSM.	59
3.5	Block diagram of microwave ESR spectrometer.	60
3.6	The flow chart of the experimental procedure.	62
4.1	Variation in density and molar volume for different concentration of Ni NPs.	67
4.2	Electronic polarizability as a function of Ni NPs.	68
4.3	Ni NPs concentration dependent Vickers hardness.	69
4.4	XRD pattern of $40\text{ZnO}-(58-y)\text{P}_2\text{O}_5-\text{Sm}_2\text{O}_3-y\text{NiO}$ with $y = 0.0$ and $2.0$ mol% glasses.	71
4.5	TEM image for $40\text{ZnO}-57\text{P}_2\text{O}_5-\text{Sm}_2\text{O}_3-2.0\text{NiO}$ glass.	72
4.6	Average size of Ni NPs.	72
4.7	Selected area electron diffraction (SAED) pattern of $40\text{ZnO}-57.5\text{P}_2\text{O}_5-\text{Sm}_2\text{O}_3-1.5\text{NiO}$ glass.	73
4.8	High resolution TEM image of $40\text{ZnO}-57.5\text{P}_2\text{O}_5-\text{Sm}_2\text{O}_3-1.5\text{NiO}$ glass.	74
4.9	IR absorption peaks of glass ZPSN glass samples.	75
4.10	Raman spectra of all ZPSN glass samples.	77

4.11	Ni NPs concentration dependent Raman intensity for the peak of (a) $708\text{ cm}^{-1}$ and (b) $1200\text{ cm}^{-1}$ .	78
4.12	Optical absorption spectra of $\text{ZnO-P}_2\text{O}_5:\text{Sm}^{3+}$ for ZPS1 glass.	80
4.13	The absorption spectra of ZPSN glasses.	81
4.14	Inset shows the shoulder occurs in the region of absorption spectra.	82
4.15	UV-Vis absorption and de-convoluted spectra of glass without $\text{Sm}_2\text{O}_3$ and with 1 mol% Ni NPs.	83
4.16	The relations of energy band gap, $E_g$ and urbach energy, $E_u$ .	85
4.17	The Ni NPs concentration dependent energy band gap and Urbach energy of ZPSN glass.	86
4.18	PL spectra of samarium doped zinc phosphate glass embedded with Ni NPs.	89
4.19	The PL spectra of ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{11/2}$ transition.	90
4.20	Decay analysis of x (Ni NPs) =0.5 mol% at ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{11/2}$ transition.	91
4.21	The FWHM of ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{7/2}$ and ${}^4\text{G}_{5/2} \rightarrow {}^6\text{H}_{9/2}$ transitions.	92
4.22	Partial energy level diagram of $\text{Sm}^{3+}$ ion in vicinity of Ni NPs showing all relevant transitions.	93
4.23	$M(H)$ graph of pure Nickel bulk (Burgei <i>et.al.</i> , 2003)	95



4.24	$M(H)$ graph of ZPSN glass.	96
4.25	The saturation magnetization, $M_s$ of ZPSN glasses.	97
4.26	ESR spectra of glasses sample.	98
4.27	Composition dependent of $g$ -factor and resonance magnetic field of sample glasses.	99
4.28	The line width of glasses.	100

**LIST OF SYMBOLS**

$E$	-	Energy
$E_g$	-	Energy band gap
$h\nu$	-	Photon energy
$\nu$	-	Wavenumber
$\Delta E$	-	Urbach energy
$\Delta E$	-	Different energy
$n$	-	Refractive index
$\delta$	-	Bonding parameter
$\beta$	-	Nephelauxetic
$\tau$	-	Decay half-life
$I$	-	Incident intensity
$\rho$	-	Density
$V_m$	-	Molar volume
$V_t$	-	Ionic packing density
$V_i$	-	Packing density parameter
$x_i$	-	Molar fraction
$N$	-	Ion concentration
$R_M$	-	Molar refractivity
$\alpha_e$	-	Electronic polarizability
$N$	-	Avogadro's number
$H_v$	-	Vickers Hardness
$L$	-	Applied Load
$\alpha$	-	Face Angle ( $136^\circ$ ).
$d$	-	The Mean Diagonal

$l_o$	-	Length
$2\theta$	-	Bragg angle
$d$	-	Interatomic spacing
$m_s$	-	Electron spin energy
$g_e$	-	Gyromagnetic
$\mu_B$	-	Bohr magneton
$\mu_o$	-	Magnetic field constant
$\nu$	-	Frequency
$H_r$	-	Resonance magnetic field
$H, B$	-	Magnetic field
$V$	-	Volume
$J$	-	Angular momentum
$S$	-	Spin
$L$	-	Orbital
$M$	-	Magnetization
$\vec{E}$	-	Electric field
$M_s$	-	Saturation magnetization
$M_r$	-	Remanence
$\chi_m$	-	Magnetic susceptibility
$H_c$	-	Coercive force
$m$	-	Dipole moment

**LIST OF ABBREVIATIONS**

A/D	-	Analog/Digital
BB	-	Bragg Brentano
BO	-	Bridging oxygen
CB	-	Conduction band
CCD	-	Charge coupled device
DL	-	Deuterium lamp
DOS	-	Density of state
DTA	-	Differential thermal analysis
ESR	-	Electron spin resonance
ET	-	Energy transfer
FCC	-	Face centered cubic
FFT	-	Fast Fourier transform
FT-IR	-	Fourier transform infra-red
FWHM	-	Full-width at half maxima
GSA	-	Ground state absorption
HL	-	Halogen lamp
HRTEM	-	High resolution transmission electron microscope
J-O	-	Judd ofelt
LED	-	Light emitting diode
LSP	-	Localized surface plasmons
LSPR	-	Localized surface plasmons resonance
M-L	-	Metal-ligand
MRI	-	Magnetic resonance imaging
NBO	-	Non-bridging oxygen

Ni	-	Nickel
NIR	-	Near Infra-Red
NMEF	-	Nanometal enhanced fluorescence
NMR	-	Nuclear magnetic resonance
NPs	-	Nanoparticles
NR	-	Non-radiative
PL	-	Photoluminescence
QEs	-	Quantum efficiency
R	-	Radiative
RE	-	Rare-earth
RI	-	Refractive index
SAED	-	Selected area electron diffraction
SPR	-	Surface plasmon resonance
TEM	-	Transmission electron microscope
TMO	-	Transition metal oxide
UV-VIS	-	Ultra violet visible
VB	-	Valence band
VSM	-	Vibrating sample magnetometer
XRD	-	X-ray diffraction

**LIST OF APPENDICES**

<b>APPENDIX</b>	<b>TITLE</b>	<b>PAGE</b>
A	Decay curve plot	121
B	VSM analysis	125
C	ESR spectrum	129
D	ESR analysis	132
E	List of journal publications	133

## CHAPTER 1

### INTRODUCTION

#### 1.1 Background of Study

The study of glass laser as a host material deserves larger attentions. This is due to the excellent laser properties of glass possesses low melting temperature, insulating behavior, excellent ability in accommodating large amount for rare-earth (RE) ions and broader emission and absorption spectra as compared to crystalline host make them promising (Brow *et.al.*, 1995; Meyer 1997; Tischendorf *et.al.*, 2001; Ohkawa *et.al.*, 2008; Chen *et.al.*, 2009; Mansour and El-Damrawi 2010; Babu *et.al.*, 2011; Joseph *et.al.*, 2012; Li *et.al.*, 2013; Liang *et.al.*, 2014; Anigrahawati *et.al.*, 2015). Therefore, phosphate exhibits better advantages as a host material. It is reported that P<sub>2</sub>O<sub>5</sub> glass is efficient for high average power pumping laser due to the high thermal shock resistance property (Chen *et.al.*, 2009). In other words, this glass has ability to maintain the efficient laser performance (Chen *et.al.*, 2009). Besides, spectroscopic quality factor of RE doped phosphate glasses (Soltani *et.al.*, 2015) is found to be in the same order than other host glasses (Selvaraju and Marimuthu 2013; Bodył *et.al.*, 2009; Agarwal *et.al.*, 2009) possess a good candidate for laser materials.

Despite, the confinement of phosphate glasses due to chemical durability is necessary to add other metal oxides as an intermediate to stabilize the glass structure (Hsu *et.al.*, 2012). Incorporation of metal oxides modifiers such as ZnO, Al<sub>2</sub>O<sub>3</sub> and MgO in the phosphate host alters the structural units of the network and thereby improves their chemical durability and physical properties (Brow *et.al.*, 1995; Marzouk *et.al.*, 2013; Thomas *et.al.*, 2013). However, the changes in the overall structure depend very much on their compositions (Liu *et.al.*, 1997). For example, the Zn ions give different form of phosphate chain through the delocalization of P=O and P-O<sup>-</sup> bonds (Liu *et.al.*, 1997; Marzouk *et.al.*, 2013). The addition of other metal oxides is needed to understand the disorder nature of the glassy state and the contribution of P-P bonds. In this study, phosphate in conjunction ZnO metal oxides evaluates the potential structural modification of bridging oxygen (BO) and non-bridging oxygen (NBO) of a host glass. The stable host glass well then suitable for doped with significant RE.

Amongst other host glass, RE doped phosphate glasses are preferred in optical communication, photonics devices and lasing materials (Liu *et.al.*, 1997; Chen *et.al.*, 2009). Particularly, this study is focused on samarium as rare-earth ions doped zinc phosphate glasses due to their functional luminescence properties. The important emission of samarium ions exits from electronic transitions of  $^4G_{5/2} \rightarrow ^6H_{5/2}$  (green),  $^4G_{5/2} \rightarrow ^6H_{7/2}$  (orange), and  $^4G_{5/2} \rightarrow ^6H_{9/2}$  (red). Despite, efficiency of those emission possess many restrictions on their commercial exploitation and usefulness in optical devices. Hence improvement of this emission efficiency by employing of different host glass, co-doped RE and inclusion of sensitizer such as metallic NPs due to concentration and resonance on the energy level structure is promising (Som and Karmakar 2008).

Important consideration on the laser glass characterization is radiative Quantum Efficiency (QEs) analysis. It is reported that radiative QEs can be obtained from the lifetimes by Judd Ofelt (J-O) analysis and laser sources dependent to different applications (Suzuki *et.al.*, 2010). J-O theory has been used to determine the electric and magnetic contribution on total transition probability for desirable



emission of RE ions. However, the calculation in all (J-O) analysis usually unconsumed the magnetic contribution. Thus the use of magnetic metal is the unique aspect of magnetic properties to study in order to increase the efficiency of the laser emission. This also due to the particular nature of electromagnetic radiation as coupled magnetic and electric fields' perpendicular to the direction of propagation.

Nickel nanoparticles (Ni NPs) are among the important materials. In periodic table nickel is in group VIIIA which is a magnetic group of material. Ni<sup>2+</sup> ions in octahedral sites exhibit several strong absorption bands in the visible and NIR regions (Zannoni *et.al.*, 1999; Padmanabham *et.al.*, 2009). Furthermore Feng *et.al.*, shows that nickel occupies the tetrahedral zinc site with cubic symmetry in nickel-zinc phosphate glasses (Feng *et.al.*, 2011). Therefore a study on Ni NPs embedded in glass is very important especially to control the structural, optical and magnetic properties of the glass. In addition, nanometers magnetic particles give a more sensitive response to the change of applied magnetic field and thus exhibit superparamagnetic coexistence of single domain materials (Chudnovsky and Gunther 1988). This reveals interesting optical and magnetic properties such as surface plasmon resonance (SPR) absorption and superparamagnetism (Anigrahawati *et.al.*, 2015; Chen *et.al.*, 2015). The investigation on Mn<sup>2+</sup>, Fe<sup>2+</sup> and Co<sup>2+</sup> (transition metal ions) with RE doped host glasses have significantly increasing the interest in their properties for magneto-optical devices such as isolator, switches and sensing application (Winterstein *et.al.*, 2013; Anigrahawati *et.al.*, 2015; Chen *et.al.*, 2015). From this research advanced understanding on the magnetic properties of rare-earth doped host glass can be studied.

Studies on nano glasses have been introduced and grown due to their interesting quantum size behavior to improve the optical characteristics of the glass. Effect of NPs on spectroscopic properties of RE doped phosphate glasses also being reported elsewhere (Soltani *et.al.*, 2015; Jiménez *et.al.*, 2011; Zhang and Noguez 2008). Nevertheless, the metallic NPs such as silver and gold have been studied to improve their capability in enhancing the luminescence and enhance the non-linear optical properties (Sazali *et.al.*, 2014; Awang *et.al.*, 2014; Yusoff and Sahar 2015).

Particularly, NPs can increase the yield of their weak optical transitions by generation of intense electric fields upon electromagnetic excitation where plasmonic metal nanostructures in the vicinity of the rare-earth (RE) ions alter their free space spectroscopic properties (Som and Karmakar 2008). This mechanism so-called nanometal enhanced fluorescence (NMEF) and it is due to the localized surface plasmons resonance (LSPR). Three main phenomena that govern the origin of the electromagnetic field enhancement are; the localized surface plasmons (LSP), the change of confinement at the metallic nanoparticles extremities and coupling the effect (Guillot and Chapple 2012). The metal nanocluster exhibited delocalized conduction electron which give absorption in the visible region due to intraband transitions (Udayabhaskar *et.al.*, 2014). Thus excitation near to resonant value of the SPR is ascribed to the amplified local field. Due to this phenomenon, it is reported that energy transfer (ET) between ions RE and NPs is possible (Awang *et.al.*, 2014). Thus nanoparticles would be the enhancer or quencher to the fluorescence of samarium ions in this glass. Therefore, this study will focus on the optical properties of the samarium ions for an optical tuning of the solid state luminescence materials.

In this study, the structural, physical, optical properties of Ni NPs on samarium doped zinc phosphate glass followed by a magnetic contribution are studied. X-Ray Diffraction (XRD), density, FT-IR and Raman analysis are able to characterize the alteration of Ni NPs on physical and structural properties of Sm<sup>3+</sup> doped zinc phosphate glass synthesized via the melt-quenching technique. Transmission electron microscopy will be used to study the size distribution of the nanocluster and UV-Vis absorption studies due to SPR band. Quenching and enhancement in fluorescence with excitation near to resonant value of the SPR attributed to the amplified local field is interested in the aspect of magnetic contribution. Meanwhile vibrating sample magnetometer and electron spin resonance will be used to study the magnetic moment of the local magnetic properties due to the nature of spin-spin interaction.

## 1.2 Problem Statement

Throughout the previous research especially on the glass involving silver and gold nanoparticles embedded in RE doped glasses, it can be seen that the enhancement on the luminescence properties of RE ions have been successfully achieved (Jiménez *et.al.*, 2011; Mahraz *et.al.*, 2013; Awang *et.al.*, 2014; Sazali *et.al.*, 2014; Soltani *et.al.*, 2015). This is due to the effect of NPs metallic particles which yields the Surface Plasmon Resonance (SPR) phenomena. SPR that governs the confining light to nanostructures interfaces (plasmon and photonic signal) can generate an intense local electromagnetic fields (Aghlara *et.al.*, 2015). This phenomenon is dominated by the force exerted by the incident electric and magnetic field on the electric charge in the matter would increase the quantum efficiency and luminescence intensity of significant RE-doped glass emission. This phenomenon is successfully contributed by the electrical dipole moment via the existence of NPs for optical studies and applications has been extensively reported (Sazali *et.al.*, 2014; Awang *et.al.*, 2014). In spite of that, the investigation of RE-doped glasses incorporated with magnetic NPs elements are of interest for magnetic studies that could lead to the development of new magneto-optical materials. This is essential for Ni NPs elements to incorporate in the glass system due to the important magnetic properties of this metal (Yeshchenko *et.al.*, 2008). Therefore, the study of the magnetic properties of samarium doped zinc phosphate glasses embedded with Ni NPs is crucial due to lack of comprehensive data to be found in literature.

Nickel is a transition metal and generally exists in valence ions which are extremely stable in the glass matrix (Rao *et.al.*, 2008). Additionally, nickel oxide may induced of a significant changes on the structural, spectroscopic and dielectric properties of the host glasses (Rao *et.al.*, 2008; Hussein and Moustaffa 1972; Elzahedb 1994; Gandhi *et.al.*, 2011; Rao *et.al.*, 2011; Perrière *et.al.*, 2013). In addition, nickel is practically importance due to their interesting in contributing the magnetic properties in the glass system. It is found that glass embedded with Ni<sup>2+</sup> ions has been an increasing demand for getting laser emission due to  ${}^3T_2(F) \rightarrow {}^3A_2(F)$

transition in NIR region (Rao *et.al.*, 2008; Rao *et.al.*, 2011; Gandhi *et.al.*, 2011). Thus is very significant to bring Ni NPs inside the magnetic environment in the glass.

The distribution of nickel ions in glassy matrix which depend on its size and shapes is a current issue. Furthermore, properties due to the formation of non-bridging oxygen and structural units of constituent atoms in glass matrices are far from being understood. Therefore, the aims of this work are to study the structural, optical and magnetic properties of samarium doped zinc phosphate glasses embedded with nickel nanoparticles.

### 1.3 Objectives

The objectives of this study are:-

- (a) To prepare series of samarium doped zinc phosphate glass at varying concentration of included nanoparticles by melt quenching method.
  - i)  $40\text{ZnO}-(60-x)\text{P}_2\text{O}_5-x\text{Sm}_2\text{O}_3$ ; where  $x = 1.0, 2.0, 3.0$  and  $4.0$  mol%.
  - ii)  $40\text{ZnO}-(59-y)\text{P}_2\text{O}_5-1\text{Sm}_2\text{O}_3-y\text{NiO}$ ; where  $y = 0.5, 1.0, 1.5$  and  $2.0$  mol%.
- (b) To verify the amorphous nature of glass, estimate the size distribution and d-spacing of nickel nanoparticles.
- (c) To determine the influence of nickel nanoparticles (mol%) on the physical, structural, optical and magnetic properties of samarium doped zinc phosphate glasses.

## 1.4 Scope of Study

In this study the melt-quenching technique is exploited to prepare the samarium doped zinc phosphate glasses embedded with Ni NPs. The glass nature is confirmed by X-Ray Diffraction (XRD) and the presence of nanoparticles is probed by TEM and HRTEM. These are very useful methods to provide morphological and crystallographic information on nickel nanoparticles distributed in samarium doped zinc phosphate glasses.

The glass density is measured by Archimedes method which is then be used to determine the molar volume and polarizability. The structural units of host glass are investigated by means of Fourier Transform Infrared (FTIR) spectroscopy and Raman analysis. The optical energy band gap, Urbach energy, refractive index, bonding characteristic and Ni NPs surface plasmon resonance mediated transient paramagnetic response are determined by using absorption spectroscopy. Meanwhile, the luminescence properties will be accomplished from Photoluminescence (PL) spectroscopy. Magnetic properties such as saturation magnetization, coercivity force, and  $g$ -factor value of Ni NPs are evaluated by means of Vibrating Sample Magnetometer (VSM) and Electron Spin Resonance (ESR) spectroscopy.

## 1.5 Significance of Study

This research is of significance to the domain of '*nanoglass*' (glass containing nanoparticles) technology as it extended the basic knowledge that currently exists in area. Plasmonic metal nanostructures which is due to the localized surface plasmons resonance (LSPR) phenomena have been used in diverse application such as electromagnetic field enhancement, high resolution optical imaging and biosensing (Aghlara *et.al.*, 2015; Choi *et.al.*, 2015; Liu *et.al.*, 2015).

One of the important property of surface plasmon is modes of electromagnetic radiations that are strongly coupled to collective oscillation of free-electrons at the interface of conductive materials (Chui and Lin 2014). It is motivated by possibility that surface plasmon are found to enhance the transmission of electromagnetic wave.

In this study,  $\text{Sm}^{3+}$ -doped phosphate shows several luminescence lines. The handfuls of Ni nanoparticles exhibiting novel optical properties of RE doped zinc phosphate glass with their extremely small dimensions, special surface nature and magnetic behavior. Having justified its significances, this research is poised to expand the studies for further research into the area of magnetic-optical properties.

It is known that lasing properties are due to the electrical and magnetic contribution. However, all of the calculation in JO analysis is based on the ignorance of magnetic factor because it can be assumed that the glass is non-magnetic. Thus the study on the emission efficiency due to magnetic contribution is the new area to explore. Despite of spectroscopies, magnetic behaviour in terms of magnetization and  $g$ -factor findings will modify the optical response of samarium doped zinc phosphate glass due to presence of Ni NPs.

## **1.6 Organization of Study**

The entire project is documented in this thesis and it consists of five chapters. Chapter 1 describes the introduction of research background, problem statement, research objectives, scope and the significance of the study. Chapter 2 is on the literature review on the active medium materials development. It contains the review of physical, structural, optical and magnetic properties of the related glass comparison with another glass system. Chapter 3 elaborates the preparation of the samples and the employed analytical techniques. The measurement technique and

instrumentations are discussed in this chapter. Chapter 4 is on the accomplished discussion of the results obtained. Finally, the conclusion and future work of current research are given in chapter 5.

## REFERENCES

- Agarwal, A., Pal, I., Sanghi, S., and Aggarwal, M. P. (2009) Judd–Ofelt Parameters and Radiative Properties of  $\text{Sm}^{3+}$  Ions Doped Zinc Bismuth Borate Glasses. *Optical Materials*, 32:339–344.
- Aghlara, H., Rostami, R., Maghoul, A., and SalmanOgli, A. (2015) Noble Metal Nanoparticle Surface Plasmon Resonance in Absorbing Medium. *Optik*, 126:417–420.
- Ahmad, F. (2014) Study the Effect of Alkali/Alkaline Earth Addition on the Environment of Borochromate Glasses by Means of Spectroscopic Analysis. *Journal of Alloys and Compounds*, 586:605–610.
- Ahmmad, S. K., Samee, M., Edukondalu, A., and Rahman, S. (2012) Physical and Optical Properties of Zinc Arsenic Tellurite Glasses. *Results in Physics*, 2:175–181.
- Al-Ani, S. K. J. (1991) Study of Optical Absorption Edges in  $\text{MgO-P}_2\text{O}_5$  Glasses. *Journal of Materials Science*, 26:3670–3674.
- Alagiri, M., Muthamizhchelvan, C., and Ponnusamy, S. (2011) Structural and Magnetic Properties of Iron, Cobalt and Nickel Nanoparticles. *Synthetic Metals*, 161:1776–1780.
- Alajerami, Y. S. M., Hashim, S., Wan Hassan, W. M. S., Ramli, A.T., and Kasim, A. (2012) Optical Properties of Lithium Magnesium Borate Glasses Doped with  $\text{Dy}^{3+}$  and  $\text{Sm}^{3+}$  Ion s. *Physica B: Condensed Matter*, 407:2398–2403.
- Amjad, R. J., Sahar, M. R., Dousti, M. R., Ghoshal, S. K., and Jamaludin, M. N. (2013) Surface Enhanced Raman Scattering and Plasmon Enhanced Fluorescence in Zinc-Tellurite Glass. *Optics Express*, 21:14282–90.



- Amjad, R. J., Sahar, M. R., Ghoshal, S. K., Dousti, M. R., Riaz, S., and Tahir, B. (2012) Enhanced Infrared to Visible Upconversion Emission in  $\text{Er}^{3+}$  Doped Phosphate Glass: Role of Silver Nanoparticles. *Journal of Luminescence*, 132:2714–2718.
- Amjad, R. J., Sahar, M. R., Ghoshal, S. K., Dousti, M. R., Riaz, S., and Tahir, B. (2012) Optical Investigation of  $\text{Sm}^{3+}$  Doped Zinc-Lead-Phosphate Glass. *Chinese Physics Letters*, 29:087304.
- Anigrahawati, P., Sahar, M. R., and Ghoshal, S. K. (2015) Influence of  $\text{Fe}_3\text{O}_4$  Nanoparticles on Structural, Optical and Magnetic Properties of Erbium Doped Zinc Phosphate Glass. *Materials Chemistry and Physics*, 155:155–161.
- Ashcroft, N. W., and Mermin, N. D. (1981) *Solid State Physics*. Philadelphia:Holt-Saunders International Editions.
- Awang, A., Ghoshal, S. K., Sahar, M. R., Arifin, R., and Nawaz, F. (2014) Non-spherical Gold Nanoparticles Mediated Surface Plasmon Resonance in  $\text{Er}^{3+}$  Doped Zinc–Sodium Tellurite Glasses: Role of Heat Treatment. *Journal of Luminescence*, 149:138–143.
- Babu, A. M., Jamalaih, B. C., Sasikala, T., Saleem, S. A., and Rama Moorthy, L. (2011) Absorption and Emission Spectral Studies of  $\text{Sm}^{3+}$ -Doped Lead Tungstate Tellurite Glasses. *Journal of Alloys and Compounds*, 509:4743–4747.
- Babu, Y. N. C. R., Naik, P. S. R., Kumar, K. V., Kumar, N. R., and Kumar, A. S. (2012) Spectral Investigations of  $\text{Sm}^{3+}$  Doped Lead Bismuth Magnesium Borophosphate Glasses. *Journal of Quantitative Spectroscopy and Radiative Transfer*, 113: 1669–1675.
- Basavapoornima, C., and Jayasankar, C. K. (2014) Spectroscopic and Photoluminescence Properties of  $\text{Sm}^{3+}$  Ions in Pb–K–Al–Na Phosphate Glasses for Efficient Visible Lasers. *Journal of Luminescence*, 153:233–241.
- Blackman, J. A., Binns, C., and Le, L. (2008) Metallic Nanoparticles, 5:1–16.
- Bodył, S., Czaja, M., and Mazurak, Z. (2009) Optical Properties of  $\text{Pr}^{3+}$ ,  $\text{Sm}^{3+}$  and  $\text{Er}^{3+}$  Ions in Apatite, Flurite and Phosphate Glasses. *Physics Procedia*, 2:515–525.
- Brow, R. K., Tallant, D. R., Myers, S. T., and Phifer, C. C. (1995) The Short-Range Structure of Zinc Polyphosphate Glass. *Journal of Non-Crystalline Solids*, 191:45-55.

- Bruni, S., Cariati, F., and Narducci, D. (1994) Infrared Specular Reflection Spectra of Copper-Zinc Phosphate Glasses. *Vibrational Spectroscopy*, 7:169–173.
- Burgei, W., Pechan, M. J., and Jaeger, H. (2003) A Simple Vibrating Sample Magnetometer for Use in A Materials Physics Course. *American Journal of Physics*, 71: 825.
- Carnall, W. T., Fields, P. R., and Rajnak, K. (1968) Electronic Energy Levels in The Trivalent Lanthanide Aquo Ions  $\text{Pr}^{3+}$ ,  $\text{Nd}^{3+}$ ,  $\text{Pm}^{3+}$ ,  $\text{Sm}^{3+}$ ,  $\text{Dy}^{3+}$ ,  $\text{Ho}^{3+}$ ,  $\text{Er}^{3+}$  and  $\text{Tm}^{3+}$ . *Journal of Chemical Physics*, 49:4424–4428.
- Carta, D., Knowles, J. C., Smith, M. E., and Newport, R. J. (2007) Synthesis and Structural Characterization of  $\text{P}_2\text{O}_5$ – $\text{CaO}$ – $\text{Na}_2\text{O}$  Sol–Gel Materials. *Journal of Non-Crystalline Solids*, 353:1141–1149.
- Chankradhar, R.P. S., Ramesh, K.P., Rao, J.L., Ramakrishna, J. R. (2005) The Effect of Mixed Alkali on EPR and Optical Absorption Spectra in Mixed Alkali Borate  $x\text{Na}_2\text{O}$ – $(30-x)\text{K}_2\text{O}$ – $70\text{B}_2\text{O}_3$  Glasses Doped with Iron Ions., 351:1289–1299.
- Changmin, L., Dianlai, Y., Yingying, Z., Zhiqiang, W., and Hai, L. (2007) Photoluminescence Characterization of  $\text{Sm}^{3+}$  -Doped Fluoroborate Ceramics *Journal of Rare Earth*, 25:143–146.
- Chanshetti, U. B., Shelke, V., Jadhav, S. M., Shankarwar, S. G., Chondhekar, T. K., Shankarwar, G., Jogad, M. S. (2011) Density and Molar Volume Studies of Phosphate Glasses. *Facta Universitatis - Series: Physics, Chemistry and Technology*, 9: 29–36.
- Chen, L., He, D., Luan, F., Hu, L., and Chen, W. (2009) An Efficient Erbium Doped Phosphate Laser Glass For High Average Power Pumping. *Journal of Alloys and Compounds*, 482:261–263.
- Chen, Q., Wang, H., Perero, S., Wang, Q., and Chen, Q. (2015) Structural, Optical and Magnetic Properties of  $\text{Fe}_3\text{O}_4$  Sputtered  $\text{TeO}_2$ – $\text{PbO}$ – $\text{B}_2\text{O}_3$  and  $\text{PbO}$ – $\text{Bi}_2\text{O}_3$ – $\text{B}_2\text{O}_3$  Glasses for Sensing Applications. *Journal of Non-Crystalline Solids*, 408:43–50.
- Chen, X., Gong, Z., Wan, Q., Wu, S., Guo, F., Zhuang, N., and Chen, J. (2015)  $\text{Ba}_3\text{Tb}(\text{PO}_4)_3$ : Crystal Growth, Structure, Magnetic and Magneto-Optical Properties. *Optical Materials*, 44:48–53.
- Chen, Z., Xu, A., Zhang, Y., and Gu, N. (2010) Preparation of NiO and CoO Nanoparticles using  $\text{M}^{2+}$ -Oleate (M = Ni, Co) as Precursor. *Current Applied Physics*, 10:967–970.

- Choi, M., Kim, N., Eom, S., Kim, T. W., Byun, K. M., and Park, H.-H. (2015) Fabrication And Characterization of Gold Nanocrown Arrays on A Gold Film for A High-Sensitivity Surface Plasmon Resonance Biosensor. *Thin Solid Films*, 587:43–46.
- Chudnovsky, E. M., and L. Gunther. (1988) Quantum Tunneling of Magnetization in Small Ferromagnetic Particles. *Physical Review Letters*, 60:661–664.
- Chui, S. T., and Lin, Z.-F. (2014) Spin Plasmonics in Magnetism. *Chinese Physics B*, 23: 117802.
- Clare, A. G. *Bio-Glasses An Introduction*. USA: Wiley. 2012
- Culea, E., Ristoiu, T., Bratu, I., and Ristoiu, D. (2000) Structural and Magnetic Behavior of Some Borate Glasses Containing Europium Ions, *Materials Science and Engineering*, B75:82–84.
- Cullity, B. D., and Graham, C. D. *Introduction to Magnetic Materials 2<sup>nd</sup>*. ed. USA: IEEE Press. 2009
- Czaja, M., Bodył, S., Gabryś-Pisarska, J., and Mazurak, Z. (2009) Applications of Judd–Ofelt Theory to Praseodymium and Samarium Ions in Phosphate Glass. *Optical Materials*, 31:1898–1901.
- Dararutana, P., Pongkrapan, S., Sirikulrat, N., Thawornmongkolkij, M., and Wathanakul, P. (2009) Raman Spectroscopic Investigation on High Refractive Index Glasses Prepared from Local Quartz Sand. *Spectrochimica Acta. Part A, Molecular and Biomolecular Spectroscopy*, 73:440–2.
- Davar, F., Fereshteh, Z., and Salavati-Niasari, M. (2009) Nanoparticles Ni and NiO: Synthesis, Characterization and Magnetic Properties. *Journal of Alloys and Compounds*, 476:797–801.
- Davis, E. A. and Mott, N. F. (1970) *Philosophy. Magazine*, 22:903–922.
- De, D., Majumdar, S., and Giri, S. (2015). Spin-glass Like Behaviour in Strongly Interacting Nanocrystalline Ni Embedded in SiO<sub>2</sub>. *Journal of Magnetism and Magnetic Materials*, 394:448–453
- Dousti, M. R., Ghoshal, S. K., Amjad, R. J., Sahar, M. R., Nawaz, F., and Arifin, R. (2013) Structural and Optical Study of Samarium Doped Lead Zinc Phosphate Glasses. *Optics Communications*, 300, 204–209.
- Dousti, R. (2014). *Role of Silver Nanoparticles on Spectroscopic Properties of Erbium-Doped Zinc Tellurite Glass*. Degree of Philosophy, Universiti Teknologi Malaysia, Skudai.

- E. Baiocchi, Montenero, A., Bettinelli, M., and Sotgiu, A. (1981) Optical and Magnetic Properties of First-Row Transition Metal Ions in Lead-Silicate Glass. *Journal of Non-Crystalline Solids*, 46:203–215.
- Edelman, I. S., Ivantsov, R., Vasiliev, A., Stepanov, S., Kornilova, E., and Zarubina, T. (2001) Superparamagnetic and Ferrimagnetic Nanoparticles in Glass Matrix. *Physica B: Condensed Matter*, 301:203–211.
- Edelman, I. S., Ivanova, O. S., Petrakovskaja, E. A., Velikanov, D. A., Tarasov, I. A., Zubavichus, Y. V., Trofimova N.N. Zaikovskii, V. I. (2015) Formation, Characterization and Magnetic Properties of Maghemite  $\gamma\text{-Fe}_2\text{O}_3$  Nanoparticles in Borate Glasses. *Journal of Alloys and Compounds*, 624:60–67.
- Eraiah, B., and Bhat, S. G. (2007) Optical Properties of Samarium Doped Zinc-Phosphate Glasses. *Journal of Physics and Chemistry of Solids*, 68:581–585.
- Eraiah, B., Smitha, M. G., and Anavekar, R. V. (2010) Elastic Properties of Lead-Phosphate Glasses Doped with Samarium Trioxide. *Journal of Physics and Chemistry of Solids*, 71:153–155.
- Feng, W. L., Pu, L. C., Yang, X. Z., and Hu, N. (2011) An Optional Explanation for Nickel Sites of Nickel–Zinc Phosphate Glasses by Their Optical Spectra and EPR  $g$ -factor. *Journal of Magnetism and Magnetic Materials*, 323:2828–2830.
- Ferhi, M., Horchani-Naifer, K., Bouzidi, C., Elhouichet, H., and Ferid, M. (2014) Crystal Structure, Electronic Properties and Optical Band Gap of  $\text{KLa}_{(1-x)}\text{Eu}_x(\text{PO}_3)_4$ . *Journal of Alloys and Compounds*, 609:222–227.
- Gandhi, Y., Krishna Mohan, N., and Veeraiyah, N. (2011) Role of Nickel Ion Coordination on Spectroscopic and Dielectric Properties of  $\text{ZnF}_2\text{-As}_2\text{O}_3\text{-TeO}_2\text{:NiO}$  Glass System. *Journal of Non-Crystalline Solids*, 357:1193–1202.
- Guillot, N., and de la Chapelle, M. L. (2012) The Electromagnetic Effect in Surface Enhanced Raman Scattering: Enhancement Optimization Using Precisely Controlled Nanostructures. *Journal of Quantitative Spectroscopy and Radiative Transfer*, 113:2321–2333.
- Halim, D. N. F. A. (2011) *Structural and Luminescence Properties of Magnesium Strontium Metaphosphate Doped with Europium and Dysprosium Ions*. Master Degree: Universiti Teknologi Malaysia, Skudai.

- Hasegawa, Y., Tsuruoka, S., Yoshida, T., and Kawai, H. (2008) Enhanced Deep-Red Luminescence of Tris ( hexafluoroacetylacetonato ) Samarium ( III ) Complex with Phenanthroline in Solution by Control of Ligand Coordination. *Journal Physics Chemistry A*, 112:803–807.
- Hassan, M. A., Farouk, M., Abdullah, A. H., Kashef, I., and Elokr, M. M. (2012) ESR and Ligand Field Theory Studies of Nd<sub>2</sub>O<sub>3</sub> Doped Borochromate Glasses. *Journal of Alloys and Compounds*, 539:233–236.
- Hemalatha, M., Suriyanarayanan, N., and Prabahar, S. (2014) Nanoscale Synthesis and Optical Features of Nickel Nanoparticles. *Optik - International Journal for Light and Electron Optics*, 125:1962–1966.
- Han, J., Wang, C., Kou, S., & Liu, X. (2013) Thermal Stability , Crystallization Behavior , Vickers Hardness and Magnetic Properties of Fe – Co – Ni – Cr – Mo – C – B – Y Bulk Metallic Glasses, *Transactions of Nonferrous Metals Society of China*, 23: 148–155.
- Hraiech, S., Ferid, M., Guyot, Y., and Boulon, G. (2013) Structural and Optical Studies Of Yb<sup>3+</sup>, Er<sup>3+</sup> and Er<sup>3+</sup>/Yb<sup>3+</sup> Co-Doped Phosphate Glasses. *Journal of Rare Earths*, 31: 685–693.
- Hsu, S. M., Wu, J. J., Yung, S. W., Chin, T. S., Zhang, T., Lee, Y. M., Chu C. M. Ding, J. Y. (2012) Evaluation of Chemical Durability, Thermal Properties and Structure Characteristics of Nb–Sr-Phosphate Glasses by Raman and NMR Spectroscopy. *Journal of Non-Crystalline Solids*, 358:14–19.
- Hussein, A. L., and Moustaffa, F. A. (1972) Spectrophotometric Studies of Some Alkali Borate Glasses Containing Nickel Oxide in Relation to Their Structure. *Journal of Non-Crystalline Solids*, 11: 64–82.
- Jayasankar, C. K., and Rukmini, E. (1997) Optical Properties of Sm<sup>3+</sup> Ions in Zinc and Alkali Zinc Borosulphate Glasses. *Optical Materials*, 8: 193–205.
- Jayasimhadri, M., Moorthy, L. R., Saleem, S. A, and Ravikumar, R. V. S. S. N. (2006) Spectroscopic Characteristics of Sm<sup>3+</sup>-Doped Alkali Fluorophosphate Glasses. *Spectrochimica Acta. Part A, Molecular and Biomolecular Spectroscopy*, 64: 939–44.
- Jiménez, J. A., Lysenko, S., Liu, H., and Sendova, M. (2011) Luminescence of Trivalent Samarium Ions in Silver and Tin Co-Doped Aluminophosphate Glass. *Optical Materials*, 33: 1215–1220.

- Jiménez, J. A., and Sendova, M. (2012) In Situ Isothermal Monitoring of The Enhancement and Quenching of  $\text{Sm}^{3+}$  Photoluminescence in Ag Co-Doped Glass. *Solid State Communications*, 152:1786–1790.
- Joseph, K., Asuvathraman, R., Venkata Krishnan, R., Joseph, J., Govindan Kutty, K. V., and Vasudeva Rao, P. R. (2012) Investigation of Thermal Expansion and Specific Heat of Cesium Loaded Iron Phosphate Glasses. *Journal of Nuclear Materials*, 429: 1–6.
- Katnack, F. L., and Hummel, F. A. (1958) Phase Equilibria in The System  $\text{ZnO}-\text{P}_2\text{O}_5$ . *Journal of the Electrochemical Society*, 105: 133.
- Kaur, M., Singh, A., Thakur, V., and Singh, L. (2015) Effect of  $\text{TiO}_2$  Substitution on Optical and Structural Aspects of Phosphate Glasses. *Journal of Molecular Structure*, 1089:95–101.
- Khaled, M.A., Elzahed, H., Fayek, S.A., El-Ocker M.M., (1994). Optical Absorption, Infrared and Differential of Borotellurite Glass Containing Nickel. *Materials Chemistry and Physics*, 37:329–332.
- Kittel C. *Introduction to Solid State Physics*. 6<sup>th</sup> Ed. Singapore: John Wiley and Sons. 1986.
- Kumar, G., Shah, J., Kotnala, R. K., Singh, V. P., Garg, G., Shirsath, S. E., ... Singh, M. (2015) Superparamagnetic Behaviour and Evidence of Weakening in Super-Exchange Interactions with The Substitution of  $\text{Gd}^{3+}$  Ions in The Mg–Mn Nanoferrite Matrix. *Materials Research Bulletin*, 63:216–225.
- Leng, J., Li, J., Ren, J., Deng, L., and Lin, C. (2015) Star–block Copolymer Micellar Nanocomposites With Mn,Zn-Doped Nano-Ferrite as Superparamagnetic MRI Contrast Agent for Tumor Imaging. *Materials Letters*, 152:185–188.
- Li, H., Liang, X., Wang, C., Yu, H., Li, Z., and Yang, S. (2014) Structural Aspects of Calcium Iron Phosphate Glass Containing Neodymium Oxide. *Journal of Molecular Structure*, 1067: 154–159.
- Li, X., Lu, A., and Yang, H. (2014) Structure of  $\text{ZnO}-\text{Fe}_2\text{O}_3-\text{P}_2\text{O}_5$  Glasses Probed by Raman and IR Spectroscopy. *Journal of Non-Crystalline Solids*, 389:21–27.
- Li, X., Yang, H., Song, X., and Wu, Y. (2013) Glass Forming Region, Structure and Properties of Zinc Iron Phosphate Glasses. *Journal of Non-Crystalline Solids*, 379:208–213.

- Liang, X., Li, H., Wang, C., Yu, H., Li, Z., and Yang, S. (2014). Physical and Structural Properties of Calcium Iron Phosphate Glass Doped with Rare Earth. *Journal of Non-Crystalline Solids*, 402:135–140.
- Lim, T. Y., Wagiran, H., Hussin, R., Hashim, S., and Saeed, M. A. (2014) Physical and Optical Properties of Dysprosium Ion Doped Strontium Borate Glasses. *Physica B: Condensed Matter*, 451:63–67.
- Linganna, K., Basavapoornima, C., and Jayasankar, C. K. (2015) Luminescence Properties of Sm<sup>3+</sup>-doped Fluorosilicate Glasses. *Optics Communications*, 344:100–105.
- Liu, H. S., Chin, T. S., and Yung, S. W. (1997). FTIR and XPS Studies of Low-melting PbO-ZnO-P<sub>2</sub>O<sub>5</sub> Glasses. *Materials Chemistry and Physics*, 50:1-10.
- Liu, L., Wang, Q., Yang, Z., Wang, W., Hu, N., Luo, H., Yang, J. (2015) Characterization of Lipid Films by an Angle-interrogation Surface Plasmon Resonance Imaging Device. *Colloids and Surfaces. B, Biointerfaces*, 128: 287–95.
- Loader, J. *Basic Laser Raman Spectroscopy*. Northern Island: Heyden and Son LTD. 1970.
- Lohr, L. L. *Spin-forbidden Electronic Excitations in Transition Metal Complexes*, Amsterdam: Elsevier, 1972
- Lu, M., Wang, F., Chen, K., Dai, Y., Liao, Q., and Zhu, H. (2015) The Crystallization and Structure Features of Barium-Iron Phosphate Glasses. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 148: 1–6.
- Mahraz, Z.A.S, Sahar, M.R., Ghoshal, S.K., Dousti, M.R., and Amjad, R.J. (2013) Silver Nanoparticles Enhanced Luminescence of Er<sup>3+</sup> Ions in Boro-Tellurite Glasses. *Materials Letters*, 112:136–138.
- Malakhovskii, A. V., Edelman, I. S., Radzyner, Y., Yeshurun, Y., Potseluyko, A. M., Zarubina, T. V., Zamkov, A. V., Zaitzev, A. I. (2003) Magnetic and Magneto-Optical Properties of Oxide Glasses Containing Pr<sup>3+</sup>, Dy<sup>3+</sup> and Nd<sup>3+</sup> Ions. *Journal of Magnetism and Magnetic Materials*, 263:161–172.
- Mallur, S. B., Czarnecki, T., Adhikari, A., and Babu, P. K. (2015) Compositional Dependence of Optical Band Gap and Refractive Index in Lead and Bismuth Borate Glasses. *Materials Research Bulletin*, 68:27–34.

- Mansour, E., and El-Damrawi, G. (2010) Electrical Properties and FTIR Spectra of ZnO–PbO–P<sub>2</sub>O<sub>5</sub> Glasses. *Physica B: Condensed Matter*, 405: 2137–2143.
- Marzouk, M. A., ElBatal, F. H., and Abdelghany, A. M. (2013) Ultraviolet and Infrared Absorption Spectra of Cr<sub>2</sub>O<sub>3</sub> Doped-Sodium Metaphosphate, Lead Metaphosphate and Zinc Metaphosphate Glasses and Effects of Gamma Irradiation: A Comparative Study. *Spectrochimica Acta. Part A, Molecular and Biomolecular Spectroscopy*, 114: 658–67.
- Masai, H., Tanimoto, T., Fujiwara, T., Matsumoto, S., Takahashi, Y., Tokuda, Y., and Yoko, T. (2012) Fabrication of Sn-Doped Zinc Phosphate Glass Using A Platinum Crucible. *Journal of Non-Crystalline Solids*, 358: 265–269.
- Massera, J., Bourhis, K., Petit, L., Couzi, M., Hupa, L., Hupa, M., Videau, J. J., Cardinal, T. (2013) Effect of The Glass Composition on The Chemical Durability of Zinc-Phosphate-Based Glasses in Aqueous Solutions. *Journal of Physics and Chemistry of Solids*, 74:121–127.
- Meyer, K. (1997) Characterization of the Structure of Binary Zinc Ultraphosphate Glasses by Infrared and Raman Spectroscopy. *Journal of Non-Crystalline Solids*, 209:227–239.
- Mitra, S., and Jana, S. (2015) Intense Orange Emission in Pr<sup>3+</sup> Doped Lead Phosphate Glass. *Journal of Physics and Chemistry of Solids*, 85, 245–253.
- Miura, T., Benino, Y., Sato, R., and Komatsu, T. (2003) Universal Hardness and Elastic Recovery in Vickers Nanoindentation of Copper Phosphate and Silicate Glasses. *Journal of the European Ceramic Society*, 23: 409–416.
- Mošner, P., Vorokhta, M., Koudelka, L., Montagne, L., Revel, B., Sklepić, K., and Mogaš-Milanković, A. (2013) Effect of Germanium Oxide on the Structure and Properties of Lithium Borophosphate Glasses. *Journal of Non-Crystalline Solids*, 375:1–6.
- Muhammad Junaid Amjad. (2013) *Effect of Silver Nanoparticles on Optical Properties of Erbium-Doped Magnesium Phosphate Glass*. Degree of Philosophy, University Teknologi Malaysia, Skudai.
- Nakamura, T., and Adachi, S. (2012) Photoluminescence Decay Dynamics of Silver/Porous-Silicon Nanocomposites Formed by Metal-Assisted Etching. *Journal of Luminescence*, 132: 3019–3026.



- Nalwa, K. S., Garg, A., and Upadhyaya, A. (2008) Effect of Samarium Doping On The Properties Of Solid-State Synthesized Multiferroic Bismuth Ferrite. *Materials Letters*, 62: 878–881.
- Naseri, M. G., Saion, E. B., Hashim, M., Shaari, A. H., and Ahangar, H. A. (2011) Synthesis and Characterization of Zinc Ferrite Nanoparticles by A Thermal Treatment Method. *Solid State Communications*, 151:1031–1035.
- Nawaz, F., Sahar, M. R., Ghoshal, S. K., Awang, A., and Ahmed, I. (2014) Concentration Dependent Structural and Spectroscopic Properties of Sm<sup>3+</sup>/Yb<sup>3+</sup> Co-Doped Sodium Tellurite Glass. *Physica B: Condensed Matter*, 433:89–95.
- Netto, C. G. C. M., Toma, H. E., and Andrade, L. H. (2013) Superparamagnetic Nanoparticles as Versatile Carriers and Supporting Materials for Enzymes. *Journal of Molecular Catalysis B: Enzymatic*, 85-86:71–92.
- Nouneh, K., Oyama, M., Diaz, R., Abd-lefdil, M., Kityk, I. V., and Bousmina, M. (2011) Nanoscale Synthesis and Optical Features of Metallic Nickel Nanoparticles by Wet Chemical Approaches. *Journal of Alloys and Compounds*, 509:5882–5886.
- Novais, a. L. F., Dantas, N. O., Guedes, I., and Vermelho, M. V. D. (2015) Spectroscopic Properties of Highly Nd-Doped Lead Phosphate Glass. *Journal of Alloys and Compounds*, 648:338–345.
- Ohkawa, H., Min, K. H., Akiyama, R., Yamamoto, K., and Sugimoto, N. (2008) Refractive Index Behavior in Phosphate Glass From The View Point Of B<sup>3+</sup> and Al<sup>3+</sup> Coordination. *Journal of Non-Crystalline Solids*, 354:90–93.
- Olley, J. A. (1973) Structural Disorder and The Urbach Edge, 13:1437–1440.
- Omrani, R. O., Kaoutar, A., El Jazouli, A., Krimi, S., Khattech, I., Jemal, M., Videau, J., Couzi, M. (2015) Structural and Thermochemical Properties of Sodium Magnesium Phosphate Glasses. *Journal of Alloys and Compounds*, 632:766–771.
- Onyiriuka, E. C. (1993). Zinc phosphate glass surfaces studied by XPS. *Journal of Non-Crystalline Solids*, 163: 268–273.
- Padmanabham, A., Gandhi, Y., Satyanarayana, T., and Veeraiah, N. (2009) Spectroscopic and Dielectric Properties of Crystallized PbO–Sb<sub>2</sub>O<sub>3</sub>–As<sub>2</sub>O<sub>3</sub>: NiO Glass System. *Journal of Alloys and Compounds*, 488: 400–408.

- Pal, I., Agarwal, A., Sanghi, S., and Aggarwal, M. P. (2013) Investigation of Spectroscopic Properties, Structure and Luminescence Spectra of Sm<sup>3+</sup> Doped Zinc Bismuth Silicate Glasses. *Spectrochimica Acta. Part A, Molecular and Biomolecular Spectroscopy*, 101:74–81.
- Park, J., Kang, E., Son, S. U., Park, H. M., Lee, M. K., Kim, J., Kim, K. W. Noh, H. Park, J., Bae, C. J., Park, J., Hyeon, T. (2005). Monodisperse Nanoparticles of Ni and NiO: Synthesis, Characterization, Self-Assembled Superlattices, and Catalytic Applications in the Suzuki Coupling Reaction. *Advanced Materials*, 17:429–434.
- Pascuta, P., Borodi, G., Jumate, N., Vida-Simiti, I., Viorel, D., and Culea, E. (2010) The Structural Role of Manganese Ions in Some Zinc Phosphate Glasses and Glass Ceramics. *Journal of Alloys and Compounds*, 504:479–483.
- Pascuta, P., Borodi, G., Popa, A., Dan, V., and Culea, E. (2010) Influence of Iron Ions on The Structural and Magnetic Properties of Some Zinc-Phosphate Glasses. *Materials Chemistry and Physics*, 123: 767–771.
- Pascuta, P., Bosca, M., Borodi, G., and Culea, E. (2011) Thermal, Structural And Magnetic Properties of Some Zinc Phosphate Glasses Doped With Manganese Ions. *Journal of Alloys and Compounds*, 509:4314–4319.
- Pavia, D. L., Lampman, G. M., and Kriz, G. S. *Introduction to Spectroscopy: A Guide for Students of Organic Chemistry*. 3<sup>rd</sup>. ed. London:Brooks Cole. 2001
- Perrière, L., Béucia, B., Ochin, P., and Champion, Y. (2013) Nickel Improves Glass-Forming Ability of Mischmetal Substituted Yttrium in The Mg–Cu Based Alloys. *Journal of Non-Crystalline Solids*, 371-372:37–40.
- Qiao, H., Wei, Z., Yang, H., Zhu, L., and Yan, X. (2009) Preparation and Characterization of NiO Nanoparticles by Anodic Arc Plasma Method. *Journal of Nanomaterials*, 795928:1–5.
- Raghava Rao, P., Murali Krishna, G., Brik, M. G., Gandhi, Y., and Veeraiah, N. (2011) Fluorescence Features of Sm<sup>3+</sup> Ions in Na<sub>2</sub>SO<sub>4</sub>–MO–P<sub>2</sub>O<sub>5</sub> Glass System—Influence of Modifier Oxide. *Journal of Luminescence*, 131: 212–217.
- Rajesh, D., Dhamodhara Naidu, M., and Ratnakaram, Y. C. (2014) Synthesis and Photoluminescence Properties of NaPbB<sub>5</sub>O<sub>9</sub>:Dy<sup>3+</sup> Phosphor Materials For White Light Applications. *Journal of Physics and Chemistry of Solids*, 75: 1210–1216.

- Rao, G. S., Sudhakar, B. K., Prasanna, H. N. L., Devasahayam, V., and Rao, M. V. S. C. S. (2011) Spectroscopic Studies of Lead Arsenate Glasses Doped with Nickel Oxide. *Journal of Non-Crystalline Solids*, 357: 1130–1135.
- Rao, P. V., Satyanarayana, T., Reddy, M. S., Gandhi, Y., and Veeraiiah, N. (2008) Nickel Ion as A Structural Probe in PbO–Bi<sub>2</sub>O<sub>3</sub>–B<sub>2</sub>O<sub>3</sub> Glass System by Means of Spectroscopic and Dielectric Studies. *Physica B: Condensed Matter*, 403(19-20), 3751–3759.
- Rao, S. C., and Jayasankar, C. K. (2013) Spectroscopic and Radiative Properties of Sm<sup>3+</sup>-Doped K–Mg–Al Phosphate Glasses. *Optics Communications*, 286:204–210.
- Rao, T. G. V. M., Rupesh Kumar, a, Neeraja, K., Veeraiiah, N., and Rami Reddy, M. (2014) Optical and Structural Investigation of Dy<sup>3+</sup>-Nd<sup>3+</sup> Co-Doped in Magnesium Lead Borosilicate Glasses. *Spectrochimica Acta. Part A, Molecular and Biomolecular Spectroscopy*, 118: 744–51.
- Ravikumar, R. V. S. S. N., Yamauchi, J., Chandrasekhar, A. V., Reddy, Y. P., and Rao, P. S. (2005) Identification of Chromium and Nickel Sites in Zinc Phosphate Glasses. *Journal of Molecular Structure*, 740: 169–173.
- Reis, S. T., Moguš-Milanković, a., Ličina, V., Yang, J. B., Karabulut, M., Day, D. E., and Brow, R. K. (2007) Iron Redox Equilibrium, Structure and Properties of Zinc Iron Phosphate Glasses. *Journal of Non-Crystalline Solids*, 353:151–158.
- Rivera, V. A. G., Ledemi, Y., El-Amraoui, M., Messaddeq, Y., and Marega, E. (2014) Green-To-Red Light Tuning by Up-Conversion Emission via Energy Transfer in Er<sup>3+</sup>-Tm<sup>3+</sup>-Codoped Germanium-Tellurite Glasses. *Journal of Non-Crystalline Solids*, 392-393:45–50.
- Saddeek, Y. B. (2005) Elastic Properties of Gd<sup>3+</sup>-Doped Tellurovanadate Glasses using Pulse-Echo Technique. *Materials Chemistry and Physics*, 91: 146–153.
- Saddeek, Y. B., Kaid, M. A., and Ebeid, M. R. (2014) FTIR and Physical Features of Al<sub>2</sub>O<sub>3</sub>–La<sub>2</sub>O<sub>3</sub>–P<sub>2</sub>O<sub>5</sub>–PbO Glasses. *Journal of Non-Crystalline Solids*, 387:30–35.
- Sahar, M. R., Hussein, A. W. M. A., and Hussin, R. (2007) Structural Characteristic of Na<sub>2</sub>O–P<sub>2</sub>O<sub>5</sub>–GeO<sub>2</sub> Glass Systems. *Journal of Non-Crystalline Solids*, 353:1134–1140.

- Salagram, M., Prasad, V. K., and Subrahmanyam, K. (2002) Optical Band Gap Studies on  $x\text{Pb}_3\text{O}_4-(1-x)\text{P}_2\text{O}_5$  lead [( II , IV )] phosphate glasses. *Optical Materials*, 18:367-372.
- Salwa A. M. A., and Elwan, R. L. (2012) Effect of  $\text{La}_2\text{O}_3$ ,  $\text{CoO}$ ,  $\text{Cr}_2\text{O}_3$  and  $\text{MoO}_3$  Nucleating Agents on Crystallization Behavior and Magnetic Properties of Ferromagnetic Glass–Ceramic in The System  $\text{Fe}_2\text{O}_3 \cdot \text{CaO} \cdot \text{ZnO} \cdot \text{SiO}_2$ . *Materials Research Bulletin*, 47:1233–1238.
- Sarantopoulou, E., Kobe, S., Kollia, Z., Podmiljšak, B., McGuinness, P., Dražić, G., and Cefalas, A. C. (2003) Magnetic and Optical Properties of Single  $4f^n$  and Mixed  $4f^{n-1}5d$  Electronic Configurations of Trivalent Rare Earth Ions in Wide Band Gap Dielectric Crystals. *Journal of Magnetism and Magnetic Materials*, 267:182–190.
- Sastry, S. S., and Rao, B. R. V. (2014) Spectroscopic Studies of Copper Doped Alkaline Earth Lead Zinc Phosphate Glasses. *Physica B: Condensed Matter*, 434:159–164.
- Sava, B. a., Elisa, M., Boroica, L., and Monteiro, R. C. C. (2013) Preparation Method and Thermal Properties of Samarium and Europium-Doped Alumino-Phosphate Glasses. *Materials Science and Engineering: B*, 178:1429–1435.
- Sazali, E. S., Sahar, M. R., Ghoshal, S. K., Arifin, R., Rohani, M. S., and Awang, A. (2014) Optical Properties of Gold Nanoparticle Embedded  $\text{Er}^{3+}$  Doped Lead–Tellurite Glasses. *Journal of Alloys and Compounds*, 607:85–90.
- Schaffer, C. E., & Jorgensen, C. K. (1958). The Nephelauxetic Series of Ligands Corresponding to Increasing Tendency of Partly Covalent Bonding. *Journal of Inorganic and Nuclear Chemistry*, 8: 143-148.
- Selvaraju, K., and Marimuthu, K. (2013) Structural and Spectroscopic Studies on Concentration Dependent  $\text{Sm}^{3+}$  Doped Boro-Tellurite Glasses. *Journal of Alloys and Compounds*, 553:273–281.
- Seshadri, M., Radha, M., Rajesh, D., Barbosa, L. C., Cordeiro, C. M. B., and Ratnakaram, Y. C. (2015) Effect of  $\text{ZnO}$  on Spectroscopic Properties of  $\text{Sm}^{3+}$  Doped Zinc Phosphate Glasses. *Physica B: Condensed Matter*, 459:79–87.
- Seshadri, M., Rao, K. V., Rao, J. L., and Ratnakaram, Y. C. (2009) Spectroscopic and Laser Properties of  $\text{Sm}^{3+}$  Doped Different Phosphate Glasses. *Journal of Alloys and Compounds*, 476:263–270.

- Shankhwar, N., Kothiyal, G. P., and Srinivasan, A. (2014) Understanding The Magnetic Behavior of Heat Treated  $\text{CaO-P}_2\text{O}_5\text{-Na}_2\text{O-Fe}_2\text{O}_3\text{-SiO}_2$  Bioactive Glass Using Electron Paramagnetic Resonance Studies. *Physica B: Condensed Matter*, 448:132–135.
- Shannon, R. D. (1976) Revised Effective Ionic Radii and Systematic Studies of Interatomic Distances in Halides and Chalcogenides. *Acta Crystallographica Section A*, 32:751-767.
- Sharma, Y. K., Surana, S. S. L., and Singh, R. K. (2009) Spectroscopic Investigations And Luminescence Spectra of  $\text{Sm}^{3+}$  Doped Soda Lime Silicate Glasses. *Journal of Rare Earths*, 27:773–780.
- Shelby, J. E. *Introduction to Glass Science and Technology*. 2<sup>nd</sup>. Ed. London:Royal Society of Chemistry. 2005
- Shih, P. Y., Yung, S. W., and Chin, T. S. (1998) Thermal and Corrosion Behavior of  $\text{P}_2\text{O}_5\text{-Na}_2\text{O-CuO}$  Glasses, *Journal of Non-Crystalline Solids*, 224:143–152.
- Shirsath, S. E., Mane, M. L., Yasukawa, Y., Liu, X., Morisako, A. (2014) Self-ignited High Temperature Synthesis and Enhanced Super-exchange Interactions of  $\text{Ho}^{3+}\text{-Mn}^{2+}\text{-Fe}^{3+}\text{-O}^{2-}$  Ferromagnetic Nanoparticles. *Physical Chemistry Chemical Physics*, 16: 2347–2357.
- SivaRamaiah, G., and LakshmanaRao, J. (2013). Electron Spin Resonance and Optical Absorption Spectroscopic Studies of  $\text{Cu}^{2+}$  Ions in Aluminium Lead Borate Glasses. *Journal of Alloys and Compounds*, 551: 399–404.
- Skomski, R. *Simple Models Of Magnetism*. New York: Oxford University Press Inc. 2008
- Smith, C. E., and Brow, R. K. (2014) The Properties and Structure of Zinc Magnesium Phosphate Glasses. *Journal of Non-Crystalline Solids*, 390:51–58.
- Soltani, I., Hraiech, S., Horchani-Naifer, K., Elhouichet, H., and Férid, M. (2015) Effect of Silver Nanoparticles on Spectroscopic Properties of  $\text{Er}^{3+}$  Doped Phosphate Glass. *Optical Materials*, 46:454–460.
- Som, T., and Karmakar, B. (2008) Infrared-to-red Upconversion Luminescence in Samarium-Doped Antimony Glasses. *Journal of Luminescence*, 128:1989–1996.
- Sreedhar, V. B., Basavapoornima, C., and Jayasankar, C. K. (2014) Spectroscopic and Fluorescence Properties of  $\text{Sm}^{3+}$ -Doped Zincfluorophosphate Glasses. *Journal of Rare Earths*, 32:918–926.

- Sun, H., Ge, F., Zhao, J., & Cai, Z. (2016). Template-directed Synthesis of Hierarchically Mesoporous Superparamagnetic Carbon-coated Nickel Nanoplates. *Materials Letters*, 164:152–155.
- Sundari, S. S., Marimuthu, K., Sivraman, M., and Babu, S. S. (2010) Composition Dependent Structural and Optical Properties of Sm<sup>3+</sup>-Doped Sodium Borate and Sodium Fluoroborate Glasses. *Journal of Luminescence*, 130:1313–1319.
- Suzuki, T., Nasu, H., Hughes, M., Mizuno, S., Hasegawa, K., Ito, H., and Ohishi, Y. (2010) Quantum Efficiency Measurements on Nd-Doped Glasses for Solar Pumped Lasers. *Journal of Non-Crystalline Solids*, 356:2344–2349.
- Tadić, M., Panjan, M., Marković, D., Milošević, I., and Spasojević, V. (2011) Unusual Magnetic Properties of NiO Nanoparticles Embedded in A Silica Matrix. *Journal of Alloys and Compounds*, 509:7134–7138.
- Thomas, S., George, R., Rathaiah, M., Venkatramu, V., Rasool, S. N., and Unnikrishnan, N. V. (2013) Structural, Vibrational And Dielectric Studies of Sm<sup>3+</sup>-Doped K–Mg–Al Zincfluorophosphate Glasses. *Physica B: Condensed Matter*, 431, 69–74.
- Tischendorf, B., Otaigbe, J. U., Wiench, J. W., Pruski, M., and Sales, B. C. (2001) A Study of Short and Intermediate Range Order in Zinc Phosphate Glasses. *Journal of Non-Crystalline Solids*, 282:147–158.
- Udayabhaskar, R., Karthikeyan, B., Ollakkan, M. S., Mangalaraja, R. V., and Baesso, M. L. (2014) Enhanced Fluorescence and Optical Power Limiting in Ag-Nanocomposite Glasses. *Chemical Physics Letters*, 593:1–6.
- Umamaheswari, D., Jamalaih, B. C., Sasikala, T., Chengaiah, T., Kim, I.-G., and Rama Moorthy, L. (2012) Photoluminescence and Decay Behavior of Tb<sup>3+</sup> Ions in Sodium Fluoro-Borate Glasses for Display Devices. *Journal of Luminescence*, 132:1166–1170.
- Vodnik, V. V, Božani, D. K., Bibi, N., Šaponji, Z. V, and Nedeljkovi, J. M. (2008) Optical Properties of Shaped Silver Nanoparticles, *Journal of Nanoscience and Nanotechnology*, 8:1–5.
- Wagh, A., Ajithkumar, M. P., and Kamath, S. D. (2014) Compositional Dependent Structural and Thermal Properties of Sm<sub>2</sub>O<sub>3</sub> Doped Zinc Fluoroborate Glasses., 2: 52–58.
- Weil, J. A., Bolton, J. R., and Wertz, J. E. *Electron Paramagnetic Resonance*. New York: John Wiley and Sons. 1993

- Weckhuysen, B. M., Heidler, R., & Schoonheydt, R. A. *Electron Spin Resonance Spectroscopy*, Springer-Verlag Berlin Heidelberg 2004.
- Widanarto, W., Sahar, M. R., Ghoshal, S. K., Arifin, R., Rohani, M. S., and Effendi, M. (2013) Thermal, Structural and Magnetic Properties of Zinc-Tellurite Glasses Containing Natural Ferrite Oxide. *Materials Letters*, 108:289–292.
- Williams, D. B., and Carter, C. B. *Transmission Electron Microscopy Part 1:Basics*. 2<sup>nd</sup>. Ed. USA: Springer. 2009
- Winterstein, A., Akamatsu, H., Möncke, D., Tanaka, K., Schmidt, M. A., and Wondraczek, L. (2013) Magnetic and Magneto-Optical Quenching In ( $\text{Mn}^{2+}$ ,  $\text{Sr}^{2+}$ ) Metaphosphate Glasses. *Optical Materials Express*, 3:184-193.
- Xiang, X., Zu, X. T., Bao, J. W., Zhu, S., Wang L. M. (2005) Optical Properties and Structure Characterization of Sapphire After Ni Ion, *Journal of Applied Physics*, 98:1–5.
- Yeshchenko, O. a., Dmitruk, I. M., Alexeenko, A. a., and Dmytruk, A. M. (2008) Optical Properties of Sol–Gel Fabricated Ni/SiO<sub>2</sub> Glass Nanocomposites. *Journal of Physics and Chemistry of Solids*, 69:1615–1622.
- Yusoff, N. binti M. (2011). *Optical Properties of Magnesium Phosphate Glass Doped Samarium*. Master Degree. Universiti Teknologi Malaysia, Skudai.
- Yusoff, N. M. (2015). *Physical and Spectroscopic Characteristic of Samarium Doped Magnesium Tellurite Glass Embedded Silver Nanoparticles*. Degree of Philosophy, University Teknologi Malaysia, Skudai.
- Yusoff, N. M., and Sahar, M. R. (2015). Effect of Silver Nanoparticles Incorporated with Samarium-Doped Magnesium Tellurite Glasses. *Physica B: Condensed Matter*, 456:191–196.
- Zarifah, N. A., Halimah, M. K., Hashim, M., Azmi, B. Z., and Daud, W. M. (2010). Magnetic Behaviour of  $(\text{Fe}_2\text{O}_3)_x(\text{TeO}_2)_{1-x}$  Glass System due to Iron Oxide. *Chalcogenide Letters*, 7:565–571.
- Zannoni, E., Cavalli, E., Toncelli, A., Tonelli, M., and Bettinelli, M. (1999) Optical Spectroscopy of  $\text{Ca}_3\text{Sc}_2\text{Ge}_3\text{O}_{12}:\text{Ni}^{2+}$ . *Journal of Physics and Chemistry*, 60:449–455.
- Zhang, J., and Lan, C. Q. (2008) Nickel and Cobalt Nanoparticles Produced by Laser Ablation of Solids in Organic Solution. *Materials Letters*, 62:1521–1524.
- Zhang, J. Z., and Noguez, C. (2008) Plasmonic Optical Properties and Applications of Metal Nanostructures. *Plasmonics*, 3:127–150.