



POLITECNICO DI TORINO
Repository ISTITUZIONALE

Comparison of Ni-Cr and Co-based alloys for fuel injectors

Original

Comparison of Ni-Cr and Co-based alloys for fuel injectors / Scavino G.; Matteis P.; Mortarino G.M.M.; Firrao D.. - (2011).

Availability:

This version is available at: 11583/2458383 since:

Publisher:

Published

DOI:

Terms of use:

openAccess

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

COMPARISON OF Ni-Cr AND Co-BASED ALLOYS FOR FUEL INJECTORS

G. Scavino, P. Matteis, G.M.M. Mortarino, **D. Firrao**

Politecnico di Torino – DISMIC
Torino, Italy

Introduction

- **reduction** of fuel consumption and pollutant emission
 - higher **efficiency** motor development
 - increase of **fuel injection pressure** in cylinders
 - higher **stresses** in injection system components



- inadequacy of steels → use of **Co based alloys** or **Ni-Cr alloys** for components mechanically stressed at high temperature
- **literature about these alloys** mainly concerns wear and corrosion resistance at high temperature, with **few data on high temperature fatigue**



A Ni-Cr alloy is compared with previously examined Co-based ones

Materials & specimens

Tensile and fatigue cylindrical (not notched) specimens, 8 mm diameter

- **“weloral” Ni-Cr alloy made by powder metallurgy + HIP**
- “stellite 6” Co alloys, produced by casting, or by powder metallurgy + HIP

Experimental methods

Mechanical tests

- hardness and micro-hardness tests at R.T.
- tensile tests at R.T., at 250 or 500 °C
- pulsed traction fatigue tests ($R \approx 0$) up to $2 \cdot 10^6$ cycles at 500 °C

Crystallographic and micro-structural tests

- both on as received material, and after the 500 °C treatment
- X ray diffraction (Co anode)
- optical and scanning electron metallography and EDS micro-analysis

Fractography

Chemical composition (% wt.)

HIP PM Ni-Cr Alloy

Ni	C	Cr	Al	Co	Si	Mn	Fe	V	Mg
bal.	0.46	48.5	0.055	0.023	0.41	0.11	0.14	0.028	0.028

Cast Co Alloy


Co	C	Cr	W	Ni	Si	Mn	Fe	V	Nb
bal.	1.19	25.5	5.21	1.99	1.56	0.69	0.85	0.028	0.034

HIP PM Co Alloy


Co	C	Cr	W	Ni	Si	Mn	Fe	V	Nb
bal.	1.48	27.2	4.78	0.30	1.21	0.21	0.44	0.021	0.002

XRD Analyses – HIP PM Ni-Cr alloy (Bragg-Brentano geometry, Co anode)

- ≈ 70 % FCC Ni with some Cr in solid solution
- ≈ 30 % BCC Cr
- Possible Cr carbides



Alloy position in the Ni-Cr phase diagram



XRD Analyses - Co alloys (Bragg-Brentano geometry, Co anode)


❖ **Cast alloy:**

- ❖ Probable prevalence of Co_{FCC} in respect to Co_{HCP}
- ❖ Other phases: Cr carbides and intermetallic compounds
- ❖ Possible phase evolution on heating at 500 °C

❖ **HIP PM alloy:**

- ❖ Prevalence of Co_{FCC} , with some Co_{HCP}
- ❖ Possible presence of intermetallic compounds and carbides
- ❖ No phase evolution on heating at 500 °C


Microstructures - HIP PM Ni-Cr alloy (OM)



Microstructures - HIP PM Ni-Cr alloy


image analysis of SEM – back-scattered (BS) electrons images

50 x 50 μm




Cr-rich BCC phase (black): $\approx 30\%$

Cast Co alloy microstructure



OM, 456 x 362 μm

SEM (BS)



Main primary dendrites

Inter-dendritic carbides (lamellar)

No differences after 500 C treatment

Matrix

Cr	Co	W	Mo	Si
24	71	3.5	0.24	0.65



Cr carbides

Cr	Co	W	Mo
78	15	6.3	0.43

Co, W carbides

Cr	Co	W	Mo
21	47	29	2.7

HIP PM Co Alloy microstructure




Co rich matrix, dispersed carbides, about 2 μm diameter. Grain size in the range of 5-40 μm with the most part in the range 5-10 μm .

Hardness and microhardness





Alloy	Macroscopic hardness	HV 0.05 Dendritic zones	HV 0.05 Carbides rich zones
HIP NiCr Alloy	370 HV100	-	-
Cast Co Alloy	370 HV50	400-430	530-1100
HIP Co Alloy	460 HV50	-	-

Cast sample: scattered results on precipitated carbide zone (hardness indent large in respect to dimension of carbides)

Mechanical tests







Fractography – HIP PM NiCr alloy, tensile fracture at 500 C





The fracture is microscopically ductile (microvoids coalescence) and probably follows the sintered powder boundaries

Fractography – cast Co alloy, tensile fracture at 500 C



Mainly inter-dendritic fracture (a), with some trans-dendritic quasi-cleavage fracture

Fractography – HIP PM Co alloy tensile fracture at 500 C



The fracture is ductile, nucleated by the presence of an inclusion

Fatigue - HIP PM Ni-Cr alloy

pulsed traction fatigue tests ($R \approx 0$), up to $2 \cdot 10^6$ cycles, at **500 °C**

Strength Mpa	Specimens results										Results	
	1	2	3	4	5	6	7	8	9	10	X	O
660					X		X				2	
650								X			1	
640		X		O		O			X		2	2
630												
620			O									1
610												
600	O											1

Fatigue limit (for $2 \cdot 10^6$ cycles) \approx 640 MPa

X: specimen broken before $2 \cdot 10^6$ cycles

O: specimen completes $2 \cdot 10^6$ cycles

CAST Co-Alloy

pulsed traction fatigue tests ($R \approx 0$), up to $2 \cdot 10^6$ cycles, at **500 °C**

Strenght	Specimens results										Results	
Mpa	1	2	3	4	5	6	7	8	9	10	X	O
410	X		X								2	
400							X				1	
390		O		X		O		X		X	3	2
380									O			1
370					O							1

Fatigue limit (for $2 \cdot 10^6$ cycles) \approx 390 MPa

X: specimen broken before $2 \cdot 10^6$ cycles

O: specimen completes $2 \cdot 10^6$ cycles

HIP PM Co-alloy

pulsed traction fatigue tests ($R \approx 0$), up to $2 \cdot 10^6$ cycles, at **500 °C**

Strength Mpa	Specimens results										Results	
	1	2	3	4	5	6	7	8	9	10	X	O
740	X										1	
720												
700		X									1	
680				X		O					1	1
660			O		O							2

Fatigue limit (for $2 \cdot 10^6$ cycles) \approx 660 MPa





X: specimen broken before $2 \cdot 10^6$ cycles

O: specimen completes $2 \cdot 10^6$ cycles

Fractography – HIP PM NiCR alloy, fatigue fracture at 500 C

640MPa


660MPa





propagation

Nucleation zone (detail)

Fractography – HIP NiCR alloy, fatigue tests at 500 C



Fractography – cast Co alloy, fatigue fracture at 500 C



Nucleation and
propagation fatigue
fracture zones


detail of stair-step
fatigue propagation

Fractography – HIP PM Co alloy, fatigue test at 500 °C




Fracture surface observed by means of Stereo Macro-scope.

The fatigue fracture is nucleated by the presence of an inclusion.



Nucleation zone (detail)



Discussion and conclusions (I/II)

- ★ Hipped PM Ni-Cr are biphasic, with about 70% Ni-rich FCC and 30% Cr BCC phases (confirmed by XRD analyses), with 1-5 μm grain size, with some porosity and inclusions
- ★ The cast Co alloy samples are formed by cobalt rich, FCC primary dendrites and lamellar inter-dendritic zones (eutectic mixtures) with high carbides content. EDS micro-analyses evidenced two carbide types: one with high Cr content, the other with high W content.
- ★ Hipped PM Co alloy samples present a Co rich matrix and dispersed carbides, about 2 μm diameter. Grain size is in the range of 5-40 μm with the most part in the range 5-10 μm .

Discussion and conclusions (II/II)

- ◆ The best performance both in tensile tests and in fatigue tests was observed for the hiped PM samples. In particular, in monotonic tests, the hiped Cr-Ni alloy was intermediate between the cast Co alloy and the hiped alloy. In fatigue tests the hiped Cr-Ni alloy behaved almost as the hiped Co alloy and much better than the cast Co one.
- ◆ The tensile fracture of the cast Co alloy is mainly inter-dendritic, completed by a quasi cleavage intra-dendritic fracture. In the HIP treated materials (both the Ni-Cr alloy and the Co one), a ductile fracture is nucleated by inclusions.
- ◆ In fatigue tests, the crack of cast samples is nucleated by casting defects and propagates on crystallographic planes, in a trans-dendritic way, with a stair morphology. The crack of hiped samples is nucleated by an inclusion and the fracture is mainly ductile.