

New glass coatings for high insulating greenhouses without light losses – energy saving, crop production and economic potentials

Silke Hemming, Frank Kempkes, Vida Mohammadkhani
Wageningen UR Greenhouse Horticulture, Droevendaalsesteeg 1, 6708 PB Wageningen,
The Netherlands.

Keywords: glass coating, anti-reflection, low-emission, covering material, light transmission, energy saving, k-value

Abstract

More than 90% of Dutch greenhouse area is covered with single glass. Energy losses through the covering are high during heating period (winter) but energy requirements are also high during cooling period (summer) in the case of semi-closed greenhouses. Until now, light losses of insulating coverings prevented growers from using double glass or plastic film. However, increasing energy prices allow new developments. Wageningen UR Greenhouse Horticulture studied the possibilities to use modern glass coatings to increase light transmission and save energy.

Several glass types (standard glass, 90+ glass, low-iron glass) were covered with different anti-reflection coatings from different producers. Double glasses were produced; their optical properties were determined. It was possible to produce double glasses with new coatings having a higher light transmission than traditional single greenhouse glass (83-85% for hemispherical light, compared to 82-83% for traditional single glass) and a k-value of $3.6 \text{ Wm}^{-2}\text{K}^{-1}$ (compared to $7.6 \text{ Wm}^{-2}\text{K}^{-1}$ of a traditional single glass). Other double glasses were produced using a combination of anti-reflection and modern low-emission coatings, reaching an even lower k-value of $\approx 2.4 \text{ Wm}^{-2}\text{K}^{-1}$, however, showing a slight light loss (78.5% for hemispherical light).

Calculations of greenhouse climate (temperature, humidity, CO_2) and energy consumptions year-round were carried out with a validated dynamic climate model. Additionally the effects on tomato production (dry matter) were calculated for the different prototypes of coated and insulated glass. Double materials show the highest energy saving with 25-33%, depending on the composition but also low-emission coatings on single glass decrease the energy use with 15-20%. Economic calculations with current tomato and energy prices showed that single and double glasses with anti-reflection coating currently have the highest potentials.

INTRODUCTION

With increasing energy prices the need for energy saving is high in horticulture. The energy saving potentials of double layered covering materials for greenhouse applications have been pointed out in many research studies before (e.g. Andersson and Nielsen 2000; Bot 2001; Villeneuve et al. 2005; Zhang et al. 1996). However, until now suitable greenhouse covering materials combining both a high transmission and a high insulation value for greenhouse applications are missing. Though many studies focussed on the development of modern materials in order to save energy and/or achieve a better cooling of greenhouses (e.g. Hemming et al. 2006, 2007; Swinkels et al. 2001; Waaijenberg et al. 2004;), the optimum combination of materials properties is still not found. Since more than 90% of Dutch greenhouse area is covered with single glass,

energy losses through the covering are high during heating period (winter) but also during cooling period (summer) in semi-closed greenhouses. This research will show the future potentials of recently developed glass coatings (anti-reflection and low-emission) for single and double materials in order to have as well a high crop production and high energy savings year-round.

MATERIALS AND METHODS

Covering materials

In a pre-study several glass types were evaluated: greenhouse glass, greenhouse glass 90+, greenhouse glass low-iron. Glasses were covered with different anti-reflection coatings by three different producers: SA, CS and GG, applied by sputtering or etching. Double glasses were produced from all glasses; their optical properties were determined using modern light measurement equipment. The materials used are shown in Table 1 and Figure 1. In a follow-up study different prototypes of covering materials produced by GG were evaluated in order to study their energy saving potential, and their plant performance. Glasses were covered with an anti-reflection coating having partly near infrared (NIR) reflective properties, others were combined with a low-emission coating for a higher NIR-reflection. All single glasses had a thickness of 4 mm, double glasses had a distance of 8 mm (split). The materials used are shown in Table 2 and Figure 2.

Optical properties

The optical properties of the glasses described above were determined at Wageningen UR Greenhouse Horticulture laboratory in The Netherlands. The total light transmission in the PAR range (τ_{PAR} in 400-700nm) of samples with the size of 50cm by 50cm was measured with a large and a small integrating sphere (port opening 40cm * 40cm or 8cm * 8cm). Data was gathered by means of a diode-array spectrophotometer with a resolution of 1nm. The PAR transmission for perpendicular light (τ_{PAR_p}) and the PAR transmission for hemispherical light (τ_{PAR_h}) were determined following NEN 2675. The total solar spectrum (300-2500nm) was measured on a Perkin Elmer spectrophotometer. The emission coefficient was determined following EN12898. All relevant data is shown in Table 1, Table 2, Figure 1, Figure 2. From measured optical data the amount of PAR energy (400-700nm) and the amount of NIR energy (700-2500nm) entering the greenhouse was calculated. For a clear sky the radiation energy per nanometer wavelength is defined by CIE 85 (1989). Multiplying the global radiation per wavelength (or spectral range) with the measured spectral transmission of a covering material gives the fraction of the energy entering through the material into the greenhouse.

Dynamic climate model

Model calculations of greenhouse climate and energy consumption were carried with the KASPRO model developed by de Zwart (1996). The dynamic simulation model KASPRO can simulate a full-scale virtual greenhouse based on the construction elements, greenhouse equipment, different covering materials and their properties (transmission, reflection, emission), set points for inside climate and the outside climate of a given location. Output are several climate parameters, such as air temperature, relative humidity, CO₂-concentration and energy consumption. The model is based on the computation of relevant heat and mass balances (Bot, 1983). The heat balances describe both the convective and radiative processes. The mass balances are constituted from

exchange processes through leakage and ventilation (de Jong, 1990). They include canopy transpiration (Stanghellini, 1987) and condensation at cold surfaces. De mass balances around the CO₂-concentration are based on losses of CO₂ by ventilation and photosynthesis, and gains of CO₂ by dosing and respiration. Greenhouse climate is controlled by a replica of commercially available climate controllers. A standard Venlo glass-greenhouse with a trellis bar of 9.6 m carrying two roofs of 4.8 meter is assumed with a distance between two trellis of 5 m for all calculations. Three glass panes of 1.675 m are in between two trellis bars. A standard energy screen is installed inside the greenhouse. The total set of differential equations is solved numerically (de Zwart, 1996). Tomato is chosen as model crop. Plant datum is 8th December, last harvest takes place on 25th November next year. Climate set points are according to Dutch horticultural practice. Crop production is calculated in terms of dry matter production.

RESULTS AND DISCUSSION

In a pre-study several glass types (greenhouse glass, greenhouse glass 90+, greenhouse glass low-iron) were covered with different anti-reflection coatings by three different producers (SA, CS, GG). Double glasses were produced from all glasses (Table 1). The light transmission of the basic materials greenhouse glass, greenhouse glass 90+, greenhouse glass low-iron differ, depending on their origin and their amount of iron content. Standard greenhouse glass single has a hemispherical light transmission of 82.4%, greenhouse glass 90+ single of 83.2% and greenhouse low-iron glass single of 84.4%. Applying an anti-reflection coating results in a decrease of reflection from about 12% to about 5.5-6.5% (data not shown). The coating from SA results in an increase of 6.8% transmission for hemispherical light in average. Applying an anti-reflection coating of CS or GG results in an increase of 7.3-7.4% transmission for hemispherical light. If double glasses are produced from these basic glasses, the application of an anti-reflection coating on all sides of the glasses has a large effect on the light transmission. While the light transmission of a double glass without any coating has a transmission for hemispherical light of 71.6%-75.1% depending on the original glass type (Table 1), these transmission values are increased up to 82.2%-86.0%. That means that, while traditional double glass is losing about 10% of light, modern double glass, coated with anti-reflection coating have comparable transmissions as traditional single greenhouse glass. Some glasses will even give higher light levels inside the greenhouse. From the spectral transmission of the different glasses with anti-reflection coating (Figure 1) we see, that the CS and GG coating are increasing the whole range of PAR (400-700nm), while the SA coating mainly increases the red part of the spectrum. It is remarkable that the GG coating cuts a large part of UV (300-400nm) and is reflecting part of NIR (700-2500nm).

For a follow-up study several prototypes of glass covering materials (single and double) were produced and covered with different coatings (anti-reflection coating with partly NIR reflection and low-emission coating with high NIR reflection). The aim was both to increase light transmission by adding an anti-reflection coating and/or to reduce energy losses by adding a low-emission coating and by producing double layered glass panes decreasing the k-value. Measurements of the optical properties (Table 2) combined with greenhouse light transmission data show that differences in global radiation sum and PAR radiation sum on crop level occur (Table 3). While the anti-reflection coating increases light transmission of single and double materials, the low-emission coating slightly reduces light transmission, when used as double material. On the other side the anti-reflection coating reduces the amount of global radiation by reflecting part of the

NIR, which leads to an improved k-value, from 7.6 to 7.1 $\text{Wm}^{-2}\text{K}^{-1}$. The low-emission coating reduces the amount of global radiation on crop level even more by reflecting higher amounts of NIR, decreasing the k-value to 5.7 $\text{Wm}^{-2}\text{K}^{-1}$. Both double materials show a highly decreased k-value of 3.6 and 2.3 $\text{Wm}^{-2}\text{K}^{-1}$ in the case of only anti-reflective coating and combined anti-reflective and low-emission coatings respectively. That leads to energy savings in winter. One of the research questions is, if this is also advantageous in summer, in cooled greenhouses.

Calculations for a virtual traditional tomato greenhouse equipped with different GG glasses were carried out. Table 3 shows the difference in modelled (inside) cover temperature at day and night time. The double glasses and the low-emission coating cause a higher cover temperature. This results in a lower condensation towards the inner surface of the cover and in an increase of humidity levels. Therefore a need for higher ventilation occurs (Table 3). Double layered coverings show a lower CO_2 concentration inside the greenhouse especially during spring until autumn.

Looking deeper into that mechanism, we can conclude that the CO_2 lack is on one hand caused by a lower CO_2 production by the boiler, due to a lower energy consumption of the greenhouse with double glass or with low-emission coating. On the other hand it is caused by a higher need for ventilation due to higher humidity levels, but also because of higher temperatures and lower heat losses due to the lower k-value. This effect is explained in Figure 3. The single material with low-emission coating shows a much higher cover temperature than the reference material. This leads to higher convective energy losses. At the same time radiation losses are very low and compensate this effect. This situation is advantageous in winter, the result is a lower energy consumption than in the reference. However, in summer low radiation losses are disadvantageous, since that leads to higher temperatures inside the greenhouse and a higher need for ventilation. Double materials show comparable effects, energy losses are even lower in winter due to the insulating split (Figure 3), in summer the low k-value leads to a higher need for ventilation (Table 3). In case of semi-closed greenhouses the need for cooling will be increased for materials with low-emission coating even though the amount of NIR coming inside the greenhouse is reduced (Table 6). The same is true for double materials, the low k-value does not seem to be advantageous during hot periods.

The combination of CO_2 , temperature, humidity and PAR radiation results in a net photosynthesis production (dry weight). Year round dry weight production is shown in Table 4. While it is 8.3 $\text{kg}\cdot\text{m}^{-2}$ in the reference situation (equal to about 54 kg fresh weight), it is increased by single glass with anti-reflection coating to 9.0 $\text{kg}\cdot\text{m}^{-2}$ dry weight production. The double glass with anti-reflection coating gives the same result than the reference, since the PAR levels are higher but a lack of CO_2 occurs. The double glass with anti-reflection and low-emission coating results in a decreased dry weight production of 7.6 $\text{kg}\cdot\text{m}^{-2}$. The last is mainly caused, not by a lower PAR transmission, but by a large lack of CO_2 (Table 3). Additional CO_2 can be applied from an external source in order to compensate this lack of CO_2 . If this is done, the dry matter production can be increased to levels above the reference in case of GG single AR-AR and GG double AR-AR-AR-AR. GG single AR-low ϵ will be equal to the reference. In case of GG double AR-AR-low ϵ -AR dry weight production is still below reference since PAR transmission remains the limiting factor for production (Table 4).

The year-round gas consumption is 34.5 $\text{m}^3\cdot\text{m}^{-2}$ in the reference and 25.7 and 23.1 $\text{m}^3\cdot\text{m}^{-2}$ in case of the GG double materials without and with low-emission coating respectively (Table 3). Double materials are able to reduce the energy consumption with

25% for GG double AR-AR-AR-AR, GG double AR- low ϵ -AR-AR has the highest energy saving with 33%. Extra energy losses due to a higher need for ventilation caused by higher humidity levels are already included in these figures. The energy consumption of GG single AR-AR is slightly increased. Although PAR transmission of the glass is higher than the reference, the partly NIR blocking effect of the coating (Figure 2) causes a higher energy consumption during the heating period. This is not the case for other anti-reflection coatings from SA and CS as used in the pre-study. Since those glasses increase the amount of global radiation coming inside the greenhouse (Figure 1), energy consumption is decreased by 1-2% in case of single glasses (Hemming et al. 2006).

If we carry out an economical analysis, we can conclude that there is some possibility to invest in new materials (Table 5). In the economic analysis benefits from the changed crop yields under the different covering materials are considered, as well as energy costs related to changed gas consumption. Other variable costs like labour, water, nutrients, crop protection, substrate, packaging and auction costs vary with crop yield and are calculated on yearly base considering typical average Dutch costs and prices from KWIN (2008). Investment costs for greenhouse and equipment are not considered and are assumed to be equal in all situations. The result of the economic analysis is the possible extra yearly investment for the covering material and necessary adaptations of the greenhouse construction (in case of double materials). Single anti-reflection coated glass and also double anti-reflection coated glass are most beneficial with a possible yearly investment of €2.0-2.5 per m². The latter is more sustainable in terms of lower energy consumption, however also more expensive. The use of low-emission coatings does not seem to be very attractive (€0.90 possible investment per m² per year). The use of external CO₂ can overcome part of the disadvantages during summer and improves the possible yearly investment for the covering up to €1.32 per m² per year (data not shown).

ACKNOWLEDGEMENTS

This research was funded by the European Commission (EC), “Efficient use of input in protected horticulture” (EUPHOROS), grant agreement 211457. The project is co-financed by the Dutch Ministry of Agriculture, Nature and Food quality (LNV).

Literature cited

- Andersson, N. E. and O. F. Nielsen 2000. Energy Consumption, Light Distribution and Plant Growth in Greenhouse partly insulated with non-transparent Material. *Gartenbauwissenschaft* 65 (5): 190–194
- Bot, G.P.A. 2001. Developments in indoor sustainable plant production with emphasis on energy saving. *Computers and Electronics in Agriculture* 30: 151–165.
- Bot, G.P.A. 1983. Greenhouse climate: from physical processes to a dynamic model. Ph. D. Thesis Agricultural University Wageningen, The Netherlands.
- Cie, 1989. Solar Spectral Irradiance. CIE 85, ISBN 978 3 900734 22 0.
- Hemming, S.; Kempkes, F.; Braak, N. van der; Dueck, T.A.; Marissen, A. 2007. Greenhouse cooling by NIR-reflection. *Acta Horticulturae* 719 . - p. 97 - 106.
- Hemming, S.; Kempkes, F.L.K.; Mahammadkhani, V.; Stanghellini, C.; Swinkels, G.L.A.M.; Holterman, H.J. 2006. Anti-reflectie-coating voor tuinbouwglas, eerste praktijkervaringen. Wageningen UR Glastuinbouw, report 130, pp. 59.
- Jong, T. de 1990. Natural ventilation of large multi-span greenhouses. Ph. D. Thesis Agricultural University Wageningen, The Netherlands.
- KWIN 2008. Kwantitative informatie voor de glastuinbouw. WUR Glastuinbouw.

- Stanghellini, C. 1987. Transpiration of greenhouse crops. An aid to climate management. Ph. D. Thesis, Agricultural University Wageningen, The Netherlands.
- Swinkels, G.L.A.M., P. J. Sonneveld; G. P. A. Bot 2001. Improvement of Greenhouse Insulation with Restricted Transmission Loss through Zigzag Covering Material. J. agric. Engng Res. 79 (1), 91-97
- Villeneuve, J., D. de Halleux, A. Gosselin, D. Amar 2005. Concept of Dynamic Liquid Foam Insulation for Greenhouse Insulation and the Assessment of Its Energy Consumption and Agronomic Performances. Acta Horticulturae 691: 605-610.
- Waaijenberg, D., S. Hemming, G. Bot en J. Campen 2004. The solar greenhouse: a highly insulated greenhouse with an inflated roof system with PVDF or ETFE membranes, Acta Horticulturae 691, 561 – 568.
- Zhang, Y., L. Gauthier, D. de Halleux, B. Dansereau, A. Gosselin 1996. Effect of covering materials on energy consumption and greenhouse microclimate. Agricultural and Forest Meteorology 82: 227-244.
- Zwart, H.F. de 1996. Analyzing energy-saving options in greenhouse cultivation using a simulation model. IMAG-DLO rapport 96-05.

Tables

Table 1 Optical properties of different greenhouse glasses from three different producers (SA, CS, GG) with anti-reflection coatings

Type greenhouse glass	Type coating	Transmission perpendicular τ_{PARp} [-]	Transmission hemispherical τ_{PARh} [-]
CS basic single	no	0.893	0.824
CS basic single	AR-AR	0.942	0.893
CS basic double	no	0.808	0.716
CS basic double	AR-AR-AR-AR	0.897	0.822
CS low-iron single	no	0.910	0.844
CS low-iron single	AR-AR	0.959	0.911
CS low-iron double	no	0.840	0.751
CS low-iron double	AR-AR-AR-AR	0.929	0.860
SA 90+ single	no	0.903	0.832
SA 90+ single	AR-AR	0.970	0.906
SA 90+ double	no	0.829	0.732
SA 90+ double	AR-AR-AR-AR	0.942	0.836
GG 90+ single	no	0.903	0.832
GG 90+ single	AR-AR	0.965	0.905
GG 90+ double	no	0.829	0.732
GG 90+ double	AR-AR-AR-AR	0.934	0.850

Table 2 Optical properties of different greenhouse glasses (GG) with anti-reflection and/or low-emission coatings

Type greenhouse glass	Type coating	Transmission perpendicular τ_{PARp} [-]	Transmission hemispherical τ_{PARh} [-]	Emission coefficients $\epsilon_{up} / \epsilon_{inside\ up} / \epsilon_{inside\ down} / \epsilon_{down}$ [-]	NIR reflection factor [-]	k-value material [Wm ⁻² K ⁻¹]
single (ref)	no	0.897	0.822	0.89/-/-/0.89	0	7.60
single	AR-AR	0.965	0.905	0.85/-/-/0.85	0.24	7.14
single	AR-low ϵ	0.901	0.838	0.85/-/-/0.11	0.32	5.73
double	AR-AR-AR-AR	0.934	0.850	0.85/0.85/0.85/0.85	0.36	3.61
double	AR-AR-low ϵ -AR	0.872	0.785	0.85/0.17/0.85/0.85	0.42	2.37

Table 3 Year-round global and PAR radiation, CO₂-concentration, covering temperature (inside), condensation at covering, vapour loss through ventilation openings and relative humidity under different greenhouse glasses calculated by KASPRO

	Ref	GG single AR-AR	GG single AR-lowε	GG double AR-AR- AR-AR	GG double AR-AR- lowε -AR
global radiation sum at crop level [kJ.cm ⁻²]	265.1	252.4	223.1	224.2	199.5
PAR radiation sum at crop level [kJ.cm ⁻²]	132.7	143.2	132.7	136.6	126.2
CO ₂ concentration [ppm]	737	738	706	701	689
window opening [%]	21.9	21.4	23.8	24.0	25.2
T _{cov} day [°C]	14.7	14.7	17.3	17.7	19.8
T _{cov} night [°C]	10.2	10.2	12.5	12.8	13.6
Relative humidity day [%]	85	85.4	86.5	87.1	87.2
Relative humidity night [%]	84.3	84.3	87.6	88.1	88.7
Condensation at covering [kg.m ⁻²]	113.6	114.9	49.7	36.5	10.5
Vapor loss by ventilation [kg.m ⁻²]	495.3	483.6	536.8	547.4	573.2

Table 4 Year-round energy consumption, dry weight production and CO₂ concentration under different greenhouse glasses calculated by KASPRO, CO₂ use from boiler only and additional CO₂ use from an external source.

		Ref	GG single AR-AR	GG single AR-lowε	GG double AR-AR- AR-AR	GG double AR-AR- lowε -AR
CO₂ source						
boiler	CO ₂ concentration 11:00-16:00 h [ppm]	747	750	721	715	704
	gas use from boiler [m ³ .m ⁻²]	34.5	35.5	28.4	25.7	23.1
	Dry weight production [kg.m ⁻²]	8.3	9.0	8.0	8.3	7.6
	dosage CO ₂ [kg.m ⁻²]	26.1	27.1	24.4	25.2	24.8
boiler & external	CO ₂ concentration 11:00-16:00 h [ppm]	798	800	794	790	787
	gas use from boiler [m ³ .m ⁻²]	33.7	34.7	27.7	25.0	22.4
	Dry weight production [kg.m ⁻²]	9.0	9.8	9.0	9.3	8.5
	dosage CO ₂ [kg.m ⁻²]	43.5	43.8	46.1	47.3	48.3

Table 5 Economic analysis of different covering materials considering benefits from the crop yield, energy costs related to gas consumption and other variable costs on yearly base (traditional greenhouse)

	Ref	GG single AR-AR	GG single AR-lowε	GG double AR-AR- AR-AR	GG double AR-AR- lowε -AR
Benefit / crop yield [€·m ² ·year ⁻¹]	46.96	50.81	45.52	46.88	42.67
Energy costs / gas consumption [€·m ² ·year ⁻¹]	10.40	10.70	8.66	7.91	7.16
Variable costs [€·m ² ·year ⁻¹]	23.73	25.09	23.14	23.63	22.16
Total benefit - costs [€·m ² ·year ⁻¹]	12.83	15.03	13.72	15.35	13.36
Possible yearly investment for greenhouse covering (compared to reference [€·m ² ·year ⁻¹])	-	2.19	0.89	2.51	0.53

Table 6 Year-round energy consumption [m³ gas.m⁻²] under different greenhouse glasses (GG) with anti-reflection and/or low-emission coatings calculated by KASPRO (semi-closed, cooled greenhouse).

	Ref	GG Single AR-AR	GG single AR-lowε	GG double AR-AR- AR-AR	GG double AR-AR- lowε -AR
Gas use [$\text{m}^3 \cdot \text{m}^{-2}$]	33.8	34.9	28.2	25.4	23.0
Gas use [%]		3.4	-16.5	-24.6	-32.0
Cool energy [$\text{MJ} \cdot \text{m}^{-2}$]	450	409	470	481	524
Cool energy [%]		-9.3	4.4	6.9	16.3

Figures

Figure 1 Spectral transmission of glass with different anti-reflection coatings from three different producers (SA, CS, GG) for perpendicular PAR (400-700nm)




Figure 2 Spectral transmission of glass with coatings (anti-reflection and low-emission) for perpendicular global radiation (300-2500nm)




Figure 3 Cover temperature, energy loss by radiation and convection under different greenhouse glasses (GG) with anti-reflection and/or low-emission coatings calculated by KASPRO on a typical winter (left) summer (right) and day.

