Supporting Information

Spherical LDH–Ag°-montmorillonite heterocoagulated system with pH-dependent sol-gel structure for controlled accessibility of AgNPs immobilized on the clay lamellae

Ágota Deák¹, László Janovák¹, Szabolcs Péter Tallósy², Tamás Bitó³, Dániel Sebők⁶, Norbert Buzás⁴, István Pálinkó⁵ and Imre Dékány^{1,4,6}*

¹Deparment of Physical Chemistry and Materials Science, University of Szeged, H-6720, Szeged, Rerrich B. tér 1, Hungary

²Institute of Clinical Microbiology and Diagnostics, Faculty of Medicine, University of Szeged, Semmelweis str. 6, H-6725 Szeged, Hungary

³Department of Obstetrics and Gynaecology, University of Szeged, H-6725, Szeged, Semmelweis str. 1, Hungary

⁴Department of Medical Chemistry, Faculty of Medicine, University of Szeged, H-6720, Szeged, Dóm tér 8, Hungary

⁵Department of Organic Chemistry, University of Szeged, H-6720, Szeged, Dóm tér 8, Hungary

⁶MTA-SZTE Supramolecular and Nanostructured Materials Research Group, University of Szeged, H-6720, Szeged, Dóm tér 8, Hungary




Figure S1. UV-Vis spectra of 3 wt% initial Na-mont. and Ag^0 -mont. dispersions and pure 30 ppm AgNPs sol for reference. The inserted TEM picture shows a single montmorillonite lamella containing ~20 nm surface AgNPs.




Figure S2. A typical charge titration curve representing the streaming potential values of LDH(sph) as a function of added SDS surfactant at pH= 3.2 (a), and the determined specific surface charges of the LDH(sph) sample at different pH values (b).




Figure S3. Absorbance spectra at various concentrations of Ag° -mont. suspensions (**a**) and the calibration line from the spectra (**b**). The released Ag° -mont. amount in percentage vs time at pH= 3 and 6 (**c**). The inserted picture shows the schematic drawing of a Hanson vertical diffusion cell.




Figure S4. SAXS curves of the LDH(sph)–Ag°-montm. (= 25/75%), pure Na-montm. and pure Ag°-montm. samples at pH= 3.0 (**a**) and in $Ih^3 vs$. h^3 representation (Porod plot) (**b**).