



La Science à l'œuvre pour le
at work for Canada

NRC Publications Archive Archives des publications du CNRC

Fabrication of proton exchange membranes using melt processing technologies

Mokrini, Asmae; Vuillaume, Pascal; Diaz-Quijada, Gerardo; Robitaille, Lucie

NRC Publications Record / Notice d'Archives des publications de CNRC:

<http://nparc.cisti-icist.nrc-cnrc.gc.ca/npsi/ctrl?action=rtdoc&an=11344012&lang=en>

<http://nparc.cisti-icist.nrc-cnrc.gc.ca/npsi/ctrl?action=rtdoc&an=11344012&lang=fr>

Access and use of this website and the material on it are subject to the Terms and Conditions set forth at

http://nparc.cisti-icist.nrc-cnrc.gc.ca/npsi/jsp/nparc_cp.jsp?lang=en

READ THESE TERMS AND CONDITIONS CAREFULLY BEFORE USING THIS WEBSITE.

L'accès à ce site Web et l'utilisation de son contenu sont assujettis aux conditions présentées dans le site

http://nparc.cisti-icist.nrc-cnrc.gc.ca/npsi/jsp/nparc_cp.jsp?lang=fr

LISEZ CES CONDITIONS ATTENTIVEMENT AVANT D'UTILISER CE SITE WEB.

Contact us / Contactez nous: nparc.cisti@nrc-cnrc.gc.ca.



National Research
Council Canada

Conseil national
de recherches Canada

Canada

Fabrication of proton exchange membranes using melt processing technologies.

Asmae Mokrini, Pascal Vuillaume, Gerardo Diaz, Lucie Robitaille

Industrial Materials Institute – National Research Council of Canada. 75 de
Mortagne, Boucherville (QC) Canada
Asmae.mokrini@cnrc-nrc.gc.ca

This presentation reports new routes to prepare functional polymers for PEMFC applications developed in our group. Several melt-processing technologies, such as twin-screw extrusion, melt blowing, calendaring and compression moulding were used to prepare advanced polymer blends and nanocomposites based on fluoropolymers and hydrocarbon elastomers. The properties of these polymer blends are to a large level determined by the processing history and the interfacial properties. Our work has shown that materials developed exhibit a valuable combination of mechanical, chemical and electrochemical properties while being melt processed. The use of melt processable ionomers is also expected to provide a significant cost-reduction compared to conventional PEM fabrication technologies and will ease the scale-up toward mass production.

Blend membranes preparation and interface modification are addressed to obtain optimized semi-fluorinated and hydrocarbon composite membranes. Semi-fluorinated electrolyte materials recently developed at IMI showed a conductivity similar or higher than commercial PFSA-based PEM. These electrolytes show a room temperature conductivity of $8 \cdot 10^{-2}$ S/cm when fully humidified, with a mechanical resistance up to 20 MPa for an elongation at break of 200%. The membranes maintained their mechanical strength after an outstanding 6000 hydration/dehydration cycles. The conductivity and fuel cell performance is expected to be enhanced, particularly at high temperature and low RH by the incorporation of the fillers based on HPA/clays complexes and heterocycles/silica nanoparticles being developed presently.