

Г



Title	Synthesis of acyl chitin derivatives and miscibility characterization of their blends with poly(-caprolactone)
Author(s)	Sugimoto, Masao; Kawahara, Mariko; Teramoto, Yoshikuni; Yoshiyuki Nishio
Citation	Carbohydrate Polymers (2010), 79(4): 948-954
Issue Date	2010-03-17
URL	http://hdl.handle.net/2433/97920
Right	c 2009 Elsevier Ltd. All rights reserved.
Туре	Journal Article
Textversion	author

1	Synthesis of acyl chitin derivatives and miscibility characterization of their blends with
2	poly(<i>\varepsilon</i> -caprolactone)
3	
4	
5	
6	Masao Sugimoto, Mariko Kawahara, Yoshikuni Teramoto*, Yoshiyuki Nishio
7	
8	Division of Forest and Biomaterials Science, Graduate School of Agriculture, Kyoto University,
9	Kyoto 606-8502, Japan
10	
11	*Corresponding author. Tel.: +81-75-753-6252; fax: +81-75-753-6300.
12	E-mail address: teramoto@kais.kyoto-u.ac.jp (Y. Teramoto)

14 ABSTRACT

Chitin derivatives having a normal acyl group (side-chain carbon number, N = 2-6) at different 1516degrees of substitution (DS) were synthesized by a homogenous reaction of crab shell chitin with various acyl chlorides in N,N-dimethylacetamide-LiCl solution. NMR analysis quantitatively 17demonstrated the acylations not only for C3/C6 hydroxy protons but also for C2 amino proton(s). 18 Solution cast blend films of the acyl chitin products with poly(*ɛ*-caprolactone) (PCL) were provided 19for the miscibility characterization by differential scanning calorimetry. The critical total-DS 2021required for attaining a miscibility of the blending polymer pair decreased with an increase in N. 22The degree of miscibility was enhanced definitely with an increase in ester-DS, but it made less correlation with amide-DS. In analogy with cellulose ester/PCL blend systems, a structural 2324affinity of the ester side-group of the chitinous component considered with a repeating unit of PCL may be a crucial factor for the miscibility attainment. 25

- 26
- 27 Key words: acyl chitin; degree of substitution; $poly(\varepsilon$ -caprolactone); polymer blend; miscibility
- 28

29 1. Introduction

30

31Chitin, which is supplied in abundance by marine crustaceans, is a representative of a naturally 32occurring polysaccharide derived from animal sources. It is structurally similar to cellulose and can be regarded as cellulose with the hydroxyl group at position C2 replaced by an acetylamino 33 group. However, the difference in property between chitin and cellulose arises due to the presence 34of amino groups in the former, which is advantageous in that it can provide distinctive biological 35 functions, for example, bioassimilability and antibacteriality. Therefore, chitin has a large 36 potential for developing as specially functionalized materials in medical, pharmaceutical, food, and 37textile industries. 38

Chitin has a highly ordered structure because of intra- and intermolecular hydrogen bondings. 39 Its rigid crystalline structure with multiple hydrogen bonds causes serious problems based on its 40 41poor solubility and thermal-moldability. To improve the processibility for subsequent applications, acylation has been extensively studied as a modification reaction, where carboxylic acids (Teramoto 42et al., 2006; Yang et al., 2009), acid anhydrides (Hirano & Ohe, 1975; Kurita et al., 1977; Nishi et 43al., 1979; Shoruigin & Hait, 1935), and acyl chlorides (Fujii et al., 1980; Kaifu et al., 1981; Kurita 4445et al., 1988) have been used as attacking reagents. However, it is still not so easy to thermally mold the product (Acyl-Ch) alone, because the glass transition temperature and melting or flowing 46point are fairly high; marked thermal decomposition can be a serious problem. In order to alter the 47thermal properties of Acyl-Ch, the utilization of plasticizer is an effective method. If we adopt 48 flexible polymers as plasticizer, we can avoid possible problems in the use of low molecular weight 49plasticizers, such as fume generation in the molding process and bleeding out in long-term 50applications. 51

52 As is well established, polymer/polymer blending is an important method to modify the original 53 physical properties of one or both of the components, or to obtain new polymeric materials having 54 wide-ranging properties. Blend works of chitinous polymers including deacetylated product

(chitosan) have been facilitated (Honma et al., 2003; Ko et al., 1997; Kubota et al., 1998; Lee et al.,
1996; Miyashita et al., 1995, 1996, 1997a, b; Nishio et al., 1999) and the number of examples is still
increasing. Among them, chitinous blends with water-soluble or hydrophilic synthetic polymers
(Aoi et al., 1995; Kubota et al., 1998; Lee et al., 1996; Miyashita et al., 1995, 1996; Nishio et al.,
1999) may be of importance from a standpoint of application as biomedical materials.

Meanwhile, aliphatic polyesters, which provide good biocompatibility and environmental 60 degradability, have also attracted considerable interest as candidate materials for a blending partner 6162 of chitinous (Honma et al., 2003; Ikejima & Inoue, 2000; Ikejima et al., 1999; Mi et al., 2002; Mi et al., 2003; Sarasam & Madihally, 2005; Senda et al., 2002; Wan et al., 2008) and other biomass 63 64 polymers (Kusumi et al., 2008; Nishio et al., 1997; Teramoto et al., 2009). Several preparation methods of chitinous blends with aliphatic polyesters proved to be a potential route leading to 65 biomaterials applicable for tissue engineering (Sarasam & Madihally, 2005; Wan et al., 2008) and 66 67 drug delivery systems (Mi et al., 2002, 2003); these studies were based on the control of the inter-component morphology on the micrometer scale, however. Generally, it seems more difficult 68 to obtain intimate mixtures of chitinous polymers and aliphatic polyesters on the scale of a few 69 nanometers, which can be judged to be thermodynamically miscible in the amorphous fraction of 7071the mixture.

72In the present study, a representative aliphatic polyester, $poly(\varepsilon$ -caprolactone) (PCL), was chosen as a counterpart for Acyl-Ch blends. In contrast to chitinous polymers, PCL is easily 73heat-moldable due to a rather low melting temperature (~60 °C); therefore this is an eligible partner 74Acyl-Ch derivatives having various normal acyl side groups (- COC_nH_{2n+1} ; for blending. 75side-chain carbon number, N = n + 1 = 2-6), i.e., acetate (Ac-Ch), propionate (Pr-Ch), butyrate 76 (Bu-Ch), valerate (Va-Ch), and caproate (Ca-Ch), were synthesized by a homogeneous reaction of 77crab shell chitin with different acyl chlorides in N,N-dimethylacetamide (DMAc)-LiCl solution. 7879Formerly, one of the authors (Y. N.) has prepared several cellulose ester (CE) derivatives and investigated an effect of the side-chain length on the blend miscibility with PCL (Kusumi et al., 80

2008; Nishio et al., 1997). It was reported that cellulose butyrate (CB) and valerate (CV) 81 exhibited the highest miscibility. In that case, a dipole-dipole interaction between the carbonyl of 82 83 PCL and that in the side groups of CB and CV appeared to be an important factor for the miscibility. A possibility of further contribution of a structural similarity was also pointed out; because CB and 84 CV have the same structural unit as that of PCL, if the carbon atoms in a glucopyranose unit are 85 taken into account. A main objective of the present study is to clarify the relationship between the 86 ability of Acyl-Ch to form a miscible blend with PCL and the side-chain structure in terms of 87 88 side-chain length (N) and degree of substitution (DS), through observations of the thermal behavior for the binary polymer mixtures. We also intend to compare the extent of blend miscibility 89 between Acyl-Ch/PCL and CE/PCL systems, possibly, both of them being 90 a biodegradation-controllable material of great promise based on a difference in the degradation 91behavior between the constituents (Kusumi et al., in press; Teramoto & Nishio, 2004). 92

- 93
- 94

95 2. Experimental section

96

97 2.1 Materials

98

An original material of chitin isolated from crab shells (Fluka 22720 Chitin Lot & Filling code: 99 405226/1 12900) was purified by treatment with aqueous hydrochloric acid and sodium hydroxide 100 solutions according to a Hackman's method (Hackman, 1954). The nominal molecular weight of 101102 the chitin material is 400,000. The degree of deacetylation (DD) of the purified chitin (p-Ch) was 103 5.0 %, determined by infrared spectroscopy (Sannan et al., 1978). The viscosity average 104 molecular weight (M_v) was evaluated for a deacetylated product of the p-Ch, treated with 50 wt% aqueous NaOH at 95±5 °C, by measuring the intrinsic viscosity ([η]) in a solvent of 0.1:4.0:0.2 M 105NaCl/urea/acetic acid (Tokura, 1991); where the Mark-Houwink Sakurada equation, $[\eta] = KM_v^{\alpha}$, 106

107 was used with $K = 8.93 \times 10^{-4}$ dL/g and $\alpha = 0.71$. The corresponding viscosity average degree of 108 polymerization (DP) was determined to be 380 for the p-Ch.

109 PCL with a nominal weight average molecular weight of 15,000 was purchased from Scientific Polymer Products, Inc., and it was used after purification by dissolution in tetrahydrofurane (THF; 110Wako Pure Chemical Industries, Ltd.) and reprecipitation into distilled water. Reagent-grade DMAc, 111 N,N-dimethylformamide (DMF), and dimethyl sulfoxide (DMSO) were purchased from Nacalai 112Tesque, Inc. and stored over molecular sieves 4A before use. Lithium chloride (LiCl) was 113purchased from Nacalai Tesque, Inc., Japan and dried at 120 °C for 12 h in a vacuum oven. 114Triethylamine (TEA), propionyl chloride, *n*-butyryl chloride, *n*-valeryl chloride, and *n*-caproyl 115chloride were obtained from Aldrich or Wako Pure Chemical Industries, Ltd. and used without 116 117further purification. Other solvents were all guaranteed reagent-grade and used as received.

118

119 2.2 Preparation of chitin solution

120

The p-Ch sample was first treated with water, methanol, and DMAc in succession by a solvent exchange technique (Miyashita et al., 1997a; Nishio et al., 1987). The DMAc-wet chitin was then added to a solvent system DMAc-LiCl and stirred at room temperature for 5 days. The solvent DMAc-LiCl was used at a salt concentration of 7 wt% with respect to DMAc. The actual concentration of chitin in the clear solution was controlled at 0.5 wt%; this was determined precisely by weighing the solid film regenerated from a portion of the solution.

127

128 2.3 Synthesis of Acyl-Ch derivatives

129

Acyl-Ch derivatives were synthesized with acid chloride/base catalyst from the chitin solution in a way similar to that used in previous studies for cellulose (Kusumi et al., 2008; Nishio et al., 132 1997). Taking an example of synthesis for Va-Ch, the typical procedure can be summarized as

follows. A solution of 0.098 mol TEA (10 eq/glucopyranose unit) in DMAc (\approx 15 mL) was slowly 133134added dropwise to 400 g of chitin solution (containing 2 g chitin). After 30 min, a solution of 0.28 135mol *n*-valeryl chloride (28 eq/glucopyranose unit) in DMAc (\approx 36 mL) was added to the chitin solution. 136The reactive solution system was stirred continuously at 50 °C under a nitrogen After reaction over a prescribed time period (6-48 h), the solution was added 137 atmosphere. dropwise into a vigorously stirred, large excess amount of distilled water. Then the product 138obtained as precipitate was filtered, dissolved in acetone, and reprecipitated in a large excess of 139distilled hexane, which was followed by standing with slow stirring and collection by filtration. 140Via further repetition of this purification procedure, the collected Va-Ch product was dried at 40 °C 141142in vacuo for three days.

143

144 2.4 Preparation of Acyl-Ch/PCL blends

145

Acyl-Ch/PCL blends were cast in film form from mixed polymer solutions by solvent evaporation. A 1.0 wt% solution of Acyl-Ch and that of PCL were prepared in DMF separately and mixed with each other in the desired proportion which ranged from 10/90 to 95/5 in a weight percent ratio of Acyl-Ch:PCL. After stirring at room temperature for 24 h, each mixed solution (transparent) was poured into a Teflon tray and a film sheet was made by evaporating DMF at 50 °C under reduced pressure (<10 mmHg). The as-cast samples were washed with distilled water and dried at 40 °C in vacuo for 3 days.

153

154 2.5 Measurements

155

Gel permeation chromatography (GPC) was carried out with a Tosoh HLC-8220 GPC apparatus. The measuring conditions were as follows: column, two Tosoh TSK Super HZM-H columns connected with each other; flow rate, 0.25 mL/min; temperature 40 °C; eluent, THF; standard, 159 monodipersed polystyrene.

¹H NMR spectra were measured at 25 °C for purified Acyl-Ch derivatives by using a Varian INOVA300 apparatus. The solvent was CDCl₃, pyridine- d_5 or CF₃COOD and the concentration was 10 mg/mL. Tetramethylsilane was employed as an internal standard. 128 scans were conducted.

FT-IR spectra were measured with a Shimadzu FT-IR 8600C apparatus. All the measurements were carried out at 25 °C. Samples were dried at 80 °C in vacuo for 24 h and a standard KBr pellet method was employed for all the measurements.

Differential scanning calorimetry (DSC) was carried out with a Seiko DSC6200/EXSTAR6000 167The temperature proof-readings were calibrated with an indium standard. 168 apparatus. The 169 calorimetry measurements were made on ca. 5-mg samples at a scanning rate of 20 °C/min under a nitrogen atmosphere. The samples were first heated to 200 °C and immediately quenched to -140 170171°C. In this first cycle, the thermal histories of the respective samples were equalized completely. Then the second scans were run from -140 °C to 200 °C to record stable thermograms. The glass 172173transition temperature (T_g) was determined from the midpoint of the discontinuity in heat flow.

174

175

- 176 **3. Results and discussion**
- 177

178 Characterization of Acyl-Ch derivatives

179

The degree of total acyl substitution (total-DS) of each of the Acyl-Ch products was determined by ¹H NMR measurements. Figure 1 demonstrates a ¹H NMR spectrum obtained for a Bu-Ch sample. In the spectrum, the intensity of the methyl-group proton signals (δ 0.8–1.1 ppm) of acyl moiety was compared with that of the signals (δ 3.1–5.8 ppm) from the chitinous backbone protons located in the anhydroglucosamine unit. We designated a resonance peak area derived from the 185 methyl protons of acyl groups as [A], and an area of the resonance signals from the protons of 186 glucopyranose as [B]. Then, for Ac-Ch, Pr-Ch, Bu-Ch, Va-Ch, and Ca-Ch, the respective total-DS 187 values were calculated by

- 188 total-DS = ([A] / 3) / ([B] / 7)
- 189 Hereafter, Acyl-Ch of total-DS = x is encoded as Acyl_x-Ch.

In the present acylation system, for detailed molecular characterization, we should take into 190consideration the reaction of acyl chlorides not only with protons in the hydroxyl groups but also 191 with C2-NH₂ and C2-NHCOR of chitin (DD = 5 % for p-Ch). This is supported by FT-IR 192193 spectroscopy qualitatively. Figure 2 displays FT-IR spectra of p-Ch and selected Bu-Ch samples. As can be seen from the spectral data, no absorption was present in the spectral region associated 194 with NH_2 (1625 cm⁻¹) after the acylation. Instead, for the Bu-Chs, a remarkable development in 195absorption was observed in 1750 cm⁻¹ (ester C=O). With an increase in total-DS (\geq 2.50 in Fig. 2), 196 the amide I band (1660 cm⁻¹, C=O of NHCOR) shifted to the side of higher frequency, implying the 197 suppression of the intramolecular hydrogen bondings of the C=O with O6H and/or N-H (Focher et 198 al., 1992; Pearson et al., 1960). Further increasing total-DS gave rise to a suppression in the amide 199 I band, while a new absorption at 1710 cm⁻¹ (C=O of N(COR)₂) was present and it became 200prominent with increasing total-DS. This observation indicates the occurrence of N-acylation of 201202the acetamide and/or N,N-diacyl substitution on the glucosamine residue. Similar N,N-diacyl substitution was reported previously for the acylation of chitosan with acyl chloride in refluxed 203pyridine and chloroform (Fujii et al., 1980). 204

Detailed quantitative molecular characterization for Acyl-Ch samples can be conducted by ¹H NMR. A series of the spectra exhibited signals of the protons of acetamide methyl (1.8 ppm) and amide N-H (6.1 ppm), other than those of the acyl methyl and chitinous backbone discussed above for the estimation of total-DS. Since there is no NH_2 moiety in the chitin derivatives after the acylation as has been shown in the FT-IR measurements (Fig. 2), the ¹H NMR data were used for the determination of amide-DS, ester-DS, and DD, where amide-DS and ester-DS denote the average number of acyl substitution associated with C2-NH₂/C2-NHCOR and C3-OH/C6-OH, respectively, per glucosamine residue of chitin. In Fig. 1, we designate a peak area of the resonance of the acetamide methyl protons as [C] and an area of the resonance signal from the amide N-H proton as [D]. Then, the values of DD, amide-DS, and ester-DS are able to be determined by following equations, respectively:

216
$$DD = (1 - ([C] / 3) / ([B] / 7)) \times 100 (\%)$$

amide-DS = total-DS - ([C] /
$$3 + [D]$$
)

$$218$$
 ester-DS = total-DS - amide-DS

Table 1 tabulates the four parameters evaluated for the Acyl-Ch products prepared in this study. In a general trend, Acyl-Ch samples with higher total-DS incorporated higher ester-DS. Amide-DS was estimated to be >1 for most of the Acyl-Ch products, reflecting the replacement of *N*-acetate with another acyl group for these samples. Eventually, DD values were determined to be 10–80 %, raised noticeably from an initial value 5 % for p-Ch.

The series of Acyl-Ch was found to have improved solubility in conventional solvents, compared with chitin. As listed in Table 1, Acyl-Ch derivatives with higher DS and longer side chains showed better solubility in ordinary organic solvents. Particularly, Pr-Ch, Bu-Ch, Va-Ch, and Ca-Ch with higher total-DSs (3.06–3.77, 2.50–3.33, 2.32–3.09, and 2.64–2.94, respectively) were soluble in MeOH, differing from the corresponding CE samples with similar acyl DSs.

Values of the weight-average molecular weight (and the corresponding weight average DP) of representative Acyl-Ch samples were determined by GPC, as follows: 8.81×10^4 (210), 12.8×10^4 (267), 12.4×10^4 (244), and 12.3×10^4 (225), for Pr_{3.16}-Ch, Bu_{3.33}-Ch, Va_{3.48}-Ch, and Ca_{3.42}-Ch, respectively. Taking into consideration a viscosity average DP (380) of p-Ch, the DP of the Acyl-Ch products tended to slightly decrease, indicating some extent of scission of the chitinous backbone chain in the acylation reaction. The molecular weight distributions for the above four products were 2.89 (Pr_{3.16}-Ch), 2.51 (Bu_{3.33}-Ch), 1.94 (Va_{3.48}-Ch), and 2.25 (Ca_{3.42}-Ch).

Binary blend films of Acyl-Ch products with PCL were prepared in a wide range of compositions by solution casting from DMF solution. Thus obtained blend films were visually homogeneous, but the transparency decreased with an increase in PCL content. Higher transparency was usually observed for the blends of Acyl-Ch samples of higher total-DSs.

Polymer-polymer miscibility is commonly estimated by the determination of the glass transition 243temperature (T_g) of the blends. If any blend of a binary polymer system exhibits a single glass 244transition between the T_g values of both components and a composition-dependent shift in T_g of the 245blend is observed, then the system can be regarded as a highly miscible one on the $T_{\rm g}$ -detection 246scale that is usually assumed to be less than a couple of tens of nanometers (Kaplan, 1976; Nishio, 2472481994; Utracki, 1990). If one component is crystalline, observation of a regression in the 249development of crystallinity of the crystallizable component (PCL in the present study), caused by addition of the second component (i.e. Acyl-Ch), is a common feature which is shared with other 250crystalline/amorphous polymer pairs that are capable of forming a miscible phase in their blends 251(Imken et al., 1976; Nishi & Wang, 1975). 252

253In this work, the respective blend systems were classified into immiscible, partially miscible, and miscible ones from their DSC measurements from the viewpoints of $T_{\rm g}$ -shift and crystallinity 254regression. The PCL homopolymer gave a T_g signal centering -61.0 °C and besides a sharp 255melting endotherm with a peak maximum ($T_{\rm m}$) at 55.2 °C. The other component Acyl-Ch 256derivatives were almost amorphous and no melting signal was observed in the present thermal 257scanning. As listed in Table 1, a sharp depression of the T_g of chitin (> 200 °C) to the lower 258temperature side was observed along with the increase in total-DS as well as in N. However, no 259glass transition was observed for several samples of lower DSs, in which the acylation was 260261insufficient for internal plasticization of the carbohydrate backbone.

Figure 3a shows DSC thermograms obtained for $Pr_{2.76}$ -Ch/PCL blends. It is judged that the

blending polymer pair is poorly miscible, from observation of the less-significant shift in T_g for both components. In particular, the compositions of 20/80–90/10 showed two independent glass transitions. In addition, the melting endotherm of PCL was observable for every composition with the peak area reducing in direct proportion to the PCL content. Thus, the thermal properties of the respective polymer components were never affected by the presence of the other component in the Pr_{2.76}-Ch/PCL blends.

On the other hand, Va_{2.86}-Ch indicated somewhat better miscibility with PCL. As shown in Fig. 2693b, a series of Va_{2.86}-Ch/PCL blends gave rise to an appreciable degree of elevation in the PCL T_g . 270A similar shift in T_g was observed for the Acyl-Ch component at compositions of 95/5–70/30. 271Furthermore, a cold-crystallization phenomenon took place after onset of the glass transition of the 272273blend on heating for the compositions of 20/80-60/40, reflecting a relatively slow kinetics of 274crystallization of the PCL component from the molten mixtures with Va_{2.86}-Ch. It should also be 275noted that the PCL crystallinity almost vanished when the Va_{2.86}-Ch content reached 90 wt%. These results supports that the polymer pair may be miscible at a certain level in the non-crystalline 276state of the mixture. Therefore, this type of blend system was judged to be partially miscible. 277

Figure 3c demonstrates an example of a miscible pair. Highly butyrated Bu_{3.08}-Ch can be 278279taken as miscible with PCL in the amorphous mixing state, since a single T_g was detected and varied between the T_g values of the two constituent polymers, depending on the blend composition. 280281The crystallinity of the PCL component disappeared completely when the Bu_{3.08}-Ch content increased to 85 wt%. Several other systems composed of a highly substituted Acyl-Ch/PCL pair 282provided similar thermogram data and they were determined to be miscible. In more careful 283inspection, however, the T_g shift was prominent only at compositions rich in Acyl-Ch (> 80 wt%). 284In addition, in such miscible Acyl-Ch/PCL systems, the crystallization habit of PCL remained 285clearly even at 80/20 composition. Contrary to this, in the previous CE/PCL series judged as 286287miscible, the PCL crystallinity was no longer detectable at compositions containing > 60 wt% CE and the blend T_g shifted more conspicuously and smoothly in the composition range of 100/0–60/40 288

(Kusumi et al., 2008). These observations imply that the highly substituted Acyl-Chs generally
show a somewhat lower degree of miscibility with PCL, in comparison with the previously used
CEs.

292

293 Insight into factors for miscibility attainment and comparison with cellulosic systems

294

Figure 4 summarizes the result of the miscibility estimation for Acyl-Ch blends with PCL as a 295function of the number N of carbons in the normal acyl substituent as well as of the substitution 296parameters, total DS, ester DS, and amide DS. For comparison, the corresponding result for CE 297blends with PCL is shown in Fig. 5, compiling the previous data (Kusumi et al., 2008; Nishio et al., 2981997) and a complementary one for cellulose caproate (DS = 2.79 for N = 6) which was prepared 299especially for the present study. Ac-Ch (N = 2) was immiscible with PCL even in the highly 300 301 acetylated state of DS \approx 3.8, as in the situation with cellulose acetate (Higeshiro et al., 2009; Nishio et al., 1997). Other Acyl-Ch products, Pr-Ch (N = 3), Bu-Ch (N = 4), Va-Ch (N = 5), and Ca-Ch 302 (N = 6) showed miscibility with PCL when totally high-substituted grades of them were used. A 303 critical total-DS value for the miscibility attainment, total-DS_{cr}, decreased with an increase in N. 304 305However, for the blend series of Acyl-Ch of N = 3-6, total-DS_{cr} value was generally higher than the 306 critical (ester-)DS for the corresponding CE/PCL system. It should also be recalled that the series of miscible Acyl-Ch/PCL combinations generally showed a lower degree of miscibility with PCL, 307 in comparison with the miscible CE blends, as deduced already from the inspection of $T_{\rm g}$ shift and 308 PCL-crystallinity regression. Such a lower degree of the miscibility can be attributed partly to a 309 steric hindrance of the bulky planar acetamide structure on the chitinous backbone, to the 310 accessibility of oxycaproyl segments of the PCL component. For the miscible CE/PCL blends, we 311inferred a possible contribution of dipole-dipole interaction between the carbonyl of PCL and that in 312the side groups of CE (Kusumi et al., 2008); in the Acyl-Ch/PCL systems, however, similar 313contribution would be suppressed by the steric hindrance mentioned above. 314

It was also reported for the CE/PCL system that a structural affinity of the ester side-group of 315316the cellulosic component considered with a repeating unit of PCL may be a crucial factor for 317 miscibility attainment (Kusumi et al., 2008; Nishio et al., 1997). Namely, as shown in Fig. 6, for instance, the butyryl side-group is structurally identical with the repeating unit of PCL, if the 318carbons in the glucopyranose ring are taken into account. For the present Acyl-Ch series, however, 319 the N-acyl substitution at C2 position can not contribute to the improvement of such an affinity, 320 although the esterification at C3/C6 positions can do. Therefore, higher total-DS_{cr} values would 321be required for the miscibility attainment. Actually, the miscibility increased with an increase in 322ester-DS (Fig. 4b), but there is less correlation between the miscibility and amide-DS (Fig. 4c). 323

Any of CEs with N = 3-5 showed good miscibility with PCL at DSs of ≥ 2.2 , and particularly 324butyrate of N = 4 did even at a comparatively low DS of 1.9 (Fig. 5). However, cellulose caproate 325(N = 6) and enanthate (N = 7) having fairly longer side-chains were estimated to show a relatively 326 327 lower degree of miscibility with PCL (Kusumi et al., 2008). It was assumed, exceptionally, that these CEs would be able to aggregate to form a specific, mesomorphic ordered assembly, as was 328 also suggested for some cellulose triester (Takada et al., 1994) and chitin 3,6-O-diester (Teramoto et 329al., 2006) derivatives having a longer acy substituent. On the other hand, the N-dependence of the 330 331advent of miscibility for the Acyl-Ch blend systems differs from that for the CE systems, namely, 332 the miscibility of the former systems increased with an increase in N so far as the side-chain lengths of ≤ 6 . In particular, Ca-Ch of N = 6 exhibited the lowest total-DS_{cr}, signifying the highest 333 miscibility with PCL. This may be because the caproyl side-chains virtually identical to the 334 repeating unit of PCL can contribute to the enhancement of the miscibility even if it is introduced 335by "N-acylation". 336

Further investigation of the side-chain length effect on the miscibility state may be made in terms of isothermal crystallization behavior of the PCL component in miscible Acyl-Ch/PCL blend systems. The topic including crystallization kinetics and spherulitic morphology will be reported in no distant future.

342

343 Conclusions

344

We prepared chitin derivatives having various normal acyl groups (-OCOC_nH_{2n+1}; side-chain carbon number, N = n + 1 = 2-6) by homogeneous reaction of crab-shell chitin with different acyl chlorides in DMAc-LiCl solution. The degrees of *O*- and *N*-acyl substitutions were separately evaluated by NMR analysis successfully. It was thus shown that the acylating reaction took place not only to the protons in the C3/C6-hydroxyl groups but also to the protons in C2-NH₂ and C2-NHCOR of the starting chitin (DD = 5 %). The replacement of *N*-acetate with another acyl group also arose in these samples.

Subsequently, miscibility characterization was carried out for blends of Acyl-Ch products with PCL. DSC thermal analysis demonstrated that the critical total-DS required for the miscibility attainment, total-DS_{cr}, decreased with an increase in side-chain carbon number *N*. However, for the series of Acyl-Ch blends, the respective total-DS_{cr} values were higher than the critical (ester-)DS for the corresponding CE/PCL system. It was also perceived that the miscibility found for several Acyl-Ch/PCL combinations was generally of a lower degree, in comparison with that for the CE/PCL blends.

In analogy with the CE/PCL systems, the structural affinity of the ester side-group of the chitinous component considered with a repeating unit of PCL may be a crucial factor. However, the *N*-acyl substitution at C2 position seems not to contribute so greatly to the improvement of such an affinity. In support of this, the blend miscibility of Acyl-Chs (N = 3-6) with PCL was enhanced with an increase in ester-DS, but there is less correlation between the miscibility and amide-DS.

364

365

366 **References**

Aoi, K., Takasu, A., & Okada, M. (1995). New chitin-based polymer hybrids. 1. Miscibility of
poly(vinyl alcohol) with chitin derivatives. *Macromolecular Rapid Communications, 16*,
757-761.

- Focher, B., Naggi, A., Torri, G., Cosani, A., & Terbojevich, M. (1992). Structural differences
 between chitin polymorphs and their precipitates from solutions: Evidence from CP-MAS
 ¹³C-NMR, FT-IR and FT-Raman spectroscopy. *Carbohydrate Polymers*, *17*, 97-102.
- Fujii, S., Kumagai, H., & Noda, M. (1980). Preparation of poly(acyl)chitosans. *Carbohydrate Research*, 83, 389-393.
- Hackman, R. (1954). Studies on chitin. 1. Enzymatic degradation of chitin and chitin esters.
 Australian Journal of Biological Sciences, 7, 168-178.
- 378 Higeshiro, T., Teramoto, Y., & Nishio, Y. (2009). Poly(vinyl pyrrolidone-*co*-vinyl 379 acetate)-*graft*-poly(ε -caprolactone) as a compatibilizer for cellulose 380 acetate/poly(ε -caprolactone) blends. *Journal of Applied Polymer Science*, *113*, 2945-2954.
- Hirano, S., & Ohe, Y. (1975). Facile *n*-acylation of chitosan with carboxylic anhydrides in acidic
 solutions. *Carbohydrate Research*, *41*, C1-C2.
- Honma, T., Senda, T., & Inoue, Y. (2003). Thermal properties and crystallization behaviour of blends of poly(ε -caprolactone) with chitin and chitosan. *Polymer International*, 52, 1839-1846.
- Ikejima, T., & Inoue, Y. (2000). Crystallization behavior and environmental biodegradability of the
 blend films of poly(3-hydroxybutyric acid) with chitin and chitosan. *Carbohydrate Polymers*,
 41, 351-356.
- Ikejima, T., Yagi, K., & Inoue, Y. (1999). Thermal properties and crystallization behavior of
 poly(3-hydroxybutyric acid) in blends with chitin and chitosan. *Macromolecular Chemistry and Physics*, 200, 413-421.
- 392 Imken, R. L., Paul, D. R., & Barlow, J. W. (1976). Transition behavior of poly(vinylidene

- fluoride)/poly(ethyl methacrylate) blends. *Polymer Engineering and Science*, 16, 593-601.
- Kaifu, K., Nishi, N., & Komai, T. (1981). Preparation of hexanoyl, decanoyl, and dodecanoylchitin.
 Journal of Polymer Science, Polymer Chemistry Edition, 19, 2361-2363.
- Kaplan, D. S. (1976). Structure-property relationships in copolymers to composites: Molecular
 interpretations of the glass transition phenomemon. *Journal of Applied Polymer Science*, 20,
 2615-2629.
- Ko, M. J., Jo, W. H., Kim, H. C., & Lee, S. C. (1997). Miscibility of chitosans polyamide 6 blends. *Polymer Journal*, 29, 997-1001.
- Kubota, N., Konaka, G., & Eguchi, Y. (1998). Characterization of blend films of chitin regenerated
 from porous chitosan with poly(vinyl alcohol). *Sen'I Gakkaishi*, *54*, 212-218.
- Kurita, K., Chikaoka, S., Kamiya, M., & Koyama, Y. (1988). Studies on chitin. 14. *N*-Acetylation
 behavior of chitosan with acetyl chloride and acetic ahnydride in a highly swelled state. *Bulletin of the Chemical Society of Japan, 61*, 927-930.
- Kurita, K., Sannan, T., & Iwakura, Y. (1977). Studies on chitin. 3. Preparation of pure chitin,
 poly(*n*-acetyl-D-glucosamine), from water-soluble chitin. *Die Makromolekulare Chemie*, *178*,
 2595-2602.
- Kusumi, R., Inoue, Y., Shirakawa, M., Miyashita, Y., & Nishio, Y. (2008). Cellulose alkyl
 ester/poly(ε-caprolactone) blends: Characterization of miscibility and crystallization
 behaviour. *Cellulose*, 15, 1-16.
- (in 412Kusumi, R., Lee. S. Н., Teramoto, Y., & Nishio, Y. press). Cellulose ester-graft-poly(ε -caprolactone): Effects of copolymer composition and intercomponent 413miscibility on the enzymatic hydrolysis behavior. *Biomacromolecules*, 10.1021/bm900666y. 414
- 415 Lee, Y. M., Kim, S. H., & Kim, S. J. (1996). Preparation and characteristics of β -chitin and 416 poly(vinyl alcohol) blend. *Polymer*, *37*, 5897-5905.
- 417 Mi, F. L., Lin, Y. M., Wu, Y. B., Shyu, S. S., & Tsai, Y. H. (2002). Chitin/PLGA blend microspheres
- 418 as a biodegradable drug-delivery system: Phase-separation, degradation and release behavior.

- 419 *Biomaterials*, 23, 3257-3267.
- Mi, F. L., Shyu, S. S., Lin, Y. M., Wu, Y. B., Peng, C. K., & Tsai, Y. H. (2003). Chitin/PLGA blend
 microspheres as a biodegradable drug delivery system: A new delivery system for protein.
 Biomaterials, 24, 5023-5036.
- Miyashita, Y., Kobayashi, R., Kimura, N., Suzuki, H., & Nishio, Y. (1997a). Transition behavior and
 phase structure of chitin/poly(2-hydroxyethyl methacrylate) composites synthesized by a
 solution coagulation bulk polymerization method. *Carbohydrate Polymers*, *34*, 221-228.
- Miyashita, Y., Sato, M., Kimura, N., Nishio, Y., & Suzuki, H. (1996). Effect of deacetylation of
 chitin on the miscibility of chitin/poly(vinyl alcohol) blends (in Japanese, with English
 abstract). *Kobunshi Ronbunshu*, 53, 149-154.
- Miyashita, Y., Yamada, Y., Kimura, N., Nishio, Y., & Suzuki, H. (1995). Preparation and miscibility
 characterization of chitin/poly(*n*-vinyl pyrrolidone) blends (in Japanese, with English
 abstract). *Sen'I Gakkaishi*, *51*, 396-399.
- Miyashita, Y., Yamada, Y., Kimura, N., Suzuki, H., Iwata, M., & Nishio, Y. (1997b). Phase structure
 of chitin poly(glycidyl methacrylate) composites synthesized by a solution coagulation bulk
 polymerization method. *Polymer*, *38*, 6181-6187.
- Nishi, N., Noguchi, J., Tokura, S., & Shiota, H. (1979). Studies on chitin. 1. Acetylation of chitin. *Polymer Journal*, 11, 27-32.
- Nishi, T., & Wang, T. T. (1975). Melting point depression and kinetic effects of cooling on
 crystallization in poly(vinylidene fluoride)-poly(methyl methacrylate) mixtures.
 Macromolecules, 8, 909-915.
- Nishio, Y. (1994). Hyperfine composites of cellulose with synthetic polymers. In R. D. Gilbert (Ed).
 Cellulose polymers, blends and composites (pp. 95-113). Munich, New York: Hanser Gardner
 Publications.
- 443 Nishio, Y., Koide, T., Miyashita, Y., Kimura, N., & Suzuki, H. (1999). Water-soluble polymer
- blends with partially deacetylated chitin: A miscibility characterization. Journal of Polymer

- 445 Science, Part B: Polymer Physics, 37, 1533-1538.
- Nishio, Y., & Manley, R. S. (1988). Cellulose-poly(vinyl alcohol) blends prepared from solutions in
 N,N-dimethylacetamide-lithium chloride. *Macromolecules*, 21, 1270-1277.
- 448 Nishio, Y., Matsuda, K., Miyashita, Y., Kimura, N., & Suzuki, H. (1997). Blends of 449 poly(ε -caprolactone) with cellulose alkyl esters: Effect of the alkyl side-chain length and 450 degree of substitution on miscibility. *Cellulose*, *4*, 131-145.
- Nishio, Y., Roy, S. K., & Manley, R. S. (1987). Blends of cellulose with polyacrylonitrile prepared
 from *N*,*N*-dimethylacetamide-lithium chloride solutions. *Polymer*, *28*, 1385-1390.
- Pearson, F. G., Marchessault, R. H., & Liang, C. (1960). Infrared spectra of crystalline
 polysaccharides. 5. Chitin. *Journal of Polymer Science*, 43, 101-116.
- 455 Sannan, T., Kurita, K., Ogura, K., & Iwakura, Y. (1978). Studies on chitin. 7. IR spectroscopic
 456 determination of degree of deacetylation. *Polymer*, *19*, 458-459.
- 457 Sarasam, A., & Madihally, S. V. (2005). Characterization of chitosan-polycaprolactone blends for
 458 tissue engineering applications. *Biomaterials*, 26, 5500-5508.
- 459 Senda, T., He, Y., & Inoue, Y. (2002). Biodegradable blends of poly(ε-caprolactone) with
 460 alpha-chitin and chitosan: Specific interactions, thermal properties and crystallization
 461 behavior. *Polymer International*, *51*, 33-39.
- 462 Shoruigin, P. P., & Hait, E. (1935). Acetylation of chitin. Berichte der Deutschen Chemischen
 463 Gesellschaft [Abteilung] B: Abhandlungen, 68B, 971-973.
- Takada, A., Fujii, K., Watanabe, J., Fukuda, T., & Miyamoto, T. (1994). Chain-length dependence of
 the mesomorphic properties of fully decanoated cellulose and cellooligosaccharides.
 Macromolecules, 27, 1651-1653.
- Teramoto, Y., Lee, S. H., & Endo, T. (2009). Phase structure and mechanical property of blends of
 organosolv lignin alkyl esters with poly(ε-caprolactone). *Polymer Journal*, *41*, 219-227.
- 469 Teramoto, Y., Miyata, T., & Nishio, Y. (2006). Mesomorphic assemblage of chitin normal acylates
- and rapid enthalpy relaxation of their side chains. *Biomacromolecules*, 7, 190-198.

- 471 Teramoto, Y., & Nishio, Y. (2004). Biodegradable cellulose diacetate-*graft*-poly(L-lactide)s:
 472 Enzymatic hydrolysis behavior and surface morphological characterization.
 473 *Biomacromolecules*, 5, 407-414.
- Tokura, S. (1991). Analysis of chitin and chitosan. In A. Ohtakara, & M. Yabuki (Eds.). *Chitin and chitosan: Experimental manual* (in Japanese) (pp. 49-77). Tokyo: Gihoudo.
- 476 Utracki, L. A. (1990). *Polymer alloys and blends*. Munich: Hanser Gardner Publications.
- Wan, Y., Wu, H., Cao, X., & Dalai, S. (2008). Compressive mechanical properties and
 biodegradability of porous poly(caprolactone)/chitosan scaffolds. *Polymer Degradation and Stability*, 93, 1736-1741.
- 480 Yang, B. Y., Ding, Q., & Montgomery, R. (2009). Preparation and physical properties of chitin fatty
- 481 acids esters. *Carbohydrate Research*, *344*, 336-342.

Figure captions

Fig. 1. ¹H NMR spectrum of $Bu_{2.86}$ -Ch in CDCl₃.

Fig. 2. FT-IR spectra of Bu-Ch and p-Ch.

Fig. 3. DSC thermograms obtained for (a) $Pr_{2.76}$ -Ch/PCL, (b) $Va_{2.86}$ -Ch/PCL, and (c) 490 Bu_{3.08}-Ch/PCL blends. Arrows indicate a T_g position taken as the midpoint of a baseline shift.

Fig. 4. Miscibility maps for different Acyl-Ch/PCL blends, as a function of the number N of carbons in the side-chain and the substitution parameters: (a) total-DS, (b) ester-DS, and (c) amide-DS. Symbols indicate that a given pair of Acyl-Ch/PCL is miscible (circle), immiscible (cross), or partially miscible (triange).

Fig. 5. Miscibility map for different CE/PCL blends, as a function of the number of carbons in the
side-chain and the acyl DS. Symbols indicate that a given pair of CE/PCL is miscible (circle),
immiscible (cross), or partially miscible (triange).

501 Fig. 6. Schematic representation of the similarity in chemical structure between the repeating unit502 of PCL and the butyryl side-groups in CB and Bu-Ch.

Table 1

	Solubility											$T_{\rm g}$ /°C	
	total-DS	amide-DS	ester-DS	DD (%)	THF	chloroform	acetone	pyridine	DMF	DMAc	DMSO	methanol	-
p-Ch					_	-	_	-	_	-	-	-	NE^b
Ac-Ch	1.89	NE	NE	NE	-	-	-	-	-	-	-	-	NE
	2.65	NE	NE	NE	-	-	-	-	-	±	-	-	NE
Pr-Ch	3.89	NE	NE	NE	-	-	-	-	±	+	±	-	196
	2.76	1.09	1.67	36.5	-	-	_	+	+	+	+	±	167
	2.89	1.27	1.62	43.1	+	+	+	+	+	+	+	+	148
	3.06	1.24	1.82	44.2	+	+	+	+	+	+	+	+	111
Bu-Ch	3.16	1.30	1.86	44.5	+	+	+	+	+	+	+	+	140
	3.77	1.77	2.00	80.0	+	+	+	+	+	+	+	+	133
	1.65	1.07	0.58	10.2	-	_	-	+	-	-	-	-	NE
	1.84	1.50	0.34	61.3	-	_	-	+	+	+	+	-	190
	2.50	1.03	1.47	18.8	±	_	+	+	+	+	+	+	175
	2.66	0.99	1.67	14.9	+	+	+	+	+	+	+	+	140
Va-Ch	3.08	1.19	1.89	36.7	+	+	+	+	+	+	±	+	110
	3.33	1.33	2.00	48.9	+	+	+	+	+	+	±	+	103
	1.64	1.31	0.33	33.6	-	-	-	-	-	-	-	-	NE
	1.82	1.17	0.66	18.6	-	±	-	±	±	±	±	-	NE
	2.32	0.97	1.35	25.5	+	+	+	+	+	+	+	+	153
Ca-Ch	2.86	1.49	1.37	70.7	+	+	+	+	+	+	+	+	107
	3.09	1.30	1.79	49.5	+	+	+	+	+	+	+	+	115
	3.48	1.48	2.00	48.6	+	+	+	+	+	+	+	±	53
	2.64	1.04	1.60	37.2	+	+	+	+	+	+	+	+	131
	2.80	1.14	1.66	42.7	+	+	+	+	+	+	+	+	110
	2.94	1.09	1.85	36.8	+	+	+	+	+	+	+	+	110
	3.42	1.42	2.00	60.9	+	+	+	+	+	+	+	±	91

Substitution parameters, solubility data^{*a*}, and T_g for Acyl-Ch samples

^{*a*} +, soluble; \pm , partially soluble; –, insoluble; temperature, 25°C; concentration, 10 mg/mL. ^{*b*} not evaluable.



Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Fig. 6