



US008691385B2

(12) **United States Patent**
Littman et al.

(10) **Patent No.:** **US 8,691,385 B2**
(45) **Date of Patent:** **Apr. 8, 2014**

(54) **COATED AEROGEL BEADS**

(56) **References Cited**

(75) Inventors: **Howard Littman**, Niskayuna, NY (US);
Joel L. Plawsky, Albany, NY (US);
John D. Paccione, Voorheesville, NY (US)

U.S. PATENT DOCUMENTS

5,248,222	A	9/1993	Littman et al.	
5,254,168	A	10/1993	Littman et al.	
7,019,037	B2 *	3/2006	Zemanian et al.	516/100
7,621,668	B2	11/2009	Littman et al.	
2006/0269734	A1 *	11/2006	Krajewski et al.	428/304.4
2007/0205491	A1 *	9/2007	Tew	257/632
2008/0105373	A1 *	5/2008	Ristic-Lehmann et al.	156/286
2009/0082479	A1 *	3/2009	Cho	521/141
2010/0080949	A1 *	4/2010	Ou et al.	428/80

(73) Assignee: **Rensselaer Polytechnic Institute**, Troy, NY (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

OTHER PUBLICATIONS

Park, K.-B., et al., "Mortar properties obtained by dry premixing of cementitious materials and sand in a spout-fluid bed mixer", Cement and Concrete Research, 2005.

(21) Appl. No.: **13/552,305**

* cited by examiner

(22) Filed: **Jul. 18, 2012**

Primary Examiner — Sheeba Ahmed

(65) **Prior Publication Data**

US 2012/0295115 A1 Nov. 22, 2012

(74) *Attorney, Agent, or Firm* — Heslin Rothenberg Farley & Mesiti P.C.

Related U.S. Application Data

(57) **ABSTRACT**

(62) Division of application No. 11/940,118, filed on Nov. 14, 2007, now Pat. No. 8,235,577.

Methods and apparatus for coating particulate material are provided. The apparatus includes a vessel having a top and a bottom, a vertically extending conduit having an inlet in the vessel and an outlet outside of the vessel, a first fluid inlet in the bottom of the vessel for introducing a transfer fluid, a second fluid inlet in the bottom of the vessel for introducing a coating fluid, and a fluid outlet from the vessel. The method includes steps of agitating a material, contacting the material with a coating material, and drying the coating material to produce a coated material. The invention may be adapted to coat aerogel beads, among other materials. A coated aerogel bead and an aerogel-based insulation material are also disclosed.

(60) Provisional application No. 60/865,722, filed on Nov. 14, 2006.

(51) **Int. Cl.**
B32B 5/16 (2006.01)

10 Claims, 8 Drawing Sheets

(52) **U.S. Cl.**
USPC **428/407**; 428/323; 428/327

(58) **Field of Classification Search**
None
See application file for complete search history.




Figure 1




Figure 2

Figure 3





Figure 4






Figure 5




Figure 6



Figure 7




Figure 8




Figure 9




Figure 10

COATED AEROGEL BEADS**CROSS-REFERENCE TO RELATED APPLICATIONS**

This application is related to concurrently filed, commonly assigned application Ser. No. 13/552,298 and is a divisional of application Ser. No. 11/490,118 filed on Nov. 14, 2007, now U.S. Pat. No. 8,235,577, which claims priority from U.S. Provisional Patent Application Ser. No. 60/865,722, filed on Nov. 14, 2006, the disclosures of which are hereby incorporated by reference herein in their entirety.

The subject matter of the present application may also be related to the inventions described in application Ser. No. 11/567,100 filed on Dec. 5, 2006, now U.S. Pat. No. 7,621,668, and provisional application 60/868,468, filed on Dec. 4, 2006. The disclosures of these applications are also included by reference herein in their entirety.

STATE AND FEDERAL FUNDED RESEARCH

The invention described herein was made with New York State support under State Grant Number C010331 from the New York State Department of Transportation. The State of New York may have certain rights to this invention.

The invention described herein was also made with support of the National Aeronautics and Space Administration (NASA) under Federal Grant Number NNM05AA04A. The U.S. Government may have certain rights to this invention.

BACKGROUND OF THE INVENTION**1. Technical Field**

This invention relates, generally, to systems, methods, and apparatus for coating particulate material and the coated particulate material so produced. More particularly, the present invention provides improved draft tube spout fluid bed (DTSFB) having the capability to coat particles with fluids, for example, for coating aerogel beads to provide a useful engineering material, for instance, an improved insulating material.

2. Description of Related Art

Coating particulate material can often enhance the physical and chemical properties of the material, for example, by reducing absorption of liquids and gases or simply protecting the particulate material from environmental degradation. For instance, the coating of particulate material can provide the following enhancements to particulate material: improved insulation properties, both thermal and electrical; improved abrasion resistance; and improved strength.

Aerogel beads were first developed in the 1930s and are the lightest solids known. Aerogels are low-density materials that have proven to be effective insulators. They typically have a thermal conductivity on the order of 0.01 Watts/meter-Kelvin, that is, less than one-third the thermal conductivity of polyurethane foam. However, only recently has the commercial scale production of aerogels been economically feasible. Aerogels are typically referred to by the nicknames "frozen smoke," "solid smoke," or "blue smoke."

Due to their insulating properties and their low density, approximately, 140 kilograms per cubic meter, aerogels have been proposed for insulation in a broad range of applications from insulating liquid natural gas (LNG) supertankers, to insulating superconductor power cables, to insulating spacecraft, such as, insulating the external fuel tanks or crew return vehicle of the space shuttle.

However, typically, untreated aerogels are porous and tend to absorb gases and liquids. For example, about 95% of the surface of aerogel beads contain pores having an average pore size of about 20 nanometers (nm). The absorption of fluids by aerogels may typically destroy the material or, at the very least, interfere with the insulating properties of the beads. The present inventors sought to overcome the porous nature of aerogels by coating aerogels to minimize or prevent the absorption or infiltration of fluids, for example, by applying a polymer coating. However, the very light, low-density nature of aerogels makes them difficult to handle, especially when attempting to coat these minute particles, typically, less than 5 millimeter (mm) in diameter. Aspects of the present invention overcome these technical difficulties, as well as overcoming the disadvantages and limitations of the prior art methods and apparatus.

One device that has been used to handle particulate material is a draft-tube, spout-fluid-bed (DTSFB) mixer. The design and operation of the DTSFB mixer were investigated by Littman, et al. and are disclosed in U.S. Pat. Nos. 5,248,222 and 5,254,168, both of Littman (one of the co-inventors of the present invention), et al. (the disclosures of which are included by reference herein). Recent developments of the DTSFB mixer were reported by Plawsky, et al. (2003), the disclosure of which is also incorporated by reference herein, in which a "first generation" mixer was disclosed. Further improvements in the DTSFB mixer were reported by Park, et al. (2006) in which a "second generation" DTSFB mixer was designed and tested. (The disclosure of Park, et al. (2006) is also included by reference herein.) Aspects of the present invention provide advantages over both Park, et al. (2006) and Plawsky, et al. (2003), and other prior art methods and apparatus.

SUMMARY OF THE INVENTION

Aspects of the present invention provide improved methods and apparatus for coating particulate material using different mechanics than the prior art coating systems. From an industrial point of view, aspects of the invention are easily scaled up from very small units to very large units in a very predictable manner. According to aspects of the invention, methods and apparatus are provided which produce coated particulate materials, for example, coated aerogels, that having improved insulation properties, both thermal and electrical; improved abrasion resistance; and improved strength compared to non-coated particulate materials. Aspects of the invention are based on two main components, namely, a pneumatic coating device and a collection device, such as, a vessel containing a bag filter, which is commonly used for air pollution control and solids recovery.

One aspect of the invention is a particulate material coating apparatus including a vessel having a top and a bottom, the vessel adapted to contain the particulate material; a vertically extending conduit (also known as a "draft tube") having an inlet in the vessel and an outlet outside of the vessel; a first fluid inlet in the bottom of the vessel, the first fluid inlet directed toward the inlet of the vertically extending conduit wherein a flow of a first fluid introduced by the first fluid inlet produces a flow of at least some of the particulate material and the first fluid through the vertically extending conduit; a second fluid inlet in the bottom of the vessel, the second fluid inlet adapted to introduce a second fluid to the flow of fluid introduced by the first fluid inlet, the second fluid adapted to coat at least some of the particulate material; and a fluid outlet from the vessel. The second fluid inlet is typically adapted to introduce the second fluid in the form of a spray, for example,

3

the second fluid inlet may include an orifice, for instance, an orifice having a diameter of about 0.020 inches.

In one aspect, the apparatus may include means for regulating the flow of fluid from the fluid outlet from the vessel, for example, an automated valve, wherein at least one parameter of the flow of the particulate material and fluid through the vertically extending conduit is varied. The parameter varied may be particle flow velocity, fluid flow velocity, voidage, or a combination thereof, for example, for a given total fluid inlet flow.

Another aspect of the invention is a method for coating particulate material including introducing the particulate material to a vessel having a top and a bottom, a vertically extending conduit having an inlet in the vessel and an outlet outside of the vessel, a first fluid inlet in the bottom of the vessel directed toward the inlet of the vertically extending conduit, a second fluid inlet in the bottom of the vessel, and a fluid outlet; introducing a first fluid into the first fluid inlet to produce a flow of the first fluid that produces a flow of at least some of the particulate material and the first fluid through the vertically extending conduit; introducing a second fluid to the second fluid inlet whereby the second fluid is introduced into the flow of the first fluid; and coating at least some of the particulate material with the second fluid. In one aspect, the method further comprises regulating the flow of fluid from the outlet wherein at least one parameter of the flow of the particulate material and fluid through the vertically extending conduit is varied. The parameter may include particle flow velocity, fluid flow velocity, voidage, or combinations thereof, for example, for a given total fluid inlet flow. In one aspect, the particulate material comprises aerogel particles and coating comprises sealing at least some pores in the aerogel particles. The second fluid may comprise an alcohol, a water-based polymer, a solvent-based polymer, or a polyurethane. The second fluid may be air, nitrogen, an inert gas, or another suitable gas.

Another aspect of the invention is a method for coating aerogel beads including agitating a plurality of aerogel beads with a first fluid stream; contacting the agitated beads with a second fluid stream having at least one non-volatile component and at least one volatile component; evaporating at least some of the at least one volatile component contacting the beads wherein at least some of the non-volatile component adheres to a surface of the beads. In one aspect, the method may further comprise transporting the plurality of aerogel beads and the first fluid through a conduit. In another aspect, at least some of the evaporating is practiced during transport through the conduit.

A further aspect of the invention is a coated aerogel material comprising a plurality of aerogel beads at least partially coated with a polymer, for example, coated with a polyvinyl alcohol, a polymethyl methacrylate (PMMA), or a polyurethane, among other volatile materials. In one aspect, the aerogel beads comprise about 1 mm to about 5 mm aerogel beads, typically, about 1 mm to about 3 mm aerogel beads, for example, about 2 mm aerogel beads. Aspects of the present invention provide coated aerogel material having improved insulation properties, both thermal and electrical; improved abrasion resistance; and improved strength, among other things, compared to uncoated aerogel materials.

A still further aspect of the invention is an insulating material comprising a plurality of aerogel beads at least partially coated with a polymer, for example, coated with a polyvinyl alcohol, a polymethyl methacrylate, or a polyurethane, among other volatile materials. In one aspect, the aerogel beads comprise about 1 mm to about 5 mm aerogel beads,

4

typically, about 1 mm to about 3 mm aerogel beads, for example, about 2 mm aerogel beads.

These and other aspects, features, and advantages of this invention will become apparent from the following detailed description of the various aspects of the invention taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE FIGURES

The subject matter, which is regarded as the invention, is particularly pointed out and distinctly claimed in the claims at the conclusion of the specification. The foregoing and other objects, features, and advantages of the invention will be readily understood from the following detailed description of aspects of the invention taken in conjunction with the accompanying drawings in which:

FIG. 1 is a schematic diagram, in cross-section, of a particulate material coating apparatus according to one aspect of the invention.

FIG. 2 is a detailed schematic diagram of the lower section of the apparatus shown in FIG. 1 as identified by detail 2 in FIG. 1.

FIG. 3 is a perspective view of a particulate material coating apparatus according to another aspect of the invention.

FIG. 4 is a front elevation view of the apparatus shown in FIG. 3.

FIG. 5 is a perspective view of the feeding and treating apparatus shown in FIG. 3.

FIG. 6 is a perspective, in cross section, of the inlet of the feeding and treating apparatus shown in FIG. 5.

FIG. 7 is a photograph of magnified aerogel particles as treated according to aspects of the invention.

FIG. 8 is a photograph of a magnified aerogel particle as treated according to aspects of the invention.

FIG. 9 is a photograph of further magnified aerogel particles as treated according to aspects of the invention.

FIG. 10 is a photograph of further magnified aerogel particles as treated according to aspects of the invention.

DETAILED DESCRIPTION OF ASPECTS OF THE INVENTION

Aspects of the present invention may be utilized to coat particulate material in a broad range of applications. For example, aspects of the invention may be used for, but are not limited to, coating particulates, for example, coating any particulate material that is recognizable by those of skill in the art, for example, pharmaceuticals; food stuffs; cosmetics; metals, such as, powder manufacturing powder metals; ceramics; and like particulates. Though the following description of aspects of the invention may refer to the use of aspects of the invention in coating aerogel beads, aspects of the present invention are not limited to handling and treating aerogel beads. It will be understood that one or more other particulate materials may also be handled and treated according to aspects of the invention in similar fashions.

FIG. 1 is a schematic diagram, in cross-section, of a particulate material coating apparatus 10 according to one aspect of the invention. Apparatus 10 includes a vessel 12, for example, a circular cylindrical vessel, though any non-circular or non-cylindrical vessel may be used, as appropriate. Vessel 12 includes a substantially closed top 14 and a substantially closed bottom 16 and, according to aspects of the invention, contains particulate material 18. Though closed bottom 16 is illustrated as having a conical, upwardly expanding geometry in FIG. 1, it will be understood that bottom 16 may comprise any conventional vessel shape, including a

circular or rectangular cylindrical bottom **17** as shown in phantom in FIG. 1. Particulate material **18** may include any particulate material, for example, a powder, pellets, beads, chips, chunks, and the like, which may be metallic or non-metallic, for example, sand, stone, plastics, polymers, pharmaceuticals, saw dust, wood chips, food particles, ceramics, porous material, catalysts, catalytic materials, absorbents, adsorbents, ion exchange resins, and the like. In one aspect, particulate material **18** may comprise aerogel beads, for example, beads of a low-density solid-state material derived from gel in which the liquid component of the gel has been replaced with gas. The aerogel beads may comprise aerogel materials based on silica, alumina, chromia, tin oxide, or carbon, among other materials. The aerogel beads may have diameters ranging from about 50 micrometers [μm] to about 5 millimeters [mm].

In one aspect, particulate material **18** may comprise a plurality of particulate materials, for examples, materials intended to be mixed by apparatus **10**, for instance, sand and cement or two or more pharmaceuticals. In one aspect, particulate material **18** may comprise a material having sufficient voidage, that is, space between particles, that when placed in vessel **12** a fluid, for example, a gas or liquid, may be passed through particulate material **18**, for example, in a direction indicated by arrows **15**. Particulate material **18** may form a level of material **19**, below top **14** of vessel **12** whereby a void space **21** is provided in top **14** of vessel **12**, for example, an annular void space. Void space **21** may provide a plenum into which fluid passes after passing through material **18** prior to, for example, exiting vessel **12**.

According to aspects of the invention, vessel **12** of apparatus **10** includes at least one conduit, pipe, or tube **20** (which may be referred to in the art as a “draft tube”) having an open first end **22** positioned inside vessel **12** and an open second end **24** positioned outside or inside of vessel **12**. Conduit **20** may typically be directed vertically within vessel **12**, as shown in FIG. 1; however, conduit **20** may be oriented at any angle, that is, an angle from the vertical, while effecting the desired function described in this specification and attached claims. Optionally, the open second end **24** of conduit **20** may be located in a second vessel **25** (shown in phantom in FIG. 1). A typical second vessel **25** that may be used in aspects of the invention is described and discussed with respect to FIG. 3 below, though any vessel which is adapted to collect particulate material discharged from open second end **24** may be used. Conduit **20** may have any convenient cross-section, for example, circular, oval, or rectangular, but is typically circular in cross section. In one aspect, conduit **20** may be directed substantially vertically in vessel **12** whereby conduit **20** forms an annular region **26** in vessel **12** between the outside of conduit **20** and the inside of vessel **12**.

Vessel **12** includes at least one fluid inlet **28** positioned in the bottom **16** of vessel **12** for receiving a fluid **36** (that is, a liquid or gas) and at least one fluid outlet **32** positioned in top **14** of vessel **12**. Fluid **36** may be a multiphase fluid, for example, a fluid containing a liquid and solids, a fluid containing a liquid and a gas, a fluid containing a gas and solids, or a fluid containing a liquid, a gas, and solids. It will be understood by those in the art, that the multiphase fluid may contain one or more liquids, one or more gases, or one or more different solids depending upon the treatment to be performed in vessel **12**. Vessel **12** may also include at least one inlet **33**, for example, positioned in top **14**, for instance, for introducing particulate material **18** to vessel **12**. Inlet, or fluid jet, **28** comprises a conduit having a fluid outlet **30** (see FIG. 2) directed toward inlet **22** of conduit **20**. According to aspects of the invention, inlet **28** is so positioned whereby fluid intro-

duced to inlet **28** and directed toward inlet **22** of conduit **20** produces a flow of at least some of particulate material **18** and fluid through the conduit **20**, as indicated by arrows **23**. Due to the typical expansion of fluid flow as the fluid leaves inlet **28**, the diameter of inlet **28** may be smaller than the diameter of inlet **22**. Also, the spacing of inlet **28** from inlet **22** may be varied, for example, the elevation of inlet **28** may be varied, for instance, depending upon the nature of the fluid introduced and the particulate material **18**. In some aspects of the invention, the flow of fluid through inlet **28** may be augmented by one or more additional fluid inlets **29** for introducing a fluid **37**, for example, the same or different fluid **36** introduced to inlet **28**.

According to aspects of the invention, vessel **12** includes a means or mechanism **40** for introducing a coating fluid **41** to vessel **12**. For example, as shown in FIG. 1, mechanism **40** may be one or more spray nozzles **43** adapted to introduce fluid **41** to contact and coat at least some of the particulate material **18**, for example, as material **18** is being transported through conduit **20**. Spray nozzles **43** may be any fluid injection device adapted to expose material **18** to fluid **41**, for example, spray nozzles **43** may introduce a fine mist of liquid, a flow of liquid in a gas, or a flow of gas. In one aspect, mechanism **40** may comprise one or more spray nozzles provided by Spraying Systems Company of Wheaton, Ill., for example, a spraying system having an SU2A air atomizing spray nozzle set up with a fluid cap **2050** and air cap **70**, having a nozzle diameter of about 0.020 inches, though other spraying nozzle systems may be used. Coating fluid **41** may comprise any fluid adapted to coat material **18** being handled, and coating fluid **41** may vary depending upon the nature of material **18** being coated. In one aspect, where material **18** comprises aerogel beads, coating fluid **41** may comprise a polyvinyl alcohol, for example, an OPADRY water-based cationic polymer provided by Colorcon; a polymethyl methacrylate, for example, a water-based anionic polymer, a solvent based cationic polymer or a solvent-based neutral polymer marketed under the trademark EUDRAGIT by Degussa; or a urethane, for example, a polyurethane solution or a waterborne polyurethane solution, among others.

According to aspects of the invention, the outlet **32** may include some means **34** for regulating or controlling the flow of fluid through outlet **32**. Outlet **32** may be a conduit and means **34** may be a valve, for example, a ball, a needle, a globe, or gate valve. In aspects of the invention, means **34** controls the flow of fluid from outlet **32** whereby at least one parameter of the flow of particulate material **18** and fluid through the conduit **20** is varied. For example, varying the flow through outlet **32** may vary particle flow velocity, fluid flow velocity, voidage, or a combination of two or more of these parameters. In one aspect of the invention, vessel **12** may include at least one means **35** for controlling the pressure drop across conduit **20**. For example, means **35** may comprise a dp cell or a differential pressure indicator having high and low pressure taps appropriately positioned in vessel **12** and/or vessel **25**. Contrary to prior art devices, for example, the device disclosed by Plawsky, et al. (2003), by controlling or regulating the pressure drop across conduit **20**, aspects of the present invention permit the operator to regulate or control the flow of the particulate material through conduit **20**, for example, to control the flow regime in conduit **20** or control the solids fraction of the particulate material flowing through conduit **20**. In FIG. 1, means **35** is illustrated schematically for reference only; however, in aspects of the invention, a pressure drop across conduit **20** may be controlled by mean of a restriction in conduit **20** or a restriction down stream of conduit **20**, for example, a restriction in optional vessel **25** or

a restriction in a conduit leading from vessel **25**, such as, a valve. The controlling of the pressure drop across conduit **20** may be practiced by controlling or regulating the pressure in vessel **12**, by controlling or regulating the pressure in optional vessel **25**, or both.

FIG. 2 is a detailed schematic diagram of the lower section of the apparatus **10** shown in FIG. 1 as identified by Detail 2 in FIG. 1. According to aspects of the invention, as a fluid, for example, a gas or a liquid, is introduced to vessel **12** through inlet **28**, as indicated by arrows **36**, the fluid enters vessel **12** and entrains and/or agitates at least some of particulate material **18** into open end **22** of conduit **20**, as indicated by arrows **38**, and transfers particulate material **18** through conduit **20**, as indicated by arrow **23**. As described in, for example, U.S. Pat. No. 5,248,222, the introduction of a pressurized fluid, typically, air (though other gases or liquids may be used), into inlet **28** (and/or other inlets **29**) agitates and/or entrains the particulate material **18** above inlet **28** whereby particulate material **18** will flow like a fluid. In one aspect of the invention, this agitation and/or aeration of particulate material is often referred to as "fluidization," whereby a normally solid particulate material **18** is induced to behave somewhat like a fluid under the influence of the fluid introduced to inlet **28** and, possibly, inlets **29**. The fluidization of the particulate material and the consequent creation of a pressure differential between the open end **22** and open end **24** of conduit **20** promotes the flow of the aerated particulate material **18** from open end **22**, through conduit **20**, and out of open end **24**.

According to aspects of the invention, while material **18** is entrained, agitated, and/or fluidized by fluid introduced by inlet **28**, at least one further fluid **41** is introduced by means **40**, for example, one or more nozzles **43**, to contact the material **18** with fluid **41**. In one aspect, fluid **41** comprises a fluid adapted to at least coat at least some of the surface of the individual particles of material **18**. In one aspect, at least 25% of the surface of particulate material **18** is receives at least some fluid **41**. In another aspect of the invention, at least 50% or even at least 75%, of the surface area of the material receives at least some fluid **41**. In some aspects more than 90% or even substantially 100% of the surface area of material **18** may be covered or coated with fluid **41**.

During or after coating material **18** with fluid **41**, the fluid **41** is allowed to "dry" onto the surface of material **18**, for example, by evaporation of any volatile components present in fluid **41**, whereby at least some non-volatile component of fluid **41** adheres to at least some of the surface of particulate material **18**, to provide a coated particular material **18**. In one aspect, at least some of the surface of particulate material **18**, for example, at least 25% of the surface, is coated with a non-volatile component of fluid **41**. In another aspect of the invention, at least 50% or even at least 75%, of the surface area of the material is coated with a non-volatile component of fluid **41**. In some aspects, more than 90% or even substantially 100% of the surface area of material **18** may be covered or coated with a non-volatile component of fluid **41**. According to aspects of the invention, this drying or evaporation of volatile components may be accelerated by the fluid flow introduced via inlet **28**. For example, the fluid introduced via inlet **28** may comprise a fluid having little or no concentration of the volatile component of fluid **41**, for example, fluid **41** may be a low humidity air or low humidity nitrogen, among other gases. In another aspect, the fluid introduced to inlet **28** may be heated, for example, heated air, to enhance evaporation of the volatile components of fluid **41**.

In some aspects of the invention, at least some of the fluid introduced through inlets **28** and **29** may also pass through particulate material **18** in annulus **26**, as indicated by arrows

42, and exit vessel **12** through outlet **32**. Thus, according to aspects of the invention, apparatus **10** may comprise an apparatus for handling or transporting particulate material **18** through conduit **20**; an apparatus for treating particulate material **18** with a fluid **36**, that is, for treating particulate material **18** in conduit **20**, in annulus **26**, or a combination thereof; an apparatus for mixing one or more particulate materials; or a combination thereof. However, unlike prior art apparatus, in apparatus **10** according to aspects of the present invention, the nature of the flow of material in conduit **20** and annulus **26** may be moderated and controlled, for example, by manipulating the pressure drop across conduit **20**, for instance, by manipulating valve **34** in outlet **32**. As noted above, the pressure drop across conduit **20** may be varied in numerous ways according to the invention, for example, by introducing a restriction to conduit **20**; by introducing a restriction to a down stream flow, for example, by means of a pressure control element, such as, a valve; or by providing a vessel **25** downstream of conduit **20**, for example, a vessel in which pressure is regulated. In one aspect of the invention, the concentration of the solid particles **18** transferred through conduit **20** may be regulated and/or controlled by regulating and/or controlling the pressure drop across conduit **20**, for example, by manipulating a valve in an outlet from a downstream vessel.

Apparatus **10** shown in FIGS. 1 and 2, with or without means **35** for controlling the pressure drop across conduit **20**, may be used to handle, coat, treat, and/or react particulate material **18** or for handling, treating, or reacting fluid **36**. For example, apparatus **10** may comprise a mixing apparatus for mixing two or more materials. Apparatus **10** may also comprise a treatment apparatus, for example, an apparatus for treating the fluid introduced to inlet **28** with the particulate material **18**. Apparatus **10** shown in FIGS. 1 and 2, with or without means **35** for controlling the pressure drop across conduit **20**, may be used to execute a chemical or physical reaction, for example, a reaction that particulate material **18** may or may not take part in, for example, may or may not catalyze, using at least part of the fluid streams **36** entering through inlet **28** (or auxiliary inlets **29**). A chemical or physical reaction may take place in the annular region **26**, or in conduit **20**, or both in region **26** and in conduit **20**. A reaction may also take place in down stream vessel **25**. Particulate material **18** may return at least in part through inlet **33** after residence in vessel **25**, for example, where a physical or chemical reaction may have taken place prior to return through inlet **33**, though substantially all of the material **18** passed to vessel **25** may be returned to vessel **12**. Typical chemical or physical reactions that may be practiced in vessel **12** may include, but are not limited to, catalytic oil cracking, protein separations, particle mixing, and particle coating, among others.

According to aspects of the invention, particulate material **18** may comprise one or more particulate materials, such as sand and cement, that when aerated, coated, and transported through conduit **20** are at least partially mixed or agitated to provide a mixture of coated particulate material discharged from open end **24** of conduit **20**. For example, during transport through conduit **20**, the inventors surmise that the turbulent eddies generated in conduit **20** provide shearing forces that overcome particle surface effects, such as van der Waals forces and electrostatic forces that hold individual particles in clumps, to break up clusters and clumps of particulate material and provide a more uniformly mixed material. In another aspect of the invention, as discussed above, apparatus **10** may comprise a coating apparatus by which one or more particulate materials **18** may be coated with a material contained in

fluid 41 introduced to means 40, for example, a nozzle 43, before or during transport through conduit 20.

FIG. 3 is a perspective view of a particulate material coating apparatus 100 according to another aspect of the invention. FIG. 4 is a front elevation view of apparatus 100 shown in FIG. 3. Apparatus 100 includes a feeding and treating apparatus 102 and a drying and collecting apparatus 104. Similar to apparatus 10 shown in FIGS. 1 and 2, in one aspect of the invention, feeding and treating apparatus 102 conveys particulate material while coating the material conveyed, for example, aerogel beads. Apparatus 102 includes a vessel 112, for example, a circular cylindrical vessel, having a substantially closed top 114 and a substantially closed bottom 116 and, according to aspects of the invention, contains particulate material 118 (not shown). Particulate material 118 may include any particulate material, for example, particulate materials that may comprise particulate material 18 described above. In one aspect, particulate material 118 may comprise aerogel beads. Apparatus 102 includes a plurality of inlet conduits in bottom 116 and at least one outlet conduit 120, for example, a “draft tube,” in top 114. Further details of apparatus 102 are illustrated and described with respect to FIG. 5, which illustrates a detailed perspective view of apparatus 102.

As shown in FIG. 4, drying and collecting apparatus 104 is mounted above apparatus 102 and is adapted to receive particulate material 118 fed by apparatus 102 through conduit 120. Apparatus 104 also includes a vessel 212, for example, a circular cylindrical vessel, having a substantially closed top 214 and a substantially closed bottom 216 and, according to aspects of the invention, contains particulate material 119 transferred from apparatus 102, for example, coated particulate material 118. Apparatus 104 includes at least one inlet in communication with the at least one outlet conduit 120 from apparatus 102 and at least one outlet conduit 220 in top 214. Though closed bottom 216 may comprise any conventional vessel geometry, in the aspect of the invention shown in FIGS. 3 and 4, bottom 216 comprises an eccentric conical bottom, for example, offset to avoid interference with conduit 120. Bottom 216 may include one or more outlets 218 for discharging treated particulate material 119, for example, to storage or further treatment. Outlet 218 may be in direct communication with one or more inlets 133 into apparatus 102, for example, via one or more conduits 222, whereby treated particulate material 119 may be re-introduced to apparatus 102 for further treatment, for example, for further coating. Conduit 222 may include one or more flow control or flow isolation devices.

FIG. 5 is a detailed perspective view of the feeding and treating apparatus 102 shown in FIGS. 3 and 4 and FIG. 6 is a cross-sectional view of the detailed perspective view of bottom 116 of apparatus 102 shown in FIG. 5. As shown, bottom 116 comprises a conical divergent transition 117 having divergent side walls, an inlet 128, mounted by flange 132, directed to the apex of conical transition 117, and a plurality of inlets 130 directed into the divergent sidewalls of transition 117. Conical transition 117 surrounds an open end 122 of conduit 120, that is, a “draft tube,” and is mounted to vessel 112 by means of flange 134. According to aspects of the invention, bottom 116 also includes a nozzle 140 having an orificed end 142 adapted to direct a fluid stream toward the open end 122 of conduit 120. For example, nozzle 142 may be provided by model F24-SU2A nozzle provided by Spraying Systems Company. Typically, nozzle 140 may be centrally located within inlet 128, for example, mounted by two or more equally-spaced supports positioned about the inside diameter of inlet 128 and, possibly, along the length of inlet 128.

In a manner similar to that described with respect to FIG. 2 above, according to aspects of the invention, as a fluid, for example, a gas or a liquid, is introduced to inlet 128, the fluid enters vessel 112 and entrains at least some particulate material 118 (not shown) into open end 122 of conduit 120 and transfers particulate material 118 through conduit 120. The entrainment and/or transfer of the particulate material 118 may be supplemented or augmented by introducing one or more fluids via inlets 130. As noted above, the fluidization of the particulate material 118 and the consequent creation of a pressure differential between the open end 122 of conduit 120 and the distal open end 124 of conduit 120 promotes the flow of the aerated particulate material 118 from open end 122, through conduit 120, and out of open end 124 in apparatus 104.

Again, as discussed above, according to aspects of the invention, while material 118 is agitated, aerated, or fluidized by fluid introduced by inlet 128 and/or inlets 130, at least one further fluid is introduced by means of nozzle 140 to contact the dispersed material 118 with fluid. In one aspect, the fluid introduced via nozzle 140 may comprise a fluid having a non-volatile component which is adapted to at least partially coat the individual particles of material 118. In one aspect, at least some of the surface of particulate material 118, for example, at least 25% of the surface, is coated with a least some of the non-volatile component of the fluid. In another aspect of the invention, at least 50% or even at least 75%, of the surface area of particulate material 118 receives at least some of the non-volatile component of the fluid. In some aspects more than 90% or even substantially 100% of the surface area of material 118 may be covered or coated.

During or after coating material 118 with the fluid, the fluid is allowed to “dry” onto the surface of material 118, for example, by evaporation of any volatile components present in the fluid, whereby at least one non-volatile component of the fluid adheres to the surface of particulate material 118, to provide a coated particular material 119. According to aspects of the invention, this drying or evaporation of volatile components may be accelerated by the fluid flow introduced via inlet 128. For example, the fluid introduced via inlet 128 may comprise a fluid having a little or no concentration of the volatile component of the fluid introduced to nozzle 140. In another aspect, the fluid introduced to inlet 128 may be heated, for example, heated air, to enhance evaporation of the volatile components of the fluid introduced through nozzle 140. In another aspect of the invention, drying or evaporation may be promoted by heating the vessel 112, for example, heating the bottom 116 and/or the transition 117. The heating of vessel 112 may be practiced with an internal or external heating device, for example, a heat exchanger mounted about vessel 112 with appropriate insulation.

With the aid of the illustrations of the aspects of the invention found in FIGS. 1 through 6, the following discussion will illustrate and underscore the advantages of aspects of the present invention compared to the prior art. The present invention, which may be referred to in the art as a type of draft-tube-spout, fluid-bed (DTSFB) apparatus, provides improvements over prior art DTSFB apparatus. For example, as discussed above, according to aspects of the present invention, a DTSFB apparatus is provided in which the feeder section, that is, apparatus 102 in FIGS. 3 and 4, is separated from the separator section, that is, apparatus 104 in FIGS. 3 and 4. This arrangement allows the fluid flow rate in the draft tube, for example, tube 120 in FIGS. 3 and 4, and the pressure drop across the draft tube to be independently specified. As a result, either the solids fraction flowing through the draft tube,

the particle velocity flowing through the draft tube, or both of these parameters can be set and varied, for example, independently set and varied.

The inventors have established that the particle mass flux through a draft tube, W_d , can be defined as a function of solids fraction flowing through draft tube, $(1-\epsilon_d)$; the particle density, ρ_p ; and the particle velocity, v_d , by the relationship in Equation 1.

$$W_d=(1-\epsilon_d)\rho_p v_d[\text{Equation 1}]$$

According to aspects of the invention, as a result of the relationship defined by Equation 1, the processing time of the particles (that is, the transit time of the particles in the draft tube as defined by particle velocity, v_d) and the environment in which the particles are processed (that is, the solids fraction of the particles in the draft tube) can both be varied independently. This versatility contrasts with prior art DTSFB apparatus in which only one of these parameters (that is, particle velocity time or solids fraction) can be specified independently.

This limitation of the prior art is associated with the typical inability of prior art DTSFB mixers to differentiate the pressure drop across the draft tube (for example, the dynamic pressure difference from the inlet **22** to the outlet **24** of draft tube **20** in FIG. 1) from the pressure drop across the annular bed (for example, the pressure difference from the bottom of the annular bed **26** from the bottom of vessel **12** to the void space **21** at the top of the particulate material **18** in FIG. 1). For example, a typical prior art DTSFB apparatus is illustrated in FIG. 1 of Plawky, et al. (2003), in which the outlet of the draft tube and the top of the DTSFB vessel are in fluid communication, that is, are at relatively the same pressure. In contrast, according to aspects of the present invention, these pressure drops can be different and varied independently. This advantage of aspect of the present invention will be elaborated up further below.

The pressure drop across the annulus of a DTSFB apparatus, that is, in both prior art apparatus and aspects of the present invention, may be determined as a function of the flows to the inlet of the DTSFB apparatus. Once these flow rates are defined, the rate of fluid flow, for example, the rate of mass fluid flow, through the draft tube is determined by a material balance of the flows into and out of the inlet of the DTSFB apparatus, for example, as illustrate by the flows shown in FIG. 2. The material balance about vessel **12** (see FIG. 1) is defined by Equation 2:

$$F_d=F_{jo}+F_{axo}+F_s-F_a[\text{Equation 2}]$$

Where, in Equation 2,

F_d =the mass fluid flow rate in the draft tube, arrow **23** in FIG. 2;

F_{jo} =the mass fluid flow rate through the inlet nozzle, arrows **36** in FIG. 2;

F_{axo} the mass fluid flow rate through the auxiliary nozzles, arrow **37** in FIG. 2;

F_s =the mass fluid flow rate through the spray nozzle, for example, the coating fluid, arrow **41** in FIG. 2; and

F_a =the mass fluid flow rate through the annulus, arrows **42** in FIG. 2.

Again, once the draft tube flow rate, F_d , and the solids fraction, $(1-\epsilon_d)$, are established, the pressure drop across the draft tube, ΔP_d , may be defined. By varying any one of the flow rates in Equation 2, the pressure drop across the draft tube, ΔP_d , may be varied. As noted above, typically, in prior art DTSFB apparatus the pressure drop across the draft tube must be substantially the same as the pressure drop across the annular bed. However, according to aspects of the present

invention, the pressure drop across the draft tube may vary from the pressure drop across the annular bed.

According to other aspects of the invention, the fluid velocity and the particle velocity or their difference in the draft tube are a function of the drag force on the particles. That is, once the fluid velocity is known, the particle velocity may also be known. Moreover, in aspects of the invention, changes in the particle velocity may be effected by varying the inlet flow conditions, for example, by varying the mass fluid flow rate through the inlet nozzle, F_{jo} ; varying the mass fluid flow rate through the auxiliary nozzles, F_{axo} ; and/or varying the mass fluid flow rate through the annulus, F_a . According to aspects of the invention, once the particle velocity is fixed or known, the solids fraction, $(1-\epsilon_d)$, can be varied by varying the pressure drop, ΔP_d , across the draft tube.

Prior art DTSFB apparatus require the determination of the split in mass flow between the draft tube, F_d , and the annulus, F_a . This data is typically obtained through experimentation on the specific apparatus used. For example, no general guidance or predictions of this flow split is available in the prior art literature. If F_a is fixed or known, F_d can be determined; but again, in the prior art, the pressure drop across the annulus, ΔP_a , and the pressure drop across the draft tube, ΔP_d , are typically the same. Aspects of the present invention are not limited by this restriction; that is, in aspects of the present invention, the pressure drop across the annulus, ΔP_a , and the pressure drop across the draft tube, ΔP_d , may, and typically will, be different. This distinction can provide enhanced operational versatility to aspects of the present invention compared to the prior art.

These limitations of prior art DTSFB apparatus are particularly acute when handling low-density particulate, such as aerogel beads. Specifically, when attempting to handle low-density particulate material in prior art DTSFB apparatus, the annulus pressure drop, ΔP_a , will typically impose an undesirably high-pressure drop across the draft tube, ΔP_d . Light, low-density particles typically do not require a high-pressure drop across the draft tube to transport the particles through the draft tube. As a result, should the operating regime of the prior art DTSFB apparatus impose a relatively higher pressure drop across the annulus, ΔP_a , a comparable relatively higher pressure drop will also be imposed across the draft tube. Due to the low-density of the particles, such a higher pressure drop across the draft tube will propel a higher solids fraction through the draft tube, which typically may be undesirable, especially, in coating applications.

In contrast, according to aspects of the present invention, the pressure drop across the draft tube, ΔP_d , and the pressure drop across the annulus, ΔP_a , may be independent; that is, the pressure drop across the draft tube, ΔP_d , may not be dictated by the annulus pressure drop, ΔP_a . According to aspects of the invention, the pressure drop across the draft tube may be relatively low, for example, lower than the pressure drop across the annulus. For instance, when transporting low-density particulate material, for example, aerogel beads (having an density of about 140 kg/m³) that can be transported with a lower pressure drop across the draft tube, aspects of the present invention are far superior to prior art DTSFB apparatus.

Though theoretically, when handling low-density materials, such as aerogel beads, in a prior art DTSFB apparatus, the pressure drop across the draft tube may simply be reduced by lowering the pressure drop across the annulus, for example, by reducing the bed height in the annulus. However, the inventors have found that, though the pressure drop across the annulus can be reduced by reducing the bed height of the particulate material in the annulus, in practice, the desirable

pressure drops across the draft tube for low-density materials require that the pressure drop across the annulus, and the bed height, may be markedly low. As a result, such low bed heights are difficult, if not impossible, to maintain in practically-designed DTSFB apparatus. Only by using aspects of the present invention, where the draft tube pressure drop may be independent of the annulus pressure drop, is the handling of low-density particulate material, such as, aerogel beads, practical or even possible. However, aspects of the invention may also be used to handle high-density particulate material, for example, glass beads.

The aspects of the invention illustrated in FIGS. 3 through 6 were used by the inventors to coat particulate material according to aspects of the invention. Prior to formal experimentation, as is typical, the inventors investigated the desirable sizes and operating parameters. The following investigation, experimentation, aspects of the invention are discussed with reference to the use of aerogel beads as the particulate material. However, the inventors recognize and it is to be understood that aspects of the invention may be applied to any particulate material, including but not limited to pharmaceuticals; food stuffs; cosmetics; metals, such as, powder manufacturing powder metals; ceramics; and like particulates.

The inventors' objective in performing the following investigation was to produce a coated aerogel bead and/or a coated aerogel bead material, for instance, a material that can be applied to a surface, for example, by spraying, or formed into a desired shape, for example, by molding. In one aspect, the coated aerogel bead and/or material may comprise an insulating material, for example, a thermal or electrical insulating material. In the following experiments, the aerogel beads used comprised 1 to 3 mm aerogel beads provided by Cabot Inc., though any similar or equivalent aerogel beads may be used in aspects of the invention.

According to one aspect and as described below, a method may be practiced using a DTSFB apparatus as described in FIGS. 1-6; however, the inventors recognize that aspects of the invention may also be practiced in other apparatus that are adapted to perform the methods recited. The DTSFB apparatus may be adapted to agitate and/or suspend the aerogel beads in a first fluid, for example, air, nitrogen, or an inert gas, among other gases, and then exposing the agitated and/or suspended aerogel to a second fluid, that is, the "coating fluid," containing at least one volatile component and at least one non-volatile component whereby when the volatile component are allowed to volatilize or evaporate at least some of the non-volatile component remains on the surface of the aerogel beads. In this discussion and in the description of aspects of the invention that and in the attached claims, a "non-volatile" component comprises a component of the liquid that is not volatile under the temperature and pressure conditions under which the process is performed, for example, at a temperature less than about 250 degrees C. (about 482 degrees F.) and a pressure less than 2 atmospheres. Conversely, a "volatile component" is one that does volatilize or evaporate under the temperature and pressure conditions under which the process is performed. For example, in the investigation described below, the second fluid comprises a fluid containing a non-volatile polymer and a volatile component, such as, water, alcohol, or a solvent, that is introduced to the beads as a spray or fine mist. According to one aspect of the invention, attrition, wear, or damage to the aerogel beads is minimized or prevented. In addition, according to one aspect of the invention, the volatile component of the second

fluid volatilizes or evaporates quickly enough that substantially little or no penetration of the aerogel bead by the second fluid occurs.

In order to better understand the potential for penetration of the second fluids in to the aerogel beads, the inventors proposed the following relationships in Equations 3 and 4.

$$\frac{\Delta P}{\Delta x} = \frac{P_{atm} - (\gamma / r_o)}{L_{pore}} \quad \text{[Equation 3]}$$

and

$$v_{avg} = -(\Delta P / \Delta x) r_o^2 / (8\mu) \quad \text{[Equation 4]}$$

where

$\Delta P / \Delta x$ is the driving pressure drop radially into the pores of the aerogel bead, N/m³;

P_{atm} is the prevailing atmospheric pressure, assumed 101,000 N/m²;

γ is the surface tension of the second fluid, assumed 26.9 × 10⁻³ J/m²;

r_o is the radius of the aerogel beads, assumed 10 nanometers [nm];

L_{pore} is the length the pore in the surface of the bead, assumed 1 micrometer [μm];

v_{avg} is the average velocity of the second fluid through the pores of the aerogel beads, mm/s; and

μ is the viscosity of the second fluid, assumed 1 N-s/m².

By evaluating Equations 3 and 4 with the assumed values, the following parameters were estimated for the processing of aerogel beads.

$$\frac{\Delta P}{\Delta x} = -2.7 \times 10^{11} \text{ N/m}^3$$

and

$$v_{avg} = 3.3 \times 10^{-3} \text{ mm/s.}$$

The resulting design specifications for the experiments performed are listed in Table 1 and the resulting design calculation parameters appear in Table 2.

TABLE 1

DTSFB Apparatus Aerogel Coating Design Specifications		
Fluid, particle, and bed properties	Particle Density (ρ_p)	140 kg/m ³
	Air Density (ρ_a), at 298 K	1.165 kg/m ³
	Air Viscosity (μ_a) at 298 K	18.64 × 10 ⁻⁶ Ns/m ²
	Annulus Voidage (ϵ_a)	0.42
Geometric Properties	Particle diameter (d_p)	1 mm
	Draft tube diameter (D_d)	41.15 mm
	Draft tube length (l_d)	2 m
	Annulus inner diameter (D_i)	44.45 mm
	Annulus Outer diameter (D_o)	149.1 mm
	Height of particles in annulus (H_a)	0.5 m
Inlet flow rates	Jet and Auxiliary flow ($F_{jo} + F_{axo}$)	866 liters/min.
	Spray flow (F_s)	34 liters/min.
	Total flow	900 liters/min.
Draft tube conditions	Superficial air velocity (U_d)	10 m/s
	Solids fraction ($1 - \epsilon_d$)	0.01

15

TABLE 2

DTSFB Apparatus Aerogel Coating Design Calculation Results	
Draft tube pressure drop (ΔP_d)	96.2 Pa (0.386 in. of H ₂ O)
Annulus pressure drop (ΔP_a)	236.6 Pa (1.07 in. of H ₂ O)
Particle flux (W_d)	12.6 kg/m ² s
Particle Mass Flow (G_d)	0.0167 kg/s
Minimum Fluidizing Velocity (U_{mf})	0.043 m/s
Slip Velocity ($U_s + v_s$)	0.042 m/s
Terminal Velocity (U_T)	1.133 m/s
Superficial air velocity (U_d)	10 m/s

According to aspects of the invention, apparatus 100 shown in FIGS. 3 through 6, was operated under the conditions listed in Tables 1 and 2. In addition the spray nozzle 140 shown in FIG. 6 was operated under the conditions that appear in Table 3. In these experiments, spray nozzle 140 comprised a SU2A atomizing spray nozzle system provided by Spraying Systems Company, though in aspects of the invention any similar or equivalent commercially available spraying system may be used.

TABLE 3

DTSFB Apparatus Aerogel Coating Spray Nozzle Parameters	
Nozzle orifice diameter	0.020 inches
Air Pressure	4-60 psig
Air Capacity	0.8-2.7 scfm
Liquid pressure	3-40 psi
Liquid capacity	2-284 ml/min.
Spray time	<10 mins.

The aerogel beads were provided to vessel 112 in system 102 from a bead source (not shown) by means of a bead hopper (not shown) having a pneumatic injector, though other types of transfer systems may be used. The transport fluid in system 102, that is, the fluid introduced to inlets 144 and 130 (that is, $F_{jo} + F_{axco}$), comprised ambient air heated to about 50 degrees C. and introduced at the rate that appears in Table 1. The transport fluid may range in temperature from about 10 degrees C. to about 150 degrees C., for example, from 30 degrees C. to about 100 degrees C. In one aspect, vessel 112 may also be heated, for example, by means of a thermal blanket or by means of a heat exchanger through which a heated fluid, for example, air or water, may be passed. The walls of vessel 112 may be heated to about 10 degrees C. to about 150 degrees C., for example, from 30 degrees C. to about 100 degrees C. In these experiments, the walls of vessel 12 were heated to about 40 degrees C.

The coating fluid in system 102, that is, the fluid introduced to inlets 140 (that is, F) comprised one of fluids listed in Table 4. The coating fluid may be heated, for example, to a temperature ranging from about 10 degrees C. to about 250 degrees C., for example, from 30 degrees C. to about 100 degrees C.

TABLE 4

DTSFB Apparatus Aerogel Coating Fluids	
Colorcon OPADRY II polyvinyl alcohol, water-based cationic polymer	
Eudragit ¹ L30 D55 polymethyl methacrylate, water-based anionic polymer	
Eudragit ¹ E12,5 polymethyl methacrylate, solvent-based cationic polymer	
Eudragit ¹ NE30 D polymethyl methacrylate, solvent-based neutral polymer	
Eudragit ¹ RL 12,5 polymethyl methacrylate, solvent-based cationic polymer	
Water-borne polyurethane solution	

¹Eudragit solutions can be mixed with virtually any solvent to control viscosity, surface tension, etc., as needed.

16

During processing, the aerogel beads in vessel 112 are agitated, aerated, and transported into the open end 122 of conduit 120. At substantially the same time as this agitation and transport, a coating fluid is introduced by means of spray nozzle 140 to the vicinity of the open end 122 whereby at least some of the aerogel beads are exposed to the coating fluid. The coated beads are then transported through conduit, or draft tube, 120 to vessel 212 in apparatus 104 and discharged from open end 124 of conduit 120. According to the aspects of the present invention, the at least partially coated aerogel beads that are discharged from open end 124 may typically settle to the bottom of vessel 212, for example, in the off-set conical bottom of vessel 212. In one aspect, the at least partially coated beads may then be forwarded to further processing, or returned to apparatus 102 for further coating, for example, via conduit 222 and inlet 133 in top 114 of vessel 112. For example, in one aspect, the aerogel beads may be treated, that is, coated, in apparatus 102 repeatedly, for example, at least twice, but may be recycled from apparatus 104 to apparatus 102 three or more, or four or more times, depending upon, among other things, the size of the particles being coated and the amount or extent of coating desired.

While the coated aerogel beads may be recirculated to apparatus 102, the fluid stream introduced to vessel 212 via conduit 120 may be discharged from vessel 212, for example, from one or more outlets 220, and forwarded to re-use as a transfer medium or for further processing. For example, the fluid, typically, gaseous, stream discharged from vessel 212 may be treated to remove any aerogel beads or other particulate. For instance, the fluid stream discharged from vessel 212 may be scrubbed or filtered, for example, filtered in a conventional "bag-house" filter or other filtering medium (not shown), prior to being further processed or re-used.

FIGS. 7 through 10 illustrate typical coated aerogel beads produced with the apparatus 100 shown in FIGS. 3 through 6 according to one aspect of the invention. FIG. 7 illustrates a magnified view of aerogel beads coated in a first trial according to aspects of the invention as magnified 20 times. FIG. 8 illustrates a magnified view of one coated aerogel bead produced in the same trial as the beads shown in FIG. 7 when magnified 50 times. In this first trial, the aerogel beads were coated with a pharmaceutical grade polyvinyl alcohol, specifically, Opradry II polyvinyl alcohol. The beads were coated for a total processing time of about 1 minute at a temperature of about 90 degrees C. The results of this trial produced coated beads with substantially no penetration of the coating fluid into the beads and minimal bead attrition due to processing.

FIG. 9 illustrates a magnified view of aerogel beads coated in a second trial according to aspects of the invention as magnified 20 times. FIG. 10 illustrates a magnified view of coated aerogel beads produced from the same second trial as FIG. 9 when magnified 50 times. In this second trial, the aerogel beads were again coated with a pharmaceutical grade polyvinyl alcohol, specifically, Surelease brand polyvinyl alcohol. The beads were coated for a total processing time of about 10-20 minutes at a temperature of about 90 degrees C. The results of this second trial produced coated beads with substantially no penetration of the coating fluid into the beads, minimal bead attrition due to processing, and more compete, smoother coverage of the bead surface than produced from the first trial. Some difficulties with the spraying nozzle were encountered in the second trial, which may have impacted the uniformity of the particle coating. The inventors believe that improved control of the temperature of the sprayed coating will likely overcome this difficulty.

Examination of the coated aerogel particles shown in the photographs of FIGS. 8 and 10 clearly illustrate the presence of coating material on the surface of the aerogel particles. Though these photographs illustrate the partial coating of the surface of the aerogel particles, even this particle coating provides particles having enhanced properties. However, according to aspects of the invention, the extent of the coverage or coating of aerogel particles can be enhanced by, among other things, repeated exposure to the coating fluid, for example, by recycling of the particles for repeat treatment in apparatus 100, or optimization of the operating parameters of the treatment, for example, varying the temperature or rate of flow of the coating fluid. These and other modifications of aspects of the present invention are included within the scope of aspects of the invention.

In any event, the first and second coating trials with apparatus 100 illustrated in FIGS. 3 through 6, clearly illustrate the effectiveness of aspects of the present invention when coating aerogel beads to produce an aerogel-based material, for example, an insulation material. The coated beads exhibit little or no penetration of the coating fluid into the beads while subjecting the beads to little or no wear or attrition, thus ensuring the integrity of the beads, especially, their insulating properties. The inventors are optimistic that apparatus 100 can be an effective device for coating other types of particulate material, for example, other types of low-density particulate material, that can, for example, provide the designer a novel material for any application where thermal or electrical insulation is desired.

While several aspects of the present invention have been described and depicted herein, alternative aspects may be provided by those skilled in the art to accomplish the same objectives. Accordingly, it is intended by the appended claims to cover all such alternative aspects as fall within the true spirit and scope of the invention.

The invention claimed is:

1. A coated particulate material consisting of a plurality of separate individual aerogel beads, each bead having a surface at least partially covered with a polymer coating, the polymer coating comprising a surface adhering non-volatile residual portion of a dried bead coating fluid received on the surface.

2. The coated particulate material as recited in claim 1 wherein the aerogel beads comprise about 1 mm to about 5 mm aerogel beads.

3. The coated particulate material as recited in claim 1 wherein the polymer comprises at least one of a polyvinyl alcohol, a polymethyl methacrylate, and a polyurethane.

4. An insulating material comprising a plurality of separate individual aerogel beads, each bead having a surface at least partially covered with a polymer coating, the polymer coating comprising a surface adhering non-volatile residual portion of a dried bead coating fluid received on the surface.

5. The insulating material as recited in claim 4 wherein the aerogel beads comprise about 50 micrometer to about 5 millimeter aerogel beads.

6. The insulating material as recited in claim 4 wherein the polymer comprises at least one of a polyvinyl alcohol and a polyurethane.

7. The coated particulate material as recited in claim 1, wherein at least 75% of the surface of each bead is covered with the polymer coating.

8. The coated particulate material as recited in claim 1, wherein at least 90% of the surface of each bead is covered with the polymer coating.

9. The insulating material as recited in claim 4, wherein at least 75% of the surface of each bead is covered with the polymer coating.

10. The insulating material as recited in claim 4, wherein at least 90% of the surface of each bead is covered with the polymer coating.

* * * * *