

RESEARCH WITH LARGE AREA IMAGING X-RAY
TELESCOPE-SOUNDING ROCKET PROGRAM

NASA Grant NSG-5138

1N-89
03-5-103

Final Report

For the Period 1 December 1976 through 28 February 1999

Principal Investigator
Dr. Paul Gorenstein

February 1999


Prepared for:

National Aeronautics and Space Administration
Goddard Space Flight Center/Wallops Flight Facility
Wallops Island, VA 23337

Smithsonian Institution
Astrophysical Observatory
Cambridge, Massachusetts 02138

The Smithsonian Astrophysical Observatory
is a member of the
Harvard-Smithsonian Center for Astrophysics

The NASA Technical Officer for this grant is Larry J. Early, Code 840.0, GSFC/Wallops Flight Facility, Wallops Island, VA 23337.



1 Introduction

This report describes the activities of and results from the final year of NASA Grant NSG-5138. The grant had been funded through several cycles of the three year NASA SR&T program. Previous results have been reported in a series of semi-annual and annual reports. We do not repeat what was previously reported. In this final report we report upon only the activities of the past and final year of the grant. Projects begun during the tenure of this grant will continue under the support of a new NASA SR&T grant that was awarded during the most recent three year proposal cycle.

Four lines of study were carried out during the final year. They are:

testing of graded d-spacing multilayer reflectors for hard X-ray telescopes

study of replicated substrates for multilayer reflectors,

design of our system for producing multilayer reflectors,

study of wide field and high throughput X-ray telescopes.

Each of these is described below.

2 Production and Testing of Multilayer Reflectors Upon Replicated Substrates

We entered into a collaboration with O. Citterio of the Brera Observatory to produce replicated substrates from polished masters, coat them with multilayer reflectors, and measure their performance. These coatings consist of many layers of alternating light and heavy materials. This work is the first step in a project to replicate integral cylindrical grazing incidence mirrors from mandrels and coat their interior surfaces with graded d-spacing multilayers. The final product will be a prototype telescope that focuses X-rays up to 100 keV in energy.

Initially, we work with flats rather than cylinders, because they are easier to fabricate and test. Also, the multilayer coatings are initially constant period rather than depth graded period because such coatings are easier to evaluate. They reflect a given energy X-ray at a specific angle, in analogy to Bragg reflection of crystals. Also the replication process is epoxy casting rather than electroforming, the process which we would like to utilize eventually. There is reason to believe that the behavior of both types of replicas will be similar with respect to separating from the mandrel and their ability to provide a smooth substrate for the coatings. Production of small flats is done more conveniently and less expensively by epoxy replication than by electroforming.

In this collaborative project SAO provides the mandrels, the epoxy materials, and is responsible for the application and testing of the multilayer coatings. Since our own facilities that would coat and measure the performance of the replicated substrates were still under development, we sub-contracted these two activities to the National Institute of Science Technology (NIST). The Brera Observatory is responsible for producing the replicated substrates.

During the final year of this grant we completed one round of substrate production, coating, and X-ray reflectivity measurements. The results are promising because we obtained good performance from a replicated substrate that was separated with carbon. The process and results are described in a paper by Romaine et al, 1997 which is reproduced in Appendix A.

3 Production and Testing of Graded d-Spacing Multilayer Reflectors Upon Primary Substrates

One of the coatings of great interest is the deep W/Si graded d-spacing multilayer. This coating has a relatively high reflection efficiency up the 69.5 keV K edge of tungsten. We have been collaborating with European Synchrotron Radiation Facility (ESRF), the University of Copenhagen and Osmic, Inc. in producing and testing these coatings. The most significant result of the past year was the publication of a paper by Hoghoj et al, 1997 entitled "Focusing of hard X-rays with a W/Si supermirror" based upon tests carried out at the ESRF. This coating reflects harder X-rays three or more times more efficiently than single metallic coatings. This paper is reproduced in Appendix B.

4 Design of Multilayer Deposition Chamber

With additional support from the Smithsonian Astrophysical Observatory we began the design and development of facilities to deposit multilayer coatings on flat and cylindrical substrates. Our motivation for this is the lack of facilities capable of coating the interior surfaces of cylinders. Therefore, we need our own facilities to proceed with the development of double conical mirrors whose substrates are integral shells. Integral shells are the approach we favor for a future high X-ray focusing telescope system because they offer much better angular resolution than substrates which are segmented into azimuthal quadrants. However, coating the interior surfaces of these closed shells requires special deposition facilities which do not exist at present.

We formulated a plan to develop a facility that contains two chambers, a small much less expensive one that can coat small flats and a large chamber that can coat large cylindrical substrates including the interiors of cylinders. The small chamber which we refer to as the "R&D" chamber can coat flats more quickly and less expensively. It will be used primarily as a research tool, for example, experimenting with novel coating materials. With the larger chamber which we call "the cylindrical chamber" we intend to coat a prototype cylindrical mirror. It will be capable of depositing coatings on the interior surface of a cylinder with diameter between 5 and 12 inches. To obtain useful information for the operation of our future chambers we carried out parametric studies at other facilities of how certain deposition parameters affect the smoothness of the coatings. Hussain et al, 1997 using a deposition facility at Boston University found that the best film qualities, e.g. high density and low roughness at obtained at lower pressure. Although this is not fundamentally new information, some fit is retained as commercial trade secrets and is not in the open literature. Also, the experience of these depositions were useful in the design of own facilities.

5 High Throughput X-Ray Telescopes

An analytic concept study of an ultra high throughput X-ray astronomy was undertaken by the Principal Investigator who does not charge his labor to this program. No equipment was purchased. Therefore, this activity did not result in any expenditure by this program. However, the results were promising and this study will be continued.

APPENDIX A

Application of Multilayer Coatings to Replicated Substrates

S. Romaine, A. Hussain, J. Everett, A. Clark, R. Bruni, P. Gorenstein

Harvard-Smithsonian Center for Astrophysics
60 Garden Street, Cambridge, MA 02138

M. Ghigo, F. Mazzoleni, O. Citterio

Osservatorio Astronomico di Brera-Milano
Via E. Bianchi, 46 - 22055 Merate, Italy

J. Pedulla

National Institute of Standards and Technology
Physics Laboratory
Gaithersburg, MD 20899

Abstract

We are engaged in a program to develop focussing hard X-ray telescopes in a double conical or Wolter 1 geometry that function up to 100 keV by employing small graze angles and multilayer coatings. Directly polished substrates are not an option because they are too thick to be nested efficiently. The only alternative is to fabricate the very thin substrates by replication. Our objective is the production of integral cylindrical substrates because they should result in better angular resolution than segmented foil geometries. In addition, integral cylinders would be more resistant to possible stress from deep multilayer coatings than segmented ones. Both electroforming of nickel (method of SAX, JET-X, and XMM) and epoxy replication are under consideration. Both processes can utilize the same types of mandrels and separation agents. While electroforming can produce substrates that are thin, the high density of the nickel may result in high weight optics for some missions. For convenience, experimentation with replication and coating is being carried out initially on flats. Our replication studies include trials with gold and carbon separation agents. This paper reports on our efforts with epoxy replicated optics.

Keywords: X-ray Telescopes, Multilayers, Replicated Substrates

1 INTRODUCTION

As part of a program to develop multilayer grazing incidence optics for a hard X-ray telescope, epoxy replication is being investigated for the production of light weight, high resolution cylindrical optics. The

study reported here used epoxy replication of flat substrates (as opposed to cylindrical) to facilitate the coating and X-ray testing of multilayers. Superpolished fused silica substrates were used as masters to produce epoxy replicated surfaces on which multilayers were deposited. This study was undertaken to compare the results of gold and carbon as separation materials in the replication process. After the epoxy replication, nickel/carbon multilayers were deposited and the X-ray reflectivity measured. The multilayers were deposited using dual ion beam assisted deposition at low ambient pressure ($\approx 10^{-4}$ Torr). The results from six samples are reported in this paper; four of the samples were epoxy replicated and the other 2, which were superpolished fused silica were used as controls.

Results of X-ray reflectivity measurements of the multilayers on the 2 different separation materials is reported below and compared with the results from 2 control samples. The carbon replicated substrates show a higher reflectivity at 8 keV than the gold replicas. Results of surface roughness from AFM measurements and from modelled data is also given below; it has been shown [4] that a surface roughness of less than 5 Å is needed for good X-ray reflectivity performance up to 100 keV.

2 SAMPLES

Dual ion beam assisted deposition was used to deposit multilayers on 6 different test samples. Nominal d-spacing and γ (ratio between nickel and period) for the Ni/C multilayers is 40 Å and 0.4, respectively. The 6 samples consisted of: 2 control samples (a bare silica substrate and a silica substrate with 1000 Å of DC magnetron sputtered carbon); 2 epoxy replicated substrates with carbon used as the separation agent; 2 epoxy replicated samples with gold used as the separation agent. Three different coating runs were used to deposit the multilayers. The list of samples coated in each run is shown in table 1. The number of periods deposited was 50 in all cases. During the third deposition run, there was an inadvertent parameter change after the first 28 periods; the last 22 periods of this coating run were deposited with d-spacing of 36 Å and γ of 0.39 (as confirmed by the modelled data). This change results in the 'double Bragg peaks' for these samples which can be seen in the reflectivity data presented below.

3 MEASUREMENTS

3.1 X-ray Reflectivity Measurements

Grazing incidence 8 keV X-ray reflectivity measurements were carried out on all 6 multilayer coated samples and the results are presented in figures 1 through 6. Figure 1 and 2 present the results from the measurements of the multilayers on the 2 control samples which were coated during the same coating run. Figure 1 (S521) is a bare fused silica substrate and figure 2 (S480) is a fused silica substrate with 1000 Å of DC magnetron sputtered carbon. Although the intensity of the first order Bragg peaks is similar for both samples, the intensity of the 2nd and 3rd order peaks of the carbon coated silica has decreased significantly. Table 1 gives the interface roughness calculated from the X-ray model, and as shown, the roughness associated with sample S480 is greater than that of sample S521.

Figure 3 and 4 contain the reflectivity measurements from coating run #2, one carbon replica (S463) and one gold replica (S514). Clearly the Bragg peaks of the gold replica have less intensity than that of the carbon replica; in addition, the carbon replica shows a clear 4th order peak not visible in the measurements of the gold replica. Comparing the carbon replica (fig. 3) with the carbon coated silica (fig. 2), the carbon replica yields the better reflectivity. In the case of both S480 and S463, the multilayer was deposited on a DC magnetron sputtered surface. However, sample S463 was a replica therefore the carbon surface onto which

the multilayer was deposited was the separated carbon, and therefore may have had a smoother surface, as indicated by the X-ray model results of interface roughness shown in table 1.

The results from the 3rd set of samples coated is shown in figures 5 and 6. Again, one sample (S494) was a carbon replica and one (S492) was a gold replica. As already mentioned, the deposition parameters changed during the run and 2 different d-spacings were deposited, which results in the 'double Bragg peaks' seen in the 8 keV X-ray reflectivity. It is still clear from this data that the multilayers on the carbon replica yield a greater reflectivity than the same multilayers on the gold replica.

3.2 Microroughness Data

It is well known that surface microroughness has a strong effect on the intensity of the grazing incidence specular reflection [2, 3]. This effect becomes more pronounced the higher the energy of incident photons (i.e. the smaller the grazing angle). Microroughness results from AFM measurements are presented in Table 1 along with the model calculations of interface roughness for the multilayers.

Surface Microroughness (Å)				
Sample Number	Sample Description	AFM $1\mu / 10\mu$	post-coat (model)	Coating run #
521	bare silica	N/A	4.0	1
480	silica with carbon	N/A	5.5	1
463	carbon replica	2.7/2.3	3.7	2
494	carbon replica	1.1/1.2	3.7	3
492	gold replica	3.4/2.8	5.5	3
514	gold replica	4.6/5.1	5.5	2

Table 1: X-ray modelled and AFM measured microroughness data for the 6 samples discussed in the text

4 DISCUSSION and CONCLUSIONS

The quality of the multilayers deposited on carbon replicas, gold replicas, bare silica and bare silica coated with carbon has been investigated using hard X-rays. The carbon replicas show a higher reflectivity than the gold replicas in both cases and the modelled interface roughness for the carbon replicas is less than that of the gold. The modelled interface roughness of the multilayer on the fused silica with carbon overcoat (sample 480) is also greater than that of the carbon replicas. This may be due to the fact that for the replicas, the multilayer is being deposited on the 'separated carbon' which is the bottom surface of the sputtered carbon, whereas the multilayer deposited on sample 480 is deposited on the top surface of the sputtered carbon.

These preliminary results indicate that using carbon as a separation agent in epoxy replication yields a surface with smaller microroughness, which leads to a multilayer with smaller interface roughness and hence a surface with higher specular reflectivity. This study is ongoing [1] and more complete results will be presented at the conference.

5 ACKNOWLEDGEMENTS

We wish to thank Atkinson Systems of Hudson, NH for providing the DC magnetron carbon coatings. This work was supported by NASA contracts NAG8-1194 and NSG-5138.

References

- [1] A. Hussain, et al., 1997, "Studying Density vs. Ar-pressures for Optimization of DC-magnetron Sputter Deposition of Ni/C Multilayers for Hard X-ray Telescopes", this volume.
- [2] A. M. Clark, et al., 1996, "Correlation Between X-ray Reflectivity Measurements and Surface Roughness of AXAF Coated Witness Samples," Proc. SPIE, 2805, p.268(1996).
- [3] D.L. Windt et al., "Surface Finish Requirements for soft X-ray Mirrors", Applied Optics 33, 2025-2031 (1994).
- [4] K.D.Joensen et al., "Medium-sized grazing incidence high energy X-ray Telescopes employing continuously graded multilayers", Proc. SPIE, 1736, p.239(1992).





Figure 1. Specular reflectivity vs. grazing angle for multilayers deposited on bare fused silica substrate. ($E=8.048$ keV)

Figure 2. Specular reflectivity vs. grazing angle for multilayers deposited on fused silica substrate coated with 1000 ÅDC magnetron sputtered carbon. ($E=8.048$ keV)






Figure 3. Specular reflectivity vs. grazing angle for multilayers deposited on carbon replica. ($E=8.048$ keV)

Figure 4. Specular reflectivity vs. grazing angle for multilayers deposited on gold replica. ($E=8.048$ keV)

X-RAY REFLECTIVITY MEASUREMENT COMPARISONS
Ni/C MULTILAYER // Replica 494 + C



X-RAY REFLECTIVITY MEASUREMENT COMPARISONS
Ni/C MULTILAYER // Replica 492 + Au




Figure 5. Specular reflectivity vs. grazing angle for multilayers deposited on carbon replica. ($E=8.048$ keV) (note: 2 different d-spacings were deposited here as discussed in the text.)

Figure 6. Specular reflectivity vs. grazing angle for multilayers deposited on gold replica (see note for figure 5). ($E=8.048$ keV)

APPENDIX B

Reprinted from

NIM B

Beam Interactions with Materials & Atoms

Nuclear Instruments and Methods in Physics Research B 132 (1997) 528–533

Focusing of hard X-rays with a W/Si supermirror

Peter Høghøj ^{a,*}, Eric Ziegler ^a, Jean Susini ^a, Andreas K. Freund ^a,
Karsten D. Joensen ^{b,1}, Paul Gorenstein ^b, James L. Wood ^c

^a *European Synchrotron Radiation Facility, BP 220, F-38043 Grenoble Cedex, France*

^b *Harvard-Smithsonian Center for Astrophysics, 60 Garden St., Cambridge, MA 02138, USA*

^c *Osmic Inc., 1788 Northwood Drive, Troy, MI 48084, USA*

Received 21 April 1997; revised form received 27 June 1997



ELSEVIER

BEAM INTERACTIONS WITH MATERIALS AND ATOMS

Nuclear Instruments and Methods in Physics Research – Section B

Editors:

Prof. H.H. Andersen

The Niels Bohr Institute, Ørsted Laboratory,
Universitetsparken 5, DK 2100 Copenhagen Ø, Denmark
Tel. +45 35320482, fax +45 35320460, e-mail nimb@fys.ku.dk

Temporary address from April 1, 1997 to April 1, 1998:

Institut de Physique Nucléaire
F-91406 Orsay Cedex, France

Tel. +33 1 69156604, fax +33 1 69154507, e-mail nimb@fys.ku.dk

Dr. L.E. Rehn

Materials Science Division, Bldg 223, Rm S231, Argonne National Laboratory,
9700 South Cass Avenue, Argonne, IL 60439, USA

Tel. +1 630 2529297, fax +1 630 2523308, e-mail lynn_rehn@qmgate.anl.gov

Editorial Board:

P. BAUER (Linz)

K. BETHGE (Frankfurt)

T. DIAZ DE LA RUBIA (Livermore)

A. DUNLOP (Palaiseau)

R. ELLIMAN (Canberra)

G. FOTI (Catania)

K.S. JONES (Gainesville)

W.N. LENNARD (Ontario)

M. MANNAMI (Kyoto)

A. NYLANDSTED LARSEN (Aarhus)

F. PÁSZTI (Budapest)

S.T. PICRAUX (Albuquerque)

D.B. POKER (Oak Ridge)

H.L. RAVN (Geneva)

K. SIEGBAHN (Uppsala)

M. SZYMONSKI (Cracow)

T. TOMBRELLO (Pasadena)

H. URBASSEK (Kaiserslautern)

A.E. WHITE (Murray Hill)

I. YAMADA (Kyoto)

ZHU Jieqing (Shanghai)

Aims and scope

Section B of Nuclear Instruments and Methods in Physics Research (NIM B) provides a special forum for the discussion of all aspects of the interaction of energetic beams with atoms, molecules and aggregate forms of matter. This includes ion beam analysis and ion beam modification of materials, as well as studies of the basic interaction mechanisms of importance for this work. The Editors invite submission of both theoretical and experimental papers of original research in this area.

Information for Advertisers

Advertising orders and enquiries can be sent to: International: Elsevier Science, Advertising Department, The Boulevard, Langford Lane, Kidlington, Oxford, OX5 1GB, UK; tel. +44 (0) 1865 843565, fax +44 (0) 1865 843976. USA, Canada: Weston Media Associates, Dan Lipner, P.O. Box 1110, Greens Farms, CT 06436-1110, USA; tel. +1 203 261 2500, fax +1 203 261 0101. Japan: Elsevier Science Japan, Marketing Services, 1-9-15 Higashi-Azabu, Minato-ku, Tokyo 106, Japan; tel. +81 3 5561 5033, fax +81 3 5561 5047.

Abstracted/indexed in:

Current Contents: Engineering, Technology and Applied Sciences; EI Compindex Plus; Engineering Index; INSPEC; Physics Briefs.

Subscription information 1997

Volumes 121–133 of Nuclear Instruments and Methods in Physics Research - Section B (ISSN 0168-583X) are scheduled for publication. A combined subscription to NIM A volumes 384–401 and NIM B volumes 121–133 is available at a reduced rate.

Subscriptions are accepted on a prepaid basis only and are entered on a calendar year basis. Issues are sent by SAL (Surface Air Lifted) mail wherever this service is available. Airmail rates are available upon request. For orders, claims, product enquiries (no manuscript enquiries) please contact the Customer Support Department at the Regional Sales Office nearest to you:

New York: Elsevier Science, P.O. Box 945, New York, NY 10159-0945, USA; tel +1 212 633 3730 (Toll free number for North American customers: 1-888-4ES-INFO (437-4636)), fax +1 212 633 3680, e-mail usinfo-f@elsevier.com

Amsterdam: Elsevier Science, P.O. Box 211, 1000 AE Amsterdam, The Netherlands; tel +31 20 485 3757, fax +31 20 485 3432, e-mail nlinfo-f@elsevier.nl

Tokyo: Elsevier Science, 9-15, Higashi-Azabu 1-chome, Minato-ku, Tokyo 106, Japan; tel +81 3 5561 5033, fax +81 3 5561 5047, e-mail kyf04035@niftyserve.or.jp

Singapore: Elsevier Science, No. 1 Temasek Avenue, #17-01 Millenia Tower, Singapore 039192; tel +65 434 3727, fax +65 337 2230, e-mail asiainfo@elsevier.com.sg

Claims for issues not received should be made within six months of our publication (mailing) date.

US Mailing notice: Nuclear Instruments and Methods in Physics Research – Section B (ISSN 0168-583X) is published semi-monthly (for five months of the year), monthly from August to December, three times a month in May, and four times in April, by Elsevier Science B.V., Molenwerf 1, P.O. Box 211, 1000 AE Amsterdam, The Netherlands. Annual subscription price in the USA is US\$ 6396 (valid in North, Central and South America only), including air speed delivery. Periodicals postage paid at Jamaica, NY 11431.

USA Postmasters: Send address changes to Nuclear Instruments and Methods in Physics Research – Section B, Publications Expediting, Inc., 200 Meacham Avenue, Elmont, NY 11003. Airfreight and mailing in the USA by Publications Expediting Inc.

© The paper used in this publication meets the requirements of ANSI/NISO Z39.48-1992 (Permanence of Paper).

Printed in The Netherlands



North-Holland, an imprint of Elsevier Science



ELSEVIER

Nuclear Instruments and Methods in Physics Research B 132 (1997) 528-533

NIM B
Beam Interactions
with Materials & Atoms

Focusing of hard X-rays with a W/Si supermirror

Peter Høghøj^{a,*}, Eric Ziegler^a, Jean Susini^a, Andreas K. Freund^a,
Karsten D. Joensen^{b,1}, Paul Gorenstein^b, James L. Wood^c

^a European Synchrotron Radiation Facility, BP 220, F-38043 Grenoble Cedex, France

^b Harvard-Smithsonian Center for Astrophysics, 60 Garden St., Cambridge, MA 02138, USA

^c Osmic Inc., 1788 Northwood Drive, Troy, MI 48084, USA

Received 21 April 1997; revised form received 27 June 1997

Abstract

The performances of single coating mirrors and supermirrors for hard X-rays are compared. It is found that supermirrors can reflect X-rays at a θ/λ ratio more than three times larger than for single coating mirrors. A W/Si supermirror is applied to the focusing of a white beam of X-rays and is found to efficiently reflect and focus X-rays for energies up to 69.5 keV. At higher energies the performance is limited by the absorption of W above the absorption edge. © 1997 Elsevier Science B.V.

PACS: 07.85; 95.55.Ka

Keywords: Supermirror; X-ray optics; Hard X-rays; X-ray focusing; W/Si multilayer

1. Introduction

Until recently, the use of reflective optics at short X-ray wavelengths was limited by the low critical angles of mirror materials. These mirrors reflect by total external reflection for grazing angles θ lower than a critical angle θ_c . Above the critical angle, reflection can be obtained by Bragg diffraction in, for example, periodic multilayers [1-3], which have been used to focus [4] X-rays.

However, diffraction from periodic structures provides only a limited bandpass and periodic multilayers can therefore not be used where a polychromatic beam is required. For such applications supermirrors [5-9], which are aperiodic multilayers that, like traditional mirrors, show substantial reflectivity for all angles lower than a critical angle, can be used. Supermirrors have for some time been applied to neutron optics [10-12], but they have yet to find their way into X-ray optics and instrumentation. Before that can happen we need to compare the performance of traditional mirrors and supermirrors and to show that supermirrors can be applied to optical problems, such as focusing a divergent, polychromatic beam of hard X-rays.

* Corresponding author. Present address: Institut Laue Langevin, BP 156, F-38042 Grenoble Cedex 9, France. Tel.: +33 (0) 4 76 20 70 19; fax: 33 (0) 4 76 20 77 00; e-mail: hoghoj@ill.fr.

¹ Present address: Niels Bohr Institute, Oersted Laboratory of Physics, Universitetsparken 5, DK-2100 Copenhagen Ø, Denmark.

Traditional mirrors and supermirrors reflect X-rays by different physical mechanisms, and consequently the limits to their performance as X-ray optical elements are also different. In the following we derive and compare expressions for the maximal scattering vectors q_z that are efficiently reflected by conventional mirrors and supermirrors. The optical index of a mirror material is

$$n = 1 - \delta - i\beta. \quad (1)$$

In the X-ray region the real part decrement δ is typically in the range 10^{-7} – 10^{-5} . For small grazing angles where $\sin\theta \approx \theta$ it follows from Snell-Descartes' law that

$$\theta_c \approx \sqrt{2\delta}. \quad (2)$$

In the X-ray region well away from absorption edges, δ can be approximated by the contribution from the Thomson scattering [13]

$$\delta \approx Z(r_0\lambda^2/2\pi)N, \quad (3)$$

where Z is the atomic number, λ the wavelength of the incoming radiation, r_0 the classical electron radius, and N is the number of atoms per unit volume. Eq. (3) allows a fast survey of δ for various elements. The highest value of δ among potential mirror materials is found for iridium. Inserting Eq. (3) in Eq. (2) with the values for Ir, the condition for total reflection ($\theta \leq \theta_c$) is

$$\theta/\lambda \leq 7.0 \times 10^{-2} \text{ nm}^{-1} \quad (4)$$

or in terms of θ and energy E

$$E [\text{keV}] \theta [\text{mrad}] \leq 86. \quad (5)$$

In a supermirror the reflection mechanism is first order diffraction. The condition for reflection can be found from Bragg's law (neglecting refraction)

$$m\lambda = 2d \sin \theta \quad (6)$$

with the reflection order $m = 1$, and period d . The condition for reflection is then

$$\theta/\lambda \leq 1/(2d_{\min}), \quad (7)$$

where d_{\min} is the smallest period in the supermirror. Analogous to Eq. (5) we find

$$E [\text{keV}] \theta [\text{mrad}] \leq 6.2 \times 10^2 / (d_{\min} [\text{nm}]). \quad (8)$$

If desired, Eqs. (4) and (7) can be multiplied by 4π to give a condition for the momentum transfer q_z . It follows that a supermirror with $d_{\min} = 2.4$ nm can show considerable reflectivity at q_z up to three times higher than that of any single layer mirror. However, unlike the neutron case, supermirrors for X-rays have reflectivities much below unity because of absorption [7]. This is particularly true for energies immediately above the absorption edge of one of the layer materials. Interface roughness also reduces the reflectivity, especially for small d -spacings. On the other hand, the increased reflecting angles are an advantage in most optical systems, leading to shorter mirrors less prone to optical aberrations, having a potential for higher resolution and a larger field of view.

2. Experimental setup

The supermirror used in this experiment has been described elsewhere [8]. It is a 600 period W/Si multilayer with the d -spacing of the i th layer from the top being

$$d_i = a(b + i)^{-c}, \quad (9)$$

where $a = 110$ Å, $b = -0.6$, $c = 0.27$, and the ratio of each W layer thickness to the respective bilayer thickness is $\Gamma = d_w/d = 0.33$. The sample was deposited on a $170 \times 50 \times 10$ mm³ superpolished SiC substrate at Osmic Inc. Fig. 1 shows the reflectivity of the W/Si supermirror before bending.




Fig. 1. Measured (solid line) and simulated (dashed line) reflectivity of a flat supermirror at 2.95 mrad.

The supermirror was mounted in a bender [14,15] modified to accommodate thick substrates and bent to a cylindrical shape. The surface figure of the supermirror was verified at every stage of the experiment with a Wyko 6000 Fizeau interferometer [16] capable of measuring height variations down to $0.006 \mu\text{m}$ over length scales of 0.5–150 mm. Fig. 2 shows the cylindrical figure of the central $40 \times 110 \text{ mm}^2$ of the mirror upon bending. The contour plot in Fig. 2 reveals a small twist and a slightly saddle-like shape. The latter is an effect of antielastic bending [15]. The figure of the bent mirror was further measured with a Long Trace Profiler (LTP) at the Metrology Lab at ESRF [16]. The slope of the surface $\mathcal{S}(x) = \partial z(x) / \partial x$ was measured to a precision better than $1 \mu\text{rad}$ at 1 mm intervals along the length of the sample. The data are shown in Fig. 3 along with a fit to the data assuming a cylindrical shape. A fit to the middle 80 mm of the mirror used for focusing experiments yielded a radius of curvature $R_c = 630 \text{ m}$ with a RMS slope error $\sigma_\varphi = 1.1 \mu\text{rad}$ compared to a cylindrical shape. The height data from the measurements with the Fizeau interferometer can be differentiated in order to obtain slope data and are found to agree well with the LTP data.

The cylindrically bent supermirror was then mounted on a diffractometer in a high energy dispersive setup [17] schematically shown in Fig. 4. The source was a tungsten anode high energy X-




Fig. 2. Figure of the bent supermirror as measured with a WYKO 6000 Fizeau interferometer. The contours are drawn at intervals of $0.5 \mu\text{m}$.




Fig. 3. Slope (crosses) along the x -axis of the bent supermirror as measured with the Long Trace Profiler. The line is a fit to the data assuming a cylindrical shape. The right scale shows the slope error (circles), i.e. the difference between the data and the fit.




Fig. 4. Schematic (top view) of the setup used in the focusing experiment. S1 and S2 are slits. α_1 is the divergence of the incident beam, and α_2 is the variation of the slope of the mirror over the illuminated area. p is the source to mirror distance and q is the focal length.

ray tube (Philips) operated at 100 kV/1.0 mA giving a Bremsstrahlung spectrum superimposed with the tungsten $K\alpha$ and $K\beta$ emission. The source size in the focusing plane was defined by a 20 mm thick lead slit S1 with a width of $w_{S1} = 100 \mu\text{m}$ placed at the tube exit. The incident beam was further defined by a similar second slit S2 with width $200 \mu\text{m}$ placed 3.334 m after the first slit. A guard slit was used to remove radiation scattered by S2. The supermirror was placed at a distance $p = 4.000 \text{ m}$ from the first slit. The height of the beam at the mirror was 3 mm.

The width of the direct and reflected beams were measured using a knife-edge approach. In this approach a polished lead piece mounted on rotation and translation stages with steps of 0.001° and $1 \mu\text{m}$, respectively, was scanned through the beam while the intensity was recorded by a Ge solid state detector operated in single channel integral mode. In this method the intensity is seen to drop as the knife edge crosses the beam and the beam profile can be obtained by differentiation. After alignment the supermirror was set to an angle of incidence $\theta = 2.94 \text{ mrad}$. The beam-spot width was measured at several distances from the supermirror. The smallest width (FWHM) of $F_{\text{meas}} = 29.2 \mu\text{m}$ was found for a distance $q = 1.000 \text{ m}$ and should be compared to an ideal theoretical width $F_{\text{theo}} = (q/p)w_{\text{Sl}} = 25 \mu\text{m}$. The result is shown in Fig. 5 together with the profile of the direct beam measured at $q = 1.000 \text{ m}$. The direct beam profile has a trapezoidal shape as expected from a beam defined by slits. The FWHM for the direct beam was $D_{\text{meas}} = 295 \mu\text{m}$, the inte-

grated intensity was 5604 c/s with a peak flux of $20 \text{ c/s}/\mu\text{m}$, while for the focused beam the integrated intensity was 2401 c/s with a peak flux of $77.3 \text{ c/s}/\mu\text{m}$. The results obtained with knife-edge scans were verified by taking photos of the direct and reflected beams using Kodak HR X-ray film. The results are shown in Fig. 6.

From geometrical optics the distance mirror to focus q is given by the lens equation

$$\frac{1}{q} + \frac{1}{p} = \frac{2}{R_c \sin \theta} \quad (10)$$

but the experimentally observed q was 17% smaller than the one obtained from Eq. (10). However, using the raytracing program SHADOW [18] we find the value of q to be strongly dependent on the deviation of the surface figure from the cylindrical case. Furthermore, the measured values for the width of the focused beam was found to be in good agreement with values obtained from raytracing using the actual shape of the mirror as measured with the LTP.

Fig. 7 shows the reflectivity $R(E)$ of the bent supermirror at $\theta = 2.94 \text{ mrad}$. The reflectivity was found by measuring the spectrum of the reflected beam with the Ge-detector connected to a multichannel analyzer and normalizing it with




Fig. 5. (a) Intensity as a function of knife-edge position for the direct beam as defined by slits (squares) and the focused beam (circles) for $\theta = 2.94 \text{ mrad}$ at $q = 1000 \text{ mm}$. A fit to the data assuming a Gaussian flux distribution for the focused beam is shown (solid line); (b) beam flux profile in the direction of the scan for the direct beam (dashed line) and focused beam (solid line) as found from differentiating the intensity with respect to the knife-edge position.




Fig. 6. Photos of the direct beam (left) and focused beam (right) at $q = 1000 \text{ mm}$. The photos were recorded on Kodak HR X-ray film and magnified using an optical microscope.




Fig. 7. Measured (solid line) and calculated reflectivity (short dashed line) as a function of energy at an angle of incidence $\theta = 2.94$ mrad for the bent W/Si supermirror. The flux gain in the focal plane as compared to the direct beam is given on the right ordinate. Compared with Fig. 1 only small differences in the reflectivity modulation are observed. The differences are due to the increased range of incidence angles. The gain in flux is a result of the focusing of the beam as shown in Figs. 5 and 6. For comparison the theoretical reflectivity of an Ir mirror is shown (long dashed line).

the spectrum of the direct beam. The measured reflectivity is higher than 30% for energies lower than the W absorption edge at 69.5 keV. For energies below 20 keV it was difficult to obtain absolute reflectivities due to the behavior of the detector response function combined with low intensity. The reflectivity simulations shown in Fig. 7 were done using the recursive method of Parratt [19] and the design parameters. The drop in reflectivity with energy is very sensitive to the roughness, which was fitted to be $\sigma = 4.3$ Å using the expression proposed by Névoit–Croce [20]. The slits defined the divergence of the incident beam to $\alpha_1 = 0.06$ mrad. As seen in Fig. 3 the slope varied by $\alpha_2 = 0.14$ mrad over the 80 mm illuminated part of the mirror. From Fig. 4 it is seen that α_1 and α_2 contribute to the angle of incidence θ with opposite sign. Furthermore, the intensity distributions are both well approximated by the uniform distributions as seen from the intensity profiles of the direct beam in Fig. 5 and the distribution of slope in Fig. 3. Consequently, the simulated data were convoluted with a uniform distribution of width $\alpha = \alpha_2 - \alpha_1 = 0.08$ mrad and with the Gaussian energy resolution σ_E of the Ge detector using Eq. (11).

$$R(E, \theta) = \frac{1}{\sigma_E \sqrt{2\pi\alpha}} \int_{E-4\sigma_E}^{E+4\sigma_E} \int_{\theta-\alpha/2}^{\theta+\alpha/2} R(E', \theta') \times \exp(-((E - E')/\sigma_E)^2/2) d\theta' dE'. \quad (11)$$

From monochromatic experiments σ_E was found to change from about 0.12 keV at $E = 15$ to 0.18 keV at $E = 100$ keV.

The reduction of the beam size gives a gain in flux while the reflectivity lower than unity gives a loss. When comparing focusing optics to simply reducing the size of the direct beam with slits, the interesting value is the flux gain G , which can be defined as

$$G(E) = (D_{\text{meas}}/F_{\text{meas}})R(E), \quad (12)$$

where D_{meas} and F_{meas} are the measured widths of the direct beam and focused beam, respectively. $G(E)$ is plotted on the right y -axis of Fig. 7. The flux gain is in the range 7–3 in the 20–70 keV energy range.

3. Conclusion

A comparison of supermirrors to conventional mirrors shows that supermirrors have the ability to efficiently reflect X-rays at q_z up to more than three times the critical angle or energy of conventional mirrors. Such performance makes supermirrors interesting optical elements for high energy X-rays.

The results demonstrate the capability of bent supermirrors to focus X-rays at high energies. At $\theta = 2.94$ mrad the bent W/Si supermirror showed reflectivities of 30–70% for energies below the tungsten absorption edge at 69.5 keV. By bending the supermirror to a near cylindrical shape and applying it in a 4 to 1 focusing scheme in one dimension the beam was focused to a size 10 times smaller than that of the direct beam. The resulting flux gain was from 3 to 7 in the above mentioned energy range. By using other multilayer materials similar results should be possible even for energies above 100 keV. The focusing properties of the bent supermirror are well understood and no deterioration of the reflectivity was observed upon bending.

The fact that line to line focusing should be done with an elliptical mirror rather than a cylindrical one has little influence on the results. However, in the case of a synchrotron beamline with smaller source size and larger source demagnification q/p the contribution of spherical aberrations to the focal width would be more significant and an elliptical mirror should be used (as shown in [15]). By focusing in two dimensions even larger gains in flux could be obtained. Finally, this first experiment with a focusing supermirror shows the potential of supermirrors as X-ray optical elements and the new possibilities they open in X-ray instrumentation in areas such as synchrotron radiation and astrophysics applications.

References

- [1] J. Du Mond, J.P. Youtz, *Phys. Rev.* 48 (1935) 703.
- [2] E. Spiller, A. Segmüller, J. Rife, R.-P. Haelbich, *Appl. Phys. Lett.* 37 (1980) 1048–1050.
- [3] T.W. Barbee, Jr., *Opt. Engrg.* 25 (8) (1986) 898–915.
- [4] R. Fourme, P. Dhez, J.P. Benoit, R. Kahn, J.M. Dubuisson, P. Besson, J. Frouin, *Rev. Sci. Instrum.* 63 (1) (1991) 982–987.
- [5] F. Mezei, *Comm. Phys.* 1 (1976) 81–85; F. Mezei, P.A. Dagleish, *Comm. Phys.* 2 (1976) 41–43.
- [6] J. Schelten, K. Mika, *Nucl. Instr. and Meth.* 160 (1979) 287–294.
- [7] K.D. Joensen, F.E. Christensen, H.W. Schnopper, P. Gorenstein, J. Susini, P. Høghøj, R. Hustache, J. Wood, K. Parker, Medium-sized grazing incidence high-energy X-ray telescopes employing graded multilayers, in: R. Hoover (Ed.), *Multilayer and Grazing Incidence X-ray/EUV Optics II*, vol. 1736, SPIE, San Diego, 1992, p. 239.
- [8] K.D. Joensen, P. Høghøj, F. Christensen, P. Gorenstein, J. Susini, E. Ziegler, J. Wood, Multilayered supermirror structures for hard X-ray synchrotron and astrophysics instrumentation, in: R. Hoover (Ed.), *Multilayer and Grazing Incidence X-ray/EUV Optics II*, SPIE Proceedings, vol. 2011, SPIE, San Diego, 1993, pp. 360–372.
- [9] K.D. Joensen, P. Gorenstein, P. Høghøj, F.E. Christensen, X-ray Supermirrors: Novel multilayer structures for broad band hard X-ray applications, in: *Physics of X-ray Multilayer Structures Technical Digest, 1994 Technical Digest Series*, vol. 6, Optical Society of America, Jackson Hole, 1994, pp. 159–162.
- [10] F. Mezei, Very high reflectivity supermirrors and their applications, in: C. Majkrzak (Ed.), *Thin-film Neutron Optical Devices: Mirrors, Supermirrors, Multilayer Monochromators, Polarizers, and Beam Guides*, SPIE Proceedings, vol. 983, SPIE, San Diego, 1988, pp. 10–17.
- [11] C. Majkrzak, C.J. Glinka, S.K. Satija, Applications of mirrors, supermirrors, and multilayers at the National Bureau of Standards cold neutron research facility, in: C. Majkrzak (Ed.), *Thin-Film Neutron Optical Devices: Mirrors, Supermirrors, Multilayer Monochromators, Polarizers, and Beam Guides*, SPIE Proceedings, vol. 983, SPIE, San Diego, 1988, pp. 129–143.
- [12] M. Rossbach, O. Schärpf, W. Kaiser, W. Graf, A. Schirmer, W. Faber, J. Duppich, R. Zeisler, *Nucl. Instr. and Meth. B* 35 (1988) 181–190.
- [13] A.G. Michette, *Optical Systems for Soft X-rays*, Plenum Press, New York, 1986.
- [14] M. Krisch, Ph.D. Thesis, University of Dortmund (1993).
- [15] E. Ziegler, O. Hignette, M. Lingham, A. Souvorov, X-ray focusing using elliptically bent multilayers, in: *Optics for High-Brightness Synchrotron Radiation Beamlines II*, SPIE Proceedings, vol. 2856, SPIE, Denver, 1996, pp. 61–67.
- [16] J. Susini, *Opt. Engrg.* 34 (2) (1995) 361–376.
- [17] P. Høghøj, K. Joensen, F.E. Christensen, J. Susini, E. Ziegler, A.K. Freund, E. Lüken, C. Riekel, Measurement of multilayer reflectivities from 8 keV to 130 keV, in: R. Hoover (Ed.), *Multilayer and Grazing Incidence X-ray/EUV Optics II*, SPIE Proceedings, vol. 2011, SPIE, San Diego, 1993, pp. 354–359.
- [18] C. Welna, G.J. Chen, F. Cerrina, *Nucl. Instr. and Meth. A* 347 (1994) 344–347.
- [19] L.G. Parratt, *Phys. Rev.* 95 (1954) 359–369.
- [20] L. Névoit, P. Croce, *Revue Phys. Appl.* 15 (1980) 761–779, in French.

BEAM INTERACTIONS WITH MATERIALS AND ATOMS

Nuclear Instruments and Methods in Physics Research – Section B

Instructions to Authors

Submission of papers

Contributions should be submitted to one of the Editors (see inside front cover). It is suggested that manuscripts originating from Europe, India, The Middle East and Africa be sent to Prof. H.H. Andersen, and from The Americas, The Far East and Australasia, to Dr. L.E. Rehn.

Manuscript and figures should be submitted in duplicate, with one set of good quality figure material for production of the printed figures. If possible, please submit also an electronic version of your contribution on diskette.

Short contributions of less than 1500 words and not subdivided into sections may be published as Letters to the Editor in a shorter time than regular articles as the proofs will normally be corrected by the Publisher.

Submission of a manuscript implies that it is not being considered for publication elsewhere and that the authors have obtained the necessary authority for publication.

Manuscript preparation

Manuscripts should be written in good English. They should be typed throughout with double line spacing and wide margins on numbered, single column pages. See notes opposite on electronic manuscripts.

Structure. Please adhere to the following order of presentation: article title, author(s), affiliations, abstract, PACS codes and keywords, main text, acknowledgements, appendices, references, figure captions, tables.

Corresponding author. The name, full postal address, telephone and fax numbers and e-mail address of the corresponding author should be given on the first page.

Classification codes/keywords. Please supply one to four classification codes (PACS and/or MSC), and up to six keywords of your own choice that describe the content of your article in more detail.

References to other publications should be numbered consecutively within square brackets and listed together at the end of the text. In the case of multiple authorship all authors should be listed in the references; only in case of more than ten authors is the first author et al. acceptable.

Illustrations

The Publisher requires a set of good quality drawings and original photographs to produce the printed figures.

Line drawings should be 1.5–3 times larger than the printed size; the height of letters and numbers should, after reduction, fall within the range 1.2–2.4 mm. Do not use too narrow pen widths for machine-plotted graphs. Shaded areas should be shown by means of cross-hatching or a matrix of dots, rather than a continuous grey wash.

Photographs should not already be screened (overprinted with the point matrix used by printers). The top side of a photograph should be marked if necessary.

Colour figures can be printed in colour when this is essential to the presentation. Authors will be charged for colour reproduction. Further information can be obtained from the Publisher.

After acceptance

Notification. You will be notified by the Editor of the acceptance of your contribution, and invited to send an electronic file of the accepted version to the Publisher, if this is not yet available. After acceptance any correspondence should be addressed to the Publisher at the coordinates below.

Page proofs are sent out to the Author in order to check that no undetected errors have arisen in the typesetting or file conversion process. In the proofs only typesetting errors may be corrected. No changes in, or additions to, the accepted paper will be accepted.

Copyright transfer. In the course of the production process the authors will be asked to transfer the copyright of the article to the publisher. This transfer will ensure the widest possible dissemination of information.

Electronic manuscripts

If possible, an electronic version of the manuscript should be submitted on a diskette together with the hard copies of the text and figures, or should be sent (after acceptance) by e-mail or on a diskette to the Publisher. It is the responsibility of the Author to ensure that the electronic version exactly matches the hard copy. No deviations from the version accepted for publication are permissible without the prior and explicit approval by the Editor. Such changes should be clearly indicated on an accompanying print-out of the file.

LaTeX articles and articles prepared with any of the well known word processors can be handled by the Publisher. Further information can be obtained from the Publisher.

Author benefits

No page charges. Publishing in Nuclear Instruments and Methods in Physics Research – Section B is free.

Free offprints. The corresponding author will receive 50 offprints free of charge. An offprint order form will be supplied by the publisher for ordering any additional paid offprints.

Discount. Contributors to Elsevier Science journals are entitled to a 30% discount on all Elsevier Science books.

Correspondence with the Publisher

After acceptance of an article any correspondence should be addressed to Elsevier Science B.V., NIM-B, P.O. Box 2759, 1000 CT Amsterdam, The Netherlands
Tel. +31 20 485 2500, fax +31 20 485 2431
e-mail nimb-j@elsevier.nl



North-Holland, an imprint of Elsevier Science

