

NASA/TM—1998-207425



# Experimental and Computational Studies of the Interactions of $\text{BF}_3$ With Fluoroethers

David W. Ball  
Cleveland State University, Cleveland, Ohio

Michael J. Zehe and Wilfredo Morales  
Lewis Research Center, Cleveland, Ohio

Prepared for the  
Annual Meeting  
sponsored by the Society of Tribologists and Lubrication Engineers  
Detroit, Michigan, May 17–21, 1998

National Aeronautics and  
Space Administration

Lewis Research Center

---

July 1998

Available from

NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076  
Price Code: A03

National Technical Information Service  
5287 Port Royal Road  
Springfield, VA 22100  
Price Code: A03

# EXPERIMENTAL AND CALCULATIONAL STUDIES OF THE INTERACTIONS OF $\text{BF}_3$ WITH FLUOROETHERS

David W. Ball  
Department of Chemistry  
Cleveland State University  
Cleveland, Ohio 44115

Michael J. Zehe  
National Aeronautics and Space Administration  
Lewis Research Center  
Cleveland, Ohio 44135

and

Wilfredo Morales  
National Aeronautics and Space Administration  
Lewis Research Center  
Cleveland, Ohio 44135

## ABSTRACT

$\text{BF}_3$  was co-condensed with  $(\text{C}_2\text{H}_5)_2\text{O}$ ,  $(\text{CF}_3\text{CH}_2)_2\text{O}$ , and  $(\text{C}_2\text{F}_5)_2\text{O}$  in excess argon at 15 K. Infrared spectra of the matrices showed a definite Lewis acid-base interaction between  $\text{BF}_3$  and diethyl ether; a weak but definite interaction with bis(2,2,2-trifluoroethyl)ether, and no observable interaction with perfluoroethyl ether. Molecular orbital (MO) calculations complemented the experimental observations by revealing that fluorine atoms on the ethers decreased electron localization about the oxygen atom. Thus, the experimental data and MO calculations indicated a clear trend between strength of interaction with  $\text{BF}_3$  and the degree of ether F substitution. The implications of the results for commercial perfluoro ether lubricant/metal oxide surface interactions are discussed.

**KEY WORDS:** Infrared spectroscopy, chemical attack, fluorocarbons

## INTRODUCTION

The chemistry of perfluoroalkyl ethers has come under increasing study recently because of their application to lubrication of computer magnetic media and spacecraft devices (Refs. 1 and 2). The behavior of commercial fluids, and model compounds that mimic their chemistry, has been studied both theoretically (Refs. 3 and 4) and experimentally for exposure to the influence of electrons (Ref. 5), Lewis acids (Refs. 6 to 9), metal oxides (Refs. 9 and 10), and bare metal surfaces (Refs. 11 and 12). Much attention has been given to the catalytic decomposition of perfluoroalkyl ethers which occurs when they are heated in the presence of metal oxides or halides. The effectiveness of the surfaces in catalyzing the decomposition is a strong function of the fluoroether's structure. A number of workers have observed that the presence of an -O-CF<sub>2</sub>-O- (acetal) linkage greatly enhances their reactivity towards catalyzed breakdown by metal oxides (Refs. 8 and 13).

The postulated mechanisms for this catalyzed breakdown usually involve an initial acid-base interaction between the surface metal ions and the lone electron pairs on the fluoroether oxygen atoms followed by chain scission. Kasai et al. (Refs. 7 and 10) used <sup>19</sup>F NMR and mass spectrometry to study the Lewis acid-catalyzed breakdown of several perfluoroethers of different structures. The initial step in the mechanism they proposed, as well as that of most other mechanisms advanced, is the donation of electron density from oxygen atoms in the chain to one or more acidic metal atoms on the Lewis acid surface. Although this mechanism is a well-established process for hydrocarbon ethers, one expects that for perfluoroethers the oxygen atoms will exhibit a much lower basicity and therefore vulnerability to attack.

Alternate mechanisms which do not involve Lewis acid attack on the oxygen atoms have been proposed. Zehe and Faut (Ref. 8) studied the catalyzed breakdown of commercial fluids by  $\alpha\text{-Fe}_2\text{O}_3$  and proposed a mechanism involving acidic attack on the nonbonding electrons on the fluorine atoms. Basu et al. (Refs. 14 to 16) studied decomposition of hydrocarbon ethers and  $(\text{CF}_2\text{H})_2\text{O}$  on planar and powdered  $\text{Al}_2\text{O}_3$ . They observed decomposition to occur for  $(\text{CF}_2\text{H})_2\text{O}$  in contact with powdered  $\text{Al}_2\text{O}_3$ , even after pre-adsorbing pyridine to block Lewis acid sites. They concluded that Lewis sites were not involved in the reaction, and postulated that the first step in the decomposition was a nucleophilic attack by surface oxygen on a carbon atom in the ether.

Infrared matrix-isolation spectroscopy has been used successfully for producing and studying reaction complexes, including Lewis acid-base adducts. This technique has been applied by Ault (Refs. 17 and 18) to the study of a large number of Lewis acid-base complexes, both strongly and weakly bound. Strong Lewis acids such as  $\text{BF}_3$  and  $\text{SO}_3$  have been co-condensed at high dilution with weak Lewis bases, and complexation observed through shifts in the measured vibrational frequencies. With a given base, rough correlations have been observed between the strength of the acidity or basicity and the measured spectral shifts.

In this paper, an infrared matrix-isolation apparatus was used to investigate the interaction between the strong Lewis acid  $\text{BF}_3$  with

diethyl ether, bis(2,2,2-trifluoroethyl)ether and perfluoroethyl ether. The results were used to assess the Lewis acid-base hypothesis for the postulated decomposition mechanism of commercial perfluoroether lubricants by metal oxides. Molecular orbital (MO) calculations were performed on the interaction between  $\text{BF}_3$  and the three ethers to aid the analysis of the experimental data.

## EXPERIMENTAL

The matrix isolation apparatus used in this study has been previously described (Ref. 19). Briefly, sample vapors were co-condensed, inside a vacuum chamber, onto the polished surface of a gold-plated copper block which was kept at 15 K. Sample vapors were introduced into the vacuum chamber via stainless steel tubing and were regulated with high precision needle valves. Deposition rates were measured manometrically. Deposition onto the gold-plated surface typically lasted 30 min to 2 hr. After deposition, the Fourier transform infrared spectrum was measured by reflection off the gold-plated surface through ZnSe windows using a Fourier transform infrared spectrometer at  $2\text{ cm}^{-1}$  resolution. Five hundred scans were measured and averaged.

$\text{BF}_3$  (99.5+%),  $(\text{C}_2\text{H}_5)_2\text{O}$  (reagent grade),  $(\text{CF}_3\text{CH}_2)_2\text{O}$  (97+%),  $(\text{C}_2\text{F}_5)_2\text{O}$  (97%), and Ar (99.9995%) were used without further purification. CAUTION:  $\text{BF}_3$  is a highly toxic, moisture-sensitive gas; only small quantities should be used at a time, under a fume hood.  $(\text{CF}_3\text{CH}_2)_2\text{O}$  is a convulsant and should be used only in adequate ventilation or in a fume hood.

## CALCULATIONAL

The AM1 self-consistent field molecular orbital procedure developed by Dewar and co-workers (Ref. 20) was used in this study. Computations were performed using a commercial software package, utilizing the RHF option, on a Pentium based, 166 MHz, desktop computer. Complete geometric optimization during energy minimization was performed on all single molecules and for all interacting pairs of molecules. The convergence criterion for energy minimization was selected so that the change in total energy on successive iterations was less than  $0.01\text{ kJ/mol \AA}$ . Configuration interaction was not used.

## RESULTS

### Experimental

When  $\text{BF}_3$  was co-condensed with diethyl ether in excess Ar at 15 K, new absorptions were measured in the infrared spectrum. Figure 1(a) shows the wavelength region  $1300$  to  $600\text{ cm}^{-1}$  for  $\text{BF}_3$  in Ar, illustrating the  $\text{BF}_3$  bending mode (Ref. 21) (split into two absorptions following the natural 20%/80%  $^{10}\text{B}/^{11}\text{B}$  isotopic abundance of boron). Several new absorptions appeared, indicated by the features in Fig. 1(c) marked with an asterisk. The absorptions appearing at  $1241.1$  and  $1207.6\text{ cm}^{-1}$  are very close to the

positions reported by Hunt and Ault (Ref. 18) for the antisymmetric B-F stretches of the  $\text{BF}_3/(\text{CH}_3)_2\text{O}$  complex. A broad absorption appearing at  $875.8\text{ cm}^{-1}$  corresponds to the symmetric C-O stretch of the ether moiety. A new absorption at  $762.0\text{ cm}^{-1}$  can be assigned to a symmetric B-F stretch; a very weak feature at  $796.8\text{ cm}^{-1}$  could be the  $^{10}\text{B}$  counterpart.

When  $\text{BF}_3$  was co-condensed with  $(\text{CF}_3\text{CH}_2)_2\text{O}$ , new absorptions appeared. These new absorptions are illustrated in Figs. 2 and 3. All of the new absorptions shown in Fig. 2, occurring at  $1229.6$ ,  $1220.0$ , and  $1161.1\text{ cm}^{-1}$ , appeared very close to the infrared absorptions of the parent molecules. Another absorption, not shown in the figures and occurring at  $1330.0\text{ cm}^{-1}$ , appeared to be a shift of a parent fluoroether absorption. Figure 3(a) shows the infrared spectrum of  $\text{BF}_3$  between  $740$  and  $600\text{ cm}^{-1}$ , where the out-of-plane bending vibration of the planar  $\text{BF}_3$  molecule absorbs.  $^{10}\text{BF}_3$  absorbs at  $705\text{ cm}^{-1}$ , and  $^{11}\text{BF}_3$  at  $678\text{ cm}^{-1}$ . These absorptions show an approximate intensity ratio expected for naturally occurring boron. Figure 3(c) shows the same region for the co-deposited  $\text{BF}_3/(\text{CF}_3\text{CH}_2)_2\text{O}$  sample and indicates two broad absorptions at  $694.9$  and  $668.0\text{ cm}^{-1}$  that are present only upon co-condensation.

When  $\text{BF}_3$  was co-condensed with  $(\text{C}_2\text{F}_5)_2\text{O}$  in excess Ar, no new absorptions were observed. In a subsequent test,  $\text{BF}_3$  and  $(\text{C}_2\text{F}_5)_2\text{O}$  were co-condensed at 15 K without Ar. No new absorptions appeared upon condensation.

### Calculational

Before computational runs were performed on the interaction between the ether molecules and the  $\text{BF}_3$  molecule, a preliminary test of the AM1 program was made. This test involved the analysis of the computational results between the interaction of  $\text{NH}_3$  and  $\text{BF}_3$ .  $\text{NH}_3$  is a molecule that interacts strongly with surface Lewis acid sites and is widely used as a poison to block the effect of these sites. Select optimized geometries of the  $\text{BF}_3\text{-NH}_3$  complex are shown in Fig. 4 and total energy values are listed in Table I.

The B-N distance was  $1.782\text{ \AA}$  and the net charges on the  $\text{BF}_3$  and  $\text{NH}_3$  groups were  $\pm 0.326$  respectively. The calculated dihedral angle of the  $\text{BF}_3$  group,  $-130.7^\circ$ , showed that this molecule was distorted from its normal planar trigonal geometry. The total energy of the  $\text{BF}_3\text{-NH}_3$  system was  $51\text{ kJ/mol}$  lower than the added total energy of the isolated molecules. The HOMO orbital plot (a two dimensional contour) for the this system is shown in Fig. 5. A strong electron withdrawal of the nitrogen 2p orbital toward the boron atom was observed. These MO calculations on the  $\text{BF}_3/\text{NH}_3$  system confirmed that the AM1 method was able to reproduce computationally the formation of a well-known Lewis acid-base adduct.

The optimized structure and total energy for the  $\text{BF}_3\text{-(C}_2\text{H}_5)_2\text{O}$  system are shown in Fig. 6 and Table I. The B—O distance was  $1.908\text{ \AA}$ . The net charges on  $\text{BF}_3$  and the ether were  $\pm 0.119$ . The  $\text{BF}_3$  molecule had a dihedral angle of  $-158.2^\circ$ . The total energy of the  $\text{BF}_3\text{-(C}_2\text{H}_5)_2\text{O}$  system was  $19\text{ kJ/mol}$  lower than the added total energy of the isolated molecules. The HOMO orbital plot (Fig. 7) showed substantial withdrawal of the orbital, around the oxygen atom, toward the boron atom.

The optimized structure and total energy for the  $\text{BF}_3\text{---}(\text{CF}_3\text{CH}_2)_2\text{O}$  system are shown in Fig. 8 and Table I. The B—O distance was 2.007 Å, and net charges on the  $\text{BF}_3$  and ether molecules were  $\pm 0.057$ . The  $\text{BF}_3$  dihedral angle was  $-167.0^\circ$ . The total energy of the  $\text{BF}_3\text{---}(\text{CF}_3\text{CH}_2)_2\text{O}$  system was 8 kJ/mol lower than the added total energy of the isolated molecules. The HOMO orbital plot (Fig. 9) showed a slight withdrawal of the orbital, around the oxygen atom, toward the  $\text{BF}_3$  molecule.

The optimized structure and total energy for the  $\text{BF}_3\text{---}(\text{C}_2\text{F}_5)_2\text{O}$  system are shown in Fig. 10 and Table I. The B—O distance was 5.182 Å, and the net charges on the  $\text{BF}_3$  molecule and ether molecule were both zero. The  $\text{BF}_3$  dihedral angle was  $-180.0^\circ$ . The total energy of this system equaled the added total energy of the isolated molecules. The HOMO orbital plot (Fig. 11) showed no orbital withdrawal toward the  $\text{BF}_3$  molecule.

## DISCUSSION

New absorptions found when diethyl ether was co-condensed with  $\text{BF}_3$  indicated a Lewis acid-base complex was formed. Several of the new absorptions appeared in spectral regions that were similar to new vibrations in  $\text{BF}_3$ /dimethyl ether samples reported by Hunt and Ault (Ref. 18). The new absorptions at 1241.1 and 1207.6  $\text{cm}^{-1}$  are assigned to the antisymmetric B-F stretching vibration of the  $\text{BF}_3$  moiety. The 875.8  $\text{cm}^{-1}$  peak appears in the expected region for the symmetric C-O stretching vibration, and the absorptions at 796.8 and 762.0  $\text{cm}^{-1}$  coincide with the symmetric B-F stretch. These two absorptions have the correct approximate 1:3 intensity ratio, suggesting assignment to a vibration involving a boron atom. No boron isotopic splitting was seen for either the 1241.7 or the 1207.6  $\text{cm}^{-1}$  absorption. The assignments to  $\text{BF}_3\text{---}(\text{C}_2\text{H}_5)_2\text{O}$  are similar to those of the  $\text{BF}_3$ /dimethyl ether matrix spectra (Ref. 18). The absorptions of  $\text{BF}_3\text{---}(\text{C}_2\text{H}_5)_2\text{O}$  and their approximate assignments are listed in Table II.

When  $\text{BF}_3$  was co-condensed with bis(2,2,2 trifluoroethyl)ether, new absorptions were again detected. These new absorptions are listed in Table III. However, instead of appearing in spectral regions characteristic of a Lewis acid-base interaction, the new absorptions appeared to be only slightly shifted from the absorptions of the parent molecules; they are assigned as such in Table III. This suggests that the interaction between  $\text{BF}_3$  and  $(\text{CF}_3\text{CH}_2)_2\text{O}$ , while apparent, is weak. This weak interaction is best illustrated by the 10  $\text{cm}^{-1}$  shifts in the out-of-plane bending vibrations of  $^{10}\text{BF}_3$  and  $^{11}\text{BF}_3$  shown in Fig. 7. The same red shift in energy as well as the proper intensity ratio of the absorptions at 694.9 and 668.0  $\text{cm}^{-1}$  supports the idea of a mutually perturbing influence of the dopant molecules, not the formation of a new bona fide molecular complex.

When  $\text{BF}_3$  was co-condensed with perfluorodiethyl ether in excess argon, no new infrared absorptions were detected. While it is certainly possible that new infrared-active vibrations were too weak to be detected, it is more probable that there is no interaction between  $\text{BF}_3$  and  $(\text{C}_2\text{F}_5)_2\text{O}$  under these conditions. The increased electron-withdrawing capacity of more fluorine substituents on the ether seems to prevent any sort of detectable interaction in these circumstances. This lack of reactivity is not unique; Ault (Ref. 17) reported no Lewis acid/base adducts forming between  $\text{SiF}_4$  and any oxygen-containing bases. Neat co-condensation

of  $\text{BF}_3$  with  $(\text{C}_2\text{F}_5)_2\text{O}$  also failed to yield any new absorptions: the infrared spectrum was simply the sum of the two neat components.

MO calculations supported the experimental observation that a true Lewis acid-base adduct was formed between  $(\text{C}_2\text{H}_5)_2\text{O}$  and  $\text{BF}_3$ . The orbital displacement toward the  $\text{BF}_3$  molecule was very similar to the  $\text{NH}_3$  orbital displacement toward  $\text{BF}_3$ . MO calculations for the  $(\text{CF}_3\text{CH}_2)_2\text{O}\text{---}\text{BF}_3$  system, like the experimental results, revealed a slight interaction but not a true Lewis acid-base complexation. The calculations for the  $(\text{C}_2\text{F}_5)_2\text{O}\text{---}\text{BF}_3$  showed no interaction between the two molecules, in accord with the experimental results. A comparison of all three HOMO plots revealed that fluorine substitution resulted in decreased electron localization about the oxygen atom.

## CONCLUSIONS

The catalytic degradation of commercial fluororether lubricants by metal halides and metal oxides is of continuing interest to tribologists and engineers in the development of advanced lubrication systems. With very few exceptions, the proposed catalysis mechanisms involve an initial acidic attack of the ether's oxygen lone-pair electrons by surface acid sites. The results reported in this study confirmed the greatly lowered reactivity of highly fluorinated ethers towards Lewis acid-base complexation. They suggest that initiation of the catalyzed degradation by metal oxides involves a more complicated process than mere electron transfer from ether oxygen to surface sites. The experiments and MO calculations conducted in this study indicated that classic complex formation between the Lewis acid  $\text{BF}_3$  and fluoroether's oxygen atoms did not occur, thus suggesting that decomposition of commercial poly(perfluoroether) lubricants by metal oxide surfaces is necessarily assisted by some other process. Future studies will focus on elucidating this process.

## REFERENCES

- (1) Fusaro, R.L. and Khonsari, M.M.; "Liquid Lubrication for Space Applications," NASA TM-105198, July (1992).
- (2) Moulder, J.F., Hammond, J.S., and Smith, K.L.; "Using Angle Resolved ESCA to Characterize Winchester Disks," *Appl. Surf. Sci.*, 25, pp 446-454 (1986).
- (3) Pacansky, J. and Liu, B.; "Structural Studies on Perfluorinated Ethers," *J. Phys. Chem.*, 89, pp. 1883-1887 (1985).
- (4) Pacansky, J., Miller, M., Hatton, W., Liu, B., and Scheiner, A.; "Study of the Structures of Perfluoro Ethers," *J. Amer. Chem. Soc.*, 113 (No. 1), pp 329-343 (1991).
- (5) Pacansky, J., Waltman, R.J., and Wang, C.; "Irradiation of Poly(perfluoropropylene oxide) by a 175 Kilovolt Electron Beam," *J. Fluorine Chem.*, 32, pp 283-288 (1986).
- (6) Carré, D.J. and Markowitz, J.; "The Reaction of Perfluoropolyalkylether Oil with  $\text{FeF}_3$ ,  $\text{AlF}_3$ , and  $\text{AlCl}_3$  at Elevated Temperatures," *ASLE Trans.*, 28, pp 40-46 (1985).
- (7) Kasai, P.H. and Wheeler, P.; "Degradation of Perfluoropolyethers Catalyzed by Aluminum Chloride," *Appl. Surf. Sci.*, 52, pp 91-106 (1991).

- (8) Zehe, M.J. and Faut, O.D.; "Acidic Attack of PFPE Lubricant Molecules by Metal Oxide Surfaces," NASA TM-101962, Oct. (1989).
- (9) Sianesi, D. and Fontanelli, R.; "Perfluoro Polyethers. Their Structure and Reaction with Aluminum Chloride," Makrom. Chem., 102, pp 115-124 (1967).
- (10) Kasai, P., Tang, W.T., and Wheeler, P.; "Degradation of Perfluoropolyethers Catalyzed by Aluminum Oxide," Appl. Surf. Sci., 51 (No. 3), pp 201-211 (1991).
- (11) Walczek, M.M., Leavitt, P.K., and Thiel, P.A., "Oxygenated Fluorocarbons Adsorbed at Metal Surfaces: Chemisorption Bond Strengths and Decomposition," J. Amer. Chem. Soc., 109, pp 5621-5627 (1987).
- (12) Herrera-Fierro, P., Jones, W.R., and Pepper, S.V.; "Interfacial Chemistry of a Perfluoropolyether Lubricant Studied by XPS and TDS," NASA TM-105840, Oct. (1992).
- (13) Morales, W.; "Surface Catalytic Degradation Study of Two Linear Perfluoropolyalkylethers at 345 C," NASA TP-2774, Nov. (1987).
- (14) Ng, L., Chen, J.G., Basu, P., and Yates, J.T.; "Electron Stimulated Decomposition of Alkyl and Fluoroalkyl Ethers Adsorbed on  $Al_2O_3$ ," Langmuir, 3, pp 1161-1167 (1987).
- (15) Chen, J.G., Basu, P., Ballinger, T.H., and Yates, J.T.; "A Transmission Infrared Spectroscopic Investigation of the Reaction of Dimethyl Ether with Alumina Surfaces," Langmuir, 5, pp 352-356 (1989).
- (16) Basu, P., Ballinger, T. H., and Yates, J. T.; "Fluoroalkyl Ether Chemistry on Alumina," Langmuir, 5, pp 502-510 (1989).
- (17) Ault, B.S.; "Matrix Isolation Studies of Lewis Acid/Base Interactions: Infrared Spectra of the 1:1 Adduct  $SiF_4:NH_3$ ," Inorg. Chem., 20, pp 2817-2822 (1981).
- (18) Hunt, R.L. and Ault, B.S.; "Matrix Isolation Spectroscopic Study of the Boron Trihalide-Dimethyl Ether 1:1 Adducts," Spectrosc. Int. J., 1, pp 45-61 (1982).
- (19) Worden, D. and Ball, D.W.; "Reaction of  $NO_2$  with Cu Atoms in Ar Matrices," J. Phys. Chem., 96, pp 7167-7169 (1992).
- (20) Dewar, J.J.S., Zoebisch, E.G., Healy, E.F., and Steward, J.J.P.; "AM1: A New General Purpose Quantum Mechanical Molecular Model," J. Am. Chem. Soc., 107, pp 3902-3909 (1985).
- (21) Nakamoto, K.; "Infrared and Raman Spectra of Inorganic and Coordination Compounds," 4<sup>th</sup> edition. Wiley Interscience: New York, NY, p 123 (1967).

Table I.—Total Energy Calculations

Molecule	Total energy/kJ mol <sup>-1</sup>	System	Total energy/kJ mol <sup>-1</sup>
BF <sub>3</sub>	-147,694	BF <sub>3</sub> /NH <sub>3</sub>	-171,731
NH <sub>3</sub>	-23,986	BF <sub>3</sub> /(C <sub>2</sub> H <sub>5</sub> ) <sub>2</sub> O	-241,395
(C <sub>2</sub> H <sub>5</sub> ) <sub>2</sub> O	-93,682	-----	-----
(CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O	-366,713	BF <sub>3</sub> /(CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O	-514,415
(C <sub>2</sub> F <sub>5</sub> ) <sub>2</sub> O	-548,705	BF <sub>3</sub> /(C <sub>2</sub> F <sub>5</sub> ) <sub>2</sub> O	-696,398

Table II.—Infrared Absorptions of the BF<sub>3</sub>-(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub>O Complex In Ar Matrices

Frequency	Approximate assignment
1241.1	antisym B-F str
1207.6	antisym B-F str
875.8	sym C-O str
796.8	sym <sup>10</sup> B-F str
762.0	sym <sup>11</sup> B-F str

Table III.—Infrared Absorptions of the BF<sub>3</sub>-(CF<sub>3</sub>CH<sub>2</sub>)<sub>2</sub>O Complex In Ar Matrices

Frequency	Approximate assignment
1330.0	perturb. of (CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O
1229.6	perturb. of (CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O
1220.1	perturb. of (CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O
1116.1	perturb. of (CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O
694.9	perturb. of ν <sub>2</sub> , <sup>10</sup> BF <sub>3</sub>
668.0	perturb. of ν <sub>2</sub> , <sup>10</sup> BF <sub>3</sub>




Figure 1.—Infrared spectra of BF<sub>3</sub> and diethyl ether in excess argon at 15K. New absorptions are marked with an \*. (a) BF<sub>3</sub>:Ar = 3:1000. (b) (C<sub>2</sub>H<sub>5</sub>)<sub>2</sub>O:Ar = 8:1000. (c) BF<sub>3</sub>:(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub>O:Ar = 4:7:1000.




Figure 2.—Infrared spectra of  $\text{BF}_3$  and bis(2,2,2-trifluoroethyl)ether in excess argon at 15K. New absorptions are marked with \*. (a)  $\text{BF}_3:\text{Ar} = 3:1000$ . (b)  $(\text{CF}_3\text{CH}_2)_2\text{O}:\text{Ar} = 2:1000$ . (c)  $\text{BF}_3:(\text{CF}_3\text{CH}_2)_2\text{O}:\text{Ar} = 3:2:1000$ .





Figure 3.—Infrared spectra showing the perturbation of the  $\text{BF}_3$  modes by  $(\text{CF}_3\text{CH}_2)_2\text{O}$  in excess Ar at 15K. Sample concentrations are same as in Figure 2. Note that the new absorptions marked with \* are separated by almost the same amount as the unperturbed  $10,11\text{BF}_3$ .



Net atomic charge on  $\text{BF}_3$ :  $-0.326$   
 B-N distance:  $1.782 \text{ \AA}$   
 $\angle \text{F}_1\text{BF}_2\text{F}_3$ :  $-130.7^\circ$

Figure 4.—Optimized molecular interaction between  $\text{BF}_3$  and  $\text{NH}_3$ .





Figure 5.—HOMO orbital plot for  $\text{BF}_3\text{-NH}_3$  interaction.



Net atomic charge on  $\text{BF}_3$ :  $-0.119$   
 B-O distance:  $1.908 \text{ \AA}$   
 $\angle \text{F}_1\text{BF}_2\text{F}_3$ :  $-158.2^\circ$

Figure 6.—Optimized molecular interaction between  $\text{BF}_3$  and  $(\text{C}_2\text{H}_5)_2\text{O}$ .






Figure 7.—HOMO orbital plot for  $\text{BF}_3\text{-(C}_2\text{H}_5)_2\text{O}$  interaction.



Net atomic charge on  $\text{BF}_3$ :  $-0.057$   
 B-O distance:  $2.007 \text{ \AA}$   
 $\angle \text{F}_1\text{BF}_2\text{F}_3$ :  $-167.0^\circ$

Figure 8.—Optimized molecular interaction between  $\text{BF}_3$  and  $(\text{CF}_3\text{CH}_2)_2\text{O}$ .



Net atomic charge on  $\text{BF}_3$ :  $0$   
 B-O distance:  $5.182 \text{ \AA}$   
 $\angle \text{F}_1\text{BF}_2\text{F}_3$ :  $-180^\circ$

Figure 10.—Optimized molecular interaction between  $\text{BF}_3$  and  $(\text{C}_2\text{F}_5)_2\text{O}$ .




Figure 9.—HOMO orbital plot for  $\text{BF}_3$ - $(\text{CF}_3\text{CH}_2)_2\text{O}$  interaction.




Figure 11.—HOMO orbital plot for  $\text{BF}_3$ - $(\text{C}_2\text{F}_5)_2\text{O}$  interaction.



# REPORT DOCUMENTATION PAGE

*Form Approved*  
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

<b>1. AGENCY USE ONLY (Leave blank)</b>		<b>2. REPORT DATE</b> July 1998	<b>3. REPORT TYPE AND DATES COVERED</b> Technical Memorandum	
<b>4. TITLE AND SUBTITLE</b> Experimental and Calculational Studies of the Interactions of BF <sub>3</sub> With Fluoroethers			<b>5. FUNDING NUMBERS</b>  WU-523-22-13-00	
<b>6. AUTHOR(S)</b>  David W. Ball, Michael J. Zehe, and Wilfredo Morales				
<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b> National Aeronautics and Space Administration Lewis Research Center Cleveland, Ohio 44135-3191			<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  E-11183	
<b>9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b> National Aeronautics and Space Administration Washington, DC 20546-0001			<b>10. SPONSORING/MONITORING AGENCY REPORT NUMBER</b>  NASA TM-1998-207425	
<b>11. SUPPLEMENTARY NOTES</b> Prepared for the Annual Meeting sponsored by the Society of Tribologists and Lubrication Engineers, Detroit, Michigan, May 17-21, 1998. David W. Ball, Cleveland State University, Department of Chemistry, Cleveland, Ohio 44115; Michael J. Zehe and Wilfredo Morales, NASA Lewis Research Center. Responsible person, Michael J. Zehe, organization code 5140, (216) 433-5833.				
<b>12a. DISTRIBUTION/AVAILABILITY STATEMENT</b>  Unclassified - Unlimited Subject Category: 23  This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			<b>12b. DISTRIBUTION CODE</b>  Distribution: Nonstandard	
<b>13. ABSTRACT (Maximum 200 words)</b>  BF <sub>3</sub> was co-condensed with (C <sub>2</sub> H <sub>5</sub> ) <sub>2</sub> O, (CF <sub>3</sub> CH <sub>2</sub> ) <sub>2</sub> O, and (C <sub>2</sub> F <sub>5</sub> ) <sub>2</sub> O in excess argon at 15 K. Infrared spectra of the matrices showed a definite Lewis acid-base interaction between BF <sub>3</sub> and diethyl ether; a weak but definite interaction with bis(2,2,2-trifluoroethyl)ether, and no observable interaction with perfluoroethyl ether. Molecular orbital (MO) calculations complemented the experimental observations by revealing that fluorine atoms on the ethers decreased electron localization about the oxygen atom. Thus, the experimental data and MO calculations indicated a clear trend between strength of interaction with BF <sub>3</sub> and the degree of ether F substitution. The implications of the results for commercial perfluoro ether lubricant/metal oxide surface interactions are discussed.				
<b>14. SUBJECT TERMS</b>  Chemistry; Lubrication; Catalysis			<b>15. NUMBER OF PAGES</b> 12	
			<b>16. PRICE CODE</b> A03	
<b>17. SECURITY CLASSIFICATION OF REPORT</b> Unclassified	<b>18. SECURITY CLASSIFICATION OF THIS PAGE</b> Unclassified	<b>19. SECURITY CLASSIFICATION OF ABSTRACT</b> Unclassified	<b>20. LIMITATION OF ABSTRACT</b>	