

NASA/TM—1998-208487

372 778



# Mechanical Properties of Degraded PMR-15 Resin

Luis C. Tsuji and Hugh L. McManus  
Massachusetts Institute of Technology, Cambridge, Massachusetts

Kenneth J. Bowles  
Lewis Research Center, Cleveland, Ohio

---

August 1998

## The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized data bases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to [help@sti.nasa.gov](mailto:help@sti.nasa.gov)
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:  
NASA Access Help Desk  
NASA Center for AeroSpace Information  
7121 Standard Drive  
Hanover, MD 21076

NASA/TM—1998-208487



# Mechanical Properties of Degraded PMR-15 Resin

Luis C. Tsuji and Hugh L. McManus  
Massachusetts Institute of Technology, Cambridge, Massachusetts

Kenneth J. Bowles  
Lewis Research Center, Cleveland, Ohio

National Aeronautics and  
Space Administration

Lewis Research Center

---

August 1998

Trade names or manufacturers' names are used in this report for identification only. This usage does not constitute an official endorsement, either expressed or implied, by the National Aeronautics and Space Administration.

Available from

NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076  
Price Code: A03

National Technical Information Service  
5287 Port Royal Road  
Springfield, VA 22100  
Price Code: A03

# MECHANICAL PROPERTIES OF DEGRADED PMR-15 RESIN

Luis C. Tsuji,<sup>1</sup> Hugh L. McManus,<sup>1</sup> and Kenneth J. Bowles<sup>2</sup>  
National Aeronautics and Space Administration  
Lewis Research Center  
Cleveland, Ohio 44135

## SUMMARY

Thermo-oxidative aging produces a nonuniform degradation state in PMR-15 resin. A surface layer, usually attributed to oxidative degradation, forms. This surface layer has different properties from the inner material. A set of material tests was designed to separate the properties of the oxidized surface layer from the properties of interior material. Test specimens were aged at 316 °C in either air or nitrogen, for durations of up to 800 hr. The thickness of the oxidized surface layer in air aged specimens, and the shrinkage and coefficient of thermal expansion (CTE) of nitrogen aged specimens were measured directly. Four-point-bend tests were performed to determine modulus of both the oxidized surface layer and the interior material. Bimaterial strip specimens consisting of oxidized surface material and unoxidized interior material were constructed and used to determine surface layer shrinkage and CTE. Results confirm that the surface layer and core materials have substantially different properties.

## INTRODUCTION

### Background

Polymer matrix composite materials are being increasingly considered for use in environments that challenge their durability. Such applications include turbine engine structures and high speed aircraft skins. In these environments the materials are exposed to high temperature and to oxygen, both of which contribute to the degradation of the polymer matrix.

Significant progress has been made in the understanding of the aging effects on the thermo-oxidative stability of polymer matrix composites (refs. 1 to 3). Much of this work has focused on PMR-15 resin as a representative material. Thermo-oxidative aging produces a nonuniform degradation state in PMR-15 resin. While thermal degradation occurs throughout the material, oxidative degradation occurs only where oxygen diffuses into the material. This produces an oxidized surface layer that has different properties from the unoxidized inner material. Current models of coupled diffusion-reaction mechanisms (refs. 4 to 6) attempt to capture the behavior of this chemical degradation. However, there is a need for data on material properties of degraded material(s), in order to link the diffusion-reaction models of chemical degradation to thermo-mechanical models (ref. 7).

Air aged material specimens have an oxidized surface layer and an unoxidized inner material which have different material properties. Tests performed on such specimens as if they were homogeneous produce results that are difficult to interpret and may have little meaning. Tests must be carefully designed to separate the properties of the surface layer from the properties of the inner material.

### Problem

The problem addressed here is to separate the properties of the oxidized surface layer from the properties of the unoxidized inner material, in PMR-15 resin specimens aged in air for various times at 316 °C. Specifically, the thickness of the oxidized surface layer and the modulus, CTE, and shrinkage of both surface and inner material are determined as functions of aging duration.

<sup>1</sup>Graduate Student and Associate Professor, respectively, Department of Aeronautics and Astronautics, Massachusetts Institute of Technology, 77 Massachusetts Avenue, Cambridge MA 02139.

<sup>2</sup>Senior Material Engineer, NASA Lewis Research Center, 21000 Brookpark Road, Cleveland OH 44135.

## Approach

The approach to this problem is primarily experimental. The main challenge of this project, and the problem that drove the experimental design, is how to determine the shrinkage and CTE of the oxidized surface layer. The shrinkage is small, and the changes are slight. Typical measurements of length are confounded with the effects of surface erosion on the ends, and the stress and strain interactions of the surface layer and the unoxidized inner material. In order to determine the surface layer shrinkage and the surface layer CTE, a new test based on a bimaterial strip model was designed and used.

The new test involved the manufacturing of specimens that resembled a bimaterial strip, with the oxidized surface material on one side, and unoxidized inner material on the other side. These specimens were manufactured simply by slicing a piece of an aged specimen lengthwise through the thickness. When one side contracts or expands relative to the other, the specimen curves. By utilizing a bimaterial strip model, the amount of curvature and the change in curvature with temperature can be used to determine the surface layer shrinkage and the CTE. An illustration of the curvature specimen is shown in figure 1.

In order to calculate the surface layer shrinkage and CTE from the curvature and change in curvature with temperature, several other properties must be known. These include surface layer thickness, modulus of both the oxidized surface layer and unoxidized material, shrinkage of unoxidized aged material, and CTE of unoxidized aged material. These properties are determined from other tests.

Surface layer thickness is measured simply by polishing a cross section of a specimen and measuring the surface layer. The modulus of unoxidized aged material is determined by standard four-point bend test, which is illustrated in figure 2. The modulus of the oxidized surface layer is derived using basic beam theory from a bend test of an air aged specimen, as surface layer thickness and the modulus of the unoxidized material are known. Figure 2 also illustrates the bend test of an air-aged specimen. Shrinkage of unoxidized aged material is measured simply by measuring the length of a specimen both before and after aging. The CTE of unoxidized aged material is determined from a typical test using thermo-mechanical analysis, illustrated in figure 3.

## EXPERIMENTAL PROCEDURE

### Overview

Specimens were cut from plaques of PMR-15 resin. Each specimen was then measured to determine initial dimensions. After initial measurements were completed, the specimens were aged in an oven at 316 °C. Half of the specimens were aged in air in the oven, and half were aged in nitrogen in a nitrogen chamber placed inside the oven. Once specimens were removed from the aging ovens, their dimensions were remeasured. They were then tested to determine modulus by using four point bend tests. After bend testing, the specimens were cut again into smaller specimens for bimaterial strip curve tests, thermomechanical analysis (TMA), and for measuring surface layer thickness. Typically five specimens were used per test.

### Specimen Preparation

These experiments used 152.4 by 152.4 mm PMR-15 neat resin plaques from the same batch as the resin plaques used by Kamvouris and Roberts (ref. 8), so that comparisons could be made. The plaques were made from HyComp 100, a PMR-15 powder supplied by HyComp, Inc. The powder was compression molded using an automated heated press with vacuum. Both temperature and pressure were ramped gradually, to a 2-hr hold at 316 °C and 9.3 MPa. The material was not given a separate post cure before aging.

Specimens were cut from the plaques using a water-cooled micromachining diamond saw. The specimens were cut to the dimensions specified for four-point bend testing in the ASTM Standard Test Method for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials (D 790M). Specimens measured approximately 54- by 10- by 2.5-mm. After aging, dimensional measurements, and bend testing were completed, the specimens were further cut into smaller pieces for use in other tests. These pieces are illustrated in figure 4. Long thin specimens approximately 53 × 3 × 1 mm were cut for use in bimaterial strip curvature tests. Specimens approximately 26 × 3 × 2.5 mm were cut for determining layer thickness. Specimens approximately 5 × 3 × 2.5 mm were cut for use in thermomechanical analysis.

Specimens were dried for 24 hr at 120 °C and stored in sealed plastic bags inside a dessicator, and were dried again before each measurement for at least 30 min in a 120 °C oven, except for the TMA specimens, which were dried for two or more hours.

Specimens were aged in a Blue M oven at 316 °C. Specimens aged in air were placed on a tray in the oven, while specimens aged in nitrogen were placed inside a nitrogen chamber inside the oven. Specimen groups were aged 24, 48, 96, 168, 240, 336, 465, 633, and 801 hr. One group was not aged.

## Tests

Nitrogen Aged Specimen Shrinkage.—Shrinkage of nitrogen aged specimens was determined from direct measurements of the length of the bend test specimens before and after aging. Measurements were made using a traveling measuring microscope, which measured to 0.001 mm. The coordinates of each corner were recorded for both the top and bottom of each specimen. This produced four measurements of length for each specimen. The shrinkage could then be determined by comparing the length of each specimen before aging to the length after.

Bend Tests.—An Instron 4505 load frame with a 4500 controller was used for the bend tests. Steel four point bend fixtures with ceramic rollers were used. The load span to support span ratio was two. The bend tests conformed to ASTM D 790M, with one exception. Because of difficulties obtaining an accurate means of measuring center point deflection, load frame crosshead deflection was used instead. To compensate for slack and compliance of the load train, a test with a rigid bar in the fixture was performed to determine the compliance of the system. This was then used to correct the load versus displacement data for the tested specimens. Specimens were not tested to failure.

Thermomechanical Analysis.—Thermomechanical analysis was used to determine the CTE of nitrogen aged specimens. A TA Instruments model 2940 was used to measure the expansion of the small specimens as temperature was increased. CTE was determined from the slope of expansion versus temperature, over the range of temperature from room temperature to 316 °C.

Surface Layer Thickness.—Surface layer thickness specimens were mounted in epoxy and the cross section of the specimen was polished, to enable viewing of the surface layer with microscopy. Photomicrographs were then taken of the specimens. The thickness of the surface layer was then determined from measurements taken from the photomicrographs. This method of examination was known to produce measurable results due to the experience of Bowles, using similar material and aging conditions (ref. 9).

Curvature Tests.—Specimen curvature at room temperature was determined by measuring the location of three points on the edge of the curvature specimens, using a travelling measuring microscope that measured to 0.001 mm. Measurements were taken on both sides of each specimen. To make measurements at elevated temperatures, specimens were placed in the oven of the Instron 4505 test machine. Measurements were made using a cathetometer that looked through the oven window at the specimens. Specimens were placed on small stands in the oven, and measurements were taken of the height and span of the arc, as shown in figure 1.

## ANALYSIS

### Assumptions

The following analysis rests on a few basic assumptions. First is that the surface layer has uniform properties throughout the layer. This assumption is supported by the work of Cunningham, who showed both experimentally and with models that the surface degradation occurs on a sharp front, with little apparent gradient in degradation level within the surface layer (ref. 10). Second is the assumption that the moduli of the surface and interior layers have the same temperature dependence. This assumption is as yet unsupported, but effects only the surface layer CTE calculations in this work. Third is the assumption that viscoelastic relaxation is negligible. Relaxation would tend to make measurements of shrinkage underestimates of actual shrinkage. Finally, it is assumed that the nitrogen-aged specimens and the apparently unoxidized core material in the air aged specimens have the same properties.

### Nitrogen Aged Specimen Shrinkage

The shrinkage of a nitrogen aged specimen, which represents the shrinkage of unoxidized aged resin, is simply as follows:

$$\epsilon_{sc} = \frac{(l_{aged} - l_0)}{l_0} - (\alpha_{c(aged)} - \alpha_{c(o)})\Delta T \quad (1)$$

where  $\epsilon_{sc}$  is the shrinkage strain of the unoxidized material,  $l_{aged}$  is the aged length, and  $l_0$  is the unaged length. The second term compensates for the small difference between the aged and unaged core material CTE's,  $\alpha_{c(aged)}$  and  $\alpha_{c(o)}$ , with  $\Delta T$  being the difference between the aging temperature and room temperature.

#### Bend Tests

The modulus of nitrogen aged specimens,  $E_c$ , was calculated according to ASTM D 790M:

$$E_c = \frac{0.17L^3m}{wt^3} \quad (2)$$

where  $L$  is the support span,  $w$  is the specimen width,  $t$  is the specimen thickness, and  $m$  is the slope of the tangent to the initial straight-line portion of the load-deflection curve. For the specimens tested, the load-deflection curves were very linear.

Modulus of the oxidized surface layer,  $E_s$ , was determined by using basic beam theory:

$$E_s = \frac{1}{I_s} \left( \frac{L^3m}{96} - E_c I_c \right) \quad (3)$$

where  $L$  is the support span,  $m$  is the slope of the tangent to the initial straight line portion of the load deflection curve, and:

$$I_c = \frac{(w - 2t_s)(t - 2t_s)^3}{12} \quad (4)$$

$$I_s = \frac{wt^3}{12} - I_c \quad (5)$$

where  $t$  is the total thickness, and  $t_s$  is the thickness of the surface layer.

#### Thermomechanical Analysis of Nitrogen Specimens

CTE of the unoxidized core material was determined from thermomechanical analysis of nitrogen aged specimens. The TMA testing machine determined the slope of dimensional change versus temperature. From there calculating the CTE was simply:

$$\alpha_c = \frac{m_{CTE}}{t} \quad (6)$$

where  $\alpha_c$  is the coefficient of thermal expansion and  $m_{CTE}$  is the slope of the dimension change versus temperature.

#### Surface Layer Thickness

Surface layer thickness was determined by optical microscope measurement of prepared cross sections. Calculations were only to convert scale.



## Curvature Tests

The curvature tests are based on a model of a bimaterial beam, as illustrated in figure 1. Since the beam is unrestrained, the moment balance is of the form:

$$M = 0 = \int \sigma z dz \quad (7)$$

where the stress includes a thermal expansion term and a shrinkage term:

$$\sigma = E(\epsilon - \alpha \Delta T - \epsilon_s) \quad (8)$$

Using Bernoulli-Euler beam theory, the strain term can be expressed as:

$$\epsilon = kz + \epsilon_0 \quad (9)$$

where  $k$  is the curvature and  $\epsilon_0$  is the strain at the neutral axis. Thus stress can be expressed as

$$\sigma = E(kz + \epsilon_0 - \alpha \Delta T - \epsilon_s) \quad (10)$$

and the moment is then of the form:

$$M = \int E(kz + \epsilon_0 - \alpha \Delta T - \epsilon_s) z dz \quad (11)$$

It would be desirable to transfer coordinates to the neutral axis before integrating. The location of the neutral axis, as shown in figure 5 is

$$z^* = \frac{E_s \left( t_c + \frac{t_s}{2} \right) t_s + E_c \left( \frac{t_c}{2} \right) t_c}{E_s t_s + E_c t_c} \quad (12)$$

where  $t_s$  is the thickness of the surface layer and  $t_c$  is the thickness of the unoxidized core material. Establishing the new coordinate system we have:

$$\begin{aligned} \zeta_1 &= t_s + t_c - z^* \\ \zeta_2 &= t_c - z^* \\ \zeta_3 &= -z^* \end{aligned} \quad (13)$$

Thus the moment balance equation becomes:

$$M = 0 = \int_{\zeta_2}^{\zeta_1} E_s (k\zeta + \epsilon_0 - \alpha_s \Delta T - \epsilon_{ss}) \zeta d\zeta + \int_{\zeta_3}^{\zeta_2} E_c (k\zeta + \epsilon_0 - \alpha_c \Delta T - \epsilon_{sc}) \zeta d\zeta \quad (14)$$

Where  $\alpha_s$  and  $\alpha_c$  are the surface layer and core CTE's respectively, and  $\epsilon_{ss}$  and  $\epsilon_{sc}$  are the surface layer and core shrinkage strains. Curvature  $k$  can be determined from measurements as:

$$k = \frac{8h}{s^2} \quad (15)$$

Where  $h$  is the height of the arc and  $s$  is the span. Plotting values of  $k$  versus temperature and fitting a line to the data produces a graph like figure 6, where  $k'$  is the slope of  $k$  versus  $T$  and  $k''$  is the curvature at the cure temperature of 316 °C, where  $\Delta T$  is zero. Thus  $k$  can be expressed as:

$$k = k' \Delta T + k'' \quad (16)$$

Integrating and simplifying the moment balance equation leads to:

$$M = 0 = \frac{1}{3} a E_s k + \frac{1}{3} b E_c k - \frac{1}{2} c E_s \epsilon_{ss} - \frac{1}{2} d E_c \epsilon_{sc} - \left[ \frac{1}{2} c E_s \alpha_s + \frac{1}{2} d E_c \alpha_c \right] \Delta T \quad (17)$$

where

$$\begin{aligned} a &= \zeta_1^3 - \zeta_2^3 \\ b &= \zeta_2^3 - \zeta_3^3 \\ c &= \zeta_1^2 - \zeta_2^2 \\ d &= \zeta_2^2 - \zeta_3^2 \end{aligned} \quad (18)$$

and, as a consequence of the choice of axis,

$$c E_s = -d E_c \quad (19)$$

For  $\Delta T = 0$ , we can find

$$M = 0 = \frac{1}{3} a E_s k'' + \frac{1}{3} b E_c k'' - \frac{1}{2} c E_s \epsilon_{ss} - \frac{1}{2} d E_c \epsilon_{sc} \quad (20)$$

Solving for surface layer shrinkage:

$$\epsilon_{ss} = \frac{\frac{2}{3} a E_s k'' + \frac{2}{3} b E_c k''}{c E_s} + \epsilon_{sc} \quad (21)$$

Now for arbitrary  $\Delta T$  it is possible to determine the coefficient of thermal expansion of the surface layer material. Inserting equation (19) into equation (17) and solving:

$$\alpha_s = \frac{\frac{2}{3} a E_s k + \frac{2}{3} b E_c k}{c E_s \Delta T} - \frac{\epsilon_{ss}}{\Delta T} + \frac{\epsilon_{sc}}{\Delta T} + \alpha_c \quad (22)$$

It is convenient to present shrinkage strain  $\epsilon_s$  as a percent shrinkage  $P_s$ ; this can be calculated simply from:

$$P_s = -100 \epsilon_{ss} \quad (23)$$

## RESULTS AND DISCUSSION

### Format for Plotting

Data for each specimen was reduced individually. Results from replicate specimens (typically five per condition but occasionally as few as three) were then averaged, and the standard deviation were calculated. Symbols in the following plots indicate the mean, and error bars represent plus-minus one standard deviation.

### Surface Layer Thickness

Surface layer thickness are shown in figure 7. Surface layer thickness increases with aging duration, but the rate of growth decreases. The curve very closely resembles similar measurements made by Bowles (ref. 9).

## Modulus

The results of the bend tests are shown in figure 8. The measured value of the stiffness for the nitrogen aged specimens remained rather constant regardless of aging duration. The calculated value for the stiffness of the oxidized surface layer indicates a significant increase in the modulus over that of unoxidized material. However, the modulus of oxidized material also remains rather constant with aging duration.

## Surface Layer Shrinkage

Shrinkage of nitrogen aged specimens and calculations of the shrinkage of the oxidized surface layer are shown in figure 9. Values for strain were derived using equations (1) and (21), then converted to percent shrinkage for plotting using equation (23). The plots indicate that oxidized surface layer shrinkage is significantly greater than that of the inner unoxidized material. Shrinkage increases as aging duration increases although the unoxidized nitrogen aged specimen shrinkage appears to approach a limit as aging duration increases. Oxidized surface layer shrinkage does not appear to have a similar limiting behavior.

## Coefficient of Thermal Expansion

Thermomechanical testing was used to determine CTE of nitrogen aged specimens. The CTE of the oxidized surface layer was derived from curve test results as was shown in equation (22). A plot of CTE versus aging duration is shown in figure 10 for nitrogen aged specimens and for the calculated value of the oxidized surface layer. The data indicates that the CTE of material aged in nitrogen decreases slightly as time increases. The calculated CTE of the oxidized surface layer decreases more markedly.

## DISCUSSION AND CONCLUSION

This set of experiments successfully provides separate properties for the surface layer and the inner material of aged PMR-15 resin. These properties will be valuable for both greater understanding of aged material behavior, and also as data that can be used to complete models of thermo-oxidative degradation.

The core and surface layer material prove to be notably different. This difference explains some of the complex observed behavior of thermo-oxidatively aged specimens. For example, it was observed that curvature specimens at room temperature curved towards the interior material, when it was initially assumed that the specimens would curve toward the shrunken surface layer. Curvature specimens at the aging temperature curve toward the surface layer. Changes in CTE seen in this experiment explain this behavior. The increased stiffness and shrinkage seen in the surface layer also helps to explain surface cracking observed in other investigations in air-aged specimens. The shrinkage of the surface is restrained by the core, resulting in tensile stresses, which are only enhanced by the material's increased modulus.

## REFERENCES

1. Nam, J.D., and Seferis, J.C.: "Anisotropic Thermo-oxidative Stability of Carbon Fiber Reinforced Polymeric Composites," SAMPE Quarterly, May, 1992.
2. Bowles, K.J., and Meyers, A.: "Specimen Geometry Effects on Graphite/PMR-15 Composites During Thermo-Oxidative Aging," NASA TM-87204, Cleveland, OH, 1986.
3. Bowles, K.J., Roberts, G.D., and Kamvouris, J.E.: "Long-Term Isothermal Aging Effects on Carbon Fabric-Reinforced PMR-15 Composites: Compression Strength," NASA TM-107129, 1995.
4. McManus, H.L., and Cunningham, R.: "Coupled Materials and Mechanics Analyses of Durability Tests for High Temperature Polymer Matrix Composites," ASTM STP 1302: High Temperature and Environmental Effects on Polymeric Composites, 1997, pp. 1-17.
5. Cunningham, R., and McManus, H.L.: "Coupled Diffusion-Reaction Models for Predicting the Distribution of Degradation in Polymer Matrix Composites," Symposium on Composite Materials, AMSE International Mechanical Engineering Congress and Exposition, Atlanta, GA, Nov. 1996.

6. McManus, H.L., Foch, B., and Cunningham, R.: "Mechanism-Based Modeling of Long-Term Degradation," DURACOSYS 97: Progress in Durability Analysis of Composite Systems, Blacksburg VA, Sept. 1997, and submitted to the Journal of Composites Technology and Research, March 1998.
7. McManus, H.L., and Chamis, C.C., "Stress and Damage in Polymer Matrix Composite Materials Due to Material Degradation at High Temperatures," NASA TM-4682, 1996.
8. Kamvouris, J.E., Roberts, G.D., Pereira, J.M., and Rabzak, C.: "Physical and Chemical Aging Effects in PMR-15 Neat Resin," ASTM Second Symposium on High Temperature and Environmental Effects on Polymeric Composites, 1995, Norfolk, VA, preprint.
9. Bowles, K.J., Jayne, D., and Leonhardt, T.A.: "Isothermal Aging Effects on PMR-15 Resin," SAMPE Quarterly, Vol. 24, No. 2, 1993, pp. 2-9.
10. Cunningham, R.A., Massachusetts Institute of Technology, S.M. Thesis, 1997, pp. 138-146.





Figure 1.—Curve test schematic.




Figure 2.—Four-point bend test schematics.




Figure 3.—CTE test schematic.




Figure 4.—Specimen cutting illustration.




Figure 5.—Neutral axis and coordinate system.




Figure 6.—Sample graph of curvature versus temperature, showing  $k'$  and  $k''$ .




Figure 7.—Oxidized surface layer thickness versus aging duration.




Figure 8.—Bend modulus versus aging duration.




Figure 9.—Shrinkage versus aging duration. (2nd paragraph page 7)






Figure 10.—CTE versus aging duration. (3rd paragraph page 7)

<b>REPORT DOCUMENTATION PAGE</b>			<i>Form Approved</i> OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
<b>1. AGENCY USE ONLY (Leave blank)</b>		<b>2. REPORT DATE</b> August 1998	<b>3. REPORT TYPE AND DATES COVERED</b> Technical Memorandum	
<b>4. TITLE AND SUBTITLE</b>  Mechanical Properties of Degraded PMR-15 Resin			<b>5. FUNDING NUMBERS</b>  WU-523-21-13-00	
<b>6. AUTHOR(S)</b>  Luis C. Tsuji, Hugh L. McManus, and Kenneth J. Bowles				
<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b>  National Aeronautics and Space Administration Lewis Research Center Cleveland, Ohio 44135-3191			<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  E-11266	
<b>9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b>  National Aeronautics and Space Administration Washington, DC 20546-0001			<b>10. SPONSORING/MONITORING AGENCY REPORT NUMBER</b>  NASA TM-1998-208487	
<b>11. SUPPLEMENTARY NOTES</b>  To be published in Proceedings of Time Dependent and Non-Linear Effects in Polymers and Composites (ASTM STP 1357). Luis C. Tsuji and Hugh L. McManus, Massachusetts Institute of Technology, 77 Massachusetts Avenue, Cambridge, Massachusetts 02139-4307; Kenneth J. Bowles, NASA Lewis Research Center. Responsible person, Kenneth J. Bowles, organization code 5150, (216) 433-3197.				
<b>12a. DISTRIBUTION/AVAILABILITY STATEMENT</b>  Unclassified - Unlimited Subject Category: 24  This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			<b>12b. DISTRIBUTION CODE</b>	
<b>13. ABSTRACT (Maximum 200 words)</b>  Thermo-oxidative aging produces a non-uniform degradation state in PMR-15 resin. A surface layer, usually attributed to oxidative degradation, forms. This surface layer has different properties from the inner material. A set of material tests was designed to separate the properties of the oxidized surface layer from the properties of interior material. Test specimens were aged at 316 °C in either air or nitrogen, for durations of up to 800 hours. The thickness of the oxidized surface layer in air aged specimens, and the shrinkage and coefficient of thermal expansion (CTE) of nitrogen aged specimens were measured directly. Four-point-bend tests were performed to determine modulus of both the oxidized surface layer and the interior material. Bimaterial strip specimens consisting of oxidized surface material and unoxidized interior material were constructed and used to determine surface layer shrinkage and CTE. Results confirm that the surface layer and core materials have substantially different properties.				
<b>14. SUBJECT TERMS</b>  Polymers; Thermal aging; Mechanical properties; Thermal properties			<b>15. NUMBER OF PAGES</b> 19	
			<b>16. PRICE CODE</b> A03	
<b>17. SECURITY CLASSIFICATION OF REPORT</b> Unclassified	<b>18. SECURITY CLASSIFICATION OF THIS PAGE</b> Unclassified	<b>19. SECURITY CLASSIFICATION OF ABSTRACT</b> Unclassified	<b>20. LIMITATION OF ABSTRACT</b>	